

# **ROYAL ROAD MINERALS LIMITED**

## **NI 43-101 TECHNICAL REPORT FOR THE LUNA ROJA PROPERTY NORTHEASTERN NICARAGUA**



**Effective Date: June 5<sup>th</sup>, 2020**

Report Prepared by Luna Recursos Naturales

Qualified Person: Robert Nigel Chapman, B.Sc. HONS, M.AIG.

Date and Signature Page

**NI 43-101 TECHNICAL REPORT FOR THE LUNA ROJA PROPERTY**  
**NORTHEASTERN NICARAGUA**

**Effective Date: June 5<sup>th</sup>, 2020**

**Prepared for Royal Road Minerals**

**Property Location (UTM WGS 84, Zone 16N)**

Easting	Northing
780,750	1,542,950

**Prepared by Luna Recursos Naturales**

**Qualified Person Mr Nigel Chapman B.Sc. HONS, M.AIG.**



Signed and sealed:

Date: 5<sup>th</sup> June 2020

Location: Lima, Peru



Prepared by Luna Resources Naturales  
Effective Date: June 5<sup>th</sup>, 2020

Page 2 of 161

## Table of Contents

Date and Signature Page .....	2
List of Figure .....	5
List of Tables.....	5
1    Summary .....	6
2    Introduction .....	9
3    Reliance on Other Experts.....	11
4    Property Description and Location .....	12
5    Accessibility, Climate, Local Resources, Infrastructure and Physiography .....	16
5.1    Accessibility .....	16
5.2    Climate .....	17
5.3    Local Resources and Infrastructure.....	17
5.4    Physiography .....	17
6    History .....	18
7    Geological Setting and Mineralisation .....	19
7.1    Regional Geology.....	19
7.2    Local Geology .....	21
7.3    Property Geology .....	21
8    Deposit Type.....	24
9    Exploration .....	25
9.1    Soil Sampling .....	25
9.2    Grab Sampling .....	26
9.3    Channel Sampling.....	27
9.4    Ground Based Geophysics.....	29
10    Drilling .....	30
11    Sampling Preparation, Analyses and Security .....	145
11.1    Float Sampling .....	145
11.2    Channel Sampling.....	145
11.3    Half Core Sampling.....	146
11.4    Sample Analysis.....	146
11.5    Analytical Methods .....	147
11.6    Sample Security (Chain of Custody) .....	148
11.7    Quality Control Performance .....	148

11.8 Qualified Persons Opinion on the Adequacy of Sample Preparation, Security and Analysis.....	152
12 Data Verification.....	153
13 Mineral Processing and Metallurgical Testing .....	155
14 Mineral Resource Estimates.....	155
15 Mineral Reserves Estimates .....	155
16 Mining Methods .....	155
17 Recovery Methods .....	155
18 Project Infrastructure.....	155
19 Market Studies and Contracts.....	155
20 Environmental Studies, Permitting and Social or Community Impact.....	155
21 Capital and Operating Costs.....	155
22 Economic Analysis .....	155
23 Adjacent Properties.....	156
24 Other Relevant Data and Information .....	158
25 Interpretation and Conclusions.....	159
26 Recommendations .....	160
27 References.....	161

## List of Figure

Figure 4-1: Property location .....	12
Figure 5-1: Property Access.....	16
Figure 7-1: Regional Geology .....	20
Figure 7-2: Property Geology Map.....	22
Figure 7-3: Property Geology Cross Section.....	23
Figure 8-1: Potential deposit types (porphyry, epithermal and skarn mineralisation .....	24
Figure 9-1: Soil Sampling .....	26
Figure 9-2: Grab Sampling .....	27
Figure 9-3: Channel Sampling.....	28
Figure 9-4: Geophysical Surveys (gold in soil anomaly (> 245 Au ppb) shown as dashed yellow line).....	29
Figure 10-1: Drill collar locations.....	31
Figure 11-1: Coase non-certified Blank Performance .....	149
Figure 11-2: Certified Blank Performance .....	149
Figure 11-3: QC Coarse duplicate Performance .....	150
Figure 11-4: Pulp duplicate performance .....	150
Figure 11-5: QC CRM Oreas 524 Performance .....	151
Figure 11-6: QC CRM Oreas 521 Performance .....	151
Figure 12-1: Luna Roja Drill Collars MCDDH004 and MCDDH005.....	153
Figure 12-2: Photographs of artisanal operations at the Property.....	154
Figure 12-3: Reviewing core from the Property stored at the RYR Core Shed in Rosita .....	154
Figure 23-1: Adjacent Properties .....	157

## List of Tables

Table 4-1: Property concession details .....	12
Table 4-2: Mineral concession annual maintenance costs .....	13
Table 4-3: Corner coordinates of concession and concession application (points shown in figure 4.2) .....	13
Table 4-4: Approximate centre of the Rosita VI concession .....	15
Table 9-1: Summary statistics: Soil sample gold assay.....	25
Table 10-1: Drill collar details.....	30
Table 10-2: Downhole survey details .....	31
Table 10-3: Details of samples submitted for analysis.....	33
Table 10-4: Assay Details.....	89
Table 11-1: Detection limits for Fire Assay AAS .....	146
Table 11-2: Select detection limits for ICP-MS (all sample types) .....	146
Table 23-1: Inferred resource - Calibre Primavera Property.....	156
Table 23-2: Inferred resource - Calibre Cerro Aeropuerto Property .....	156
Table 23-3: Inferred resource - Calibre Eastern Borosi Property.....	156
Table 23-4: Indicated resource - Calibre Rosita DJV Property .....	157
Table 23-5: Inferred resource - Calibre Rosita DJV Property .....	157
Table 26-1: Proposed Exploration Budget .....	160

## 1 Summary

Royal Road Minerals (RYR) has commissioned Luna Recursos Naturales (LRN) and Mr Nigel Chapman (QP) to produce this Technical Report to comply with NI 43-101's Standards of Disclosure for Mineral Projects but has not been filed with the Toronto Stock Exchange (TSX). This Technical Report is focused on the Luna Roja Property (Luna Roja or the Property), a Joint Venture (JV) (or Alliance) between RYR and Hemco in Nicaragua's Golden Triangle.

RYR has acquired a 50% interest in the Luna Roja Property subject to the terms of an agreement with Hemco-Mineros which was signed on September 6<sup>th</sup>, 2017

The salient points under the terms of the Agreement include:

1. Hemco and Royal Road will jointly fund on an equal basis, initial project generation and exploration of targets.
2. At any time after the commencement of permitted drilling of any project area, parties may elect to define such project area as a "designated project area" (a "DPA") following which, the applicable rights and licenses for such DPA will be held by a newly formed joint venture company, with Royal Road and Hemco each initially holding an equal 50% proportionate equity interest thereof. The Property has been defined as a DPA.
3. All project costs of any such joint venture will be co-funded by the parties based on their respective ownership of the joint venture, which will be subject to dilution in the event funds are not contributed as required.
4. If a party's interest in a joint venture is diluted below 15% of the total interest, such party's interest in the joint venture will automatically convert to a 1.5% net smelter return royalty.
5. The terms of the Alliance also restrict the parties from transferring their respective interests in the relevant licenses covered by the Alliance, except in accordance with the agreement between the parties, which includes reciprocal rights of first refusal with respect to transfers to third parties.

RYR will be the operator under the terms of the Alliance and any joint ventures formed thereunder, and certain decisions of the operator will be subject to the approval of a management committee consisting of two representatives of each of RYR and Hemco.

The Property is in Nicaragua's "Golden Triangle", a well-known historic mining region located in north-eastern Nicaragua. The Golden Triangle is estimated to have had historical production totalling more than 5 million oz of gold (Au), 4 million oz of silver (Ag), 158,000 tons of copper (Cu), and 106,000 tons of zinc (Zn) (Arengi, et al, 2003).

The Property is located 2.5km north of the municipality of Rosita and consists of two mineral concessions held in the name of Hemco, Monte Carmelo I (51.55 Ha), and Monte Carmelo II (103.1 Ha).

Property geology is dominated by folded sequences of cretaceous limestones and shallow marine sedimentary rocks. Basic dykes have interrupted the sedimentary sequences as were seen by the QP along the NE-SW faults. Multiple mineralisation styles are recognised at Luna Roja, including skarn, breccia bodies, and veins.

Artisanal miners have been active at the Property for approximately five years and have developed small pits in the oxidised skarn mineralisation at surface to a depth of 40m.

RYR has systematically explored the Property using a combination of soil, grab, chip channel sampling, ground based geophysics and diamond drilling.

A contiguous gold in soil anomaly (>200 Au ppb) extending approximately 750m northwest-southeast, which included the area exploited by artisanal miners. Subsequent grab and chip channel sampling confirmed in-situ gold mineralisation at the Property and spatially related to the gold in soil anomaly.

RYR completed a 17-hole (2472m) diamond drill program to test various targets at the Property (RYR Press Release 2<sup>nd</sup> Oct 2019). Drilling identified broad zones of auriferous skarn to 150m depth and extending 400m northwest-southeast in the area of artisanal mining activity.

DDH	From (m)	Interval (m) <sup>1</sup>	Au ppm <sup>2</sup>
MC-DDH-003	36.05	49	2.8
<i>Including</i>	41.05	22	5.3
MC-DDH-005	145.05	23	2.1
MC-DDH-008	65.00	18	2.7
MC-DDH-011	12.00	45	1.1
MC-DDH-012	24.00	49	2.4
<i>Including</i>	55.00	18	5.4
MC-DDH-013	11.00	80	1.1
<i>Including</i>	47.00	10	2.8
MC-DDH-016	0.00	69	1.5
<i>Including</i>	29.00	15	2.5

Subsequent to the diamond drilling program, RYR commissioned ground based magnetic and microgravity surveys covering of the entire Property, this work was near completion in Q1 2020 (RYR Press Release 4<sup>th</sup> Feb 2020). The gold in soil anomaly is characterised by a “grainy” magnetic (TMI RTP<sup>3</sup>) signature with punctual highs and lows. 3D inverted gravity density data highlighted a discrete density low surrounded by a density high in the south of the property area which RYR interpret may represent deeper, downthrown endoskarn and adjacent exoskarn bodies worthy of drill testing.

Mr Chapman (QP) considers that the exploration techniques, sampling methodologies, and data management practices employed by RYR at the Property are standard industry practice and appropriate for greenfield exploration. Based on his review of Standard Operating Procedures (SOP's) and Quality Control sample performance Mr Chapman (QP) considers that the drilling

---

<sup>1</sup> Downhole intervals

<sup>2</sup> Weighted average intervals

<sup>3</sup> TMI RTP = Total Magnetic Intensity Reduced to Pole

data is reliable. Mr Chapman (QP) highlights that the performance of quality control (QC) samples, particularly CRM 524 suggest reduced analytical precision at lower grade (<0.5 ppm Au). Comparison of pulverised duplicates may also indicate the presence of coarse gold, and the use of screen fire assay may therefore be warranted.

Mr Nigel Chapman (QP) considers that the Property is prospective for a range of deposit types including skarn, vein and brecciated bodies and he has recommended two programs of exploration designed to test this potential:

- Further drilling in the area of the 2019 drill program (Monte Carmelo). The purpose of drilling is twofold; In-fill drilling to facilitate the estimation of an inferred resource; and exploratory drilling to test geophysical anomalies that suggest along strike and down-dip extensions of mineralisation.

The recommended programs can be run concurrently or independently, the estimated time required to complete the recommended exploration programs is 60 days, if run concurrently, for a cost of US\$1,437,500.

RYR should evaluate the results of the recommended exploration programs before advancing to subsequent exploration programs.

Mr Chapman (QP) notes that both RYR and Hemco have significant amounts of data held in disparate forms, combining this data will be beneficial for regional exploration and exploration at Luna Roja. Mr Chapman recommends that a combined database is created using industry standard software.

Further, RYR and Hemco should quantify the impacts (economic, environmental, or otherwise) of the artisanal mining operations.

## 2 Introduction

Luna Recursos Naturales (LRN) has been commissioned by Royal Road Minerals (RYR) to prepare an independent Technical Report for the Luna Roja Property (Luna Roja or the Property), located in Nicaragua's Golden Triangle area. The purpose of this Technical Report is to document the exploration history of the Property and to present recommendations for follow-up exploration.

RYR is listed on the TSX Venture Exchange (TSXV) with the symbol RYR. RYR is an explorer-developer focused on identifying and advancing projects of exploration interest in Latin America. This Technical Report is intended to comply with NI 43-101's Standards of Disclosure for Mineral Projects.

On September 6th, 2017 RYR announced a strategic alliance (the "Alliance") with Hemco concerned with mineral exploration in Nicaragua.

The salient points under the terms of the Alliance include:

1. Hemco and Royal Road will jointly fund on an equal basis, initial project generation and exploration of targets.
2. At any time after the commencement of permitted drilling of any project area, parties may elect to define such project area as a "designated project area" (a "DPA") following which, the applicable rights and licenses for such DPA will be held by a newly formed joint venture company, with Royal Road and Hemco each initially holding an equal 50% proportionate equity interest thereof.
3. All project costs of any such joint venture will be co-funded by the parties based on their respective ownership of the joint venture, which will be subject to dilution in the event funds are not contributed as required.
4. If a party's interest in a joint venture is diluted below 15% of the total interest, such party's interest in the joint venture will automatically convert to a 1.5% net smelter return royalty.
5. The terms of the Alliance also restrict the parties from transferring their respective interests in the relevant licenses covered by the Alliance, except in accordance with the agreement between the parties, which includes reciprocal rights of first refusal with respect to transfers to third parties.
6. Royal Road will be the operator under the Alliance and any joint ventures formed thereunder, and certain decisions of the operator will be subject to the approval of a management committee consisting of two representatives of each of Hemco and Royal Road.

The mineral concessions incorporating the Luna Roja project area have been designated a DPA but have not, yet, been transferred to a newly formed joint venture company.

RYR is the operator under the Alliance and any joint ventures formed thereunder, and certain decisions of the operator are subject to the approval of a management committee consisting of two representatives of each of Hemco and RYR.

Anomalous gold mineralisation has been identified in soil, channel, and half core samples, and artisanal operators are active at the Property.

Mr Nigel Robert Chapman (QP) is Managing Director of LRN and is the Qualified Person (QP) responsible for the content of this Technical Report. Mr Chapman is a former employee of RYR, and has visited the Property on several occasions, his most recent visit was between the 8<sup>th</sup> and 15<sup>th</sup> December 2019.

All measurement presented in this Technical Report are in metric units.

Monetary values are reported in United States Dollars (US\$), Canadian Dollars (C\$), and Nicaraguan Cordoba (COB\$). Coordinates are presented in the UTM WGS84, Zone 16N system (EPSG:32616).

### 3 Reliance on Other Experts

Mr Chapman is the Qualified Person (QP) responsible for the contents of all sections of this Technical Report.

Neither Luna Recursos Naturales (LRN) nor Mr Chapman (QP) is qualified to provide comment on legal issues associated with the Project included in Section 4 of this report. Inclusion of these aspects has been based entirely on information provided by Royal Road Minerals (RYR) and has not been independently verified.

Mr Chapman (QP) has relied on the following information:

- Legal opinion on the status of the Property concessions
- Mineral concession law
- Details of agreements between RYR and third parties granting rights of access to the Property
- Environmental permissions for exploration activities.

The above listed information was discussed via email between Mr Chapman (QP) and Dr Tim Coughlin, CEO of RYR (Email 1).

## 4 Property Description and Location

Luna Roja is located in the Golden Triangle area in north-eastern Nicaragua, in the Rosita municipality of the North Caribbean Coast Autonomous Region, approximately 285 km northeast of Managua and 110 km west of the coastal town of Puerto Cabezas (Figure 4-1).




Figure 4-1: Property location

The Property consists of two (2) contiguous mineral concessions (Monte Carmelo I, and Monte Carmelo II) with a combined area of approximately 154.65 hectares (Table 4-1 and Fig 4.2). The concessions are held in the name of Hemco.

Table 4-1: Property concession details

Concession Name	Ministerial Order	Start Date	Area Applied For (Ha)	Owner	Date Concession Granted	Area Granted (Ha)
Monte Carmelo I	664-RN-MC/2006	30/11/2006	51.55	Hemco Nicaragua SA	29/07/2002	51.55
Monte Carmelo II	669-RN-MC/2006	10/06/1994	103.10	Hemco Nicaragua SA	10/06/1994	103.10

Mineral (exploration) concessions and mining (exploitation) titles in Nicaragua have been regulated according to Law 387 since 2001 (Law 387). According to Law 387:

- Mineral concessions are subject to escalating annual maintenance fees<sup>4</sup>, that are calculated according to the size of the concession and its age (Table 4-2).
- Mining titles are granted for a term of 25 years and can be renewed for an additional 25 years.
- Artisanal miners are permitted to conduct hand mining on concessions held by others. Artisanal miners not active when Law 387 was enacted are limited to a maximum of 1% of the concession area and their activities are regulated by the Ministerio de Fomento, Industria y Comercio (MIFIC).

*Table 4-2: Mineral concession annual maintenance costs*

Year after concession granted	Cost US\$/ha
1	\$ 0.25
2	\$ 0.75
3 and 4	\$ 1.50
5 and 6	\$ 3.00
7 and 8	\$ 4.00
9 and 10	\$ 8.00
10 onwards	\$ 12.00

*Table 4-3: Corner coordinates of concession and concession application (points shown in figure 4.2)*

Vertice	Concession	Easting	Northing
1	Monte Carmelo 1	779995.85	1543668.52
2	Monte Carmelo 1	781361.17	1543654.87
3	Monte Carmelo 1	781381.64	1543257.21
4	Monte Carmelo 1	780002.67	1543257.21
5	Monte Carmelo 2	779999.26	1543011.59
6	Monte Carmelo 2	781381.64	1543025.23
7	Monte Carmelo 2	781368.00	1542154.87
8	Monte Carmelo 2	779995.85	1542154.87

---

<sup>4</sup> Mr Chapman (QP) understands that maintenance fees payable for Rosita VI are paid to date




Figure4-2: Property Concessions

The holder of a mineral concession does not have the right to access the land that the concession occupies. Right of access must be negotiated with the legal owner of the land.

Conflicts between indigenous communities and encroaching settlers engaged in farming and or artisanal mining are reported in Nicaragua. Mr Chapman (QP) notes that Hemco and RYR have been proactive in engaging local parties and have agreed rights of access to the Property.

The Property is subject to a 3% NSR payable to the Nicaraguan Government, the Property is not subject to any other royalties or encumbrances and no environmental liabilities have been recorded at the Property.

*The approximate centre of the Property, in the UTM WGS 84 Zone 16N coordinate system is reported in*

Table 4-4.

Table 4-4: Approximate centre of the Rosita VI concession

Easting	Northing
780,750	1,542,950

An environmental licence from the Regional Council for North Caribbean Coast Autonomous Region is required prior to any exploration activities in the Region.

RYR and Hemco have a current and valid environmental licence for Luna Roja, the licence was granted on April 30<sup>th</sup>, 2019 and is valid for 5 years (Agreement 1). Subject to community consent, this environmental license allows RYR to drill up to 47,000 m in the Property.

Explorers must submit proposed exploration plans to the Region's Secretaria de Recursos Natural (SERENA) for approval before an environmental permit is granted. Additionally, exploration activities that imply significant ground disturbance (i.e. trenching and drilling) are subject to public consultation, and the submission and approval of an independent Environmental Impact Study.

Subsequent to the granting of the above Environmental Permit four easement / land rental agreements were agreed with the landowners for the construction of drilling platforms. All four Agreements are currently valid and will expire on the 15<sup>th</sup> April 2022, two on 17<sup>th</sup> April 2022 and the last will expire on 5<sup>th</sup> May 2022.

Mr Chapman (QP) is not aware of any significant factors or risks that may affect access, title, or ability to perform the proposed work program on the Property.

## 5 Accessibility, Climate, Local Resources, Infrastructure and Physiography

### 5.1 Accessibility

Luna Roja is located approximately 285 km northeast of the capital city of Managua and 110 km west of the Caribbean port town of Puerto Cabezas. The largest population centre near the project is the town of Rosita (Figure 5-1).

The town of Rosita can be accessed by road vehicle over a mix of paved and unpaved roads from Managua. The drive time from Managua to Rosita is approximately nine-hours. A 4x4 vehicle is recommended. Alternatively, Rosita can be accessed using a mix of air and land routes utilizing twice daily flights from Managua to the town of Bonanza. After arrival in Bonanza, travellers continue by land to Rosita, which is approximately one-hour drive time to the south.




Figure 5-1: Property Access

Access to the Property is by 4x4 vehicle over unpaved roads from the town of Rosita to the main mining area and then on foot when inside the concession area. The Property is generally accessible year-round.

## 5.2 Climate

Northeast Nicaragua has two distinct seasons. A dry season from December through May and a rainy season from June through November. The transition between the two seasons varies by two to four weeks from year to year. The rainy season is marked by clear mornings and powerful cloudbursts in the afternoon. An average of 300 mm of rain per month is reported for the rainy season with the wettest months being September and October. Fieldwork is possible throughout the year, with more favourable access from November through June.

## 5.3 Local Resources and Infrastructure

Rosita is serviced by a municipal water system sourced from a local reservoir; however, frequent water shortages are experienced due to an aging water distribution system and insufficient maintenance. It is common for individual houses or compounds to utilize private wells installed by the property owners for sourcing water. Well water needs to undergo treatment before being considered a potable source. Creeks host running water throughout the year, water from the small creeks eventually feeds into the larger Okonwas, Kuliwas, and Kuliwas Sirpi rivers to the south.

Rosita is connected to the national electrical grid managed by La Empresa Nicaraguense de Electricidad (ENEL). Intermittent power failures are common in the region and access to a backup generator is strongly recommended.

Telephone and mobile phone services are provided by global communication companies Claro and Movistar with cell phone coverage increasing every year.

Apart from mining, the principal economic activities in the region are logging, ranching, commercial agriculture, artisanal mining, and service industries. Originally the town of Rosita was built to support the historic Santa Rita mine. The town is industrialized, and the population would provide a good source of unskilled and semi-skilled labour familiar with the mining industry.

## 5.4 Physiography

The Property lies within Nicaragua's Atlantic coastal plain and is characterized by native woodland with flat to hummocky terrain with elevations ranging from 50 m above sea level (masl) to 125 masl. Cleared areas of forest in the area are separated by heavy second-growth jungle and swamps.

Mr Chapman (QP) notes that the Property is at an early stage of investigation and has not been subject to engineering studies to evaluate potential sites for mining infrastructure (i.e. camp, processing plant, tailings storage). During his visit of the Property Mr Chapman (QP) noted sites that he considers are potentially suitable for mining infrastructure and that the generally flat nature of the terrain is such that there are many potential areas where mining infrastructure could be established.

## 6 History

Nicaragua's Golden Triangle is defined between the historic mining towns of Rosita, Siuna, and Bonanza. The Golden Triangle is estimated to have had historical production totalling more than 5 million oz of gold (Au), 4 million oz of silver (Ag), 158,000 tons of copper (Cu), and 106,000 tons of zinc (Zn) (Arengi, et al, 2003).

The Property has been mined by artisanal miners targeting high-grade oxidised gold bearing skarn bodies for approximately 5 years. Artisanal mining is conducted under a toll treatment agreement with Hemco. Hemco oversee and regulate the use of explosives on-site. Ore is hand-picked, bagged and trucked to Hemco's processing facility at Bonanza. Miners have developed vertical shafts and sub-horizontal drives to follow narrow 1m to 2m gold bearing structures to a depth of approximately 40m.

Under the Alliance<sup>5</sup>, RYR has completed multiple exploration programs including, soil, grab, chip channel and diamond drilling. A contiguous 750m northwest trending gold in soil anomaly (>200 ppb Au) has been defined encompassing the area exploited by artisanal miners. Grab and chip channel sampling of outcrop and saprolite has confirmed in-situ gold mineralisation spatially related to the gold in soil anomaly and beyond. (RYR Press Release 12th March 2018 and 25<sup>th</sup> September 2018)

In 2019, RYR undertook a 17-hole, 2472m, diamond drill program to test downward and along strike extensions of gold mineralisation in the area of artisanal mining activity. (RYR Press Release 4<sup>th</sup> Sep 2018). Drilling confirmed gold mineralisation to a depth of 150m below surface and 400m along a northwest to southeast strike. Mineralisation remains open at depth and along strike to the south-east. (RYR Press Release 2<sup>nd</sup> October 2019)

A program of ground-based magnetics and micro-gravity covering the entire Property was completed in Q1 2020 (RYR Press Release 4<sup>th</sup> February 2020). The gold in soil anomaly is characterised by a "grainy" magnetic (TMI RTP<sup>6</sup>) signature with punctual highs and lows. The ground gravity survey in 2020 showed a clear circular anomaly which may represent the intrusive 'endoskarn' at depth SW of MC-DDH-017. The 2019 drilling and RYR mapping highlighted the possibility of a down-thrown unit where hole LR-DDH-017 was located.

---

<sup>5</sup> Refer to Section 2 of this Technical Report

<sup>6</sup> TMI RTP = Total Magnetic Intensity Reduced to Pole

## 7 Geological Setting and Mineralisation

### 7.1 Regional Geology

The geology of northeast Nicaragua is illustrated in Figure 7.1. Northeast Nicaragua lies within the eastern extension of the North Interior Highlands geomorphic province. Limited exposures of ultramafic rocks indicate that portions of the region are underpinned by oceanic crust of postulated Mesozoic age. These rocks are overlain and in fault contact with an interbedded sequence of limestone, mudstone, tuffaceous shale, greywacke, and marl of the early Cretaceous Todos Santos Formation. The sedimentary rocks are locally interbedded with andesitic tuffs and flows, and in places intruded by subvolcanic andesite dikes and sills, also of Cretaceous or perhaps lower Tertiary age and later stocks and plugs that include diorite, quartz diorite, granodiorite, quartz monzonite, and granite. Extensive accumulations of largely andesitic flows, breccias, and tuffs, commonly mapped as Tertiary Matagalpa Formation, cover much of eastern Nicaragua, commonly concealing these older lithologies.

In northeast Nicaragua, the Todos Santos Formation occurs in three main areas. To the west of the Property they form a nearly continuous trend within the Iyas-Bocay Graben structure. To the east of the Property this sequence is exposed as a series of northeast-trending, isolated erosional windows within pre-Tertiary and Tertiary volcanics and intrusives; the third area is about midway between the Property and the Caribbean coast, where Cretaceous limestone occurs in an east-west trending window within the volcanics and younger sedimentary rocks.

The complex interplay between plate tectonic structural elements has resulted in several compression and extensional events. One of the earliest structural elements in the region is a north trending anticline-syncline couplet formed in the Cretaceous age sedimentary rocks. Age dates in the Siuna area indicate that this folding, as well as emplacement of mineralization, occurred in the upper Cretaceous. Several episode of Tertiary age extensional tectonics are manifest in the Iyas-Bocay graben, and numerous prominent northeast-trending magnetic and topographic lineaments are also present.

The northeast-striking lineaments appear to be older and offset by other major northwest-trending faults and lineaments derived from satellite imagery and aeromagnetic data. On a regional scale, the Rosita Fault forms a segment of a 45 km long lineament, defined by a series of magnetic lows. Collectively the northeast and northwest fault and fracture patterns define a system of conjugate structures. In addition to these lineaments, there are a series of circular and semi-circular features in the region which vary from 1 to 25 km in diameter. These features are interpreted to be calderas, volcanic- intrusive related domal structures, stocks, and plugs. (Arengi 2003).

Royal Road conducted an extensive Time-Space and tectonic analysis of Nicaragua which revealed several inconsistencies in the relatively scant published literature but highlighted some favourable time-space tectonic elements which have guided the Company's target generation initiatives in-country.




Figure 7-1: Regional Geology

## 7.2 Local Geology

The local and property geology can be roughly divided in two with the eastern region underlain mainly by folded and faulted carbonate sedimentary rocks of the Todos Santos Formation and to the west are andesitic to basaltic volcanic rocks that have been intruded by a series of stocks and plugs including diorite, quartz diorite, granodiorite, quartz monzonite, and granite. Hydrothermal alteration associated with emplacement of the intrusives has led to the development of large areas of skarn and hydrothermally altered rock.

Locally, tectonically emplaced bodies of Mesozoic ultramafic rock/ophiolite crop out in the area and suggest that the region is at least partly underpinned by oceanic crust. The principal tectonic features in the Property area are a northwest-trending fault-related fold and a series of subparallel, northeast, and northwest striking accommodation faults. The most obvious of the northwest trending fault features in this area is the Rosita Fault, a broad shear zone that can be traced for at least 3 km through the Santa Rita mine toward the southeast.

The local northwest trending fault and fold structures are locally displaced by northeast striking oblique-slip accommodation faults; the north-east trending structures often contain intermediate – felsic dykes and adjacent breccias. Earlier northwest trending fault features are interpreted to be related to a deep crustal discontinuity that may represent collision-related tear faults active at the time when the Siuna plate docked with the Chortis terrane.

The geology of the nearby Rosita mine, as described by Plecash and others (1963), Bevan (1971), Wu (2012) and Wu+Solari and Wu (2017), was described as a plug of granite that intrudes the sedimentary and overlying volcanic rocks giving rise to garnet-epidote skarn, marble, and hornfels.

At Luna Roja the skarn paragenetic sequence consists of initial marble, followed by a gold-mineralized andradite- pyroxene skarn located along selective carbonate units (also possibly occurring along a pressure solution cleavage) followed by generally higher-grade, gold mineralized, haematite-magnetite-carbonate vein and breccia-related skarn. Gold is related with elevated tungsten, zinc, and manganese.

## 7.3 Property Geology

Property Geology has been described based on mapping of artisanal workings, outcrop, and diamond core-drilling.

The principal geological units identified at the property are volcanoclastics, marl, marble and skarnoid, pyroxene skarn, magnetite skarn, intermediate to felsic dykes, and quaternary deposits.

Carbonate sedimentary units and underlying intrusions have been thrust over marls and volcanic units along a northwest-southeast striking thrust fault and associated fold structure. Multiple, sub parallel northeast - southwest orientated accommodation faults, containing intermediate to felsic intrusives, crosscut and displace the volcanoclastic and sedimentary units. Zones of skarning have been developed in the folded sedimentary sequences. (Figure 7-2)




Figure 7-2: Property Geology Map




Figure 7-3: Property Geology Cross Section

## 8 Deposit Type

Nicaragua's Golden Triangle hosts various deposit types driven by intrusions, including porphyry, skarn and low-sulphidation epithermal deposits. Estimated historical production from The Golden Triangle of Nicaragua is estimated to total more than 5 million oz of gold (Au), 4 million oz of silver (Ag), 158,000 tons of copper (Cu), and 106,000 tons of zinc (Zn) (Arengi, et al, 2003).

Based on their observations, RYR has identified skarn-related gold mineralization associated with, breccia, veining, and selective replacement of carbonate rocks on the upper limb and in the hinge-zone of a northwest trending, thrust-related, inclined antiform. The skarn paragenetic sequence consists of initial marble, followed by a gold-mineralized andradite- pyroxene skarn located along selective carbonate units (also possibly occurring along a pressure solution cleavage) followed by generally higher-grade, gold mineralized, haematite-magnetite-carbonate vein and breccia-related skarn. Gold is related with elevated tungsten, zinc, and manganese.

Mr Chapman (QP) considers that Luna Roja is prospective for gold mineralisation related to intrusions, principally skarn and possibly porphyry deposits in the region of the property. These deposit types are linked genetically and temporally (Figure 8-1).




Figure 8-1: Potential deposit types (porphyry, epithermal and skarn mineralisation)

## 9 Exploration

Since entering into the Agreement<sup>7</sup>, RYR has undertaken staged exploration programs at the Property including, grab, soil, channel sampling, and magnetic and gravity surveys.

### 9.1 Soil Sampling

RYR undertook a soil survey based on east-west orientated survey lines separated by 200m with sample stations taken approximately every 25m along survey lines. In-fill surveying reduced the spacing between survey lines to 100m (Figure 9-1). A total of 383 soil samples have been taken using auger into saprolite to a maximum depth of 3m. Soil sampling identified a contiguous zone of gold soil anomalism extending approximately 750m in a northwest southeast trend. (RYR Press Release 12<sup>th</sup> March 2019) The QP is satisfied that the soil sampling assay results were not affected by the mining activity.

*Table 9-1: Summary statistics: Soil sample gold assay*

Description	Unit	Number
Sample	Count	383
Lower Detection Limit	Au ppb	1
Samples Below Detection	Count	0
Average	Mean (Au ppb)	283.9
Maximum	Au ppb	21900

---

<sup>7</sup> Refer to Section 1 of this Technical Report




Figure 9-1: Soil Sampling

## 9.2 Grab Sampling

RYR has taken 116 grab samples at the Property, assay results from these samples have been summarised in Figure 9-2. Grab samples include samples taken at the end of an auger hole that returned pieces of subcrop, waste from artisanal operations, and outcrop. Sample distribution was not systematic. Mr Chapman (QP) notes that grab samples are selective and that they are not representative of mineralisation. Gold anomalism in grab samples is spatially related gold in soil anomalism.




Figure 9-2: Grab Sampling

### 9.3 Channel Sampling

RYR has taken 256 channel samples at the Property, channel samples are described as channel, continuous channel, and linear chip samples. Continuous channel samples are taken using a circular saw, channel and linear channel samples are taken using a hammer and chisel. Sampling of linear channel samples is punctuated along the sampling interval whereas channel samples are sampled evenly across the entire interval. Mr Chapman (QP) notes that samples described as linear channel samples are not strictly channel samples as the entire interval has not been sampled.

Channel sample locations are recorded at the start of the channel, the orientation of channel samples is not recorded. Channel sample coordinates are for the start point of each channel.

Mr Chapman notes that a (one) channel samples does not have a recorded length, channel samples with recorded lengths vary between 0.5 and 1.9 m and average length 1.27 m. The location and summary gold grade data of channel samples (all types) has been presented in Figure 9-3. Areas of most anomalous gold in channel samples are coincident with the gold in soil anomaly.




Figure 9-3: Channel Sampling

#### 9.4 Ground Based Geophysics

RYR commissioned ground based magnetic and microgravity surveys covering the entire Property (Arce, 2020). The surveys have been based on 15 east-west survey lines spaced 200 m apart, a total of 20,035m of ground magnetometry and 545 gravity stations were run.

Ground based geophysics was used to aid the exploration of skarn mineralisation identified during 2019 diamond drilling programme (refer to Section 10) and to help define follow-up drilling programs.




Figure 9-4: Geophysical Surveys (gold in soil anomaly (> 245 Au ppb) shown as dashed yellow line)

Mr Chapman (QP) considers the exploration techniques and practices used by RYR at the Property are industry standard and are appropriate for gold exploration. Mr Chapman (QP) notes that the exploration completed by RYR has confirmed the presence of in-situ gold hosted in skarn structures. Further, Mr Chapman (QP) notes that the geophysical signatures suggest that potential extensions of known gold mineralisation exist and have not yet been drill-tested.

## 10 Drilling

RYR undertook a 17-hole diamond drill (DDH) scout drilling program at the Property designed to test the continuation of the surface mineralisation at depth and along strike. This program was completed in 2019 and a total of 2,472.50m have been drilled, collar locations and details are summarised in Table 10-1, and Figure 10-1.

*Table 10-1: Drill collar details*

Drill Hole	East	North	Elevation	EOH	Azimuth	Inclination
MC-DDH-001	780501.4	1543179.2	160	150.97	60	-60
MC-DDH-002	780501.8	1543181	160	124.25	30	-60
MC-DDH-003	780536.4	1543112.8	185	164.7	60	-60
MC-DDH-004	780533.6	1543113.6	184.8	36.6	320	-60
MC-DDH-005	780534.6	1543115.6	185	189.05	320	-70
MC-DDH-006	780536.6	1543108.4	186	190.62	140	-60
MC-DDH-007	780572.2	1543060.2	204.4	150.97	60	-60
MC-DDH-008	780570.8	1543058.8	203	187.6	140	-60
MC-DDH-009	780503	1543039.4	158.2	245.52	140	-60
MC-DDH-010	780501.4	1543040.2	158	100.65	360	-90
MC-DDH-011	780449.8	1543319.4	125.4	156.3	50	-50
MC-DDH-012	780548.2	1543095	192	109.8	70	-48
MC-DDH-013	780548.2	1543097	193	126.57	38	-55
MC-DDH-014	780548.4	1543094.4	192	122	130	-55
MC-DDH-015	780504.2	1543147.6	167.4	179	60	-50
MC-DDH-016	780495	1543314.4	138	112.85	15	-50
MC-DDH-017	781028	1542832	202	125.05	65	-50
<b>Total meters drilled</b>				<b>2472.50</b>		

*Coordinates are presented in UTM WGS84, Zone 16N*




Figure 10-1: Drill collar locations

Core recovery has been recorded on a run by run basis; average core recovery was >95%.

Drill collar locations have been recorded using handheld GPS to an accuracy of +/- 5m. Drill orientation was determined using compass and clinometer, typically accurate to +/- 2°. Drill core was not orientated. A concrete monument has been constructed at each collar indicating, drill hole name and end depth and the uPVC drill collar is closed by a uPVC cap.

Downhole azimuth and inclination surveys were taken using Devishot for most drill holes, drill hole MCDDH-004 and MCDDH-012 were not surveyed due to the drill rods becoming stuck and the hole was abandoned. Survey records are presented in Table 10-2.

Table 10-2: Downhole survey details

Drill Hole	Survey Depth (m)	Azimuth	Inclination	Survey Type
MCDDH-001	100.00	57.80	-59.12	Devishot
MCDDH-001	150.00	58.27	-59.28	Devishot
MCDDH-002	100.00	31.32	-58.79	Devishot
MCDDH-002	125.00	30.33	-58.97	Devishot
MCDDH-003	100.00	60.28	-59.15	Devishot
MCDDH-003	164.00	62.14	-58.52	Devishot
MCDDH-005	100.00	321.44	-68.91	Devishot
MCDDH-005	189.00	322.48	-69.13	Devishot

Drill Hole	Survey Depth (m)	Azimuth	Inclination	Survey Type
MCDDH-006	100.00	142.34	-60.31	Devishot
MCDDH-006	190.00	144.26	-60.06	Devishot
MCDDH-007	100.00	55.16	-62.00	Devishot
MCDDH-007	150.00	56.60	-61.72	Devishot
MCDDH-008	100.00	141.63	-60.04	Devishot
MCDDH-008	187.00	142.35	-58.57	Devishot
MCDDH-009	100.00	141.63	-58.84	Devishot
MCDDH-009	200.00	144.97	-57.47	Devishot
MCDDH-010	100.00	37.25	-88.78	Devishot
MCDDH-011	100.00	47.50	-51.08	Devishot
MCDDH-011	156.00	47.82	-51.35	Devishot
MCDDH-013	100.00	37.68	-55.55	Devishot
MCDDH-013	126.57	41.78	-55.81	Devishot
MCDDH-014	100.00	138.59	-48.62	Devishot
MCDDH-015	100.00	60.56	-47.61	Devishot
MCDDH-016	100.00	13.64	-48.83	Devishot
MCDDH-016	112.00	13.35	-48.98	Devishot
MCDDH-017	100.00	58.97	-47.85	Devishot

Core is quick logged at the drill site prior to transportation to the RYR's core shed. RYR geologists, clean, reconstruct and mark core prior logging, photographing (wet and dry if practical) and sampling.

Geologists log core according to written protocols developed by RYR, capturing the following details:

- Rock type, alteration minerals, and mineralisation type and concentration
- Recovery (holes MCDDH012 – 017 only) and,
- RQD

Once logged, core is typically marked for sampling on strict 1m intervals from the top of the hole to the bottom. Mr Chapman (QP) notes:

- Two samples are longer than 1m, at 2m and 1.1m
- 15 samples are shorter than 1m ranging between 0.05 and 0.92 m. Most of these samples were taken at the end of a drill hole, where drilling was stopped prior to completion of the next meter.

Sample intervals are irrespective of geology. Core samples are dispatched to Bureau Veritas for independent gold fire assay AAS and multi-element ICP-MS analysis.

RYR submitted a total of 2779 samples for analysis, including half core and Quality Control (QC) samples. QC samples submitted by RYR include high (OREAS 524) and low grade (OREAS 521) Certified Reference Material (CRM's), certified pulverised blank (OREAS 22f), non-certified quarry sourced coarse blank, half core duplicate, and crushed and pulverised duplicates inserted by Bureau Veritas at the instruction of RYR. Approximately 15% of samples submitted by RYR for analysis were QC samples.

Table 10-3: Details of samples submitted for analysis

Sample Type	Count	Percentage
Half core	2365	85.10
Coarse duplicate	57	2.05
Pulp duplicate	49	1.76
Coarse blank*	64	2.30
Fine blank (Oreas 22f)	54	1.94
CRM low-grade (Oreas 521)	96	3.45
CRM high-grade (Oreas 524)	94	3.38
<b>Total</b>	<b>2779</b>	<b>100</b>

\*Coarse blank is not certified

Fire assay and select ICP assays of half core samples (i.e. excluding QC samples) are provided in Table 10-4: Assay Details

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	15.05	16.05	1.00	2961915	0.153	1.3	60	4.5	61.2
MC-DDH-001	16.05	17.05	1.00	2961916	0.133	1.3	56	3.1	54.1
MC-DDH-001	17.05	18.05	1.00	2961917	0.016	0.1	10	0.3	14.6
MC-DDH-001	18.05	19.05	1.00	2961918	0.077	0.5	35	2.9	43.3
MC-DDH-001	19.05	20.05	1.00	2961920	0.055	0.3	40	1.5	34.4
MC-DDH-001	47.05	48.05	1.00	2961921	0.015	0.1	12	0.7	16.1
MC-DDH-001	48.05	49.05	1.00	2961922	0.021	0.1	27	0.2	8.1
MC-DDH-001	49.05	50.05	1.00	2961923	1.058	3.7	501	12.7	25.1
MC-DDH-001	50.05	51.05	1.00	2961924	0.354	3.5	168	15.9	51.6
MC-DDH-001	51.05	52.05	1.00	2961925	0.143	0.4	157	1.8	19.8
MC-DDH-001	52.05	53.05	1.00	2961926	0.746	0.5	63	1.0	3.7
MC-DDH-001	53.05	54.05	1.00	2961927	0.210	0.7	69	2.1	23.8
MC-DDH-001	54.05	55.05	1.00	2961928	0.210	0.5	60	7.8	44.7
MC-DDH-001	55.05	56.05	1.00	2961929	0.303	0.7	238	3.8	31.4
MC-DDH-001	56.05	57.05	1.00	2961930	0.107	0.6	102	0.9	42.7
MC-DDH-001	57.05	58.05	1.00	2961931	0.155	0.6	86	0.6	32.3
MC-DDH-001	58.05	59.05	1.00	2961932	0.063	0.3	60	0.7	40.5
MC-DDH-001	59.05	60.05	1.00	2961933	0.218	0.6	126	1.2	39.6
MC-DDH-001	60.05	61.05	1.00	2961935	0.099	0.6	78	0.6	41.7
MC-DDH-001	61.05	62.05	1.00	2961936	0.056	0.4	46	0.4	49.3
MC-DDH-001	62.05	63.05	1.00	2961937	0.022	0.1	12	0.2	5.3
MC-DDH-001	63.05	64.05	1.00	2961938	0.073	0.2	37	0.7	61.8
MC-DDH-001	65.05	66.05	1.00	2961941	0.038	0.2	10	0.2	65.3
MC-DDH-001	66.05	67.05	1.00	2961942	0.029	0.1	10	0.1	44.5
MC-DDH-001	67.05	68.05	1.00	2961943	0.029	0.1	7	0.1	5.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	68.05	69.05	1.00	2961944	0.025	0.1	8	0.1	55.4
MC-DDH-001	76.05	77.05	1.00	2961946	0.086	0.1	3	0.1	78.4
MC-DDH-001	77.05	78.05	1.00	2961947	0.080	0.1	6	0.2	36.2
MC-DDH-001	81.05	82.05	1.00	2961948	0.026	0.2	12	0.1	21.7
MC-DDH-001	82.05	83.05	1.00	2961949	0.121	0.2	52	0.2	15.0
MC-DDH-001	83.05	84.05	1.00	2961950	0.105	0.7	87	0.9	110.6
MC-DDH-001	84.05	85.05	1.00	2961951	0.138	0.8	98	1.4	45.0
MC-DDH-001	85.05	86.05	1.00	2961953	0.201	1.0	91	1.2	61.0
MC-DDH-001	86.05	87.05	1.00	2961954	0.061	0.3	42	0.2	40.2
MC-DDH-001	87.05	88.05	1.00	2961955	0.041	0.4	32	0.4	25.6
MC-DDH-001	142.05	143.05	1.00	2961956	0.007	0.1	16	3.4	6.6
MC-DDH-001	143.05	144.05	1.00	2961957	0.007	0.1	57	1.8	10.7
MC-DDH-001	144.05	145.05	1.00	2961958	0.013	6.2	159	26.3	1748.8
MC-DDH-001	145.05	146.05	1.00	2961959	0.067	11.1	62	44.6	2565.2
MC-DDH-001	147.05	148.05	1.00	2961962	0.009	0.1	40	1.3	19.7
MC-DDH-001	148.05	149.05	1.00	2961963	0.007	0.1	42	1.5	14.6
MC-DDH-001	149.05	150.05	1.00	2961964	0.007	0.1	9	2.2	10.5
MC-DDH-001	150.05	150.97	0.92	2961965	0.012	0.1	92	9.8	13.5
MC-DDH-011	112.00	113.00	1.00	2964341	0.000	-0.1	5	-0.1	1.1
MC-DDH-011	113.00	114.00	1.00	2964342	0.000	-0.1	1	-0.1	1.2
MC-DDH-011	114.00	115.00	1.00	2964343	0.008	-0.1	-1	-0.1	1.2
MC-DDH-011	115.00	116.00	1.00	2964344	0.000	-0.1	4	-0.1	0.9
MC-DDH-011	116.00	117.00	1.00	2964345	0.000	-0.1	3	0.4	15.6
MC-DDH-011	117.00	118.00	1.00	2964346	0.000	-0.1	5	0.4	77.1
MC-DDH-011	118.00	119.00	1.00	2964348	0.000	-0.1	10	0.3	58.1
MC-DDH-011	119.00	120.00	1.00	2964349	0.000	-0.1	2	0.1	3.7
MC-DDH-011	120.00	121.00	1.00	2964350	0.000	-0.1	6	-0.1	2.1
MC-DDH-002	18.05	19.05	1.00	2965152	0.029	0.4	30	0.5	26.1
MC-DDH-002	19.05	20.05	1.00	2965153	0.088	0.3	35	0.4	3.4
MC-DDH-002	20.05	21.05	1.00	2965154	0.258	0.9	25	0.4	4.9
MC-DDH-002	21.05	22.05	1.00	2965155	0.141	0.2	27	0.5	4.8
MC-DDH-002	52.05	53.05	1.00	2965157	0.066	0.5	54	3.8	25.0
MC-DDH-002	53.05	54.05	1.00	2965158	0.372	1.6	190	24.2	24.0
MC-DDH-002	54.05	55.05	1.00	2965159	0.337	2.0	142	17.0	29.1
MC-DDH-002	55.05	56.05	1.00	2965160	0.165	1.1	84	7.9	25.4
MC-DDH-002	56.05	57.05	1.00	2965161	0.182	1.2	107	13.3	25.7
MC-DDH-002	57.05	58.05	1.00	2965162	0.237	1.6	145	28.4	21.4
MC-DDH-002	58.05	59.05	1.00	2965164	0.382	2.8	266	36.5	26.1
MC-DDH-002	59.05	60.05	1.00	2965165	0.264	1.7	220	4.9	71.1
MC-DDH-002	60.05	61.05	1.00	2965166	0.142	1.1	52	1.2	38.4
MC-DDH-002	61.05	62.05	1.00	2965167	0.304	1.0	114	2.6	37.1
MC-DDH-002	62.05	63.05	1.00	2965168	0.303	0.9	98	1.7	18.8
MC-DDH-002	63.05	64.05	1.00	2965169	0.387	1.6	143	2.2	32.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-002	64.05	65.05	1.00	2965170	0.308	1.0	37	0.9	12.4
MC-DDH-002	65.05	66.05	1.00	2965171	0.526	1.6	273	1.0	42.3
MC-DDH-002	66.05	67.05	1.00	2965172	0.881	1.9	164	1.0	21.5
MC-DDH-002	67.05	68.05	1.00	2965174	1.099	1.6	128	8.2	42.4
MC-DDH-002	68.05	69.05	1.00	2965175	2.747	0.6	25	0.3	28.4
MC-DDH-002	69.05	70.05	1.00	2965176	3.395	0.9	71	1.1	44.2
MC-DDH-002	70.05	71.05	1.00	2965177	0.323	1.6	376	7.1	31.1
MC-DDH-002	73.05	74.05	1.00	2965180	0.116	0.2	60	2.0	7.1
MC-DDH-002	76.05	77.05	1.00	2965181	0.011	0.1	5	0.2	3.1
MC-DDH-002	77.05	78.05	1.00	2965182	0.408	0.4	29	3.9	28.7
MC-DDH-002	85.05	86.05	1.00	2965183	0.037	0.4	22	1.0	23.7
MC-DDH-002	86.05	87.05	1.00	2965184	0.023	0.3	6	0.7	13.6
MC-DDH-002	87.05	88.05	1.00	2965185	0.030	0.4	10	0.7	11.1
MC-DDH-002	88.05	89.05	1.00	2965186	0.225	1.6	121	3.2	32.1
MC-DDH-002	89.05	90.05	1.00	2965188	0.010	0.1	4	0.3	1.3
MC-DDH-002	90.05	91.05	1.00	2965189	0.034	0.2	18	1.9	3.8
MC-DDH-002	91.05	92.05	1.00	2965190	0.054	0.3	26	2.8	4.4
MC-DDH-002	92.05	93.05	1.00	2965191	0.047	0.3	6	3.6	2.6
MC-DDH-002	93.05	94.05	1.00	2965192	0.415	1.2	125	17.9	25.5
MC-DDH-002	94.05	95.05	1.00	2965193	0.290	0.6	121	4.7	9.5
MC-DDH-002	95.05	96.05	1.00	2965194	0.013	0.2	4	1.1	3.2
MC-DDH-002	105.05	106.05	1.00	2965196	0.275	1.0	8	0.3	170.0
MC-DDH-002	106.05	107.05	1.00	2965197	0.162	0.2	10	0.3	3.4
MC-DDH-002	107.05	108.05	1.00	2965198	0.543	0.8	22	0.1	26.1
MC-DDH-002	108.05	109.05	1.00	2965199	0.009	0.1	6	0.1	1.2
MC-DDH-002	109.05	110.05	1.00	2965200	0.019	0.2	26	0.2	2.4
MC-DDH-002	110.05	111.05	1.00	2965201	0.007	0.2	6	0.2	1.6
MC-DDH-002	111.05	112.05	1.00	2965202	0.007	0.2	8	0.3	2.2
MC-DDH-002	112.05	113.05	1.00	2965203	0.005	0.3	20	0.3	0.7
MC-DDH-002	113.05	114.05	1.00	2965204	0.005	0.2	5	0.1	1.4
MC-DDH-002	114.05	115.05	1.00	2965205	0.010	0.2	36	0.8	2.8
MC-DDH-002	115.05	116.05	1.00	2965207	0.024	0.4	22	0.5	3.8
MC-DDH-002	116.05	117.05	1.00	2965208	0.293	0.4	10	0.7	71.6
MC-DDH-002	117.05	118.05	1.00	2965209	1.392	0.5	25	1.0	11.5
MC-DDH-002	119.05	120.05	1.00	2965212	0.007	0.1	1	0.2	6.9
MC-DDH-002	120.05	121.05	1.00	2965213	0.005	0.1	3	0.4	1.8
MC-DDH-002	121.05	122.05	1.00	2965214	1.106	0.5	13	0.8	47.3
MC-DDH-002	122.05	123.05	1.00	2965215	1.303	0.5	43	0.2	37.7
MC-DDH-002	123.05	124.05	1.00	2965216	0.821	0.2	45	0.3	13.5
MC-DDH-002	124.05	124.25	0.20	2965218	0.688	0.2	13	0.2	5.1
MC-DDH-003	6.05	7.05	1.00	2965220	0.246	2.7	207	6.6	14.0
MC-DDH-003	7.05	8.05	1.00	2965221	0.057	0.7	35	0.8	3.1
MC-DDH-003	8.05	9.05	1.00	2965222	0.013	0.2	43	1.2	1.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	9.05	10.05	1.00	2965223	0.026	0.1	44	1.7	1.4
MC-DDH-003	10.05	11.05	1.00	2965224	0.148	0.2	117	0.6	1.3
MC-DDH-003	11.05	12.05	1.00	2965226	0.199	0.2	47	0.8	2.0
MC-DDH-003	12.05	13.05	1.00	2965227	0.184	2.5	61	0.8	2.3
MC-DDH-003	13.05	14.05	1.00	2965228	0.127	0.7	33	3.1	2.8
MC-DDH-003	14.05	15.05	1.00	2965229	0.081	9.2	31	2.7	6.3
MC-DDH-003	15.05	16.05	1.00	2965230	0.169	3.5	16	1.7	3.7
MC-DDH-003	16.05	17.05	1.00	2965231	0.022	0.5	29	6.1	2.7
MC-DDH-003	17.05	18.05	1.00	2965232	0.031	0.4	58	170.4	32.6
MC-DDH-003	19.05	20.05	1.00	2965235	0.014	0.7	74	4.6	105.0
MC-DDH-003	20.05	21.05	1.00	2965236	0.005	0.1	67	1.8	65.2
MC-DDH-003	21.05	22.05	1.00	2965237	0.010	0.1	90	18.4	64.3
MC-DDH-003	22.05	23.05	1.00	2965238	0.028	1.8	49	0.9	4.1
MC-DDH-003	23.05	24.05	1.00	2965239	0.012	0.9	14	0.2	1.0
MC-DDH-003	24.05	25.05	1.00	2965240	0.010	0.1	22	0.2	1.6
MC-DDH-003	25.05	26.05	1.00	2965241	0.055	0.1	18	0.2	0.9
MC-DDH-003	26.05	27.05	1.00	2965243	0.045	0.2	25	0.2	1.3
MC-DDH-003	27.05	28.05	1.00	2965244	0.005	0.1	7	0.1	0.6
MC-DDH-003	28.05	29.05	1.00	2965245	0.251	2.2	75	0.8	3.7
MC-DDH-003	29.05	30.05	1.00	2965246	0.020	0.4	26	0.5	3.4
MC-DDH-003	30.05	31.05	1.00	2965247	0.021	1.3	20	0.5	3.4
MC-DDH-003	31.05	32.05	1.00	2965248	0.065	2.7	65	0.8	8.4
MC-DDH-003	32.05	33.05	1.00	2965249	0.063	0.1	192	0.8	6.4
MC-DDH-003	33.05	34.05	1.00	2965250	0.086	11.1	119	1.2	9.7
MC-DDH-003	34.05	35.05	1.00	2965252	0.088	0.5	71	1.3	4.5
MC-DDH-003	35.05	36.05	1.00	2965253	0.171	0.1	68	1.2	2.1
MC-DDH-003	36.05	37.05	1.00	2965254	1.412	0.2	66	0.4	4.2
MC-DDH-003	37.05	38.05	1.00	2965255	0.560	0.1	50	0.4	2.7
MC-DDH-003	38.05	39.05	1.00	2965256	0.495	0.2	63	0.4	5.0
MC-DDH-003	39.05	40.05	1.00	2965257	0.372	0.1	70	0.2	3.0
MC-DDH-003	40.05	41.05	1.00	2965258	0.177	0.1	65	0.4	10.7
MC-DDH-003	41.05	42.05	1.00	2965259	2.247	0.3	61	0.4	20.0
MC-DDH-003	42.05	43.05	1.00	2965261	1.464	0.1	45	0.1	3.2
MC-DDH-003	43.05	44.05	1.00	2965262	2.957	0.2	38	0.2	2.3
MC-DDH-003	44.05	45.05	1.00	2965263	3.585	0.3	53	0.2	2.5
MC-DDH-003	45.05	46.05	1.00	2965264	5.225	0.5	45	0.1	2.1
MC-DDH-003	46.05	47.05	1.00	2965265	2.840	0.3	43	0.2	2.4
MC-DDH-003	48.05	49.05	1.00	2965268	3.688	0.5	38	0.2	7.5
MC-DDH-003	49.05	50.05	1.00	2965269	1.255	0.4	57	0.5	137.5
MC-DDH-003	50.05	51.05	1.00	2965270	4.322	0.5	49	0.2	4.3
MC-DDH-003	51.05	52.05	1.00	2965271	8.266	0.5	60	0.2	3.4
MC-DDH-003	52.05	53.05	1.00	2965272	10.000	0.8	33	0.2	2.7
MC-DDH-003	53.05	54.05	1.00	2965274	10.000	1.3	95	1.4	7.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	54.05	55.05	1.00	2965275	6.391	0.6	33	1.4	9.6
MC-DDH-003	55.05	56.05	1.00	2965276	0.859	0.1	25	2.0	4.2
MC-DDH-003	56.05	57.05	1.00	2965277	10.000	0.8	38	0.9	6.8
MC-DDH-003	57.05	58.05	1.00	2965278	6.909	0.5	18	0.5	4.2
MC-DDH-003	59.05	60.05	1.00	2965281	6.549	0.5	19	1.6	8.9
MC-DDH-003	60.05	61.05	1.00	2965282	0.743	0.1	22	2.4	19.8
MC-DDH-003	61.05	62.05	1.00	2965283	3.931	0.4	18	1.6	18.2
MC-DDH-003	62.05	63.05	1.00	2965284	3.780	0.3	23	1.3	10.2
MC-DDH-003	63.05	64.05	1.00	2965285	1.338	0.1	27	1.3	14.7
MC-DDH-003	64.05	65.05	1.00	2965286	0.428	0.1	19	2.2	34.4
MC-DDH-003	65.05	66.05	1.00	2965288	0.373	0.2	10	1.0	57.0
MC-DDH-003	66.05	67.05	1.00	2965289	0.013	0.1	5	0.1	69.8
MC-DDH-003	67.05	68.05	1.00	2965290	0.025	0.1	6	0.5	63.2
MC-DDH-003	68.05	69.05	1.00	2965291	0.806	0.4	56	1.8	37.8
MC-DDH-003	69.05	70.05	1.00	2965292	1.398	0.4	33	1.1	39.7
MC-DDH-003	70.05	71.05	1.00	2965293	1.359	0.5	31	1.1	31.6
MC-DDH-003	71.05	72.05	1.00	2965294	0.615	0.7	38	1.3	17.6
MC-DDH-003	72.05	73.05	1.00	2965296	0.891	0.4	38	1.5	11.0
MC-DDH-003	73.05	74.05	1.00	2965297	0.336	0.1	27	1.7	4.8
MC-DDH-003	74.05	75.05	1.00	2965298	0.862	0.2	19	2.0	14.4
MC-DDH-003	75.05	76.05	1.00	2965300	1.590	0.3	24	2.2	7.8
MC-DDH-003	76.05	77.05	1.00	2965301	0.719	0.2	27	1.3	6.8
MC-DDH-003	77.05	78.05	1.00	2965302	0.730	0.4	38	1.1	12.3
MC-DDH-003	78.05	79.05	1.00	2965303	1.934	0.5	16	0.7	7.8
MC-DDH-003	79.05	80.05	1.00	2965304	1.189	0.3	30	0.6	4.1
MC-DDH-003	80.05	81.05	1.00	2965305	0.704	0.6	144	1.8	20.9
MC-DDH-003	81.05	82.05	1.00	2965307	1.201	0.4	18	0.6	12.7
MC-DDH-003	82.05	83.05	1.00	2965308	0.596	0.3	24	0.9	6.0
MC-DDH-003	83.05	84.05	1.00	2965309	1.179	0.5	17	0.9	4.2
MC-DDH-003	84.05	85.05	1.00	2965310	0.394	0.5	71	0.5	13.8
MC-DDH-003	85.05	86.05	1.00	2965311	0.047	0.1	17	0.3	5.4
MC-DDH-003	86.05	87.05	1.00	2965312	0.107	0.2	36	0.8	17.9
MC-DDH-003	87.05	88.05	1.00	2965313	0.196	0.3	92	0.8	48.6
MC-DDH-003	88.05	89.05	1.00	2965314	0.166	0.5	126	1.5	59.9
MC-DDH-003	89.05	90.05	1.00	2965315	0.145	0.3	120	0.3	37.8
MC-DDH-003	90.05	91.05	1.00	2965317	0.134	0.3	104	0.6	37.1
MC-DDH-003	91.05	92.05	1.00	2965318	0.145	0.4	127	0.5	32.6
MC-DDH-003	92.05	93.05	1.00	2965319	0.107	0.2	91	0.5	39.7
MC-DDH-003	93.05	94.05	1.00	2965320	0.209	0.8	206	0.6	47.9
MC-DDH-003	94.05	95.05	1.00	2965321	0.007	0.1	2	0.2	1.6
MC-DDH-003	95.05	96.05	1.00	2965323	0.020	0.1	5	0.1	3.7
MC-DDH-003	96.05	97.05	1.00	2965324	0.009	0.1	1	0.2	1.4
MC-DDH-003	97.05	98.05	1.00	2965325	0.024	0.1	1	0.1	1.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	98.05	99.05	1.00	2965326	0.022	0.1	4	0.1	1.9
MC-DDH-003	99.05	100.05	1.00	2965327	0.022	0.1	3	0.2	1.4
MC-DDH-003	100.05	101.05	1.00	2965328	0.016	0.1	1	0.2	1.6
MC-DDH-003	101.05	102.05	1.00	2965329	0.005	0.1	1	0.1	2.0
MC-DDH-003	102.05	103.05	1.00	2965330	0.006	0.1	4	0.1	2.3
MC-DDH-003	104.05	105.05	1.00	2965333	0.007	0.1	13	0.6	3.7
MC-DDH-003	105.05	106.05	1.00	2965334	0.009	0.1	3	0.6	10.8
MC-DDH-003	106.05	107.05	1.00	2965335	0.008	0.1	1	0.6	3.8
MC-DDH-003	107.05	108.05	1.00	2965336	0.005	0.1	1	1.1	8.5
MC-DDH-003	108.05	109.05	1.00	2965337	0.005	0.1	6	1.0	6.9
MC-DDH-003	109.05	110.05	1.00	2965338	0.005	0.1	2	0.7	4.9
MC-DDH-003	110.05	111.05	1.00	2965339	0.005	0.1	1	0.7	7.4
MC-DDH-003	111.05	112.05	1.00	2965341	0.005	0.1	1	0.6	3.9
MC-DDH-003	112.05	113.05	1.00	2965342	0.005	0.1	1	0.9	3.6
MC-DDH-003	113.05	114.05	1.00	2965343	0.007	0.1	8	0.7	3.7
MC-DDH-003	114.05	115.05	1.00	2965344	0.006	0.1	5	1.1	3.2
MC-DDH-003	115.05	116.05	1.00	2965345	0.005	0.1	18	1.7	2.2
MC-DDH-003	116.05	117.05	1.00	2965346	0.005	0.1	10	2.3	3.5
MC-DDH-003	117.05	118.05	1.00	2965347	0.007	0.1	16	2.1	3.1
MC-DDH-003	118.05	119.05	1.00	2965348	0.007	0.1	9	1.5	2.7
MC-DDH-003	120.05	121.05	1.00	2966502	0.010	0.1	10	1.5	4.2
MC-DDH-003	121.05	122.05	1.00	2966503	0.006	0.1	7	2.1	5.2
MC-DDH-003	122.05	123.05	1.00	2966504	0.005	0.1	8	1.8	4.5
MC-DDH-003	123.05	124.05	1.00	2966505	0.005	0.1	27	1.9	4.4
MC-DDH-003	124.05	125.05	1.00	2966506	0.006	0.1	12	2.2	4.0
MC-DDH-003	125.05	126.05	1.00	2966507	0.007	0.1	13	1.7	4.2
MC-DDH-003	126.05	127.05	1.00	2966509	0.014	0.2	26	2.5	16.2
MC-DDH-003	127.05	128.05	1.00	2966510	0.292	1.3	31	1.2	443.9
MC-DDH-003	128.05	129.05	1.00	2966511	0.201	1.6	89	10.7	369.7
MC-DDH-003	129.05	130.05	1.00	2966512	0.440	0.7	72	25.1	83.2
MC-DDH-003	130.05	131.05	1.00	2966513	0.026	0.2	290	71.9	52.7
MC-DDH-003	131.05	132.05	1.00	2966514	0.409	1.9	92	46.6	131.8
MC-DDH-003	132.05	133.05	1.00	2966516	0.030	0.5	51	131.8	109.2
MC-DDH-003	133.05	134.05	1.00	2966517	0.110	0.6	179	200.6	197.1
MC-DDH-003	134.05	135.05	1.00	2966518	0.020	0.1	330	91.1	29.0
MC-DDH-003	135.05	136.05	1.00	2966519	0.006	0.1	41	2.2	38.5
MC-DDH-003	137.05	138.05	1.00	2966522	0.007	0.1	19	3.7	45.1
MC-DDH-003	138.05	139.05	1.00	2966523	0.017	0.1	74	3.2	63.3
MC-DDH-003	139.05	140.05	1.00	2966524	0.011	0.1	30	1.4	62.4
MC-DDH-003	140.05	141.05	1.00	2966525	0.009	0.1	57	2.9	89.2
MC-DDH-003	141.05	142.05	1.00	2966526	0.009	0.1	33	3.5	77.6
MC-DDH-003	142.05	143.05	1.00	2966527	0.012	0.2	87	3.0	144.9
MC-DDH-003	143.05	144.05	1.00	2966529	0.011	0.2	41	3.2	54.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	144.05	145.05	1.00	2966530	0.008	0.1	22	1.3	29.3
MC-DDH-003	145.05	146.05	1.00	2966531	0.009	0.2	35	2.7	64.5
MC-DDH-003	146.05	147.05	1.00	2966532	0.013	0.3	45	2.6	155.8
MC-DDH-003	147.05	148.05	1.00	2966533	0.009	0.2	33	2.2	74.1
MC-DDH-003	148.05	149.05	1.00	2966534	0.010	0.1	54	2.3	58.2
MC-DDH-003	149.05	150.05	1.00	2966536	0.011	0.1	101	1.3	35.8
MC-DDH-003	150.05	151.05	1.00	2966537	0.013	0.1	37	1.1	77.7
MC-DDH-003	151.05	152.05	1.00	2966538	0.017	0.2	55	1.6	58.9
MC-DDH-003	152.05	153.05	1.00	2966539	0.010	0.1	27	1.9	16.4
MC-DDH-003	153.05	154.05	1.00	2966540	0.015	0.1	49	2.9	66.2
MC-DDH-003	154.05	155.05	1.00	2966541	0.051	0.4	72	3.9	81.0
MC-DDH-003	155.05	156.05	1.00	2966543	0.029	0.4	68	2.1	127.2
MC-DDH-003	156.05	157.05	1.00	2966544	0.012	0.2	87	1.9	114.4
MC-DDH-003	157.05	158.05	1.00	2966545	0.010	0.1	50	1.6	55.3
MC-DDH-003	158.05	159.05	1.00	2966546	0.012	0.1	15	1.8	73.6
MC-DDH-003	159.05	160.05	1.00	2966547	0.012	0.1	28	1.8	67.0
MC-DDH-003	161.05	162.05	1.00	2966550	0.016	0.1	60	1.1	44.7
MC-DDH-003	162.05	163.05	1.00	2966551	0.036	0.3	52	2.0	98.8
MC-DDH-003	163.05	164.05	1.00	2966552	0.244	0.6	159	4.7	126.5
MC-DDH-003	164.05	164.70	0.65	2966553	0.022	0.4	46	2.5	79.5
MC-DDH-004	6.05	7.05	1.00	2966555	0.298	6.3	221	5.2	33.8
MC-DDH-004	7.05	8.05	1.00	2966556	0.085	3.6	130	14.5	21.3
MC-DDH-004	8.05	9.05	1.00	2966557	0.031	4.1	93	11.8	12.3
MC-DDH-004	9.05	10.05	1.00	2966558	0.125	3.9	107	7.9	34.3
MC-DDH-004	10.05	11.05	1.00	2966559	10.000	9.7	518	23.8	3070.9
MC-DDH-004	11.05	12.05	1.00	2966560	2.070	16.3	250	5.3	6725.8
MC-DDH-004	12.05	13.05	1.00	2966561	0.570	6.5	139	6.2	445.1
MC-DDH-004	13.05	14.05	1.00	2966562	0.114	4.7	194	1.9	40.9
MC-DDH-004	14.05	15.05	1.00	2966563	0.114	3.1	49	1.2	24.6
MC-DDH-004	15.05	16.05	1.00	2966564	0.821	6.5	95	4.0	991.1
MC-DDH-004	16.05	17.05	1.00	2966566	0.092	10.6	229	23.1	100.3
MC-DDH-004	17.05	18.05	1.00	2966567	0.033	2.6	67	3.6	15.6
MC-DDH-004	18.05	19.05	1.00	2966568	0.025	1.3	77	2.1	6.5
MC-DDH-004	19.05	20.05	1.00	2966569	0.039	1.0	95	3.1	4.6
MC-DDH-004	20.05	21.05	1.00	2966570	0.104	1.7	132	6.1	4.1
MC-DDH-004	21.05	22.05	1.00	2966572	0.050	1.2	73	7.7	6.0
MC-DDH-004	22.05	23.05	1.00	2966573	0.020	0.6	31	2.6	2.9
MC-DDH-004	23.05	24.05	1.00	2966574	0.014	0.2	22	1.9	2.2
MC-DDH-004	24.05	25.05	1.00	2966575	0.011	0.3	28	2.7	2.7
MC-DDH-004	25.05	26.05	1.00	2966576	0.012	0.3	10	0.6	3.6
MC-DDH-004	26.05	27.05	1.00	2966578	0.012	0.1	8	0.1	1.6
MC-DDH-004	27.05	28.05	1.00	2966579	0.015	0.1	1	0.8	3.0
MC-DDH-004	28.05	29.05	1.00	2966580	0.048	0.2	24	1.0	2.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-004	29.05	30.05	1.00	2966581	0.015	0.1	2	0.2	1.8
MC-DDH-004	30.05	31.05	1.00	2966582	0.010	0.2	4	0.2	2.0
MC-DDH-004	31.05	32.05	1.00	2966584	0.010	0.4	7	0.3	4.7
MC-DDH-004	32.05	33.05	1.00	2966585	0.209	17.4	86	12.8	28.0
MC-DDH-004	33.05	34.05	1.00	2966586	0.091	4.8	68	4.8	12.6
MC-DDH-004	34.05	35.05	1.00	2966587	0.082	1.7	116	2.1	10.5
MC-DDH-004	36.05	36.60	0.55	2966590	0.056	1.1	61	1.3	8.4
MC-DDH-005	6.05	7.05	1.00	2966592	0.100	13.9	93	9.6	55.7
MC-DDH-005	7.05	8.05	1.00	2966593	0.080	12.8	119	8.7	40.7
MC-DDH-005	8.05	9.05	1.00	2966594	0.335	2.9	83	1.7	52.5
MC-DDH-005	9.05	10.05	1.00	2966595	0.101	2.1	53	1.1	21.0
MC-DDH-005	10.05	11.05	1.00	2966596	0.146	2.6	78	1.8	42.2
MC-DDH-005	11.05	12.05	1.00	2966597	0.061	5.2	49	1.0	19.7
MC-DDH-005	12.05	13.05	1.00	2966598	0.090	5.9	40	0.5	72.5
MC-DDH-005	13.05	14.05	1.00	2966599	0.035	0.3	25	0.6	8.8
MC-DDH-005	14.05	15.05	1.00	2966601	0.076	7.1	102	1.4	21.0
MC-DDH-005	15.05	16.05	1.00	2966602	0.152	7.6	78	3.0	27.1
MC-DDH-005	16.05	17.05	1.00	2966603	0.132	4.3	98	4.6	23.0
MC-DDH-005	17.05	18.05	1.00	2966604	0.067	15.5	77	2.9	70.8
MC-DDH-005	18.05	19.05	1.00	2966605	0.036	2.7	64	1.9	44.1
MC-DDH-005	19.05	20.05	1.00	2966606	0.728	2.4	208	0.7	38.6
MC-DDH-005	21.05	22.05	1.00	2966609	0.007	0.1	12	0.1	2.9
MC-DDH-005	22.05	23.05	1.00	2966610	0.008	0.1	13	0.2	2.6
MC-DDH-005	23.05	24.05	1.00	2966611	0.032	1.7	62	2.4	4.1
MC-DDH-005	24.05	25.05	1.00	2966612	0.019	1.1	25	0.9	6.9
MC-DDH-005	25.05	26.05	1.00	2966613	0.019	0.7	11	0.4	2.6
MC-DDH-005	26.05	27.05	1.00	2966615	0.015	13.8	20	2.5	24.7
MC-DDH-005	27.05	28.05	1.00	2966616	0.008	12.7	12	1.5	25.2
MC-DDH-005	28.05	29.05	1.00	2966617	0.009	0.7	18	1.8	2.7
MC-DDH-005	29.05	30.05	1.00	2966618	0.012	2.2	8	0.9	4.4
MC-DDH-005	30.05	31.05	1.00	2966619	0.014	1.8	13	0.7	1.9
MC-DDH-005	32.05	33.05	1.00	2966622	0.245	2.3	124	1.5	6.4
MC-DDH-005	33.05	34.05	1.00	2966623	0.266	5.6	68	2.2	10.2
MC-DDH-005	34.05	35.05	1.00	2966624	0.273	34.4	89	7.2	59.1
MC-DDH-005	35.05	36.05	1.00	2966625	0.216	19.2	128	9.5	18.3
MC-DDH-005	36.05	37.05	1.00	2966626	0.020	6.4	34	1.2	15.4
MC-DDH-005	37.05	38.05	1.00	2966627	0.017	0.2	13	0.3	3.3
MC-DDH-005	38.05	39.05	1.00	2966628	0.015	0.1	8	0.1	1.5
MC-DDH-005	39.05	40.05	1.00	2966630	0.087	0.3	127	0.8	4.3
MC-DDH-005	40.05	41.05	1.00	2966631	0.005	0.1	4	0.1	0.9
MC-DDH-005	41.05	42.05	1.00	2966632	0.182	0.3	20	0.2	4.1
MC-DDH-005	42.05	43.05	1.00	2966633	0.028	0.1	6	0.1	1.2
MC-DDH-005	43.05	44.05	1.00	2966634	0.007	0.2	3	0.1	0.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	44.05	45.05	1.00	2966635	0.021	0.1	19	0.1	1.9
MC-DDH-005	45.05	46.05	1.00	2966637	0.022	0.1	23	0.2	14.8
MC-DDH-005	46.05	47.05	1.00	2966638	0.005	0.1	16	0.1	2.9
MC-DDH-005	47.05	48.05	1.00	2966639	0.005	0.1	11	0.1	0.9
MC-DDH-005	48.05	49.05	1.00	2966640	0.005	0.1	6	0.1	0.5
MC-DDH-005	49.05	50.05	1.00	2966641	0.005	0.1	9	0.1	0.5
MC-DDH-005	50.05	51.05	1.00	2966643	0.005	0.1	6	0.1	1.6
MC-DDH-005	51.05	52.05	1.00	2966644	0.016	0.1	10	0.1	1.9
MC-DDH-005	52.05	53.05	1.00	2966645	0.021	0.1	15	0.2	1.8
MC-DDH-005	53.05	54.05	1.00	2966646	0.057	0.2	41	0.1	0.7
MC-DDH-005	54.05	55.05	1.00	2966647	0.043	0.1	25	0.1	0.7
MC-DDH-005	55.05	56.05	1.00	2966648	0.055	0.2	7	0.1	11.6
MC-DDH-005	57.05	58.05	1.00	2966651	0.009	0.1	5	0.6	6.9
MC-DDH-005	58.05	59.05	1.00	2966652	0.077	0.2	20	0.3	15.0
MC-DDH-005	59.05	60.05	1.00	2966653	0.213	0.2	19	0.1	4.9
MC-DDH-005	60.05	61.05	1.00	2966654	0.151	0.2	19	0.1	1.0
MC-DDH-005	61.05	62.05	1.00	2966655	0.258	0.2	14	0.2	7.0
MC-DDH-005	62.05	63.05	1.00	2966656	0.153	0.5	42	0.2	8.0
MC-DDH-005	63.05	64.05	1.00	2966658	0.021	0.2	10	0.2	7.8
MC-DDH-005	64.05	65.05	1.00	2966659	0.052	0.2	30	0.1	10.1
MC-DDH-005	65.05	66.05	1.00	2966660	0.081	0.2	23	0.1	5.2
MC-DDH-005	66.05	67.05	1.00	2966661	0.169	0.4	50	0.2	5.0
MC-DDH-005	67.05	68.05	1.00	2966662	0.579	0.6	70	0.1	2.3
MC-DDH-005	68.05	69.05	1.00	2966663	0.012	0.2	36	0.1	4.2
MC-DDH-005	69.05	70.05	1.00	2966665	0.022	0.1	26	0.1	4.4
MC-DDH-005	70.05	71.05	1.00	2966666	0.008	0.1	28	0.1	1.9
MC-DDH-005	71.05	72.05	1.00	2966667	0.132	1.1	53	0.3	16.6
MC-DDH-005	72.05	73.05	1.00	2966668	0.138	2.9	72	0.5	30.3
MC-DDH-005	73.05	74.05	1.00	2966669	0.063	0.7	64	0.2	8.5
MC-DDH-005	74.05	75.05	1.00	2966670	0.158	0.7	173	0.7	17.7
MC-DDH-005	75.05	76.05	1.00	2966672	0.164	0.8	112	1.8	22.2
MC-DDH-005	76.05	77.05	1.00	2966673	0.115	0.4	84	3.2	17.1
MC-DDH-005	77.05	78.05	1.00	2966674	0.068	0.3	71	3.4	4.2
MC-DDH-005	78.05	79.05	1.00	2966675	0.044	0.3	57	2.5	7.8
MC-DDH-005	79.05	80.05	1.00	2966676	0.060	0.2	64	0.5	9.2
MC-DDH-005	80.05	81.05	1.00	2966677	0.005	0.1	13	0.2	0.8
MC-DDH-005	81.05	82.05	1.00	2966678	0.013	0.1	15	0.1	0.5
MC-DDH-005	83.05	84.05	1.00	2966681	0.030	1.1	28	0.2	2.1
MC-DDH-005	84.05	85.05	1.00	2966682	0.062	0.5	50	0.3	6.9
MC-DDH-005	85.05	86.05	1.00	2966683	0.044	0.3	22	0.1	1.8
MC-DDH-005	86.05	87.05	1.00	2966684	0.376	0.8	37	0.4	3.0
MC-DDH-005	87.05	88.05	1.00	2966685	0.243	8.8	73	0.5	19.4
MC-DDH-005	88.05	89.05	1.00	2966686	0.083	1.0	162	0.9	27.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	89.05	90.05	1.00	2966688	0.103	5.0	76	0.9	22.7
MC-DDH-005	90.05	91.05	1.00	2966689	0.093	2.4	63	1.0	11.7
MC-DDH-005	91.05	92.05	1.00	2966690	0.214	4.7	136	1.5	11.1
MC-DDH-005	92.05	93.05	1.00	2966691	0.024	0.2	20	0.2	1.2
MC-DDH-005	93.05	94.05	1.00	2966692	0.097	0.5	65	0.2	2.6
MC-DDH-005	94.05	95.05	1.00	2966693	0.098	1.8	39	0.3	2.6
MC-DDH-005	95.05	96.05	1.00	2966694	0.283	1.5	116	1.5	29.9
MC-DDH-005	96.05	97.05	1.00	2966696	0.753	2.1	513	5.4	159.1
MC-DDH-005	97.05	98.05	1.00	2966697	0.051	0.3	19	0.2	10.1
MC-DDH-005	98.05	99.05	1.00	2966698	0.042	0.3	14	0.1	9.3
MC-DDH-005	99.05	100.05	1.00	2966699	0.096	0.4	85	0.4	20.1
MC-DDH-005	100.05	101.05	1.00	2966700	0.158	0.4	24	0.7	16.9
MC-DDH-005	101.05	102.05	1.00	2966701	0.128	0.5	46	0.7	30.4
MC-DDH-005	102.05	103.05	1.00	2966702	0.016	0.3	19	0.6	14.8
MC-DDH-005	104.05	105.05	1.00	2966705	0.279	1.2	164	1.2	31.9
MC-DDH-005	105.05	106.05	1.00	2966706	0.070	0.3	35	0.2	10.2
MC-DDH-005	106.05	107.05	1.00	2966708	0.036	0.3	35	0.2	3.7
MC-DDH-005	107.05	108.05	1.00	2966709	0.076	0.8	72	4.1	31.5
MC-DDH-005	108.05	109.05	1.00	2966710	0.129	4.5	27	1.3	29.5
MC-DDH-005	109.05	110.05	1.00	2966711	0.136	1.8	53	2.5	64.2
MC-DDH-005	110.05	111.05	1.00	2966712	0.550	3.8	197	5.4	39.4
MC-DDH-005	111.05	112.05	1.00	2966714	0.136	1.2	56	1.9	12.2
MC-DDH-005	112.05	113.05	1.00	2966715	0.020	1.2	12	1.5	26.7
MC-DDH-005	113.05	114.05	1.00	2966716	0.005	-0.1	3	0.2	10.0
MC-DDH-005	114.05	115.05	1.00	2966717	0.016	0.2	12	0.3	23.4
MC-DDH-005	115.05	116.05	1.00	2966718	0.016	0.1	13	0.8	33.2
MC-DDH-005	116.05	117.05	1.00	2966719	0.001	-0.1	2	0.9	26.0
MC-DDH-005	118.05	119.05	1.00	2966722	0.001	-0.1	1	0.1	7.7
MC-DDH-005	119.05	120.05	1.00	2966723	0.001	-0.1	2	0.3	8.2
MC-DDH-005	120.05	121.05	1.00	2966724	0.005	-0.1	2	0.2	13.7
MC-DDH-005	121.05	122.05	1.00	2966725	0.001	-0.1	3	0.2	5.6
MC-DDH-005	122.05	123.05	1.00	2966726	0.001	-0.1	2	0.2	13.2
MC-DDH-005	123.05	124.05	1.00	2966727	0.001	-0.1	-1	0.2	13.4
MC-DDH-005	124.05	125.05	1.00	2966728	0.001	-0.1	1	0.1	8.3
MC-DDH-005	125.05	126.05	1.00	2966730	0.006	-0.1	2	0.3	27.6
MC-DDH-005	126.05	127.05	1.00	2966731	0.001	-0.1	-1	0.2	6.7
MC-DDH-005	127.05	128.05	1.00	2966732	0.007	-0.1	5	0.2	20.0
MC-DDH-005	128.05	129.05	1.00	2966733	0.009	-0.1	9	0.2	10.8
MC-DDH-005	129.05	130.05	1.00	2966734	0.001	-0.1	1	0.5	19.0
MC-DDH-005	130.05	131.05	1.00	2966735	0.001	-0.1	1	2.3	24.8
MC-DDH-005	131.05	132.05	1.00	2966736	0.010	-0.1	4	1.6	9.3
MC-DDH-005	132.05	133.05	1.00	2966738	0.006	-0.1	5	0.7	14.0
MC-DDH-005	133.05	134.05	1.00	2966739	0.006	-0.1	-1	0.8	17.7

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	134.05	135.05	1.00	2966740	0.012	0.1	5	0.8	10.1
MC-DDH-005	135.05	136.05	1.00	2966741	0.007	-0.1	2	0.4	7.5
MC-DDH-005	136.05	137.05	1.00	2966742	0.001	-0.1	2	0.3	35.8
MC-DDH-005	137.05	138.05	1.00	2966743	0.019	0.2	13	0.4	21.2
MC-DDH-005	138.05	139.05	1.00	2966745	0.009	-0.1	5	0.4	29.6
MC-DDH-005	139.05	140.05	1.00	2966746	0.016	0.1	7	2.4	67.1
MC-DDH-005	140.05	141.05	1.00	2966747	0.001	-0.1	-1	0.2	13.6
MC-DDH-005	141.05	142.05	1.00	2966748	0.001	-0.1	1	0.4	18.9
MC-DDH-005	143.05	144.05	1.00	2966751	0.001	-0.1	-1	1.2	17.2
MC-DDH-005	144.05	145.05	1.00	2966752	0.007	-0.1	6	1.2	31.6
MC-DDH-005	145.05	146.05	1.00	2966753	0.877	0.4	39	0.5	11.5
MC-DDH-005	146.05	147.05	1.00	2966754	0.918	1.6	30	0.1	3.3
MC-DDH-005	147.05	148.05	1.00	2966756	0.515	0.4	17	0.2	2.3
MC-DDH-005	148.05	149.05	1.00	2966757	1.704	1.4	65	0.2	3.5
MC-DDH-005	149.05	150.05	1.00	2966758	1.661	2.7	28	0.1	2.1
MC-DDH-005	150.05	151.05	1.00	2966759	0.071	2.2	1	0.5	2.8
MC-DDH-005	151.05	152.05	1.00	2966760	2.014	0.9	46	0.2	5.8
MC-DDH-005	152.05	153.05	1.00	2966761	1.385	1.6	49	0.3	10.9
MC-DDH-005	153.05	154.05	1.00	2966763	0.087	0.8	6	0.8	3.0
MC-DDH-005	154.05	155.05	1.00	2966764	0.372	6.6	8	0.5	1.9
MC-DDH-005	155.05	156.05	1.00	2966765	5.948	9.4	19	0.2	2.2
MC-DDH-005	156.05	157.05	1.00	2966766	0.456	1.5	18	0.1	1.5
MC-DDH-005	157.05	158.05	1.00	2966767	3.674	2.5	11	0.1	0.7
MC-DDH-005	158.05	159.05	1.00	2966768	5.264	5.9	9	0.3	1.2
MC-DDH-005	159.05	160.05	1.00	2966769	9.379	3.1	26	0.1	1.9
MC-DDH-005	160.05	161.05	1.00	2966771	4.273	3.4	39	0.2	4.8
MC-DDH-005	161.05	162.05	1.00	2966772	1.619	3.0	23	0.2	6.2
MC-DDH-005	162.05	163.05	1.00	2966773	1.495	4.4	33	0.1	2.2
MC-DDH-005	163.05	164.05	1.00	2966774	1.543	2.1	26	0.2	2.1
MC-DDH-005	164.05	165.05	1.00	2966775	1.284	1.8	27	0.2	2.8
MC-DDH-005	165.05	166.05	1.00	2966776	1.058	1.8	45	0.2	2.5
MC-DDH-005	166.05	167.05	1.00	2966777	1.286	1.4	20	0.1	3.9
MC-DDH-005	167.05	168.05	1.00	2966779	1.618	2.6	59	0.3	5.1
MC-DDH-005	168.05	169.05	1.00	2966780	0.062	0.5	8	0.3	2.7
MC-DDH-005	169.05	170.05	1.00	2966781	0.013	-0.1	1	-0.1	2.1
MC-DDH-005	170.05	171.05	1.00	2966782	0.028	-0.1	3	-0.1	3.3
MC-DDH-005	171.05	172.05	1.00	2966783	0.007	-0.1	8	-0.1	3.1
MC-DDH-005	172.05	173.05	1.00	2966784	0.007	-0.1	2	-0.1	2.6
MC-DDH-005	174.05	175.05	1.00	2966787	0.006	-0.1	7	-0.1	5.4
MC-DDH-005	175.05	176.05	1.00	2966788	0.001	-0.1	3	-0.1	3.0
MC-DDH-005	176.05	177.05	1.00	2966789	0.027	-0.1	-1	-0.1	3.7
MC-DDH-005	177.05	178.05	1.00	2966790	0.006	-0.1	-1	0.1	36.3
MC-DDH-005	178.05	179.05	1.00	2966791	0.007	-0.1	3	-0.1	13.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	179.05	180.05	1.00	2966792	0.007	-0.1	2	-0.1	6.5
MC-DDH-005	180.05	181.05	1.00	2966794	0.012	-0.1	6	-0.1	4.1
MC-DDH-005	181.05	182.05	1.00	2966795	0.009	-0.1	8	0.1	2.3
MC-DDH-005	182.05	183.05	1.00	2966796	0.012	-0.1	15	0.1	21.6
MC-DDH-005	183.05	184.05	1.00	2966797	0.011	-0.1	-1	-0.1	4.6
MC-DDH-005	184.05	185.05	1.00	2966798	0.010	-0.1	3	-0.1	5.7
MC-DDH-005	185.05	186.05	1.00	2966799	0.016	-0.1	3	-0.1	6.3
MC-DDH-005	187.05	188.05	1.00	2966802	0.007	-0.1	-1	-0.1	5.5
MC-DDH-005	188.05	189.05	1.00	2966803	0.011	-0.1	-1	-0.1	1.9
MC-DDH-006	3.05	4.05	1.00	2966805	0.090	2.8	40	0.9	6.9
MC-DDH-006	4.05	5.05	1.00	2966806	0.051	1.9	48	1.0	7.2
MC-DDH-006	5.05	6.05	1.00	2966807	0.013	2.6	11	0.2	4.7
MC-DDH-006	6.05	7.05	1.00	2966808	0.056	0.3	37	0.3	35.3
MC-DDH-006	7.05	8.05	1.00	2966809	0.065	2.2	58	0.6	42.7
MC-DDH-006	8.05	9.05	1.00	2966810	0.051	2.5	17	0.4	14.7
MC-DDH-006	9.05	10.05	1.00	2966811	0.016	0.9	20	0.3	9.8
MC-DDH-006	10.05	11.05	1.00	2966812	0.052	3.3	21	0.3	11.7
MC-DDH-006	11.05	12.05	1.00	2966814	0.109	1.7	25	0.4	39.7
MC-DDH-006	12.05	13.05	1.00	2966815	0.075	2.6	45	0.3	47.2
MC-DDH-006	13.05	14.05	1.00	2966816	0.020	0.7	44	0.3	9.0
MC-DDH-006	14.05	15.05	1.00	2966817	0.012	0.3	14	0.2	7.1
MC-DDH-006	15.05	16.05	1.00	2966818	0.001	-0.1	5	-0.1	0.4
MC-DDH-006	16.05	17.05	1.00	2966819	0.001	-0.1	4	-0.1	0.2
MC-DDH-006	17.05	18.05	1.00	2966820	0.001	-0.1	5	-0.1	0.3
MC-DDH-006	19.05	20.05	1.00	2966823	0.012	0.1	10	0.1	3.7
MC-DDH-006	20.05	21.05	1.00	2966824	0.012	-0.1	4	0.1	3.0
MC-DDH-006	21.05	22.05	1.00	2966825	0.001	-0.1	4	0.1	0.3
MC-DDH-006	22.05	23.05	1.00	2966826	0.019	0.2	26	0.3	1.2
MC-DDH-006	23.05	24.05	1.00	2966827	0.020	0.1	24	0.6	0.9
MC-DDH-006	24.05	25.05	1.00	2966828	0.001	-0.1	9	0.1	0.7
MC-DDH-006	25.05	26.05	1.00	2966829	0.001	-0.1	5	0.1	0.9
MC-DDH-006	26.05	27.05	1.00	2966831	0.086	0.7	54	15.2	9.5
MC-DDH-006	27.05	28.05	1.00	2966832	0.108	0.7	72	20.3	8.5
MC-DDH-006	28.05	29.05	1.00	2966833	0.016	-0.1	15	0.5	18.5
MC-DDH-006	29.05	30.05	1.00	2966834	0.008	-0.1	4	0.2	12.5
MC-DDH-006	30.05	31.05	1.00	2966835	0.006	-0.1	10	0.1	0.5
MC-DDH-006	31.05	32.05	1.00	2966836	0.005	-0.1	9	0.1	0.6
MC-DDH-006	32.05	33.05	1.00	2966837	0.019	0.1	30	10.7	3.0
MC-DDH-006	33.05	34.05	1.00	2966838	0.007	-0.1	22	0.1	3.4
MC-DDH-006	34.05	35.05	1.00	2966840	0.005	-0.1	28	0.1	2.8
MC-DDH-006	35.05	36.05	1.00	2966841	0.009	-0.1	24	-0.1	10.8
MC-DDH-006	36.05	37.05	1.00	2966842	0.011	0.2	18	0.5	5.7
MC-DDH-006	37.05	38.05	1.00	2966843	0.001	-0.1	27	-0.1	1.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	38.05	39.05	1.00	2966844	0.036	-0.1	55	-0.1	1.2
MC-DDH-006	39.05	40.05	1.00	2966845	0.015	0.1	24	0.2	1.8
MC-DDH-006	40.05	41.05	1.00	2966846	0.018	0.1	30	0.2	1.5
MC-DDH-006	41.05	42.05	1.00	2966847	0.001	0.1	16	0.1	0.8
MC-DDH-006	42.05	43.05	1.00	2966849	0.045	0.1	13	0.2	4.9
MC-DDH-006	43.05	44.05	1.00	2966850	0.011	-0.1	5	-0.1	2.5
MC-DDH-006	44.05	45.05	1.00	2966851	0.010	-0.1	13	0.1	20.7
MC-DDH-006	45.05	46.05	1.00	2966852	0.035	0.2	39	0.2	6.3
MC-DDH-006	46.05	47.05	1.00	2966853	0.889	2.3	31	0.3	2.1
MC-DDH-006	48.05	49.05	1.00	2966856	0.022	-0.1	17	0.1	5.0
MC-DDH-006	49.05	50.05	1.00	2966857	0.006	0.1	5	-0.1	2.2
MC-DDH-006	50.05	51.05	1.00	2966858	0.007	0.1	10	-0.1	2.8
MC-DDH-006	51.05	52.05	1.00	2966859	0.005	0.2	17	-0.1	0.7
MC-DDH-006	52.05	53.05	1.00	2966860	0.006	-0.1	8	-0.1	1.8
MC-DDH-006	53.05	54.05	1.00	2966862	0.008	-0.1	12	0.1	3.1
MC-DDH-006	54.05	55.05	1.00	2966863	0.023	-0.1	9	-0.1	0.9
MC-DDH-006	55.05	56.05	1.00	2966864	0.046	-0.1	24	0.1	6.4
MC-DDH-006	56.05	57.05	1.00	2966865	0.025	-0.1	5	0.1	9.3
MC-DDH-006	57.05	58.05	1.00	2966866	0.023	-0.1	6	-0.1	0.8
MC-DDH-006	59.05	60.05	1.00	2966869	0.292	0.9	42	0.1	1.4
MC-DDH-006	60.05	61.05	1.00	2966870	0.264	1.3	38	0.2	6.1
MC-DDH-006	61.05	62.05	1.00	2966871	0.078	0.6	46	0.3	1.1
MC-DDH-006	62.05	63.05	1.00	2966872	0.071	1.6	16	0.3	1.9
MC-DDH-006	63.05	64.05	1.00	2966873	0.291	2.3	23	0.4	1.3
MC-DDH-006	64.05	65.05	1.00	2966874	0.484	1.8	21	0.3	1.8
MC-DDH-006	65.05	66.05	1.00	2966876	0.432	4.9	55	1.9	6.2
MC-DDH-006	66.05	67.05	1.00	2966877	0.666	1.3	61	1.4	4.3
MC-DDH-006	67.05	68.05	1.00	2966878	0.601	0.8	28	0.6	3.5
MC-DDH-006	68.05	69.05	1.00	2966879	0.258	4.4	49	0.3	3.4
MC-DDH-006	69.05	70.05	1.00	2966880	0.347	2.4	112	1.2	6.1
MC-DDH-006	70.05	71.05	1.00	2966882	0.113	0.2	31	0.4	2.3
MC-DDH-006	71.05	72.05	1.00	2966883	0.118	1.7	33	2.3	5.5
MC-DDH-006	72.05	73.05	1.00	2966884	2.325	0.6	59	1.8	2.2
MC-DDH-006	73.05	74.05	1.00	2966885	0.910	1.5	38	0.2	21.7
MC-DDH-006	74.05	75.05	1.00	2966886	0.010	-0.1	4	0.4	2.1
MC-DDH-006	75.05	76.05	1.00	2966887	0.010	-0.1	-1	0.1	2.9
MC-DDH-006	76.05	77.05	1.00	2966888	0.008	-0.1	4	0.2	5.5
MC-DDH-006	78.05	79.05	1.00	2966891	0.006	-0.1	-1	0.2	2.0
MC-DDH-006	79.05	80.05	1.00	2966892	0.006	-0.1	2	0.1	1.9
MC-DDH-006	80.05	81.05	1.00	2966893	0.009	-0.1	-1	0.4	1.4
MC-DDH-006	81.05	82.05	1.00	2966894	0.011	-0.1	4	0.7	2.2
MC-DDH-006	82.05	83.05	1.00	2966895	0.016	0.2	7	0.9	5.1
MC-DDH-006	83.05	84.05	1.00	2966896	0.008	-0.1	-1	0.3	1.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	84.05	85.05	1.00	2966897	0.009	-0.1	5	1.2	4.2
MC-DDH-006	85.05	86.05	1.00	2966899	0.011	-0.1	10	0.8	4.6
MC-DDH-006	86.05	87.05	1.00	2966900	0.304	0.2	22	0.2	7.5
MC-DDH-006	87.05	88.05	1.00	2966901	0.129	0.9	67	0.2	3.3
MC-DDH-006	88.05	89.05	1.00	2966902	0.594	0.8	23	-0.1	12.7
MC-DDH-006	89.05	90.05	1.00	2966903	3.299	3.6	146	0.3	9.9
MC-DDH-006	90.05	91.05	1.00	2966904	0.057	0.3	13	-0.1	0.9
MC-DDH-006	91.05	92.05	1.00	2966905	0.039	0.3	72	0.4	3.8
MC-DDH-006	92.05	93.05	1.00	2966906	4.022	1.7	99	0.3	4.0
MC-DDH-006	93.05	94.05	1.00	2966908	1.208	4.3	14	0.3	6.4
MC-DDH-006	94.05	95.05	1.00	2966909	2.639	1.8	19	0.3	4.6
MC-DDH-006	95.05	96.05	1.00	2966910	3.183	3.0	29	0.3	6.7
MC-DDH-006	96.05	97.05	1.00	2966911	0.120	1.9	40	0.4	5.8
MC-DDH-006	97.05	98.05	1.00	2966912	0.061	1.0	24	0.4	3.2
MC-DDH-006	98.05	99.05	1.00	2966913	0.025	0.1	16	0.1	0.8
MC-DDH-006	99.05	100.05	1.00	2966914	0.018	0.4	14	0.2	0.9
MC-DDH-006	100.05	101.05	1.00	2966915	0.007	0.1	15	-0.1	1.2
MC-DDH-006	101.05	102.05	1.00	2966917	0.020	0.3	39	0.4	3.6
MC-DDH-006	102.05	103.05	1.00	2966918	0.006	0.6	17	6.5	5.7
MC-DDH-006	103.05	104.05	1.00	2966919	0.008	0.1	11	4.7	4.4
MC-DDH-006	104.05	105.05	1.00	2966920	0.005	0.4	20	5.2	192.4
MC-DDH-006	105.05	106.05	1.00	2966921	0.001	-0.1	21	4.0	62.4
MC-DDH-006	107.05	108.05	1.00	2966924	0.006	-0.1	28	2.4	9.8
MC-DDH-006	108.05	109.05	1.00	2966925	0.006	-0.1	38	12.9	9.6
MC-DDH-006	109.05	110.05	1.00	2966926	0.001	-0.1	22	6.8	5.8
MC-DDH-006	110.05	111.05	1.00	2966927	0.006	-0.1	27	7.4	11.5
MC-DDH-006	111.05	112.05	1.00	2966928	0.005	0.1	37	9.7	6.7
MC-DDH-006	112.05	113.05	1.00	2966930	0.007	-0.1	40	10.4	5.8
MC-DDH-006	113.05	114.05	1.00	2966931	0.001	-0.1	21	7.1	4.2
MC-DDH-006	114.05	115.05	1.00	2966932	0.001	-0.1	13	4.0	5.6
MC-DDH-006	115.05	116.05	1.00	2966933	0.005	-0.1	12	4.2	17.6
MC-DDH-006	116.05	117.05	1.00	2966934	0.010	-0.1	46	3.7	22.3
MC-DDH-006	118.05	119.05	1.00	2966937	0.008	0.8	75	7.6	71.2
MC-DDH-006	119.05	120.05	1.00	2966938	0.010	0.2	62	5.3	48.7
MC-DDH-006	120.05	121.05	1.00	2966939	0.012	0.3	62	13.4	78.6
MC-DDH-006	121.05	122.05	1.00	2966940	0.010	0.1	50	7.7	83.6
MC-DDH-006	122.05	123.05	1.00	2966941	0.013	-0.1	161	13.1	76.1
MC-DDH-006	123.05	124.05	1.00	2966942	0.010	0.1	48	18.9	50.4
MC-DDH-006	124.05	125.05	1.00	2966944	0.016	0.1	58	9.1	31.6
MC-DDH-006	125.05	126.05	1.00	2966945	0.013	0.1	102	8.2	29.1
MC-DDH-006	126.05	127.05	1.00	2966946	0.014	0.1	73	8.1	28.4
MC-DDH-006	127.05	128.05	1.00	2966947	0.009	-0.1	39	6.6	29.0
MC-DDH-006	128.05	129.05	1.00	2966948	0.009	0.1	42	13.6	31.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	129.05	130.05	1.00	2966950	0.007	0.1	57	11.1	63.9
MC-DDH-006	130.05	131.05	1.00	2966951	0.008	0.1	39	29.5	23.3
MC-DDH-006	131.05	132.05	1.00	2966952	0.007	-0.1	35	10.4	15.8
MC-DDH-006	132.05	133.05	1.00	2966953	0.015	0.2	70	22.5	168.9
MC-DDH-006	133.05	134.05	1.00	2966954	0.010	-0.1	39	6.0	28.0
MC-DDH-006	134.05	135.05	1.00	2966955	0.008	-0.1	37	9.4	4.7
MC-DDH-006	135.05	136.05	1.00	2966956	0.011	-0.1	42	4.3	7.8
MC-DDH-006	137.05	138.05	1.00	2966959	0.006	-0.1	21	1.8	4.5
MC-DDH-006	138.05	139.05	1.00	2966960	0.005	-0.1	19	9.0	11.0
MC-DDH-006	139.05	140.05	1.00	2966961	0.005	-0.1	21	31.4	6.4
MC-DDH-006	140.05	141.05	1.00	2966962	0.006	-0.1	24	18.1	3.0
MC-DDH-006	141.05	142.05	1.00	2966963	0.001	-0.1	18	1.6	2.9
MC-DDH-006	142.05	143.05	1.00	2966964	0.001	-0.1	11	0.9	2.2
MC-DDH-006	143.05	144.05	1.00	2966965	0.001	-0.1	10	2.1	3.7
MC-DDH-006	144.05	145.05	1.00	2966967	0.001	-0.1	6	1.1	2.6
MC-DDH-006	145.05	146.05	1.00	2966968	0.005	-0.1	13	6.3	22.8
MC-DDH-006	146.05	147.05	1.00	2966969	0.010	0.3	51	6.3	113.5
MC-DDH-006	147.05	148.05	1.00	2966970	0.011	0.3	56	4.6	146.5
MC-DDH-006	148.05	149.05	1.00	2966972	0.010	0.3	43	14.0	195.1
MC-DDH-006	149.05	150.05	1.00	2966973	0.010	0.2	34	10.2	58.8
MC-DDH-006	150.05	151.05	1.00	2966974	0.015	0.1	19	3.6	51.0
MC-DDH-006	151.05	152.05	1.00	2966975	0.005	-0.1	14	0.8	34.8
MC-DDH-006	152.05	153.05	1.00	2966976	0.001	-0.1	10	0.3	9.6
MC-DDH-006	153.05	154.05	1.00	2966977	0.008	-0.1	19	0.5	4.5
MC-DDH-006	154.05	155.05	1.00	2966979	0.001	-0.1	13	3.9	16.6
MC-DDH-006	155.05	156.05	1.00	2966980	0.006	-0.1	9	1.4	2.7
MC-DDH-006	156.05	157.05	1.00	2966981	0.001	-0.1	11	0.6	10.5
MC-DDH-006	157.05	158.05	1.00	2966982	0.001	0.5	7	0.6	4.7
MC-DDH-006	<b>158.05</b>	<b>159.05</b>	1.00	<b>2966983</b>	0.008	1.8	5	0.4	3.7
MC-DDH-006	<b>159.05</b>	<b>160.05</b>	1.00	<b>2966985</b>	0.019	0.1	14	1.4	6.4
MC-DDH-006	160.05	161.05	1.00	2966989	0.009	1.4	7	0.6	8.0
MC-DDH-006	161.05	162.05	1.00	2966990	0.001	0.3	5	0.9	3.9
MC-DDH-006	162.05	163.05	1.00	2966991	0.011	-0.1	14	1.4	2.5
MC-DDH-006	163.05	164.05	1.00	2966992	0.010	0.1	19	1.9	41.7
MC-DDH-006	164.05	165.05	1.00	2966994	0.010	-0.1	17	1.7	4.6
MC-DDH-006	165.05	166.05	1.00	2966995	0.005	0.6	14	2.8	2.4
MC-DDH-006	166.05	167.05	1.00	2966996	0.008	0.3	21	1.6	2.2
MC-DDH-006	167.05	168.05	1.00	2966997	0.007	-0.1	18	1.5	2.1
MC-DDH-006	168.05	169.05	1.00	2966998	0.006	-0.1	12	0.4	1.6
MC-DDH-006	170.05	171.05	1.00	3392002	0.009	-0.1	18	1.7	5.6
MC-DDH-006	171.05	172.05	1.00	3392003	0.006	-0.1	15	1.6	3.2
MC-DDH-006	172.05	173.05	1.00	3392004	0.009	-0.1	16	1.0	2.1
MC-DDH-006	173.05	174.05	1.00	3392005	0.001	-0.1	36	1.8	9.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	174.05	175.05	1.00	3392006	0.006	-0.1	43	1.7	9.6
MC-DDH-006	175.05	176.05	1.00	3392007	0.001	0.3	13	1.0	10.6
MC-DDH-006	176.05	177.05	1.00	3392009	0.005	0.8	13	1.0	19.0
MC-DDH-006	177.05	178.05	1.00	3392010	0.006	0.2	12	1.1	13.9
MC-DDH-006	178.05	179.05	1.00	3392011	0.001	-0.1	6	0.8	2.1
MC-DDH-006	179.05	180.05	1.00	3392012	0.001	-0.1	6	3.2	9.7
MC-DDH-006	180.05	181.05	1.00	3392013	0.001	-0.1	4	1.3	2.7
MC-DDH-006	181.05	182.05	1.00	3392014	0.001	-0.1	5	1.7	7.1
MC-DDH-006	182.05	183.05	1.00	3392016	0.001	-0.1	5	4.9	29.4
MC-DDH-006	183.05	184.05	1.00	3392017	0.001	-0.1	4	3.8	4.5
MC-DDH-006	184.05	185.05	1.00	3392018	0.001	0.1	4	0.6	6.2
MC-DDH-006	185.05	186.05	1.00	3392019	0.001	-0.1	9	3.1	28.4
MC-DDH-006	186.05	187.05	1.00	3392020	0.011	0.2	13	2.1	46.1
MC-DDH-006	187.05	188.05	1.00	3392021	0.001	0.2	2	1.1	21.4
MC-DDH-006	188.05	189.05	1.00	3392023	0.001	0.2	4	2.2	11.6
MC-DDH-006	189.05	190.05	1.00	3392024	0.001	0.1	10	1.5	27.2
MC-DDH-006	190.05	190.62	0.57	3392025	0.001	-0.1	11	1.7	17.0
MC-DDH-001	3.05	4.05	1.00	3392026	0.057	-0.1	76	1.3	17.9
MC-DDH-001	4.05	5.05	1.00	3392027	0.022	-0.1	33	0.8	19.3
MC-DDH-001	6.05	7.05	1.00	3392030	0.033	-0.1	54	1.3	16.9
MC-DDH-001	7.05	8.05	1.00	3392031	0.028	-0.1	52	1.1	19.8
MC-DDH-001	8.05	9.05	1.00	3392032	0.023	-0.1	25	0.4	32.2
MC-DDH-001	9.05	10.05	1.00	3392033	0.029	-0.1	17	0.2	21.8
MC-DDH-001	10.05	11.05	1.00	3392034	0.033	-0.1	36	0.7	15.4
MC-DDH-001	11.05	12.05	1.00	3392035	0.024	0.2	36	0.4	21.6
MC-DDH-001	12.05	13.05	1.00	3392037	0.027	0.1	32	1.0	25.5
MC-DDH-001	13.05	14.05	1.00	3392038	0.041	0.4	60	1.1	20.9
MC-DDH-001	14.05	15.05	1.00	3392039	0.102	2.2	56	3.7	70.1
MC-DDH-001	20.05	21.05	1.00	3392040	0.083	5.2	47	2.1	48.1
MC-DDH-001	21.05	22.05	1.00	3392041	0.038	0.3	40	0.8	13.3
MC-DDH-001	22.05	23.05	1.00	3392042	0.067	0.6	48	1.1	17.3
MC-DDH-001	23.05	24.05	1.00	3392044	0.038	0.2	38	0.9	19.5
MC-DDH-001	24.05	25.05	1.00	3392045	0.065	0.5	36	0.5	20.5
MC-DDH-001	25.05	26.05	1.00	3392046	0.032	0.2	16	0.3	14.9
MC-DDH-001	26.05	27.05	1.00	3392047	0.056	0.3	24	0.4	21.0
MC-DDH-001	27.05	28.05	1.00	3392048	0.021	0.1	24	0.5	20.3
MC-DDH-001	28.05	29.05	1.00	3392049	0.043	0.3	47	0.9	12.3
MC-DDH-001	29.05	30.05	1.00	3392051	0.039	0.3	26	1.3	25.6
MC-DDH-001	30.05	31.05	1.00	3392052	0.009	-0.1	5	0.7	38.4
MC-DDH-001	31.05	32.05	1.00	3392053	0.007	-0.1	4	0.3	17.4
MC-DDH-001	32.05	33.05	1.00	3392054	0.001	-0.1	3	0.3	15.9
MC-DDH-001	33.05	34.05	1.00	3392055	0.001	-0.1	1	0.3	13.7
MC-DDH-001	35.05	36.05	1.00	3392058	0.001	-0.1	1	0.1	11.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	36.05	37.05	1.00	3392059	0.017	0.1	15	0.8	17.9
MC-DDH-001	37.05	38.05	1.00	3392060	0.354	-0.1	15	0.4	17.4
MC-DDH-001	38.05	39.05	1.00	3392061	0.006	-0.1	5	0.3	17.7
MC-DDH-001	39.05	40.05	1.00	3392062	0.008	-0.1	16	0.6	27.8
MC-DDH-001	40.05	41.05	1.00	3392063	0.001	-0.1	2	0.1	18.6
MC-DDH-001	41.05	42.05	1.00	3392065	0.001	-0.1	-1	0.5	34.1
MC-DDH-001	42.05	43.05	1.00	3392066	0.010	-0.1	17	0.3	20.0
MC-DDH-001	43.05	44.05	1.00	3392067	0.001	-0.1	2	0.5	13.5
MC-DDH-001	44.05	45.05	1.00	3392068	0.001	-0.1	2	0.9	22.7
MC-DDH-001	45.05	46.05	1.00	3392069	0.001	-0.1	2	0.3	12.0
MC-DDH-001	46.05	47.05	1.00	3392070	0.022	0.2	21	0.7	24.5
MC-DDH-001	69.05	70.05	1.00	3392072	0.029	0.1	42	0.2	30.0
MC-DDH-001	70.05	71.05	1.00	3392073	0.005	-0.1	3	-0.1	39.6
MC-DDH-001	71.05	72.05	1.00	3392074	0.050	0.2	37	0.2	13.5
MC-DDH-001	72.05	73.05	1.00	3392075	0.071	0.5	56	0.2	38.4
MC-DDH-001	73.05	74.05	1.00	3392076	0.069	0.9	56	0.7	69.5
MC-DDH-001	74.05	75.05	1.00	3392077	0.054	-0.1	33	0.1	10.6
MC-DDH-001	75.05	76.05	1.00	3392079	0.018	-0.1	-1	0.2	74.3
MC-DDH-001	78.05	79.05	1.00	3392080	0.060	0.1	13	0.2	21.0
MC-DDH-001	79.05	80.05	1.00	3392081	0.009	-0.1	7	0.2	7.6
MC-DDH-001	80.05	81.05	1.00	3392082	0.008	-0.1	7	0.1	4.3
MC-DDH-001	88.05	89.05	1.00	3392083	0.008	-0.1	4	0.2	4.6
MC-DDH-001	90.05	91.05	1.00	3392086	0.001	-0.1	-1	0.2	8.8
MC-DDH-001	91.05	92.05	1.00	3392087	0.001	-0.1	6	0.1	4.9
MC-DDH-001	92.05	93.05	1.00	3392088	0.001	-0.1	3	0.1	2.7
MC-DDH-001	93.05	94.05	1.00	3392089	0.001	-0.1	-1	0.2	3.1
MC-DDH-001	94.05	95.05	1.00	3392090	0.001	-0.1	5	0.1	3.3
MC-DDH-001	95.05	96.05	1.00	3392091	0.017	0.1	12	0.3	21.2
MC-DDH-001	96.05	97.05	1.00	3392093	0.009	0.2	12	0.4	8.0
MC-DDH-001	97.05	98.05	1.00	3392094	0.021	0.1	21	0.4	13.4
MC-DDH-001	98.05	99.05	1.00	3392095	0.001	-0.1	5	-0.1	2.5
MC-DDH-001	99.05	100.05	1.00	3392096	0.001	-0.1	4	-0.1	2.1
MC-DDH-001	100.05	101.05	1.00	3392097	0.001	-0.1	2	-0.1	1.1
MC-DDH-001	101.05	102.05	1.00	3392098	0.001	-0.1	2	0.2	2.2
MC-DDH-001	102.05	103.05	1.00	3392100	0.001	-0.1	5	0.9	3.0
MC-DDH-001	103.05	104.05	1.00	3392101	0.001	-0.1	5	0.3	2.7
MC-DDH-001	104.05	105.05	1.00	3392102	0.001	-0.1	7	-0.1	1.9
MC-DDH-001	105.05	106.05	1.00	3392103	0.001	-0.1	2	1.0	3.6
MC-DDH-001	106.05	107.05	1.00	3392104	0.001	-0.1	4	-0.1	1.3
MC-DDH-001	107.05	108.05	1.00	3392105	0.001	-0.1	2	-0.1	0.7
MC-DDH-001	108.05	109.05	1.00	3392107	0.001	-0.1	5	0.1	2.2
MC-DDH-001	109.05	110.05	1.00	3392108	0.001	-0.1	-1	0.2	1.5
MC-DDH-001	110.05	111.05	1.00	3392109	0.001	-0.1	1	0.2	1.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	111.05	112.05	1.00	3392110	0.001	-0.1	9	0.2	2.4
MC-DDH-001	112.05	113.05	1.00	3392111	0.001	-0.1	16	0.1	1.5
MC-DDH-001	113.05	114.05	1.00	3392112	0.001	-0.1	3	-0.1	1.0
MC-DDH-001	114.05	115.05	1.00	3392114	0.001	-0.1	18	0.3	2.8
MC-DDH-001	115.05	116.05	1.00	3392115	0.001	-0.1	5	-0.1	1.1
MC-DDH-001	116.05	117.05	1.00	3392116	0.001	-0.1	24	-0.1	1.5
MC-DDH-001	117.05	118.05	1.00	3392117	0.001	-0.1	6	0.2	1.0
MC-DDH-001	118.05	119.05	1.00	3392118	0.001	-0.1	6	0.5	6.6
MC-DDH-001	120.05	121.05	1.00	3392121	0.001	-0.1	33	0.3	1.1
MC-DDH-001	121.05	122.05	1.00	3392122	0.001	-0.1	2	0.2	3.3
MC-DDH-001	122.05	123.05	1.00	3392123	0.001	-0.1	4	0.7	2.1
MC-DDH-001	123.05	124.05	1.00	3392124	0.001	-0.1	5	1.2	3.3
MC-DDH-001	124.05	125.05	1.00	3392125	0.001	-0.1	2	1.6	2.3
MC-DDH-001	125.05	126.05	1.00	3392126	0.001	-0.1	6	1.8	2.1
MC-DDH-001	126.05	127.05	1.00	3392128	0.001	-0.1	9	1.6	3.0
MC-DDH-001	127.05	128.05	1.00	3392129	0.001	-0.1	4	0.7	2.3
MC-DDH-001	128.05	129.05	1.00	3392130	0.001	-0.1	2	1.6	2.2
MC-DDH-001	129.05	130.05	1.00	3392131	0.001	-0.1	4	1.0	1.5
MC-DDH-001	130.05	131.05	1.00	3392132	0.001	-0.1	6	1.5	3.4
MC-DDH-001	131.05	132.05	1.00	3392133	0.007	-0.1	12	1.5	4.0
MC-DDH-001	132.05	133.05	1.00	3392135	0.001	-0.1	8	2.2	4.0
MC-DDH-001	133.05	134.05	1.00	3392136	0.006	-0.1	8	5.5	7.3
MC-DDH-001	134.05	135.05	1.00	3392137	0.006	-0.1	17	2.7	5.3
MC-DDH-001	135.05	136.05	1.00	3392138	0.001	-0.1	9	2.3	5.2
MC-DDH-001	136.05	137.05	1.00	3392139	0.006	-0.1	5	1.1	5.6
MC-DDH-001	137.05	138.05	1.00	3392140	0.001	-0.1	6	1.4	8.9
MC-DDH-001	138.05	139.05	1.00	3392142	0.008	-0.1	12	1.6	10.8
MC-DDH-001	139.05	140.05	1.00	3392143	0.006	-0.1	5	1.4	10.0
MC-DDH-001	140.05	141.05	1.00	3392144	0.008	-0.1	11	2.1	10.6
MC-DDH-001	141.05	142.05	1.00	3392145	0.007	0.2	22	2.3	6.8
MC-DDH-002	3.05	4.05	1.00	3392146	0.012	0.4	4	0.5	18.7
MC-DDH-002	5.05	6.05	1.00	3392149	0.010	0.1	6	0.2	17.9
MC-DDH-002	6.05	7.05	1.00	3392150	0.021	-0.1	5	0.3	23.5
MC-DDH-002	7.05	8.05	1.00	3392151	0.011	-0.1	3	0.5	29.6
MC-DDH-002	8.05	9.05	1.00	3392152	0.008	-0.1	6	0.6	22.1
MC-DDH-002	9.05	10.05	1.00	3392153	0.013	-0.1	11	0.4	25.0
MC-DDH-002	10.05	11.05	1.00	3392154	0.012	-0.1	7	1.5	20.9
MC-DDH-002	11.05	12.05	1.00	3392156	0.014	-0.1	5	0.4	20.6
MC-DDH-002	12.05	13.05	1.00	3392157	0.018	-0.1	6	0.6	23.8
MC-DDH-002	13.05	14.05	1.00	3392158	0.011	-0.1	6	0.3	19.6
MC-DDH-002	14.05	15.05	1.00	3392159	0.009	-0.1	6	0.3	14.7
MC-DDH-002	15.05	16.05	1.00	3392160	0.009	0.1	7	0.4	21.5
MC-DDH-002	16.05	17.05	1.00	3392161	0.017	0.1	9	0.2	11.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-002	17.05	18.05	1.00	3392163	0.010	0.1	6	0.2	6.6
MC-DDH-002	22.05	23.05	1.00	3392164	0.035	0.5	18	0.3	14.0
MC-DDH-002	23.05	24.05	1.00	3392165	0.005	-0.1	3	0.2	15.4
MC-DDH-002	24.05	25.05	1.00	3392166	0.008	-0.1	1	0.2	13.1
MC-DDH-002	25.05	26.05	1.00	3392167	0.006	-0.1	2	0.3	13.0
MC-DDH-002	26.05	27.05	1.00	3392168	0.001	-0.1	-1	1.1	24.9
MC-DDH-002	27.05	28.05	1.00	3392170	0.009	-0.1	5	0.2	14.5
MC-DDH-002	28.05	29.05	1.00	3392171	0.006	-0.1	-1	0.3	15.2
MC-DDH-002	29.05	30.05	1.00	3392172	0.008	-0.1	3	0.6	18.4
MC-DDH-002	30.05	31.05	1.00	3392173	0.006	-0.1	-1	0.5	30.1
MC-DDH-002	31.05	32.05	1.00	3392174	0.001	-0.1	-1	0.4	16.7
MC-DDH-002	33.05	34.05	1.00	3392177	0.043	0.3	30	0.8	28.4
MC-DDH-002	34.05	35.05	1.00	3392178	0.076	0.6	49	1.2	37.1
MC-DDH-002	35.05	36.05	1.00	3392179	0.021	0.2	18	1.3	54.2
MC-DDH-002	36.05	37.05	1.00	3392180	0.089	0.9	23	1.5	42.8
MC-DDH-002	37.05	38.05	1.00	3392181	0.032	0.4	27	1.8	30.3
MC-DDH-002	38.05	39.05	1.00	3392182	0.015	0.1	21	0.7	16.0
MC-DDH-002	39.05	40.05	1.00	3392184	0.011	-0.1	10	0.5	20.8
MC-DDH-002	40.05	41.05	1.00	3392185	0.053	0.4	67	1.5	24.8
MC-DDH-002	41.05	42.05	1.00	3392186	0.103	0.9	78	2.4	40.4
MC-DDH-002	42.05	43.05	1.00	3392187	0.072	0.3	77	3.1	17.6
MC-DDH-002	43.05	44.05	1.00	3392188	0.068	0.3	90	3.0	22.1
MC-DDH-002	44.05	45.05	1.00	3392189	0.029	0.1	53	1.4	16.8
MC-DDH-002	45.05	46.05	1.00	3392191	0.011	-0.1	24	0.8	22.3
MC-DDH-002	46.05	47.05	1.00	3392192	0.015	-0.1	21	0.4	16.9
MC-DDH-002	47.05	48.05	1.00	3392193	0.024	0.2	34	0.2	19.6
MC-DDH-002	48.05	49.05	1.00	3392194	0.044	0.7	33	0.9	31.7
MC-DDH-002	49.05	50.05	1.00	3392195	0.032	0.2	46	0.9	12.7
MC-DDH-002	50.05	51.05	1.00	3392196	0.076	0.4	67	3.5	11.1
MC-DDH-002	51.05	52.05	1.00	3392198	0.063	0.4	51	4.0	11.7
MC-DDH-002	71.05	72.05	1.00	3392199	0.036	0.2	20	3.0	3.9
MC-DDH-002	74.05	75.05	1.00	3392200	0.008	-0.1	-1	0.7	3.7
MC-DDH-002	75.05	76.05	1.00	3392201	0.012	-0.1	8	0.8	6.1
MC-DDH-002	78.05	79.05	1.00	3392202	0.023	0.1	4	0.7	5.9
MC-DDH-002	80.05	81.05	1.00	3392205	0.035	0.1	13	1.2	10.5
MC-DDH-002	81.05	82.05	1.00	3392206	0.015	-0.1	4	0.2	1.9
MC-DDH-002	82.05	83.05	1.00	3392207	0.013	-0.1	-1	0.9	1.9
MC-DDH-002	83.05	84.05	1.00	3392208	0.032	0.2	10	8.1	3.1
MC-DDH-002	84.05	85.05	1.00	3392209	0.013	-0.1	-1	1.1	2.9
MC-DDH-002	96.05	97.05	1.00	3392210	0.010	-0.1	3	0.6	2.1
MC-DDH-002	97.05	98.05	1.00	3392212	0.008	-0.1	7	0.4	3.0
MC-DDH-002	98.05	99.05	1.00	3392213	0.011	-0.1	7	1.1	5.4
MC-DDH-002	99.05	100.05	1.00	3392214	0.010	-0.1	6	0.4	2.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-002	100.05	101.05	1.00	3392215	0.005	-0.1	4	0.2	1.4
MC-DDH-002	101.05	102.05	1.00	3392216	0.008	-0.1	4	0.4	1.8
MC-DDH-002	102.05	103.05	1.00	3392217	0.006	-0.1	4	0.1	1.2
MC-DDH-002	103.05	104.05	1.00	3392219	0.006	-0.1	2	-0.1	3.7
MC-DDH-002	104.05	105.05	1.00	3392220	0.001	-0.1	6	-0.1	2.3
MC-DDH-007	3.05	4.05	1.00	3392222	0.141	1.8	84	4.0	46.8
MC-DDH-007	4.05	5.05	1.00	3392223	0.065	1.1	46	1.4	19.7
MC-DDH-007	5.05	6.05	1.00	3392224	0.113	2.4	85	3.2	50.0
MC-DDH-007	6.05	7.05	1.00	3392225	0.048	1.7	44	0.6	18.0
MC-DDH-007	7.05	8.05	1.00	3392226	0.050	1.4	43	0.5	4.6
MC-DDH-007	8.05	9.05	1.00	3392227	0.041	2.0	42	0.5	7.3
MC-DDH-007	9.05	10.05	1.00	3392229	0.070	4.0	23	0.4	10.0
MC-DDH-007	10.05	11.05	1.00	3392230	0.059	1.5	26	0.2	5.5
MC-DDH-007	11.05	12.05	1.00	3392231	0.103	2.2	57	0.5	6.8
MC-DDH-007	12.05	13.05	1.00	3392232	0.069	4.0	54	0.3	22.5
MC-DDH-007	13.05	14.05	1.00	3392233	0.126	7.3	135	2.0	56.1
MC-DDH-007	15.05	16.05	1.00	3392236	0.190	0.8	164	1.0	31.5
MC-DDH-007	16.05	17.05	1.00	3392237	0.056	0.4	88	1.8	37.7
MC-DDH-007	17.05	18.05	1.00	3392238	0.593	3.9	282	15.2	61.7
MC-DDH-007	18.05	19.05	1.00	3392239	0.181	1.7	125	14.1	14.4
MC-DDH-007	19.05	20.05	1.00	3392240	0.021	1.7	8	0.2	2.0
MC-DDH-007	20.05	21.05	1.00	3392241	0.016	-0.1	8	0.2	0.9
MC-DDH-007	21.05	22.05	1.00	3392243	0.020	0.2	26	0.2	1.6
MC-DDH-007	22.05	23.05	1.00	3392244	0.034	0.9	31	0.2	3.4
MC-DDH-007	23.05	24.05	1.00	3392245	0.050	0.5	121	0.7	1.0
MC-DDH-007	24.05	25.05	1.00	3392246	0.014	-0.1	60	2.5	1.9
MC-DDH-007	25.05	26.05	1.00	3392247	0.013	0.4	39	5.9	370.1
MC-DDH-007	26.05	27.05	1.00	3392248	0.120	4.0	55	20.9	13.6
MC-DDH-007	27.05	28.05	1.00	3392250	0.100	2.6	44	15.8	16.3
MC-DDH-007	28.05	29.05	1.00	3392251	0.154	1.9	68	1.4	22.8
MC-DDH-007	29.05	30.05	1.00	3392252	0.152	1.4	104	0.9	24.1
MC-DDH-007	30.05	31.05	1.00	3392253	0.213	3.1	161	1.2	24.0
MC-DDH-007	31.05	32.05	1.00	3392254	0.159	2.2	115	1.3	13.0
MC-DDH-007	32.05	33.05	1.00	3392255	0.142	3.0	106	7.8	15.8
MC-DDH-007	33.05	34.05	1.00	3392257	0.713	4.1	147	10.5	27.5
MC-DDH-007	34.05	35.05	1.00	3392258	2.974	14.3	69	2.7	50.2
MC-DDH-007	35.05	36.05	1.00	3392259	0.282	2.8	141	5.3	20.1
MC-DDH-007	36.05	37.05	1.00	3392260	0.296	4.3	92	27.4	24.9
MC-DDH-007	37.05	38.05	1.00	3392261	0.234	6.3	106	58.0	30.0
MC-DDH-007	39.05	40.05	1.00	3392264	0.033	0.2	22	2.8	15.5
MC-DDH-007	40.05	41.05	1.00	3392265	0.039	-0.1	15	1.0	3.6
MC-DDH-007	41.05	42.05	1.00	3392266	0.022	-0.1	16	1.8	15.8
MC-DDH-007	42.05	43.05	1.00	3392267	0.018	0.1	14	2.7	13.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	43.05	44.05	1.00	3392268	0.007	-0.1	3	4.3	2.4
MC-DDH-007	44.05	45.05	1.00	3392269	0.015	-0.1	7	1.6	3.5
MC-DDH-007	45.05	46.05	1.00	3392271	0.019	-0.1	12	1.9	4.7
MC-DDH-007	46.05	47.05	1.00	3392272	0.022	-0.1	16	1.4	3.4
MC-DDH-007	47.05	48.05	1.00	3392273	0.318	-0.1	76	0.6	2.0
MC-DDH-007	48.05	49.05	1.00	3392274	0.053	-0.1	18	0.5	2.3
MC-DDH-007	49.05	50.05	1.00	3392275	0.025	0.2	16	1.5	5.7
MC-DDH-007	50.05	51.05	1.00	3392276	0.029	0.5	22	1.0	8.0
MC-DDH-007	51.05	52.05	1.00	3392278	0.068	3.0	58	3.5	17.9
MC-DDH-007	52.05	53.05	1.00	3392279	0.052	1.2	36	0.2	8.0
MC-DDH-007	53.05	54.05	1.00	3392280	0.015	1.5	25	0.3	6.3
MC-DDH-007	54.05	55.05	1.00	3392281	0.017	0.3	18	0.2	10.5
MC-DDH-007	55.05	56.05	1.00	3392282	0.039	0.5	43	-0.1	14.7
MC-DDH-007	56.05	57.05	1.00	3392283	0.028	0.4	29	0.4	6.3
MC-DDH-007	57.05	58.05	1.00	3392285	0.021	-0.1	10	4.5	3.0
MC-DDH-007	58.05	59.05	1.00	3392286	0.075	0.7	14	1.5	3.1
MC-DDH-007	59.05	60.05	1.00	3392287	0.043	0.4	25	0.9	17.6
MC-DDH-007	60.05	61.05	1.00	3392288	0.018	0.3	11	0.3	13.4
MC-DDH-007	61.05	62.05	1.00	3392289	0.076	1.0	15	0.7	16.7
MC-DDH-007	63.05	64.05	1.00	3392292	0.018	0.2	11	1.5	3.8
MC-DDH-007	64.05	65.05	1.00	3392293	0.011	0.2	12	1.0	3.7
MC-DDH-007	65.05	66.05	1.00	3392294	0.030	0.9	32	2.9	1.9
MC-DDH-007	66.05	67.05	1.00	3392295	0.016	1.7	17	0.3	4.1
MC-DDH-007	67.05	68.05	1.00	3392296	0.116	4.8	48	0.5	6.0
MC-DDH-007	68.05	69.05	1.00	3392297	0.008	0.7	13	0.1	1.2
MC-DDH-007	69.05	70.05	1.00	3392299	0.676	39.8	244	67.5	56.0
MC-DDH-007	70.05	71.05	1.00	3392300	0.785	65.2	342	52.7	78.8
MC-DDH-007	71.05	72.05	1.00	3392301	1.490	4.7	108	0.6	10.8
MC-DDH-007	72.05	73.05	1.00	3392302	2.115	7.8	153	1.3	19.0
MC-DDH-007	73.05	74.05	1.00	3392303	0.870	6.9	46	0.6	9.0
MC-DDH-007	74.05	75.05	1.00	3392304	0.208	0.7	19	2.3	4.3
MC-DDH-007	75.05	76.05	1.00	3392306	0.050	0.6	26	1.4	6.7
MC-DDH-007	76.05	77.05	1.00	3392307	0.080	0.6	44	0.8	7.7
MC-DDH-007	77.05	78.05	1.00	3392308	0.071	0.3	22	0.1	1.9
MC-DDH-007	78.05	79.05	1.00	3392309	0.024	0.3	11	0.2	1.8
MC-DDH-007	79.05	80.05	1.00	3392310	0.079	0.4	19	0.2	1.3
MC-DDH-007	80.05	81.05	1.00	3392311	5.072	4.2	70	0.4	4.1
MC-DDH-007	81.05	82.05	1.00	3392313	1.329	3.6	141	3.7	13.7
MC-DDH-007	82.05	83.05	1.00	3392314	0.320	7.7	109	5.7	31.4
MC-DDH-007	83.05	84.05	1.00	3392315	0.561	1.1	20	0.3	4.4
MC-DDH-007	84.05	85.05	1.00	3392316	0.511	0.6	37	0.7	4.3
MC-DDH-007	85.05	86.05	1.00	3392317	0.152	0.3	40	0.5	5.9
MC-DDH-007	87.05	88.05	1.00	3392320	0.115	0.4	30	0.4	3.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	88.05	89.05	1.00	3392321	0.023	0.1	10	0.5	8.0
MC-DDH-007	89.05	90.05	1.00	3392322	0.057	0.5	39	1.0	20.0
MC-DDH-007	90.05	91.05	1.00	3392323	0.018	-0.1	11	0.2	4.9
MC-DDH-007	91.05	92.05	1.00	3392324	0.007	-0.1	6	0.1	1.2
MC-DDH-007	92.05	93.05	1.00	3392325	0.054	0.2	7	0.5	1.5
MC-DDH-007	93.05	94.05	1.00	3392327	0.052	0.2	20	0.7	1.2
MC-DDH-007	94.05	95.05	1.00	3392328	0.016	0.2	17	0.6	3.1
MC-DDH-007	95.05	96.05	1.00	3392329	0.012	0.1	12	0.3	1.4
MC-DDH-007	96.05	97.05	1.00	3392331	0.001	0.2	33	0.1	2.1
MC-DDH-007	97.05	98.05	1.00	3392332	0.025	0.4	44	0.4	8.3
MC-DDH-007	98.05	99.05	1.00	3392333	0.029	0.6	45	0.8	29.1
MC-DDH-007	99.05	100.05	1.00	3392334	0.054	1.0	25	1.5	47.0
MC-DDH-007	100.05	101.05	1.00	3392335	0.017	0.2	9	2.1	28.9
MC-DDH-007	101.05	102.05	1.00	3392336	0.041	0.1	5	1.3	29.1
MC-DDH-007	102.05	103.05	1.00	3392338	0.057	0.2	11	1.0	57.5
MC-DDH-007	103.05	104.05	1.00	3392339	0.034	0.2	8	0.5	42.5
MC-DDH-007	104.05	105.05	1.00	3392340	0.022	0.4	15	3.1	75.8
MC-DDH-007	105.05	106.05	1.00	3392341	0.037	0.3	11	2.5	73.5
MC-DDH-007	106.05	107.05	1.00	3392342	0.862	0.2	8	0.7	19.6
MC-DDH-007	108.05	109.05	1.00	3392345	0.140	0.4	107	0.6	128.4
MC-DDH-007	109.05	110.05	1.00	3392346	0.517	1.4	32	0.2	32.7
MC-DDH-007	110.05	111.05	1.00	3392347	0.008	-0.1	9	0.5	7.0
MC-DDH-007	111.05	112.05	1.00	3392348	0.008	0.1	11	0.3	2.9
MC-DDH-007	112.05	113.05	1.00	3392349	0.006	0.1	4	0.6	2.0
MC-DDH-007	113.05	114.05	1.00	3392350	0.001	-0.1	2	1.0	7.0
MC-DDH-007	114.05	115.05	1.00	3392352	0.001	-0.1	16	0.9	8.5
MC-DDH-007	115.05	116.05	1.00	3392353	0.012	0.7	8	2.3	36.5
MC-DDH-007	116.05	117.05	1.00	3392354	0.001	-0.1	9	2.7	5.6
MC-DDH-007	117.05	118.05	1.00	3392355	0.001	-0.1	10	2.9	5.7
MC-DDH-007	118.05	119.05	1.00	3392356	0.005	-0.1	29	1.9	4.9
MC-DDH-007	119.05	120.05	1.00	3392357	0.005	-0.1	31	1.2	4.1
MC-DDH-007	120.05	121.05	1.00	3392359	0.006	-0.1	16	2.9	7.4
MC-DDH-007	121.05	122.05	1.00	3392360	0.001	-0.1	22	4.6	7.0
MC-DDH-007	122.05	123.05	1.00	3392361	0.001	-0.1	12	2.4	5.4
MC-DDH-007	123.05	124.05	1.00	3392362	0.001	-0.1	17	3.2	8.5
MC-DDH-007	124.05	125.05	1.00	3392363	0.001	-0.1	13	1.9	18.4
MC-DDH-007	125.05	126.05	1.00	3392364	0.006	-0.1	14	1.6	14.5
MC-DDH-007	126.05	127.05	1.00	3392366	0.007	0.1	6	0.9	58.9
MC-DDH-007	127.05	128.05	1.00	3392367	0.111	0.4	12	0.3	60.7
MC-DDH-007	128.05	129.05	1.00	3392368	0.020	0.2	4	0.4	5.2
MC-DDH-007	129.05	130.05	1.00	3392369	0.032	5.8	10	0.8	27.1
MC-DDH-007	131.05	132.05	1.00	3392371	0.020	1.5	22	0.6	13.3
MC-DDH-007	132.05	133.05	1.00	3392373	0.006	-0.1	15	0.4	6.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	133.05	134.05	1.00	3392374	0.001	-0.1	12	1.1	7.6
MC-DDH-007	134.05	135.05	1.00	3392375	0.009	0.1	10	1.7	29.9
MC-DDH-007	135.05	136.05	1.00	3392376	0.029	0.1	27	0.4	42.5
MC-DDH-007	136.05	137.05	1.00	3392377	0.015	0.3	17	0.7	188.1
MC-DDH-007	137.05	138.05	1.00	3392378	0.009	0.1	14	1.0	87.6
MC-DDH-007	138.05	139.05	1.00	3392380	0.005	0.2	13	1.3	13.9
MC-DDH-007	139.05	140.05	1.00	3392381	0.005	0.2	9	0.3	4.1
MC-DDH-007	140.05	141.05	1.00	3392382	0.001	-0.1	12	0.2	7.6
MC-DDH-007	141.05	142.05	1.00	3392383	0.001	0.2	22	1.8	72.4
MC-DDH-007	142.05	143.05	1.00	3392384	0.006	0.1	37	2.1	81.4
MC-DDH-007	143.05	144.05	1.00	3392385	0.001	0.1	15	2.0	54.0
MC-DDH-007	144.05	145.05	1.00	3392387	0.006	0.3	25	2.5	214.8
MC-DDH-007	145.05	146.05	1.00	3392388	0.001	0.2	29	1.8	70.3
MC-DDH-007	146.05	147.05	1.00	3392389	0.001	-0.1	31	1.8	48.4
MC-DDH-007	147.05	148.05	1.00	3392390	0.001	0.1	21	0.8	42.2
MC-DDH-007	148.05	149.05	1.00	3392391	0.001	0.2	24	1.5	25.6
MC-DDH-007	149.05	150.05	1.00	3392392	0.006	-0.1	19	2.0	51.4
MC-DDH-007	150.05	150.97	0.92	3392394	0.001	-0.1	27	2.3	36.7
MC-DDH-008	3.00	4.00	1.00	3392395	0.044	1.3	53	5.8	15.0
MC-DDH-008	4.00	5.00	1.00	3392396	0.047	1.4	45	5.3	14.2
MC-DDH-008	5.00	6.00	1.00	3392397	0.033	0.4	83	1.4	7.8
MC-DDH-008	6.00	7.00	1.00	3392398	0.049	0.2	49	1.5	12.5
MC-DDH-008	8.00	9.00	1.00	3392401	0.038	0.5	70	0.5	9.1
MC-DDH-008	9.00	10.00	1.00	3392402	0.011	0.2	33	0.3	6.5
MC-DDH-008	10.00	11.00	1.00	3392403	0.028	1.0	45	0.3	7.0
MC-DDH-008	11.00	12.00	1.00	3392404	0.217	0.8	54	0.2	1.5
MC-DDH-008	12.00	13.00	1.00	3392405	0.139	1.0	37	0.3	3.7
MC-DDH-008	13.00	14.00	1.00	3392406	0.040	0.2	12	0.2	1.4
MC-DDH-008	14.00	15.00	1.00	3392408	0.135	0.9	13	0.3	3.6
MC-DDH-008	15.00	16.00	1.00	3392409	0.323	0.9	53	0.6	8.6
MC-DDH-008	16.00	17.00	1.00	3392410	0.047	0.1	22	0.4	9.4
MC-DDH-008	17.00	18.00	1.00	3392411	0.490	1.2	35	0.6	3.9
MC-DDH-008	18.00	19.00	1.00	3392412	0.608	3.4	75	0.9	3.0
MC-DDH-008	19.00	20.00	1.00	3392413	0.220	2.0	38	0.3	1.6
MC-DDH-008	20.00	21.00	1.00	3392415	0.017	0.6	26	0.3	4.9
MC-DDH-008	21.00	22.00	1.00	3392416	0.041	1.9	31	0.2	7.8
MC-DDH-008	22.00	23.00	1.00	3392417	0.110	0.9	23	0.2	2.8
MC-DDH-008	23.00	24.00	1.00	3392418	0.029	0.3	16	0.1	1.6
MC-DDH-008	24.00	25.00	1.00	3392419	0.048	0.9	15	0.2	1.2
MC-DDH-008	25.00	26.00	1.00	3392420	0.007	-0.1	9	0.1	0.8
MC-DDH-008	26.00	27.00	1.00	3392422	0.006	0.1	4	-0.1	3.8
MC-DDH-008	27.00	28.00	1.00	3392423	0.009	-0.1	5	-0.1	0.8
MC-DDH-008	28.00	29.00	1.00	3392424	0.001	-0.1	7	0.2	1.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	29.00	30.00	1.00	3392425	0.012	-0.1	15	0.6	1.6
MC-DDH-008	30.00	31.00	1.00	3392426	0.022	0.2	36	0.6	2.5
MC-DDH-008	32.00	33.00	1.00	3392429	0.121	1.5	75	71.6	6.1
MC-DDH-008	33.00	34.00	1.00	3392431	0.036	0.3	14	0.2	1.8
MC-DDH-008	34.00	35.00	1.00	3392432	0.035	0.2	12	0.4	2.9
MC-DDH-008	35.00	36.00	1.00	3392433	0.058	0.7	9	0.6	3.3
MC-DDH-008	36.00	37.00	1.00	3392434	0.015	-0.1	8	0.4	2.9
MC-DDH-008	37.00	38.00	1.00	3392435	0.049	0.8	23	0.2	5.1
MC-DDH-008	38.00	39.00	1.00	3392436	0.055	0.4	31	1.4	7.3
MC-DDH-008	39.00	40.00	1.00	3392438	0.041	0.2	47	1.7	8.2
MC-DDH-008	40.00	41.00	1.00	3392439	0.067	0.3	41	1.3	4.3
MC-DDH-008	41.00	42.00	1.00	3392440	0.064	0.3	44	0.7	5.2
MC-DDH-008	42.00	43.00	1.00	3392441	0.051	0.2	35	0.6	4.0
MC-DDH-008	43.00	44.00	1.00	3392442	0.056	0.2	35	0.5	4.9
MC-DDH-008	45.00	46.00	1.00	3392445	0.060	0.1	50	0.1	2.6
MC-DDH-008	46.00	47.00	1.00	3392446	0.095	0.2	59	0.2	5.5
MC-DDH-008	47.00	48.00	1.00	3392447	0.030	-0.1	22	0.3	9.0
MC-DDH-008	48.00	49.00	1.00	3392448	0.011	-0.1	8	0.1	1.9
MC-DDH-008	49.00	50.00	1.00	3392449	0.032	0.2	28	0.3	8.3
MC-DDH-008	50.00	51.00	1.00	3392450	0.006	-0.1	-1	0.1	1.0
MC-DDH-008	51.00	52.00	1.00	3392452	0.011	-0.1	22	0.3	2.1
MC-DDH-008	52.00	53.00	1.00	3392453	0.046	0.2	9	0.2	1.3
MC-DDH-008	53.00	54.00	1.00	3392454	0.056	0.1	18	0.2	2.9
MC-DDH-008	54.00	55.00	1.00	3392455	0.009	0.1	14	0.2	2.5
MC-DDH-008	55.00	56.00	1.00	3392456	0.006	0.1	6	0.1	4.9
MC-DDH-008	56.00	57.00	1.00	3392457	0.011	-0.1	6	0.2	1.4
MC-DDH-008	57.00	58.00	1.00	3392459	0.009	0.2	6	0.1	1.2
MC-DDH-008	58.00	59.00	1.00	3392460	0.031	1.6	18	0.3	2.6
MC-DDH-008	59.00	60.00	1.00	3392461	0.040	4.9	18	0.4	2.9
MC-DDH-008	60.00	61.00	1.00	3392462	0.074	3.0	25	0.5	1.5
MC-DDH-008	61.00	62.00	1.00	3392463	0.038	6.7	21	0.3	2.5
MC-DDH-008	63.00	64.00	1.00	3392466	0.325	4.8	52	1.3	3.5
MC-DDH-008	64.00	65.00	1.00	3392467	0.256	2.6	80	0.4	4.1
MC-DDH-008	65.00	66.00	1.00	3392468	0.401	1.1	31	0.3	2.4
MC-DDH-008	66.00	67.00	1.00	3392469	0.286	0.7	42	0.2	1.4
MC-DDH-008	67.00	68.00	1.00	3392470	1.585	1.2	104	0.2	1.5
MC-DDH-008	68.00	69.00	1.00	3392471	1.541	0.9	46	0.3	0.8
MC-DDH-008	69.00	70.00	1.00	3392473	3.602	1.3	95	0.2	0.8
MC-DDH-008	70.00	71.00	1.00	3392474	2.046	1.2	95	0.4	2.1
MC-DDH-008	71.00	72.00	1.00	3392475	2.118	4.5	51	0.4	2.1
MC-DDH-008	72.00	73.00	1.00	3392476	7.285	1.8	59	0.1	0.8
MC-DDH-008	73.00	74.00	1.00	3392477	2.981	0.7	38	0.3	1.2
MC-DDH-008	74.00	75.00	1.00	3392478	1.242	0.9	29	-0.1	0.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	75.00	76.00	1.00	3392480	5.153	2.0	52	0.2	0.8
MC-DDH-008	76.00	77.00	1.00	3392481	5.772	1.5	56	0.1	0.7
MC-DDH-008	77.00	78.00	1.00	3392482	5.342	3.2	70	0.2	2.3
MC-DDH-008	78.00	79.00	1.00	3392483	6.193	8.2	63	-0.1	0.5
MC-DDH-008	79.00	80.00	1.00	3392484	0.108	0.2	11	0.2	1.9
MC-DDH-008	80.00	81.00	1.00	3392485	0.062	0.3	18	0.3	2.7
MC-DDH-008	81.00	82.00	1.00	3392487	0.122	6.5	6	0.3	2.3
MC-DDH-008	82.00	83.00	1.00	3392488	1.886	3.3	42	0.2	1.0
MC-DDH-008	83.00	84.00	1.00	3392489	0.105	0.5	31	-0.1	1.6
MC-DDH-008	84.00	85.00	1.00	3392490	0.016	0.1	41	0.1	2.7
MC-DDH-008	85.00	86.00	1.00	3392491	0.022	-0.1	8	0.6	2.8
MC-DDH-008	86.00	87.00	1.00	3392492	0.014	-0.1	9	0.4	33.1
MC-DDH-008	87.00	88.00	1.00	3392494	0.013	0.2	19	1.4	188.9
MC-DDH-008	88.00	89.00	1.00	3392495	0.018	0.2	8	2.9	54.6
MC-DDH-008	89.00	90.00	1.00	3392496	0.007	-0.1	10	2.6	11.2
MC-DDH-008	90.00	91.00	1.00	3392497	0.005	-0.1	5	5.2	2.2
MC-DDH-008	91.00	92.00	1.00	3392498	0.006	-0.1	6	11.7	3.1
MC-DDH-008	93.00	94.00	1.00	3392501	0.006	-0.1	-1	0.9	2.9
MC-DDH-008	94.00	95.00	1.00	3392502	0.008	-0.1	31	0.2	1.3
MC-DDH-008	95.00	96.00	1.00	3392503	0.025	-0.1	29	0.2	3.6
MC-DDH-008	96.00	97.00	1.00	3392504	0.013	-0.1	17	8.7	17.7
MC-DDH-008	97.00	98.00	1.00	3392505	0.015	0.7	10	0.4	200.9
MC-DDH-008	98.00	99.00	1.00	3392506	0.017	0.1	7	0.1	0.6
MC-DDH-008	99.00	100.00	1.00	3392508	0.012	0.1	13	0.3	1.4
MC-DDH-008	100.00	101.00	1.00	3392509	0.025	0.1	9	0.3	1.3
MC-DDH-008	101.00	102.00	1.00	3392510	0.139	0.1	22	0.1	7.3
MC-DDH-008	102.00	103.00	1.00	3392511	0.092	0.4	15	0.2	4.3
MC-DDH-008	103.00	104.00	1.00	3392512	0.011	-0.1	2	0.1	13.1
MC-DDH-008	104.00	105.00	1.00	3392513	0.010	-0.1	22	0.1	0.7
MC-DDH-008	105.00	106.00	1.00	3392515	0.015	-0.1	4	0.3	2.2
MC-DDH-008	106.00	107.00	1.00	3392516	0.155	0.2	13	0.2	6.2
MC-DDH-008	107.00	108.00	1.00	3392517	0.295	0.5	13	0.1	11.4
MC-DDH-008	108.00	109.00	1.00	3392518	0.049	0.2	21	0.2	13.4
MC-DDH-008	109.00	110.00	1.00	3392519	0.006	-0.1	2	-0.1	3.7
MC-DDH-008	110.00	111.00	1.00	3392520	0.015	-0.1	-1	0.2	6.8
MC-DDH-008	111.00	112.00	1.00	3392522	0.015	0.1	8	0.1	4.9
MC-DDH-008	112.00	113.00	1.00	3392523	0.057	0.2	8	0.2	1.2
MC-DDH-008	113.00	114.00	1.00	3392524	0.042	0.2	12	0.1	1.2
MC-DDH-008	114.00	115.00	1.00	3392525	0.040	0.1	8	0.1	1.2
MC-DDH-008	115.00	116.00	1.00	3392526	0.040	0.1	15	0.1	0.5
MC-DDH-008	117.00	118.00	1.00	3392529	0.007	0.1	14	0.1	0.6
MC-DDH-008	118.00	119.00	1.00	3392530	0.038	0.1	20	-0.1	1.4
MC-DDH-008	119.00	120.00	1.00	3392531	0.022	-0.1	7	0.3	8.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	120.00	121.00	1.00	3392532	0.029	-0.1	20	0.4	2.8
MC-DDH-008	121.00	122.00	1.00	3392533	1.634	0.5	15	0.5	2.6
MC-DDH-008	122.00	123.00	1.00	3392534	0.057	0.2	6	0.1	1.6
MC-DDH-008	123.00	124.00	1.00	3392536	0.317	0.1	18	0.2	4.3
MC-DDH-008	124.00	125.00	1.00	3392537	0.207	0.2	16	0.4	7.2
MC-DDH-008	125.00	126.00	1.00	3392538	0.122	0.5	7	0.2	8.8
MC-DDH-008	126.00	127.00	1.00	3392539	0.073	0.2	5	0.1	3.5
MC-DDH-008	127.00	128.00	1.00	3392540	0.028	0.2	7	0.1	3.3
MC-DDH-008	128.00	129.00	1.00	3392541	0.189	0.5	23	0.3	16.8
MC-DDH-008	129.00	130.00	1.00	3392543	0.009	-0.1	43	1.6	21.1
MC-DDH-008	130.00	131.00	1.00	3392544	0.006	-0.1	29	1.7	6.0
MC-DDH-008	131.00	132.00	1.00	3392545	0.006	-0.1	84	3.9	7.2
MC-DDH-008	132.00	133.00	1.00	3392546	0.007	-0.1	38	3.8	7.7
MC-DDH-008	133.00	134.00	1.00	3392547	0.006	-0.1	28	1.8	10.9
MC-DDH-008	135.00	136.00	1.00	3392550	0.008	-0.1	47	1.8	9.1
MC-DDH-008	136.00	137.00	1.00	3392551	0.005	-0.1	28	1.3	13.2
MC-DDH-008	137.00	138.00	1.00	3392552	0.009	-0.1	15	0.8	7.1
MC-DDH-008	138.00	139.00	1.00	3392553	0.015	-0.1	36	1.0	21.9
MC-DDH-008	139.00	140.00	1.00	3392554	0.008	0.4	25	0.9	87.1
MC-DDH-008	141.00	142.00	1.00	3392557	0.064	0.5	21	0.2	1.6
MC-DDH-008	142.00	143.00	1.00	3392558	0.024	0.1	23	0.2	1.4
MC-DDH-008	143.00	144.00	1.00	3392559	0.029	-0.1	19	0.1	2.2
MC-DDH-008	144.00	145.00	1.00	3392560	0.072	0.3	65	0.2	10.6
MC-DDH-008	145.00	146.00	1.00	3392561	0.027	0.2	24	0.1	5.6
MC-DDH-008	146.00	147.00	1.00	3392562	0.015	0.7	25	4.8	234.6
MC-DDH-008	147.00	148.00	1.00	3392564	0.008	0.1	25	1.7	23.1
MC-DDH-008	148.00	149.00	1.00	3392565	0.010	0.3	40	3.1	218.6
MC-DDH-008	149.00	150.00	1.00	3392566	0.006	0.1	54	1.4	78.6
MC-DDH-008	150.00	151.00	1.00	3392567	0.010	0.2	128	5.3	118.5
MC-DDH-008	151.00	152.00	1.00	3392568	0.008	0.1	52	1.0	74.0
MC-DDH-008	152.00	153.00	1.00	3392569	0.007	0.2	50	3.3	93.4
MC-DDH-008	153.00	154.00	1.00	3392571	0.008	-0.1	29	1.2	44.1
MC-DDH-008	154.00	155.00	1.00	3392572	0.009	0.3	105	5.6	138.0
MC-DDH-008	155.00	156.00	1.00	3392573	0.007	0.3	19	2.2	109.6
MC-DDH-008	156.00	157.00	1.00	3392574	0.001	0.1	15	2.7	4.0
MC-DDH-008	157.00	158.00	1.00	3392575	0.075	-0.1	16	2.8	3.3
MC-DDH-008	158.00	159.00	1.00	3392576	0.001	-0.1	13	4.5	1.3
MC-DDH-008	159.00	160.00	1.00	3392578	0.001	-0.1	12	3.4	2.3
MC-DDH-008	160.00	161.00	1.00	3392579	0.001	-0.1	9	0.9	14.8
MC-DDH-008	161.00	162.00	1.00	3392580	0.007	-0.1	35	1.2	58.9
MC-DDH-008	162.00	163.00	1.00	3392581	0.001	-0.1	9	0.3	2.2
MC-DDH-008	163.00	164.00	1.00	3392582	0.006	-0.1	22	2.3	4.1
MC-DDH-008	165.00	166.00	1.00	3392585	0.006	-0.1	11	1.2	2.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	166.00	167.00	1.00	3392586	0.009	-0.1	9	0.9	3.4
MC-DDH-008	167.00	168.00	1.00	3392587	0.006	-0.1	14	0.6	4.6
MC-DDH-008	168.00	169.00	1.00	3392588	0.007	-0.1	15	0.8	16.0
MC-DDH-008	169.00	170.00	1.00	3392589	0.007	-0.1	15	0.8	14.4
MC-DDH-008	170.00	171.00	1.00	3392590	0.024	0.5	30	2.3	8.3
MC-DDH-008	171.00	172.00	1.00	3392592	0.020	0.1	14	0.7	3.1
MC-DDH-008	172.00	173.00	1.00	3392593	0.014	0.1	35	1.2	2.4
MC-DDH-008	173.00	174.00	1.00	3392594	0.001	0.2	5	1.7	12.6
MC-DDH-008	174.00	175.00	1.00	3392595	0.001	-0.1	4	0.9	20.5
MC-DDH-008	175.00	176.00	1.00	3392596	0.001	-0.1	4	0.1	5.2
MC-DDH-008	176.00	177.00	1.00	3392597	0.023	-0.1	4	0.9	20.3
MC-DDH-008	177.00	178.00	1.00	3392599	0.006	0.2	5	3.7	1.5
MC-DDH-008	178.00	179.00	1.00	3392600	0.006	-0.1	-1	1.5	1.7
MC-DDH-008	179.00	180.00	1.00	3392601	0.007	-0.1	-1	1.1	3.7
MC-DDH-008	180.00	181.00	1.00	3392602	0.009	-0.1	6	4.0	25.2
MC-DDH-008	181.00	182.00	1.00	3392603	0.007	-0.1	4	0.5	3.4
MC-DDH-008	182.00	183.00	1.00	3392604	0.007	-0.1	13	0.8	20.3
MC-DDH-008	183.00	184.00	1.00	3392606	0.007	-0.1	14	0.5	31.1
MC-DDH-008	184.00	185.00	1.00	3392607	0.007	-0.1	3	0.5	1.7
MC-DDH-008	185.00	186.00	1.00	3392608	0.010	0.1	3	0.6	6.6
MC-DDH-008	186.00	187.00	1.00	3392609	0.006	-0.1	3	0.2	1.6
MC-DDH-008	187.00	187.60	0.60	3392610	0.009	-0.1	4	0.4	3.0
MC-DDH-009	2.00	3.00	1.00	3392613	0.010	0.2	8	0.5	1.4
MC-DDH-009	3.00	4.00	1.00	3392614	0.005	-0.1	6	-0.1	0.4
MC-DDH-009	4.00	5.00	1.00	3392615	0.005	1.2	21	0.6	3.0
MC-DDH-009	5.00	6.00	1.00	3392616	0.033	2.3	41	0.7	10.0
MC-DDH-009	6.00	7.00	1.00	3392617	0.035	9.8	37	2.2	9.7
MC-DDH-009	7.00	8.00	1.00	3392618	0.014	2.3	12	0.7	6.8
MC-DDH-009	8.00	9.00	1.00	3392620	0.043	11.6	16	1.4	5.3
MC-DDH-009	9.00	10.00	1.00	3392621	0.031	3.0	81	1.5	10.6
MC-DDH-009	10.00	11.00	1.00	3392622	0.009	0.3	10	0.2	3.1
MC-DDH-009	11.00	12.00	1.00	3392623	0.007	-0.1	10	-0.1	0.8
MC-DDH-009	12.00	13.00	1.00	3392624	0.006	-0.1	10	-0.1	0.6
MC-DDH-009	14.00	15.00	1.00	3392627	0.012	0.5	10	0.2	0.8
MC-DDH-009	15.00	16.00	1.00	3392628	0.026	0.8	35	0.3	1.4
MC-DDH-009	16.00	17.00	1.00	3392629	0.028	0.5	23	0.9	3.6
MC-DDH-009	17.00	18.00	1.00	3392630	0.032	0.4	33	2.1	5.8
MC-DDH-009	18.00	19.00	1.00	3392631	0.011	2.1	9	1.3	1.1
MC-DDH-009	19.00	20.00	1.00	3392632	0.007	-0.1	-1	0.2	0.7
MC-DDH-009	20.00	21.00	1.00	3392634	0.007	-0.1	-1	-0.1	0.7
MC-DDH-009	21.00	22.00	1.00	3392635	0.007	-0.1	5	-0.1	1.0
MC-DDH-009	22.00	23.00	1.00	3392636	0.007	0.1	6	0.4	1.2
MC-DDH-009	23.00	24.00	1.00	3392637	0.010	0.1	5	0.2	1.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	24.00	25.00	1.00	3392638	0.009	-0.1	6	0.2	3.4
MC-DDH-009	25.00	26.00	1.00	3392639	0.005	-0.1	-1	0.2	2.3
MC-DDH-009	26.00	27.00	1.00	3392641	0.006	-0.1	1	0.2	1.5
MC-DDH-009	27.00	28.00	1.00	3392642	0.006	-0.1	2	-0.1	1.0
MC-DDH-009	28.00	29.00	1.00	3392643	0.006	-0.1	7	0.2	1.9
MC-DDH-009	29.00	30.00	1.00	3392644	0.007	-0.1	9	0.2	0.8
MC-DDH-009	30.00	31.00	1.00	3392645	0.011	-0.1	8	0.4	1.1
MC-DDH-009	31.00	32.00	1.00	3392646	0.090	2.2	89	0.7	1.8
MC-DDH-009	32.00	33.00	1.00	3392648	0.016	0.3	157	0.6	3.7
MC-DDH-009	33.00	34.00	1.00	3392649	0.008	-0.1	15	0.3	6.8
MC-DDH-009	34.00	35.00	1.00	3392650	0.032	0.2	21	0.8	9.2
MC-DDH-009	35.00	36.00	1.00	3392651	0.027	0.3	14	3.1	32.4
MC-DDH-009	36.00	37.00	1.00	3392652	0.022	0.2	7	2.1	30.0
MC-DDH-009	38.00	39.00	1.00	3392655	0.012	0.1	7	0.3	1.2
MC-DDH-009	39.00	40.00	1.00	3392656	0.040	7.9	17	3.0	2.3
MC-DDH-009	40.00	41.00	1.00	3392657	0.048	10.7	8	2.0	3.9
MC-DDH-009	41.00	42.00	1.00	3392658	0.027	2.5	8	1.0	3.8
MC-DDH-009	42.00	43.00	1.00	3392659	0.018	0.2	20	0.8	8.2
MC-DDH-009	43.00	44.00	1.00	3392660	0.006	-0.1	11	0.1	1.1
MC-DDH-009	44.00	45.00	1.00	3392662	0.006	-0.1	8	0.2	0.8
MC-DDH-009	45.00	46.00	1.00	3392663	0.006	-0.1	8	0.2	0.4
MC-DDH-009	46.00	47.00	1.00	3392664	0.006	-0.1	10	0.2	0.3
MC-DDH-009	47.00	48.00	1.00	3392665	0.008	-0.1	12	0.2	0.9
MC-DDH-009	48.00	49.00	1.00	3392666	0.052	4.5	38	2.4	13.6
MC-DDH-009	49.00	50.00	1.00	3392667	0.019	4.0	23	2.0	7.3
MC-DDH-009	50.00	51.00	1.00	3392669	0.008	0.2	1	3.4	2.1
MC-DDH-009	51.00	52.00	1.00	3392670	0.006	-0.1	4	2.4	20.9
MC-DDH-009	52.00	53.00	1.00	3392671	0.010	0.4	3	1.6	13.5
MC-DDH-009	53.00	54.00	1.00	3392672	0.008	0.1	6	28.2	2.3
MC-DDH-009	54.00	55.00	1.00	3392674	0.001	0.1	6	4.7	1.9
MC-DDH-009	55.00	56.00	1.00	3392675	0.001	-0.1	5	4.3	1.6
MC-DDH-009	56.00	57.00	1.00	3392676	0.017	-0.1	8	4.3	1.5
MC-DDH-009	57.00	58.00	1.00	3392677	0.001	0.4	3	34.8	7.9
MC-DDH-009	58.00	59.00	1.00	3392678	0.001	0.2	5	3.3	2.5
MC-DDH-009	59.00	60.00	1.00	3392679	0.005	0.1	7	6.0	4.6
MC-DDH-009	60.00	61.00	1.00	3392681	0.006	-0.1	8	0.8	3.5
MC-DDH-009	61.00	62.00	1.00	3392682	0.021	0.3	12	5.0	2.9
MC-DDH-009	62.00	63.00	1.00	3392683	0.014	-0.1	9	1.7	5.2
MC-DDH-009	63.00	64.00	1.00	3392684	0.005	-0.1	4	1.1	1.4
MC-DDH-009	64.00	65.00	1.00	3392685	0.006	-0.1	5	3.0	37.0
MC-DDH-009	65.00	66.00	1.00	3392686	0.005	-0.1	5	2.9	59.9
MC-DDH-009	66.00	67.00	1.00	3392688	0.006	0.2	9	2.8	75.4
MC-DDH-009	67.00	68.00	1.00	3392689	0.008	0.1	13	2.6	42.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	68.00	69.00	1.00	3392690	0.012	0.2	39	5.1	75.8
MC-DDH-009	69.00	70.00	1.00	3392691	0.010	0.2	37	5.0	64.1
MC-DDH-009	70.00	71.00	1.00	3392692	0.007	0.1	6	3.6	17.3
MC-DDH-009	71.00	72.00	1.00	3392693	0.001	-0.1	9	0.5	1.2
MC-DDH-009	72.00	73.00	1.00	3392695	0.006	-0.1	11	5.1	29.4
MC-DDH-009	73.00	74.00	1.00	3392696	0.006	-0.1	13	3.0	15.1
MC-DDH-009	74.00	75.00	1.00	3392697	0.001	-0.1	13	0.5	4.9
MC-DDH-009	75.00	76.00	1.00	3392698	0.001	-0.1	10	0.7	5.6
MC-DDH-009	76.00	77.00	1.00	3392699	0.017	0.1	11	1.5	2.8
MC-DDH-009	77.00	78.00	1.00	3392700	0.014	-0.1	4	3.6	23.8
MC-DDH-009	78.00	79.00	1.00	3392702	0.001	0.3	7	7.6	15.0
MC-DDH-009	79.00	80.00	1.00	3392703	0.001	0.3	8	4.0	5.9
MC-DDH-009	80.00	81.00	1.00	3392704	0.007	0.3	7	3.8	7.6
MC-DDH-009	81.00	82.00	1.00	3392705	0.001	0.1	13	1.1	4.6
MC-DDH-009	82.00	83.00	1.00	3392706	0.001	-0.1	8	2.8	2.6
MC-DDH-009	83.00	84.00	1.00	3392707	0.001	-0.1	5	6.4	3.3
MC-DDH-009	84.00	85.00	1.00	3392709	0.001	0.1	9	1.6	4.3
MC-DDH-009	85.00	86.00	1.00	3392710	0.007	0.1	12	3.8	4.4
MC-DDH-009	86.00	87.00	1.00	3392711	0.006	0.1	11	5.6	58.5
MC-DDH-009	87.00	88.00	1.00	3392712	0.008	0.5	9	4.5	5.2
MC-DDH-009	88.00	89.00	1.00	3392713	0.033	0.3	13	0.7	4.1
MC-DDH-009	89.00	90.00	1.00	3392714	0.084	0.8	19	0.2	0.8
MC-DDH-009	90.00	91.00	1.00	3392716	0.229	0.8	18	0.3	10.9
MC-DDH-009	91.00	92.00	1.00	3392717	1.067	1.0	26	0.3	7.4
MC-DDH-009	92.00	93.00	1.00	3392718	1.826	2.1	40	0.2	2.0
MC-DDH-009	93.00	94.00	1.00	3392719	0.604	1.5	17	-0.1	0.5
MC-DDH-009	94.00	95.00	1.00	3392720	1.116	2.4	8	-0.1	0.8
MC-DDH-009	95.00	96.00	1.00	3392721	3.524	3.9	26	-0.1	1.9
MC-DDH-009	96.00	97.00	1.00	3392723	0.138	2.1	68	0.9	5.6
MC-DDH-009	97.00	98.00	1.00	3392724	0.011	0.2	7	0.3	0.7
MC-DDH-009	98.00	99.00	1.00	3392725	0.007	-0.1	9	1.4	1.1
MC-DDH-009	99.00	100.00	1.00	3392726	0.007	-0.1	12	1.5	2.0
MC-DDH-009	100.00	101.00	1.00	3392727	0.012	-0.1	20	9.5	3.7
MC-DDH-009	101.00	102.00	1.00	3392728	0.001	-0.1	14	11.7	0.8
MC-DDH-009	102.00	103.00	1.00	3392730	0.006	-0.1	5	137.0	1.1
MC-DDH-009	103.00	104.00	1.00	3392731	0.009	-0.1	15	10.2	1.4
MC-DDH-009	104.00	105.00	1.00	3392732	0.009	0.4	9	1.1	1.3
MC-DDH-009	105.00	106.00	1.00	3392733	0.012	0.8	6	2.5	1.0
MC-DDH-009	106.00	107.00	1.00	3392734	0.006	0.1	8	0.8	0.7
MC-DDH-009	107.00	108.00	1.00	3392735	0.007	0.5	10	2.4	1.7
MC-DDH-009	108.00	109.00	1.00	3392737	0.007	0.2	13	2.1	2.1
MC-DDH-009	109.00	110.00	1.00	3392738	0.017	1.5	26	0.2	1.9
MC-DDH-009	110.00	111.00	1.00	3392739	0.007	0.2	12	3.1	1.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	111.00	112.00	1.00	3392740	0.006	0.2	17	0.3	0.9
MC-DDH-009	112.00	113.00	1.00	3392741	0.517	8.8	1266	1.4	28.3
MC-DDH-009	113.00	114.00	1.00	3392742	1.051	12.5	2089	3.7	45.0
MC-DDH-009	114.00	115.00	1.00	3392744	0.015	-0.1	37	1.8	1.8
MC-DDH-009	115.00	116.00	1.00	3392745	0.006	-0.1	10	0.6	2.6
MC-DDH-009	116.00	117.00	1.00	3392746	0.001	0.2	27	0.3	6.8
MC-DDH-009	117.00	118.00	1.00	3392747	0.008	0.6	22	3.0	2.0
MC-DDH-009	118.00	119.00	1.00	3392748	0.001	-0.1	23	0.7	0.7
MC-DDH-009	119.00	120.00	1.00	3392749	0.001	-0.1	11	0.7	0.4
MC-DDH-009	120.00	121.00	1.00	3392751	0.001	-0.1	3	0.3	0.9
MC-DDH-009	121.00	122.00	1.00	3392752	0.001	-0.1	5	0.9	0.4
MC-DDH-009	122.00	123.00	1.00	3392753	0.001	-0.1	6	1.0	0.6
MC-DDH-009	123.00	124.00	1.00	3392754	0.001	-0.1	11	1.9	0.7
MC-DDH-009	124.00	125.00	1.00	3392755	0.007	-0.1	11	5.7	1.7
MC-DDH-009	125.00	126.00	1.00	3392756	0.001	-0.1	10	2.0	0.8
MC-DDH-009	126.00	127.00	1.00	3392758	0.001	-0.1	6	1.0	2.5
MC-DDH-009	127.00	128.00	1.00	3392759	0.009	-0.1	13	1.7	1.9
MC-DDH-009	128.00	129.00	1.00	3392760	0.001	-0.1	6	0.5	5.7
MC-DDH-009	129.00	130.00	1.00	3392761	0.005	-0.1	20	1.1	5.5
MC-DDH-009	130.00	131.00	1.00	3392762	0.001	-0.1	13	1.4	4.9
MC-DDH-009	131.00	132.00	1.00	3392763	0.001	-0.1	13	1.8	2.3
MC-DDH-009	132.00	133.00	1.00	3392765	0.001	0.2	19	3.2	16.5
MC-DDH-009	133.00	134.00	1.00	3392766	0.001	-0.1	15	1.8	73.9
MC-DDH-009	134.00	135.00	1.00	3392767	0.001	0.2	15	6.5	103.6
MC-DDH-009	135.00	136.00	1.00	3392768	0.001	-0.1	15	3.7	2.4
MC-DDH-009	136.00	137.00	1.00	3392769	0.001	-0.1	14	0.8	0.7
MC-DDH-009	137.00	138.00	1.00	3392770	0.006	0.8	10	2.5	3.7
MC-DDH-009	138.00	139.00	1.00	3392772	0.001	0.1	15	1.0	7.3
MC-DDH-009	139.00	140.00	1.00	3392773	0.001	0.1	16	1.2	0.9
MC-DDH-009	140.00	141.00	1.00	3392774	0.001	-0.1	21	0.3	-0.1
MC-DDH-009	141.00	142.00	1.00	3392775	0.001	-0.1	12	0.3	1.5
MC-DDH-009	142.00	143.00	1.00	3392776	0.001	-0.1	10	1.5	5.1
MC-DDH-009	143.00	144.00	1.00	3392778	0.006	-0.1	13	0.4	1.8
MC-DDH-009	144.00	145.00	1.00	3392779	0.006	-0.1	11	0.6	2.2
MC-DDH-009	145.00	146.00	1.00	3392780	0.012	-0.1	15	1.0	24.9
MC-DDH-009	146.00	147.00	1.00	3392781	0.011	0.2	15	1.1	40.7
MC-DDH-009	147.00	148.00	1.00	3392782	0.012	-0.1	11	6.0	1.5
MC-DDH-009	148.00	149.00	1.00	3392783	0.008	0.2	7	1.1	66.3
MC-DDH-009	149.00	150.00	1.00	3392785	0.006	0.2	14	0.6	69.6
MC-DDH-009	150.00	151.00	1.00	3392786	0.011	0.2	15	2.7	104.3
MC-DDH-009	151.00	152.00	1.00	3392787	0.001	0.2	18	1.8	118.3
MC-DDH-009	152.00	153.00	1.00	3392788	0.006	0.6	59	2.5	374.0
MC-DDH-009	153.00	154.00	1.00	3392789	0.006	0.4	81	9.0	268.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	154.00	155.00	1.00	3392790	0.005	0.9	55	5.3	447.1
MC-DDH-009	155.00	156.00	1.00	3392792	0.009	0.3	13	4.6	51.6
MC-DDH-009	156.00	157.00	1.00	3392793	0.007	0.1	10	0.8	2.8
MC-DDH-009	157.00	158.00	1.00	3392794	0.015	0.1	12	3.3	4.0
MC-DDH-009	158.00	159.00	1.00	3392795	0.020	-0.1	11	0.9	2.3
MC-DDH-009	159.00	160.00	1.00	3392796	0.007	0.3	6	2.3	2.6
MC-DDH-009	160.00	161.00	1.00	3392797	0.016	0.2	27	0.9	6.2
MC-DDH-009	161.00	162.00	1.00	3392799	0.008	-0.1	15	0.2	1.2
MC-DDH-009	162.00	163.00	1.00	3392800	0.009	-0.1	10	0.4	1.3
MC-DDH-009	163.00	164.00	1.00	3392801	0.010	0.2	32	26.6	1.8
MC-DDH-009	164.00	165.00	1.00	3392802	0.019	0.4	11	0.8	1.9
MC-DDH-009	165.00	166.00	1.00	3392803	0.027	0.2	67	1.3	2.2
MC-DDH-009	166.00	167.00	1.00	3392804	0.008	-0.1	7	2.5	2.2
MC-DDH-009	167.00	168.00	1.00	3392806	0.022	0.2	16	1.9	10.2
MC-DDH-009	168.00	169.00	1.00	3392807	0.019	0.3	21	1.6	5.6
MC-DDH-009	169.00	170.00	1.00	3392808	0.029	0.4	37	3.5	10.2
MC-DDH-009	170.00	171.00	1.00	3392809	0.012	0.3	32	2.8	85.5
MC-DDH-009	171.00	172.00	1.00	3392810	0.007	-0.1	19	1.6	23.3
MC-DDH-009	172.00	173.00	1.00	3392811	0.009	-0.1	8	0.8	5.2
MC-DDH-009	173.00	174.00	1.00	3392813	0.008	-0.1	5	1.8	2.0
MC-DDH-009	174.00	175.00	1.00	3392814	0.008	-0.1	4	2.5	3.4
MC-DDH-009	175.00	176.00	1.00	3392815	0.007	-0.1	3	0.4	2.9
MC-DDH-009	176.00	177.00	1.00	3392816	0.006	-0.1	5	0.7	3.8
MC-DDH-009	177.00	178.00	1.00	3392817	0.006	-0.1	9	0.6	7.6
MC-DDH-009	178.00	179.00	1.00	3392818	0.005	-0.1	5	0.6	3.8
MC-DDH-009	179.00	180.00	1.00	3392820	0.008	-0.1	6	0.6	6.2
MC-DDH-009	180.00	181.00	1.00	3392821	0.001	-0.1	3	0.1	4.4
MC-DDH-009	181.00	182.00	1.00	3392822	0.005	0.1	9	0.5	32.8
MC-DDH-009	182.00	183.00	1.00	3392823	0.036	-0.1	11	0.3	3.5
MC-DDH-009	183.00	184.00	1.00	3392824	0.006	-0.1	8	0.3	2.7
MC-DDH-009	184.00	185.00	1.00	3392825	0.005	-0.1	6	0.7	5.0
MC-DDH-009	185.00	186.00	1.00	3392827	0.009	0.2	11	0.7	16.4
MC-DDH-009	186.00	187.00	1.00	3392828	0.007	0.2	15	0.9	40.5
MC-DDH-009	187.00	188.00	1.00	3392829	0.067	1.2	46	1.4	38.1
MC-DDH-009	188.00	189.00	1.00	3392830	0.064	0.8	114	4.4	8.0
MC-DDH-009	189.00	190.00	1.00	3392831	0.041	0.5	38	0.8	4.3
MC-DDH-009	190.00	191.00	1.00	3392832	0.090	1.2	71	0.6	11.4
MC-DDH-009	191.00	192.00	1.00	3392834	0.201	3.9	94	5.2	15.6
MC-DDH-009	192.00	193.00	1.00	3392835	0.400	8.1	151	1.5	12.6
MC-DDH-009	193.00	194.00	1.00	3392836	0.282	4.4	457	1.6	28.8
MC-DDH-009	194.00	195.00	1.00	3392837	0.172	3.7	160	1.0	35.8
MC-DDH-009	195.00	196.00	1.00	3392838	0.224	5.6	304	5.2	214.0
MC-DDH-009	196.00	197.00	1.00	3392839	0.263	5.1	409	4.8	194.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	197.00	198.00	1.00	3392841	0.112	0.8	115	5.8	15.7
MC-DDH-009	198.00	199.00	1.00	3392842	0.063	2.1	40	0.7	9.8
MC-DDH-009	199.00	200.00	1.00	3392843	0.056	1.9	22	0.6	4.9
MC-DDH-009	200.00	201.00	1.00	3392844	0.049	0.5	28	2.9	4.6
MC-DDH-009	201.00	202.00	1.00	3392845	0.017	0.3	18	1.2	4.5
MC-DDH-009	202.00	203.00	1.00	3392846	0.013	0.2	11	0.9	4.3
MC-DDH-009	203.00	204.00	1.00	3392848	0.010	0.2	14	1.2	9.4
MC-DDH-009	204.00	205.00	1.00	3392849	0.043	0.5	64	1.1	13.2
MC-DDH-009	205.00	206.00	1.00	3392850	0.156	2.4	228	2.0	77.6
MC-DDH-009	206.00	207.00	1.00	3392851	0.248	4.5	410	2.3	341.0
MC-DDH-009	207.00	208.00	1.00	3392852	0.015	0.3	11	0.8	2.7
MC-DDH-009	208.00	209.00	1.00	3392853	0.169	1.5	138	0.8	11.7
MC-DDH-009	209.00	210.00	1.00	3392855	0.479	3.4	377	1.9	152.2
MC-DDH-009	210.00	211.00	1.00	3392856	0.048	1.3	55	1.0	9.0
MC-DDH-009	211.00	212.00	1.00	3392857	0.062	0.9	34	0.5	6.7
MC-DDH-009	212.00	213.00	1.00	3392858	0.012	0.1	18	2.1	7.1
MC-DDH-009	213.00	214.00	1.00	3392859	0.022	0.3	13	1.8	7.9
MC-DDH-009	214.00	215.00	1.00	3392860	0.019	0.3	18	1.2	8.3
MC-DDH-009	215.00	216.00	1.00	3392862	0.027	0.4	33	3.3	39.3
MC-DDH-009	216.00	217.00	1.00	3392863	0.024	0.2	32	2.7	38.8
MC-DDH-009	217.00	218.00	1.00	3392864	0.043	0.2	55	6.4	19.5
MC-DDH-009	218.00	219.00	1.00	3392865	0.033	0.4	50	2.5	140.8
MC-DDH-009	219.00	220.00	1.00	3392866	0.010	0.2	12	1.5	23.9
MC-DDH-009	220.00	221.00	1.00	3392867	0.017	0.1	8	11.1	3.9
MC-DDH-009	221.00	222.00	1.00	3392869	0.016	0.2	11	1.7	5.3
MC-DDH-009	222.00	223.00	1.00	3392870	0.042	0.5	33	2.5	8.8
MC-DDH-009	223.00	224.00	1.00	3392871	0.052	0.3	34	1.6	6.9
MC-DDH-009	224.00	225.00	1.00	3392872	0.048	0.3	35	1.9	22.9
MC-DDH-009	225.00	226.00	1.00	3392873	0.022	0.3	29	4.2	5.8
MC-DDH-009	226.00	227.00	1.00	3392874	0.067	1.4	40	2.0	10.4
MC-DDH-009	227.00	228.00	1.00	3392876	0.020	0.3	15	1.9	8.0
MC-DDH-009	228.00	229.00	1.00	3392877	0.078	0.2	24	0.8	15.5
MC-DDH-009	229.00	230.00	1.00	3392878	0.047	1.3	19	3.9	106.0
MC-DDH-009	230.00	231.00	1.00	3392879	0.029	0.3	21	3.7	3.2
MC-DDH-009	231.00	232.00	1.00	3392880	0.009	-0.1	14	3.5	2.4
MC-DDH-009	232.00	233.00	1.00	3392881	0.009	0.4	9	3.9	7.7
MC-DDH-009	233.00	234.00	1.00	3392883	0.008	0.1	16	1.4	9.0
MC-DDH-009	234.00	235.00	1.00	3392884	0.007	0.1	9	1.9	6.3
MC-DDH-009	235.00	236.00	1.00	3392885	0.021	0.2	7	1.3	5.4
MC-DDH-009	236.00	237.00	1.00	3392886	0.009	-0.1	8	1.4	2.6
MC-DDH-009	237.00	238.00	1.00	3392887	0.017	0.1	12	2.9	3.1
MC-DDH-009	238.00	239.00	1.00	3392888	0.013	-0.1	13	1.2	2.7
MC-DDH-009	239.00	240.00	1.00	3392890	0.018	-0.1	9	1.8	5.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	240.00	241.00	1.00	3392891	0.025	0.1	24	6.7	1.8
MC-DDH-009	241.00	242.00	1.00	3392892	0.009	-0.1	15	4.2	1.3
MC-DDH-009	242.00	243.00	1.00	3392893	0.017	-0.1	20	0.8	1.8
MC-DDH-009	243.00	244.00	1.00	3392894	0.011	-0.1	12	0.6	0.9
MC-DDH-009	244.00	245.00	1.00	3392895	0.009	0.2	30	2.0	1.7
MC-DDH-009	245.00	245.52	0.52	3392897	0.010	0.1	13	2.1	3.4
MC-DDH-010	1.00	2.00	1.00	3392899	0.029	4.6	28	2.2	30.2
MC-DDH-010	2.00	3.00	1.00	3392900	0.043	3.6	16	0.8	20.6
MC-DDH-010	3.00	4.00	1.00	3392901	0.069	1.9	16	0.9	19.1
MC-DDH-010	4.00	5.00	1.00	3392902	0.043	5.5	29	1.1	4.4
MC-DDH-010	5.00	6.00	1.00	3392903	0.053	9.7	33	1.6	6.0
MC-DDH-010	6.00	7.00	1.00	3392904	0.012	0.3	10	0.3	1.4
MC-DDH-010	7.00	8.00	1.00	3392906	0.063	9.8	43	2.5	18.7
MC-DDH-010	8.00	9.00	1.00	3392907	0.027	1.4	29	0.7	2.3
MC-DDH-010	9.00	10.00	1.00	3392908	0.008	0.1	8	0.2	1.3
MC-DDH-010	10.00	11.00	1.00	3392909	0.012	2.3	2	0.3	3.5
MC-DDH-010	11.00	12.00	1.00	3392910	0.040	2.5	70	1.1	6.1
MC-DDH-010	12.00	13.00	1.00	3392911	0.030	1.0	33	0.6	8.0
MC-DDH-010	13.00	14.00	1.00	3392913	0.045	4.2	56	3.1	12.1
MC-DDH-010	14.00	15.00	1.00	3392914	0.225	37.4	50	2.6	191.4
MC-DDH-010	15.00	16.00	1.00	3392915	0.133	6.5	13	0.8	21.5
MC-DDH-010	16.00	17.00	1.00	3392916	0.121	2.1	5	0.2	2.4
MC-DDH-010	17.00	18.00	1.00	3392917	0.031	13.4	39	2.8	39.6
MC-DDH-010	18.00	19.00	1.00	3392918	0.275	7.5	13	1.4	27.4
MC-DDH-010	19.00	20.00	1.00	3392920	0.090	0.2	15	0.6	5.6
MC-DDH-010	20.00	21.00	1.00	3392921	0.068	0.3	14	0.7	2.6
MC-DDH-010	21.00	22.00	1.00	3392922	0.045	6.9	10	1.5	6.9
MC-DDH-010	22.00	23.00	1.00	3392923	0.010	0.1	5	0.1	0.5
MC-DDH-010	23.00	24.00	1.00	3392924	0.005	-0.1	6	-0.1	0.4
MC-DDH-010	24.00	25.00	1.00	3392925	0.008	-0.1	11	0.1	1.4
MC-DDH-010	25.00	26.00	1.00	3392927	0.006	0.1	6	-0.1	0.6
MC-DDH-010	26.00	27.00	1.00	3392928	0.006	-0.1	-1	-0.1	0.3
MC-DDH-010	27.00	28.00	1.00	3392929	0.006	0.1	-1	-0.1	0.4
MC-DDH-010	28.00	29.00	1.00	3392930	0.006	0.3	3	-0.1	0.7
MC-DDH-010	29.00	30.00	1.00	3392931	0.008	-0.1	3	0.1	0.6
MC-DDH-010	30.00	31.00	1.00	3392932	0.005	-0.1	2	-0.1	0.7
MC-DDH-010	31.00	32.00	1.00	3392934	0.007	-0.1	14	-0.1	2.5
MC-DDH-010	32.00	33.00	1.00	3392935	0.006	-0.1	7	-0.1	0.8
MC-DDH-010	33.00	34.00	1.00	3392936	0.011	-0.1	8	0.1	0.9
MC-DDH-010	34.00	35.00	1.00	3392937	0.012	2.1	-1	0.3	5.1
MC-DDH-010	35.00	36.00	1.00	3392938	0.012	0.6	16	0.7	67.0
MC-DDH-010	36.00	37.00	1.00	3392939	0.007	0.3	9	1.8	26.5
MC-DDH-010	37.00	38.00	1.00	3392941	0.008	0.5	11	0.3	3.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-010	38.00	39.00	1.00	3392942	0.008	0.2	14	0.5	7.3
MC-DDH-010	39.00	40.00	1.00	3392943	0.011	2.4	18	0.5	5.3
MC-DDH-010	40.00	41.00	1.00	3392944	0.032	11.7	16	1.8	72.1
MC-DDH-010	41.00	42.00	1.00	3392945	0.021	0.2	46	0.9	18.3
MC-DDH-010	42.00	43.00	1.00	3392946	0.007	0.3	38	1.9	3.5
MC-DDH-010	43.00	44.00	1.00	3392948	0.009	0.2	21	0.8	26.1
MC-DDH-010	44.00	45.00	1.00	3392949	0.011	0.1	47	0.5	29.6
MC-DDH-010	45.00	46.00	1.00	3392950	0.021	0.7	43	0.5	643.7
MC-DDH-010	46.00	47.00	1.00	3392951	0.048	1.1	40	0.2	1133.3
MC-DDH-010	47.00	48.00	1.00	3392952	0.011	0.5	6	2.1	8.1
MC-DDH-010	48.00	49.00	1.00	3392953	0.010	-0.1	5	2.9	4.5
MC-DDH-010	49.00	50.00	1.00	3392955	0.006	-0.1	5	1.3	1.3
MC-DDH-010	50.00	51.00	1.00	3392956	0.006	-0.1	4	15.7	1.3
MC-DDH-010	51.00	52.00	1.00	3392957	0.008	-0.1	8	12.4	2.2
MC-DDH-010	52.00	53.00	1.00	3392958	0.154	-0.1	36	5.5	4.1
MC-DDH-010	53.00	54.00	1.00	3392959	0.033	-0.1	13	5.6	2.8
MC-DDH-010	54.00	55.00	1.00	3392960	0.351	0.1	5	1.4	1.9
MC-DDH-010	55.00	56.00	1.00	3392962	0.105	0.1	4	2.0	20.0
MC-DDH-010	56.00	57.00	1.00	3392963	0.313	3.1	18	2.8	347.6
MC-DDH-010	57.00	58.00	1.00	3392964	0.049	1.4	28	1.5	81.4
MC-DDH-010	58.00	59.00	1.00	3392965	0.072	0.8	10	0.6	9.3
MC-DDH-010	59.00	60.00	1.00	3392966	0.033	0.3	16	0.3	15.5
MC-DDH-010	60.00	61.00	1.00	3392967	0.019	-0.1	11	0.5	4.3
MC-DDH-010	61.00	62.00	1.00	3392969	0.021	0.2	12	0.3	3.4
MC-DDH-010	62.00	63.00	1.00	3392970	0.025	0.1	6	1.0	7.1
MC-DDH-010	63.00	64.00	1.00	3392971	0.070	0.2	13	1.9	12.6
MC-DDH-010	64.00	65.00	1.00	3392972	0.028	0.1	13	1.0	5.7
MC-DDH-010	65.00	66.00	1.00	3392973	0.034	0.3	21	1.5	13.6
MC-DDH-010	66.00	67.00	1.00	3392974	0.041	-0.1	16	0.5	4.2
MC-DDH-010	67.00	68.00	1.00	3392976	0.035	0.1	3	0.4	8.1
MC-DDH-010	68.00	69.00	1.00	3392977	0.011	0.2	8	0.2	6.9
MC-DDH-010	69.00	70.00	1.00	3392978	0.017	0.2	11	1.0	5.3
MC-DDH-010	70.00	71.00	1.00	3392979	0.010	0.2	7	0.3	2.0
MC-DDH-010	71.00	72.00	1.00	3392980	0.009	0.1	3	0.4	2.8
MC-DDH-010	72.00	73.00	1.00	3392981	0.014	0.8	3	0.3	5.2
MC-DDH-010	73.00	74.00	1.00	3392983	0.061	4.3	25	1.4	14.9
MC-DDH-010	74.00	75.00	1.00	3392984	0.020	0.2	2	0.2	2.1
MC-DDH-010	75.00	76.00	1.00	3392985	0.037	0.2	34	0.1	3.7
MC-DDH-010	76.00	77.00	1.00	3392986	0.043	0.1	26	0.2	4.1
MC-DDH-010	77.00	78.00	1.00	3392987	0.015	-0.1	10	0.1	2.3
MC-DDH-010	78.00	79.00	1.00	3392988	0.036	0.2	19	0.2	8.5
MC-DDH-010	79.00	80.00	1.00	3392990	0.011	-0.1	10	0.2	2.2
MC-DDH-010	80.00	81.00	1.00	3392991	0.017	0.1	6	0.2	1.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-010	81.00	82.00	1.00	3392992	0.008	0.1	8	-0.1	1.0
MC-DDH-010	82.00	83.00	1.00	3392993	1.336	0.4	40	0.1	9.0
MC-DDH-010	83.00	84.00	1.00	3392994	1.844	0.4	47	0.1	2.0
MC-DDH-010	84.00	85.00	1.00	3392995	1.093	0.4	39	0.2	4.3
MC-DDH-010	85.00	86.00	1.00	3392997	0.774	0.6	60	-0.1	5.0
MC-DDH-010	86.00	87.00	1.00	3392998	1.397	0.5	36	0.2	3.1
MC-DDH-010	87.00	88.00	1.00	3392999	0.220	0.1	8	-0.1	7.3
MC-DDH-010	88.00	89.00	1.00	3393000	2.005	0.5	52	0.5	8.1
MC-DDH-010	89.00	90.00	1.00	3393001	0.349	0.4	17	0.3	61.4
MC-DDH-010	90.00	91.00	1.00	3393002	0.099	1.2	20	1.2	709.7
MC-DDH-010	91.00	92.00	1.00	3393004	0.040	0.6	33	4.0	134.1
MC-DDH-010	92.00	93.00	1.00	3393005	0.171	1.2	25	0.6	56.0
MC-DDH-010	93.00	94.00	1.00	3393006	0.105	0.2	31	1.9	11.3
MC-DDH-010	94.00	95.00	1.00	3393007	0.085	0.4	67	1.8	60.3
MC-DDH-010	95.00	96.00	1.00	3393008	0.025	-0.1	8	0.2	6.3
MC-DDH-010	96.00	97.00	1.00	3393009	0.018	-0.1	2	0.2	4.7
MC-DDH-010	97.00	98.00	1.00	3393011	0.013	-0.1	4	0.1	3.9
MC-DDH-010	98.00	99.00	1.00	3393012	0.920	0.5	30	0.2	19.3
MC-DDH-010	99.00	100.00	1.00	3393013	1.392	1.3	50	0.7	425.8
MC-DDH-010	100.00	100.65	0.65	3393014	0.198	0.6	44	0.3	21.4
MC-DDH-011	1.00	2.00	1.00	3393016	0.077	0.4	84	4.2	44.1
MC-DDH-011	2.00	3.00	1.00	3393017	0.033	0.2	57	2.5	38.7
MC-DDH-011	3.00	4.00	1.00	3393018	0.076	0.3	41	3	44.6
MC-DDH-011	4.00	5.00	1.00	3393019	0.229	0.3	35	1.7	14.5
MC-DDH-011	5.00	6.00	1.00	3393020	0.457	0.7	46	2.4	45.4
MC-DDH-011	6.00	7.00	1.00	3393021	0.193	0.5	37	2.4	50.4
MC-DDH-011	7.00	8.00	1.00	3393023	0.139	0.2	44	1.9	52.1
MC-DDH-011	8.00	9.00	1.00	3393024	0.012	-0.1	23	1.1	9.7
MC-DDH-011	9.00	10.00	1.00	3393025	0.053	-0.1	27	0.9	12.0
MC-DDH-011	10.00	11.00	1.00	3393026	0.028	-0.1	42	0.6	9.1
MC-DDH-011	11.00	12.00	1.00	3393027	0.320	0.4	67	1.5	19.6
MC-DDH-011	12.00	13.00	1.00	3393028	0.566	1.2	56	3.4	27.3
MC-DDH-011	13.00	14.00	1.00	3393030	0.902	2.8	50	0.9	4.8
MC-DDH-011	14.00	15.00	1.00	3393031	0.357	1.7	27	1.2	5.3
MC-DDH-011	15.00	16.00	1.00	3393032	0.214	0.3	23	0.3	2.1
MC-DDH-011	16.00	17.00	1.00	3393033	1.370	0.8	63	0.4	2.4
MC-DDH-011	17.00	18.00	1.00	3393034	1.062	0.2	21	0.2	1.1
MC-DDH-011	18.00	19.00	1.00	3393035	0.642	0.2	28	0.4	0.9
MC-DDH-011	19.00	20.00	1.00	3393037	0.263	0.1	42	0.4	1.5
MC-DDH-011	20.00	21.00	1.00	3393038	0.074	0.1	73	21.9	1.2
MC-DDH-011	21.00	22.00	1.00	3393039	0.029	0.5	15	0.7	2.4
MC-DDH-011	22.00	23.00	1.00	3393040	0.661	1.5	26	0.4	1.2
MC-DDH-011	23.00	24.00	1.00	3393041	0.109	0.7	15	0.3	1.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-011	24.00	25.00	1.00	3393042	0.336	0.6	9	0.2	0.6
MC-DDH-011	25.00	26.00	1.00	3393044	0.911	1.1	24	0.3	1.5
MC-DDH-011	26.00	27.00	1.00	3393045	0.943	0.2	26	0.4	1.2
MC-DDH-011	27.00	28.00	1.00	3393046	3.911	0.6	85	0.3	0.5
MC-DDH-011	28.00	29.00	1.00	3393047	6.926	4.0	161	0.4	1.5
MC-DDH-011	29.00	30.00	1.00	3393048	0.296	0.9	18	0.3	2.2
MC-DDH-011	30.00	31.00	1.00	3393049	0.035	-0.1	13	0.2	1.7
MC-DDH-011	31.00	32.00	1.00	3393051	0.048	0.2	21	0.2	4.3
MC-DDH-011	32.00	33.00	1.00	3393052	0.159	0.3	15	0.5	1.4
MC-DDH-011	33.00	34.00	1.00	3393053	1.107	1.0	19	0.3	1.4
MC-DDH-011	34.00	35.00	1.00	3393054	1.396	0.3	36	0.7	1.1
MC-DDH-011	35.00	36.00	1.00	3393055	0.968	0.2	22	0.8	1.2
MC-DDH-011	36.00	37.00	1.00	3393056	0.317	0.2	53	1.6	1.7
MC-DDH-011	37.00	38.00	1.00	3393058	0.073	0.2	37	1.1	10.3
MC-DDH-011	38.00	39.00	1.00	3393059	0.037	0.2	15	0.7	2.4
MC-DDH-011	39.00	40.00	1.00	3393060	0.024	-0.1	7	0.6	2.2
MC-DDH-011	40.00	41.00	1.00	3393061	0.034	-0.1	16	1.4	0.6
MC-DDH-011	41.00	42.00	1.00	3393062	3.221	3.0	75	1.0	1.7
MC-DDH-011	42.00	43.00	1.00	3393063	0.353	1.4	157	10.4	14.3
MC-DDH-011	43.00	44.00	1.00	3393065	0.628	2.6	238	15.4	19.8
MC-DDH-011	44.00	45.00	1.00	3393066	0.601	1.0	174	1.1	8.8
MC-DDH-011	45.00	46.00	1.00	3393067	0.913	0.6	71	1.1	1.4
MC-DDH-011	46.00	47.00	1.00	3393068	1.507	0.9	65	0.7	3.9
MC-DDH-011	47.00	48.00	1.00	3393069	1.274	0.7	82	0.9	2.6
MC-DDH-011	48.00	49.00	1.00	3393070	0.776	0.5	61	2.7	0.8
MC-DDH-011	49.00	50.00	1.00	3393072	1.642	0.4	86	1.4	1.0
MC-DDH-011	50.00	51.00	1.00	3393073	1.369	0.4	76	0.9	1.3
MC-DDH-011	51.00	52.00	1.00	3393074	1.050	0.3	75	1.1	4.4
MC-DDH-011	52.00	53.00	1.00	3393075	2.414	0.6	95	1.2	3.6
MC-DDH-011	53.00	54.00	1.00	3393076	0.320	0.1	79	1.0	10.0
MC-DDH-011	54.00	55.00	1.00	3393077	2.536	0.8	91	0.7	412.3
MC-DDH-011	55.00	56.00	1.00	3393079	7.166	1.9	117	0.5	475.2
MC-DDH-011	56.00	57.00	1.00	3393080	1.911	0.6	54	1.2	6.4
MC-DDH-011	57.00	58.00	1.00	3393081	0.040	-0.1	38	16.1	4.9
MC-DDH-011	58.00	59.00	1.00	3393082	0.021	-0.1	51	39.2	3.1
MC-DDH-011	59.00	60.00	1.00	3393083	0.070	-0.1	71	14.0	8.2
MC-DDH-011	60.00	61.00	1.00	3393084	0.104	-0.1	41	1.2	5.7
MC-DDH-011	61.00	62.00	1.00	3393086	0.212	-0.1	63	1.2	2.7
MC-DDH-011	62.00	63.00	1.00	3393087	0.314	0.2	117	2.1	2.4
MC-DDH-011	63.00	64.00	1.00	3393088	0.191	-0.1	22	0.5	1.3
MC-DDH-011	64.00	65.00	1.00	3393089	0.012	-0.1	24	2.1	0.8
MC-DDH-011	65.00	66.00	1.00	3393090	0.018	-0.1	15	1.2	0.9
MC-DDH-011	66.00	67.00	1.00	3393091	0.009	-0.1	17	1.2	1.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-011	67.00	68.00	1.00	3393093	0.023	0.1	20	0.9	4.1
MC-DDH-011	68.00	69.00	1.00	3393094	0.014	-0.1	19	0.8	1.6
MC-DDH-011	69.00	70.00	1.00	3393095	0.008	-0.1	19	0.6	1.0
MC-DDH-011	70.00	71.00	1.00	3393096	0.014	-0.1	21	1.0	1.2
MC-DDH-011	71.00	72.00	1.00	3393097	0.023	-0.1	34	2.5	2.9
MC-DDH-011	72.00	73.00	1.00	3393098	0.089	-0.1	65	1.6	4.0
MC-DDH-011	73.00	74.00	1.00	3393100	0.125	-0.1	102	3.9	2.2
MC-DDH-011	74.00	75.00	1.00	3393101	0.032	-0.1	50	2.6	4.7
MC-DDH-011	75.00	76.00	1.00	3393102	0.048	0.4	43	2.0	2.7
MC-DDH-011	76.00	77.00	1.00	3393103	0.521	0.2	66	1.3	6.5
MC-DDH-011	77.00	78.00	1.00	3393104	0.423	0.2	131	0.6	4.6
MC-DDH-011	78.00	79.00	1.00	3393105	0.490	0.2	28	0.6	9.8
MC-DDH-011	79.00	80.00	1.00	3393107	1.527	0.3	37	3.5	37.5
MC-DDH-011	80.00	81.00	1.00	3393108	2.131	1.5	56	0.9	14.1
MC-DDH-011	81.00	82.00	1.00	3393109	0.013	-0.1	2	0.4	0.7
MC-DDH-011	82.00	83.00	1.00	3393110	0.008	-0.1	2	-0.1	0.6
MC-DDH-011	83.00	84.00	1.00	3393111	0.007	-0.1	2	0.1	0.6
MC-DDH-011	84.00	85.00	1.00	3393112	0.005	-0.1	-1	-0.1	0.6
MC-DDH-011	85.00	86.00	1.00	3393114	0.007	-0.1	23	2.5	8.8
MC-DDH-011	86.00	87.00	1.00	3393115	0.013	0.3	24	8.1	61.6
MC-DDH-011	87.00	88.00	1.00	3393116	0.005	0.3	12	4.4	48.1
MC-DDH-011	88.00	89.00	1.00	3393117	0.005	-0.1	3	0.7	2.2
MC-DDH-011	89.00	90.00	1.00	3393118	0.010	-0.1	11	10.4	4.1
MC-DDH-011	90.00	91.00	1.00	3393119	0.006	0.1	43	5.9	17.2
MC-DDH-011	91.00	92.00	1.00	3393121	0.001	-0.1	11	0.7	3.7
MC-DDH-011	92.00	93.00	1.00	3393122	0.001	-0.1	5	0.3	2.2
MC-DDH-011	93.00	94.00	1.00	3393123	0.001	-0.1	3	0.3	1.8
MC-DDH-011	94.00	95.00	1.00	3393124	0.006	-0.1	5	0.2	1.9
MC-DDH-011	95.00	96.00	1.00	3393125	0.011	-0.1	8	0.4	3.5
MC-DDH-011	96.00	97.00	1.00	3393126	0.001	-0.1	-1	0.1	1.6
MC-DDH-011	97.00	98.00	1.00	3393128	0.022	0.1	4	0.8	9.4
MC-DDH-011	98.00	99.00	1.00	3393129	0.014	-0.1	3	0.8	8.5
MC-DDH-011	99.00	100.00	1.00	3393130	0.051	0.4	24	4.3	34.5
MC-DDH-011	100.00	101.00	1.00	3393131	0.099	0.5	26	2.4	51.5
MC-DDH-011	101.00	102.00	1.00	3393132	0.084	0.5	31	6.3	35.2
MC-DDH-011	102.00	103.00	1.00	3393133	0.009	-0.1	8	0.5	6.9
MC-DDH-011	103.00	104.00	1.00	3393135	0.001	-0.1	3	0.2	2.6
MC-DDH-011	104.00	105.00	1.00	3393136	0.001	-0.1	-1	0.2	1.5
MC-DDH-011	105.00	106.00	1.00	3393137	0.001	-0.1	-1	-0.1	1.3
MC-DDH-011	106.00	107.00	1.00	3393138	0.001	-0.1	5	-0.1	1.8
MC-DDH-011	107.00	108.00	1.00	3393139	0.001	-0.1	-1	-0.1	1.1
MC-DDH-011	108.00	109.00	1.00	3393140	0.001	-0.1	-1	-0.1	1.8
MC-DDH-011	109.00	110.00	1.00	3393142	0.001	-0.1	3	-0.1	1.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-011	110.00	111.00	1.00	3393143	0.005	-0.1	1	-0.1	3.8
MC-DDH-011	111.00	112.00	1.00	3393144	0.005	-0.1	-1	-0.1	2.3
MC-DDH-011	121.00	122.00	1.00	3393151	0.000	-0.1	2	-0.1	2.4
MC-DDH-011	122.00	123.00	1.00	3393152	0.000	-0.1	-1	0.1	2.5
MC-DDH-011	123.00	124.00	1.00	3393153	0.013	-0.1	7	0.2	2.0
MC-DDH-011	124.00	125.00	1.00	3393155	0.000	-0.1	1	-0.1	2.6
MC-DDH-011	125.00	126.00	1.00	3393156	0.000	-0.1	3	0.2	8.3
MC-DDH-011	126.00	127.00	1.00	3393157	0.000	-0.1	9	0.1	2.8
MC-DDH-011	127.00	128.00	1.00	3393158	0.000	-0.1	5	-0.1	2.0
MC-DDH-011	128.00	129.00	1.00	3393159	0.008	-0.1	9	0.2	3.8
MC-DDH-011	129.00	130.00	1.00	3393160	0.039	0.2	99	1.7	397.5
MC-DDH-011	130.00	131.00	1.00	3393162	0.021	0.2	138	15.4	264.8
MC-DDH-011	131.00	132.00	1.00	3393163	0.029	0.2	173	16.1	650.6
MC-DDH-011	132.00	133.00	1.00	3393164	0.053	0.6	55	1.0	1718.6
MC-DDH-011	133.00	134.00	1.00	3393165	0.000	-0.1	7	0.3	8.6
MC-DDH-011	134.00	135.00	1.00	3393166	0.000	-0.1	8	0.1	3.4
MC-DDH-011	135.00	136.00	1.00	3393167	0.007	-0.1	6	0.1	2.4
MC-DDH-011	136.00	137.00	1.00	3393169	0.000	-0.1	3	-0.1	23.6
MC-DDH-011	137.00	138.00	1.00	3393170	0.000	-0.1	7	-0.1	5.3
MC-DDH-011	138.00	139.00	1.00	3393171	0.034	0.1	23	0.5	48.1
MC-DDH-011	139.00	140.00	1.00	3393172	0.011	-0.1	10	0.1	2.8
MC-DDH-011	140.00	141.00	1.00	3393173	0.009	-0.1	8	0.2	5.6
MC-DDH-011	141.00	142.00	1.00	3393174	0.010	-0.1	6	0.4	8.9
MC-DDH-011	142.00	143.00	1.00	3393176	0.016	0.3	12	0.5	14.5
MC-DDH-011	143.00	144.00	1.00	3393177	0.000	-0.1	5	-0.1	2.3
MC-DDH-011	144.00	145.00	1.00	3393178	0.000	-0.1	5	-0.1	2.0
MC-DDH-011	145.00	146.00	1.00	3393179	0.000	-0.1	7	-0.1	1.6
MC-DDH-011	146.00	147.00	1.00	3393180	0.078	-0.1	48	0.2	5.8
MC-DDH-011	147.00	148.00	1.00	3393181	0.006	-0.1	17	0.2	3.8
MC-DDH-011	148.00	149.00	1.00	3393183	0.000	-0.1	18	0.3	2.4
MC-DDH-011	149.00	150.00	1.00	3393184	0.000	-0.1	4	0.2	1.1
MC-DDH-011	150.00	151.00	1.00	3393185	0.000	-0.1	3	-0.1	0.7
MC-DDH-011	151.00	152.00	1.00	3393186	0.000	-0.1	4	-0.1	0.8
MC-DDH-011	152.00	153.00	1.00	3393187	0.000	-0.1	-1	-0.1	1.1
MC-DDH-011	153.00	154.00	1.00	3393188	0.000	-0.1	2	0.5	0.7
MC-DDH-011	154.00	155.00	1.00	3393190	0.010	0.1	12	4.8	2.1
MC-DDH-011	155.00	156.00	1.00	3393191	0.000	-0.1	3	0.3	0.7
MC-DDH-011	156.00	156.30	0.30	3393192	0.000	-0.1	2	8.5	0.6
MC-DDH-012	1.00	2.00	1.00	3393193	0.064	1.8	55	1.7	5.3
MC-DDH-012	2.00	3.00	1.00	3393194	0.037	2.0	21	2.6	5.0
MC-DDH-012	3.00	4.00	1.00	3393195	0.017	0.3	17	0.8	2.0
MC-DDH-012	4.00	5.00	1.00	3393197	0.008	-0.1	13	0.5	1.0
MC-DDH-012	5.00	6.00	1.00	3393198	0.035	1.9	49	0.9	4.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-012	6.00	7.00	1.00	3393199	0.013	1.6	20	0.5	5.2
MC-DDH-012	7.00	8.00	1.00	3393200	0.015	0.4	22	0.8	3.4
MC-DDH-012	8.00	9.00	1.00	3393201	0.028	0.1	16	0.5	1.3
MC-DDH-012	9.00	10.00	1.00	3393202	0.244	0.8	192	2.1	24.4
MC-DDH-012	10.00	11.00	1.00	3393204	0.093	-0.1	23	0.8	2.9
MC-DDH-012	11.00	12.00	1.00	3393205	0.040	0.2	24	0.9	3.3
MC-DDH-012	12.00	13.00	1.00	3393206	0.020	-0.1	12	1.0	3.0
MC-DDH-012	13.00	14.00	1.00	3393207	0.014	0.1	10	1.0	2.1
MC-DDH-012	14.00	15.00	1.00	3393208	0.011	-0.1	7	3.3	1.1
MC-DDH-012	15.00	16.00	1.00	3393209	0.041	0.3	7	2.2	5.1
MC-DDH-012	16.00	17.00	1.00	3393211	0.256	0.2	5	2.2	2.3
MC-DDH-012	17.00	18.00	1.00	3393212	0.017	0.2	9	10.0	1.5
MC-DDH-012	18.00	19.00	1.00	3393213	0.117	-0.1	5	5.4	2.5
MC-DDH-012	19.00	20.00	1.00	3393214	0.016	-0.1	12	0.4	0.6
MC-DDH-012	20.00	21.00	1.00	3393215	0.012	-0.1	8	7.9	14.2
MC-DDH-012	21.00	22.00	1.00	3393216	0.009	-0.1	4	5.5	1.4
MC-DDH-012	22.00	23.00	1.00	3393218	0.021	-0.1	10	0.9	2.3
MC-DDH-012	23.00	24.00	1.00	3393219	0.071	-0.1	27	0.3	1.3
MC-DDH-012	24.00	25.00	1.00	3393220	0.773	0.3	102	0.4	1.1
MC-DDH-012	25.00	26.00	1.00	3393221	0.350	0.1	85	0.4	1.0
MC-DDH-012	26.00	27.00	1.00	3393222	0.046	0.8	18	0.5	2.8
MC-DDH-012	27.00	28.00	1.00	3393223	0.033	-0.1	43	0.6	3.1
MC-DDH-012	28.00	29.00	1.00	3393225	0.050	0.8	16	0.7	1.2
MC-DDH-012	29.00	30.00	1.00	3393226	1.544	3.1	45	1.4	1.2
MC-DDH-012	30.00	31.00	1.00	3393227	0.939	7.7	46	2.0	5.7
MC-DDH-012	31.00	32.00	1.00	3393228	0.933	0.6	123	0.4	0.9
MC-DDH-012	32.00	33.00	1.00	3393229	1.058	3.1	83	0.7	0.3
MC-DDH-012	33.00	34.00	1.00	3393230	0.968	1.3	51	0.5	1.1
MC-DDH-012	34.00	35.00	1.00	3393232	1.747	0.4	44	0.4	3.2
MC-DDH-012	35.00	36.00	1.00	3393233	1.269	1.3	31	0.4	2.0
MC-DDH-012	36.00	37.00	1.00	3393234	0.536	1.1	30	0.3	1.0
MC-DDH-012	37.00	38.00	1.00	3393235	0.015	-0.1	9	0.3	0.6
MC-DDH-012	38.00	39.00	1.00	3393236	0.013	0.2	3	0.1	0.7
MC-DDH-012	39.00	40.00	1.00	3393237	0.008	-0.1	8	0.2	0.4
MC-DDH-012	40.00	41.00	1.00	3393239	0.001	-0.1	5	0.2	1.5
MC-DDH-012	41.00	42.00	1.00	3393240	0.001	0.2	2	0.1	0.4
MC-DDH-012	42.00	43.00	1.00	3393241	0.006	0.2	11	0.9	0.4
MC-DDH-012	43.00	44.00	1.00	3393242	2.328	4.3	61	1.0	1.3
MC-DDH-012	44.00	45.00	1.00	3393243	3.702	0.9	72	0.3	1.8
MC-DDH-012	45.00	46.00	1.00	3393244	0.462	0.1	40	0.4	1.7
MC-DDH-012	46.00	47.00	1.00	3393246	0.480	5.1	47	1.1	16.5
MC-DDH-012	47.00	48.00	1.00	3393247	0.909	0.3	47	0.8	14.5
MC-DDH-012	48.00	49.00	1.00	3393248	0.433	0.7	47	1.1	24.7

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-012	49.00	50.00	1.00	3393249	0.063	0.1	23	1.0	1.0
MC-DDH-012	50.00	51.00	1.00	3393250	0.201	-0.1	13	0.7	-0.1
MC-DDH-012	51.00	52.00	1.00	3393251	0.026	0.9	20	0.8	0.4
MC-DDH-012	52.00	53.00	1.00	3393253	0.209	0.2	32	0.6	0.8
MC-DDH-012	53.00	54.00	1.00	3393254	0.678	0.2	28	0.3	0.2
MC-DDH-012	54.00	55.00	1.00	3393255	0.128	-0.1	36	0.5	5.1
MC-DDH-012	55.00	56.00	1.00	3393256	10.000	0.8	55	0.5	16.1
MC-DDH-012	56.00	57.00	1.00	3393257	5.478	2.0	50	1.0	3.7
MC-DDH-012	57.00	58.00	1.00	3393258	6.526	1.4	39	0.5	3.0
MC-DDH-012	58.00	59.00	1.00	3393260	2.896	0.6	55	0.7	13.0
MC-DDH-012	59.00	60.00	1.00	3393261	1.028	0.2	67	0.3	8.3
MC-DDH-012	60.00	61.00	1.00	3393262	0.171	-0.1	60	0.4	3.1
MC-DDH-012	61.00	62.00	1.00	3393263	2.481	0.3	46	0.2	2.0
MC-DDH-012	62.00	63.00	1.00	3393264	9.590	1.4	46	-0.1	1.5
MC-DDH-012	63.00	64.00	1.00	3393265	3.211	0.4	65	0.2	2.1
MC-DDH-012	64.00	65.00	1.00	3393267	6.149	0.7	48	0.1	1.0
MC-DDH-012	65.00	66.00	1.00	3393268	8.566	1.2	64	0.1	1.8
MC-DDH-012	66.00	67.00	1.00	3393269	8.742	1.2	66	0.2	4.0
MC-DDH-012	67.00	68.00	1.00	3393270	1.883	0.2	55	0.4	3.2
MC-DDH-012	68.00	69.00	1.00	3393271	0.722	-0.1	40	0.1	0.7
MC-DDH-012	69.00	70.00	1.00	3393272	7.597	0.5	31	0.5	1.4
MC-DDH-012	70.00	71.00	1.00	3393274	8.892	1.9	57	0.6	3.1
MC-DDH-012	71.00	72.00	1.00	3393275	5.430	2.6	63	0.6	2.8
MC-DDH-012	72.00	73.00	1.00	3393276	6.536	3.6	139	1.0	58.5
MC-DDH-012	73.00	74.00	1.00	3393277	0.016	-0.1	9	0.1	1.0
MC-DDH-012	74.00	75.00	1.00	3393278	0.019	-0.1	4	0.2	0.9
MC-DDH-012	75.00	76.00	1.00	3393279	0.030	-0.1	8	-0.1	1.3
MC-DDH-012	76.00	77.00	1.00	3393281	0.006	-0.1	3	-0.1	1.3
MC-DDH-012	77.00	78.00	1.00	3393282	0.008	-0.1	4	-0.1	1.0
MC-DDH-012	78.00	79.00	1.00	3393283	0.014	-0.1	5	0.1	0.9
MC-DDH-012	79.00	80.00	1.00	3393284	0.001	-0.1	-1	0.3	1.5
MC-DDH-012	80.00	81.00	1.00	3393285	0.008	-0.1	7	-0.1	1.2
MC-DDH-012	81.00	82.00	1.00	3393286	0.001	-0.1	5	0.2	2.0
MC-DDH-012	82.00	83.00	1.00	3393288	0.008	-0.1	3	-0.1	2.3
MC-DDH-012	83.00	84.00	1.00	3393289	0.010	-0.1	2	0.2	1.3
MC-DDH-012	84.00	85.00	1.00	3393290	0.006	-0.1	2	0.3	1.2
MC-DDH-012	85.00	86.00	1.00	3393291	0.032	-0.1	18	0.5	1.4
MC-DDH-012	86.00	87.00	1.00	3393292	0.009	-0.1	15	-0.1	1.6
MC-DDH-012	87.00	88.00	1.00	3393293	0.015	-0.1	8	0.1	1.0
MC-DDH-012	88.00	89.00	1.00	3393295	0.028	0.1	12	0.7	1.2
MC-DDH-012	89.00	90.00	1.00	3393296	0.009	-0.1	14	0.4	1.3
MC-DDH-012	90.00	92.00	2.00	3393297	0.063	0.1	11	0.2	11.6
MC-DDH-012	92.00	93.00	1.00	3393298	0.011	-0.1	5	-0.1	1.7

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-012	93.00	94.00	1.00	3393299	0.010	-0.1	8	0.1	1.4
MC-DDH-012	94.00	95.00	1.00	3393300	0.005	-0.1	8	0.2	5.2
MC-DDH-012	95.00	96.00	1.00	3393302	0.007	-0.1	8	0.4	5.6
MC-DDH-012	96.00	97.00	1.00	3393303	0.006	-0.1	-1	-0.1	1.9
MC-DDH-012	97.00	98.00	1.00	3393304	0.012	-0.1	9	1.8	2.2
MC-DDH-012	98.00	99.00	1.00	3393305	0.021	0.4	15	8.2	3.8
MC-DDH-012	99.00	100.00	1.00	3393306	0.017	0.6	32	5.7	5.9
MC-DDH-012	100.00	101.00	1.00	3393307	0.036	1.2	39	3.1	15.9
MC-DDH-012	101.00	102.00	1.00	3393309	0.036	0.3	36	0.7	10.1
MC-DDH-012	102.00	102.60	0.60	3393310	0.011	-0.1	4	0.9	5.0
MC-DDH-012	102.60	103.70	1.10	3393311	0.016	-0.1	4	0.5	3.4
MC-DDH-013	1.00	2.00	1.00	3393313	0.056	8.0	30	12.0	25.5
MC-DDH-013	2.00	3.00	1.00	3393314	0.153	11.7	36	13.3	40.0
MC-DDH-013	3.00	4.00	1.00	3393315	0.057	7.6	24	14.8	32.2
MC-DDH-013	4.00	5.00	1.00	3393316	0.010	0.3	15	4.4	1.9
MC-DDH-013	5.00	6.00	1.00	3393317	0.016	0.1	19	11.5	1.4
MC-DDH-013	6.00	7.00	1.00	3393318	0.058	0.4	36	1.5	11.0
MC-DDH-013	7.00	8.00	1.00	3393320	0.083	6.2	39	1.0	30.7
MC-DDH-013	8.00	9.00	1.00	3393321	0.040	2.2	23	3.3	3.5
MC-DDH-013	9.00	10.00	1.00	3393322	0.100	7.2	25	19.7	26.4
MC-DDH-013	10.00	11.00	1.00	3393323	0.115	2.6	76	5.4	11.5
MC-DDH-013	11.00	12.00	1.00	3393324	0.360	3.0	304	11.2	23.3
MC-DDH-013	12.00	13.00	1.00	3393325	0.322	9.1	214	26.5	50.2
MC-DDH-013	13.00	14.00	1.00	3393327	0.929	13.8	531	23.6	72.3
MC-DDH-013	14.00	15.00	1.00	3393328	0.235	3.5	176	4.2	18.8
MC-DDH-013	15.00	16.00	1.00	3393329	0.092	1.1	83	3.1	4.8
MC-DDH-013	16.00	17.00	1.00	3393330	0.136	0.4	143	2.4	4.1
MC-DDH-013	17.00	18.00	1.00	3393331	0.734	1.9	56	13.3	13.0
MC-DDH-013	18.00	19.00	1.00	3393332	6.581	1.8	74	5.7	18.0
MC-DDH-013	19.00	20.00	1.00	3393334	0.236	0.7	34	2.9	11.5
MC-DDH-013	20.00	21.00	1.00	3393335	0.477	1.0	16	0.2	1.6
MC-DDH-013	21.00	22.00	1.00	3393336	0.198	0.6	28	0.2	2.5
MC-DDH-013	22.00	23.00	1.00	3393337	0.696	1.0	33	0.2	1.0
MC-DDH-013	23.00	24.00	1.00	3393338	2.333	2.5	44	0.3	1.5
MC-DDH-013	24.00	25.00	1.00	3393339	1.619	1.6	47	0.3	3.0
MC-DDH-013	25.00	26.00	1.00	3393341	3.269	6.5	45	0.2	1.7
MC-DDH-013	26.00	27.00	1.00	3393342	0.786	1.3	19	0.3	2.2
MC-DDH-013	27.00	28.00	1.00	3393343	0.092	0.4	81	0.4	2.9
MC-DDH-013	28.00	29.00	1.00	3393344	0.409	26.3	39	1.1	16.9
MC-DDH-013	29.00	30.00	1.00	3393345	0.320	11.1	30	0.8	2.5
MC-DDH-013	30.00	31.00	1.00	3393346	1.438	2.7	90	0.4	1.4
MC-DDH-013	31.00	32.00	1.00	3393348	0.036	0.8	18	0.5	5.0
MC-DDH-013	32.00	33.00	1.00	3393349	0.296	0.7	32	0.2	1.3

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-013	33.00	34.00	1.00	3393350	0.289	5.6	42	0.2	4.7
MC-DDH-013	34.00	35.00	1.00	3393351	0.568	2.2	60	0.2	1.2
MC-DDH-013	35.00	36.00	1.00	3393352	0.136	0.3	21	0.2	2.2
MC-DDH-013	36.00	37.00	1.00	3393353	0.144	0.4	15	-0.1	0.8
MC-DDH-013	37.00	38.00	1.00	3393355	0.024	0.2	20	-0.1	2.0
MC-DDH-013	38.00	39.00	1.00	3393356	0.014	0.2	9	0.2	61.9
MC-DDH-013	39.00	40.00	1.00	3393357	0.026	1.7	12	0.4	1.5
MC-DDH-013	40.00	41.00	1.00	3393358	0.011	0.3	9	0.1	0.7
MC-DDH-013	41.00	42.00	1.00	3393359	0.044	1.2	18	0.2	3.2
MC-DDH-013	42.00	43.00	1.00	3393360	0.019	0.3	23	0.4	1.0
MC-DDH-013	43.00	44.00	1.00	3393362	0.115	-0.1	67	0.7	1.6
MC-DDH-013	44.00	45.00	1.00	3393363	0.367	0.2	58	0.4	10.7
MC-DDH-013	45.00	46.00	1.00	3393364	0.203	-0.1	32	0.3	7.1
MC-DDH-013	46.00	47.00	1.00	3393365	0.401	0.2	53	0.2	5.2
MC-DDH-013	47.00	48.00	1.00	3393366	1.294	0.4	66	0.2	3.7
MC-DDH-013	48.00	49.00	1.00	3393367	3.533	0.7	85	0.4	302.0
MC-DDH-013	49.00	50.00	1.00	3393369	3.335	1.5	468	0.3	21.3
MC-DDH-013	50.00	51.00	1.00	3393370	1.584	0.5	102	0.2	2.2
MC-DDH-013	51.00	52.00	1.00	3393371	2.281	1.3	96	0.3	4.4
MC-DDH-013	52.00	53.00	1.00	3393372	4.061	0.7	51	0.2	5.3
MC-DDH-013	53.00	54.00	1.00	3393373	4.484	0.6	30	-0.1	2.4
MC-DDH-013	54.00	55.00	1.00	3393374	1.187	0.3	26	0.5	119.2
MC-DDH-013	55.00	56.00	1.00	3393376	1.795	0.2	17	0.2	3.9
MC-DDH-013	56.00	57.00	1.00	3393377	4.774	0.5	40	0.1	2.8
MC-DDH-013	57.00	58.00	1.00	3393378	0.666	0.1	16	0.5	2.3
MC-DDH-013	58.00	59.00	1.00	3393379	0.130	-0.1	12	0.2	1.1
MC-DDH-013	59.00	60.00	1.00	3393380	0.037	-0.1	9	0.1	0.5
MC-DDH-013	60.00	61.00	1.00	3393381	0.090	-0.1	17	1.5	1.5
MC-DDH-013	61.00	62.00	1.00	3393383	0.058	0.1	31	0.6	1.2
MC-DDH-013	62.00	63.00	1.00	3393384	0.102	-0.1	22	0.6	2.4
MC-DDH-013	63.00	64.00	1.00	3393385	0.111	-0.1	48	1.6	12.4
MC-DDH-013	64.00	65.00	1.00	3393386	1.168	0.4	51	1.0	21.4
MC-DDH-013	65.00	66.00	1.00	3393387	0.790	0.3	43	1.0	11.5
MC-DDH-013	66.00	67.00	1.00	3393388	2.995	0.4	24	1.2	11.2
MC-DDH-013	67.00	68.00	1.00	3393390	0.635	0.3	92	2.2	14.5
MC-DDH-013	68.00	69.00	1.00	3393391	0.880	0.6	33	2.3	4.2
MC-DDH-013	69.00	70.00	1.00	3393392	0.426	0.3	31	1.2	4.6
MC-DDH-013	70.00	71.00	1.00	3393393	0.775	0.3	27	1.8	4.9
MC-DDH-013	71.00	72.00	1.00	3393394	0.881	0.2	34	1.1	5.1
MC-DDH-013	72.00	73.00	1.00	3393395	1.114	0.6	19	0.9	6.3
MC-DDH-013	73.00	74.00	1.00	3393397	2.788	0.4	35	0.7	5.9
MC-DDH-013	74.00	75.00	1.00	3393398	0.904	0.2	24	0.9	2.0
MC-DDH-013	75.00	76.00	1.00	3393399	4.847	1.1	18	0.7	5.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-013	76.00	77.00	1.00	3393400	6.910	1.9	18	0.7	6.7
MC-DDH-013	77.00	78.00	1.00	3393401	1.861	0.9	106	0.7	5.5
MC-DDH-013	78.00	79.00	1.00	3393402	0.677	0.5	118	1.2	10.0
MC-DDH-013	79.00	80.00	1.00	3393404	0.085	-0.1	24	0.3	5.8
MC-DDH-013	80.00	81.00	1.00	3393405	1.059	0.4	61	0.4	7.0
MC-DDH-013	81.00	82.00	1.00	3393406	0.011	-0.1	4	0.5	1.6
MC-DDH-013	82.00	83.00	1.00	3393408	0.136	0.2	14	0.4	8.3
MC-DDH-013	83.00	84.00	1.00	3393409	1.017	0.8	175	1.2	48.8
MC-DDH-013	84.00	85.00	1.00	3393410	0.107	0.2	31	0.4	12.0
MC-DDH-013	85.00	86.00	1.00	3393411	0.246	0.4	82	0.6	42.5
MC-DDH-013	86.00	87.00	1.00	3393412	0.027	0.1	15	0.2	44.4
MC-DDH-013	87.00	88.00	1.00	3393413	0.172	0.6	100	0.6	20.4
MC-DDH-013	88.00	89.00	1.00	3393415	0.513	1.1	348	0.9	20.3
MC-DDH-013	89.00	90.00	1.00	3393416	0.645	1.1	371	0.5	53.7
MC-DDH-013	90.00	91.00	1.00	3393417	0.384	1.8	252	0.3	57.1
MC-DDH-013	91.00	92.00	1.00	3393418	0.029	-0.1	9	0.2	7.6
MC-DDH-013	92.00	93.00	1.00	3393419	0.125	0.2	49	0.2	23.2
MC-DDH-013	93.00	94.00	1.00	3393420	0.050	0.2	20	0.1	46.8
MC-DDH-013	94.00	95.00	1.00	3393422	0.023	-0.1	3	0.1	4.5
MC-DDH-013	95.00	96.00	1.00	3393423	0.113	0.1	12	0.2	12.2
MC-DDH-013	96.00	97.00	1.00	3393424	0.011	-0.1	8	0.2	3.2
MC-DDH-013	97.00	98.00	1.00	3393425	0.011	0.4	8	0.2	2.2
MC-DDH-013	98.00	99.00	1.00	3393426	0.011	-0.1	9	0.2	1.9
MC-DDH-013	99.00	100.00	1.00	3393427	0.019	-0.1	10	0.4	2.0
MC-DDH-013	100.00	101.00	1.00	3393429	0.022	-0.1	11	0.3	2.7
MC-DDH-013	101.00	102.00	1.00	3393430	0.011	-0.1	8	0.3	2.5
MC-DDH-013	102.00	103.00	1.00	3393431	0.042	-0.1	13	1.2	2.9
MC-DDH-013	103.00	104.00	1.00	3393432	0.020	-0.1	107	6.3	1.9
MC-DDH-013	104.00	105.00	1.00	3393433	0.009	-0.1	5	0.7	2.9
MC-DDH-013	105.00	106.00	1.00	3393434	0.007	-0.1	10	2.7	1.9
MC-DDH-013	106.00	107.00	1.00	3393436	0.010	-0.1	-1	1.2	2.4
MC-DDH-013	107.00	108.00	1.00	3393437	0.011	-0.1	9	2.2	3.1
MC-DDH-013	108.00	109.00	1.00	3393438	0.016	-0.1	7	0.6	11.8
MC-DDH-013	109.00	110.00	1.00	3393439	0.011	-0.1	4	0.5	2.9
MC-DDH-013	110.00	111.00	1.00	3393440	0.014	-0.1	5	0.6	4.1
MC-DDH-013	111.00	112.00	1.00	3393441	0.009	-0.1	8	0.6	2.5
MC-DDH-013	112.00	113.00	1.00	3393443	0.012	-0.1	3	0.4	4.4
MC-DDH-013	113.00	114.00	1.00	3393444	0.007	-0.1	-1	0.4	3.6
MC-DDH-013	114.00	115.00	1.00	3393445	0.007	-0.1	3	0.4	5.6
MC-DDH-013	115.00	116.00	1.00	3393446	0.020	-0.1	3	0.4	8.2
MC-DDH-013	116.00	117.00	1.00	3393447	0.010	-0.1	7	0.5	4.4
MC-DDH-013	117.00	118.00	1.00	3393448	0.009	-0.1	3	0.4	3.9
MC-DDH-013	118.00	119.00	1.00	3393450	0.009	-0.1	6	0.5	4.3

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-013	119.00	120.00	1.00	3393451	0.007	-0.1	-1	0.3	4.3
MC-DDH-013	120.00	121.00	1.00	3393452	0.006	-0.1	5	0.4	5.4
MC-DDH-013	121.00	122.00	1.00	3393453	0.006	-0.1	5	0.4	3.5
MC-DDH-013	122.00	123.00	1.00	3393454	0.006	-0.1	6	0.6	20.0
MC-DDH-013	123.00	124.00	1.00	3393455	0.001	-0.1	4	1.3	5.5
MC-DDH-013	124.00	125.00	1.00	3393457	0.006	-0.1	7	1.5	4.8
MC-DDH-013	125.00	126.00	1.00	3393458	0.001	-0.1	3	1.0	6.2
MC-DDH-013	126.00	126.57	0.57	3393459	0.005	-0.1	5	1.3	14.9
MC-DDH-014	0.00	1.00	1.00	3393461	0.121	9.8	83	2.4	33.3
MC-DDH-014	1.00	2.00	1.00	3393462	0.070	0.8	65	0.9	16.8
MC-DDH-014	2.00	3.00	1.00	3393463	0.059	0.5	41	0.8	11.7
MC-DDH-014	3.00	4.00	1.00	3393464	0.079	6.5	46	0.9	18.7
MC-DDH-014	4.00	5.00	1.00	3393465	0.116	16.6	35	0.7	24.4
MC-DDH-014	5.00	6.00	1.00	3393466	0.052	3.1	14	0.3	5.3
MC-DDH-014	6.00	7.00	1.00	3393468	0.110	5.9	54	0.7	80.7
MC-DDH-014	7.00	8.00	1.00	3393469	0.046	1.1	57	1.2	17.6
MC-DDH-014	8.00	9.00	1.00	3393470	0.119	0.7	111	2.7	25.6
MC-DDH-014	9.00	10.00	1.00	3393471	0.023	0.3	50	0.4	5.6
MC-DDH-014	10.00	11.00	1.00	3393472	0.047	0.9	90	0.4	1.8
MC-DDH-014	11.00	12.00	1.00	3393473	0.053	0.4	50	0.2	1.4
MC-DDH-014	12.00	13.00	1.00	3393475	0.029	0.2	115	0.3	3.9
MC-DDH-014	13.00	14.00	1.00	3393476	1.057	3.9	357	1.1	14.8
MC-DDH-014	14.00	15.00	1.00	3393477	5.397	5.5	47	0.5	10.2
MC-DDH-014	15.00	16.00	1.00	3393478	6.077	1.9	27	0.1	2.5
MC-DDH-014	16.00	17.00	1.00	3393479	10.000	7.2	28	-0.1	8.4
MC-DDH-014	17.00	18.00	1.00	3393480	4.981	3.9	35	0.3	36.5
MC-DDH-014	18.00	19.00	1.00	3393482	0.440	4.8	28	1.5	19.7
MC-DDH-014	19.00	20.00	1.00	3393483	0.084	0.3	18	2.0	23.7
MC-DDH-014	20.00	21.00	1.00	3393484	0.035	0.1	15	1.2	5.3
MC-DDH-014	21.00	22.00	1.00	3393485	0.058	0.2	11	0.2	1.8
MC-DDH-014	22.00	23.00	1.00	3393486	0.056	0.3	60	0.7	6.0
MC-DDH-014	23.00	24.00	1.00	3393487	0.030	0.2	83	2.2	5.0
MC-DDH-014	24.00	25.00	1.00	3393489	0.216	1.7	107	2.5	15.6
MC-DDH-014	25.00	26.00	1.00	3393490	0.245	6.0	115	3.0	46.9
MC-DDH-014	26.00	27.00	1.00	3393491	0.112	1.1	64	2.4	16.0
MC-DDH-014	27.00	28.00	1.00	3393492	0.027	0.2	23	0.9	4.0
MC-DDH-014	28.00	29.00	1.00	3393494	0.051	0.3	30	1.0	4.0
MC-DDH-014	29.00	30.00	1.00	3393495	0.091	0.5	57	6.4	7.8
MC-DDH-014	30.00	31.00	1.00	3393496	0.034	0.3	36	1.8	5.3
MC-DDH-014	31.00	32.00	1.00	3393497	0.024	0.2	26	0.8	5.4
MC-DDH-014	32.00	33.00	1.00	3393498	0.068	0.8	42	28.7	10.3
MC-DDH-014	33.00	34.00	1.00	3393499	0.089	0.7	74	5.9	10.9
MC-DDH-014	34.00	35.00	1.00	3393501	0.147	1.4	116	17.2	10.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-014	35.00	36.00	1.00	3393502	0.102	1.5	61	7.0	18.6
MC-DDH-014	36.00	37.00	1.00	3393503	0.052	0.3	10	0.4	1.7
MC-DDH-014	37.00	38.00	1.00	3393504	0.044	2.4	17	0.5	5.0
MC-DDH-014	38.00	39.00	1.00	3393505	0.289	1.6	20	0.5	1.8
MC-DDH-014	39.00	40.00	1.00	3393506	0.029	0.2	15	0.2	1.0
MC-DDH-014	40.00	41.00	1.00	3393508	0.013	-0.1	6	0.2	1.5
MC-DDH-014	41.00	42.00	1.00	3393509	0.007	0.1	6	0.2	0.9
MC-DDH-014	42.00	43.00	1.00	3393510	0.019	-0.1	12	0.3	0.8
MC-DDH-014	43.00	44.00	1.00	3393511	0.112	0.5	28	0.5	2.3
MC-DDH-014	44.00	45.00	1.00	3393512	0.061	1.2	16	0.2	1.6
MC-DDH-014	45.00	46.00	1.00	3393513	0.049	0.2	5	0.1	0.7
MC-DDH-014	46.00	47.00	1.00	3393515	0.141	0.3	13	0.9	28.1
MC-DDH-014	47.00	48.00	1.00	3393516	0.020	0.2	34	3.6	79.9
MC-DDH-014	48.00	49.00	1.00	3393517	0.026	0.3	68	4.4	99.0
MC-DDH-014	49.00	50.00	1.00	3393518	0.022	0.4	55	5.1	211.3
MC-DDH-014	50.00	51.00	1.00	3393519	0.034	0.5	80	5.2	275.6
MC-DDH-014	51.00	52.00	1.00	3393520	0.023	0.4	75	5.1	155.9
MC-DDH-014	52.00	53.00	1.00	3393522	0.033	0.3	68	10.0	109.5
MC-DDH-014	53.00	54.00	1.00	3393523	0.017	0.2	53	4.8	128.0
MC-DDH-014	54.00	55.00	1.00	3393524	0.015	0.2	47	6.0	86.2
MC-DDH-014	55.00	56.00	1.00	3393525	0.014	0.2	45	5.8	73.9
MC-DDH-014	56.00	57.00	1.00	3393526	0.012	0.1	27	6.5	40.8
MC-DDH-014	57.00	58.00	1.00	3393527	0.030	0.3	33	3.5	85.8
MC-DDH-014	58.00	59.00	1.00	3393529	0.025	0.2	38	3.7	56.3
MC-DDH-014	59.00	60.00	1.00	3393530	0.030	0.2	40	3.0	67.9
MC-DDH-014	60.00	61.00	1.00	3393531	0.019	0.4	34	7.9	111.7
MC-DDH-014	61.00	62.00	1.00	3393532	0.020	0.3	33	5.5	103.9
MC-DDH-014	62.00	63.00	1.00	3393533	0.022	0.3	59	8.3	95.5
MC-DDH-014	63.00	64.00	1.00	3393534	0.017	0.3	83	7.4	121.6
MC-DDH-014	64.00	65.00	1.00	3393536	0.006	-0.1	5	6.4	30.6
MC-DDH-014	65.00	66.00	1.00	3393537	0.014	0.2	13	5.3	8.9
MC-DDH-014	66.00	67.00	1.00	3393538	0.031	-0.1	29	2.8	3.0
MC-DDH-014	67.00	68.00	1.00	3393539	0.024	-0.1	33	2.4	1.4
MC-DDH-014	68.00	69.00	1.00	3393540	0.017	-0.1	18	3.4	1.4
MC-DDH-014	69.00	70.00	1.00	3393542	0.010	-0.1	5	2.5	1.4
MC-DDH-014	70.00	71.00	1.00	3393543	0.009	0.1	8	1.3	10.1
MC-DDH-014	71.00	72.00	1.00	3393544	0.006	-0.1	5	2.3	34.1
MC-DDH-014	72.00	73.00	1.00	3393545	0.010	0.1	21	5.7	47.8
MC-DDH-014	73.00	74.00	1.00	3393546	0.012	0.2	94	3.4	121.4
MC-DDH-014	74.00	75.00	1.00	3393547	0.013	0.3	136	4.6	101.1
MC-DDH-014	75.00	76.00	1.00	3393548	0.026	0.3	132	2.9	171.1
MC-DDH-014	76.00	77.00	1.00	3393550	0.013	0.2	20	3.7	144.1
MC-DDH-014	77.00	78.00	1.00	3393551	0.007	-0.1	11	2.2	6.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-014	78.00	79.00	1.00	3393552	0.008	-0.1	9	3.0	27.6
MC-DDH-014	79.00	80.00	1.00	3393553	0.007	-0.1	10	3.2	6.1
MC-DDH-014	80.00	81.00	1.00	3393554	0.008	-0.1	6	4.6	12.4
MC-DDH-014	81.00	82.00	1.00	3393555	0.007	-0.1	6	0.5	1.8
MC-DDH-014	82.00	83.00	1.00	3393557	0.013	-0.1	8	1.6	3.1
MC-DDH-014	83.00	84.00	1.00	3393558	0.234	-0.1	22	8.2	1.6
MC-DDH-014	84.00	85.00	1.00	3393559	0.137	-0.1	9	12.8	1.2
MC-DDH-014	85.00	86.00	1.00	3393560	0.009	0.1	13	4.1	1.0
MC-DDH-014	86.00	87.00	1.00	3393561	0.009	-0.1	5	3.5	1.3
MC-DDH-014	87.00	88.00	1.00	3393562	0.017	-0.1	17	1.4	2.3
MC-DDH-014	88.00	89.00	1.00	3393564	0.006	-0.1	7	1.7	1.0
MC-DDH-014	89.00	90.00	1.00	3393565	0.006	-0.1	14	0.3	2.7
MC-DDH-014	90.00	91.00	1.00	3393566	0.009	-0.1	19	0.3	1.1
MC-DDH-014	91.00	92.00	1.00	3393567	0.008	-0.1	19	0.3	1.9
MC-DDH-014	92.00	93.00	1.00	3393568	0.092	0.2	37	0.4	2.4
MC-DDH-014	93.00	94.00	1.00	3393569	0.078	0.5	105	2.5	26.4
MC-DDH-014	94.00	95.00	1.00	3393571	0.085	0.4	136	1.6	19.2
MC-DDH-014	95.00	96.00	1.00	3393572	0.067	0.4	104	1.5	34.7
MC-DDH-014	96.00	97.00	1.00	3393573	0.042	0.3	56	1.3	40.0
MC-DDH-014	97.00	98.00	1.00	3393574	0.012	0.1	21	1.0	10.5
MC-DDH-014	98.00	99.00	1.00	3393575	0.033	0.3	54	1.0	9.6
MC-DDH-014	99.00	100.00	1.00	3393576	0.027	0.2	56	1.2	8.4
MC-DDH-014	100.00	101.00	1.00	3393578	0.010	-0.1	9	0.9	4.4
MC-DDH-014	101.00	102.00	1.00	3393579	0.018	0.3	11	1.1	7.3
MC-DDH-014	102.00	103.00	1.00	3393580	0.009	-0.1	10	0.9	2.3
MC-DDH-014	103.00	104.00	1.00	3393582	0.001	-0.1	4	0.5	1.5
MC-DDH-014	104.00	105.00	1.00	3393583	0.007	-0.1	5	0.5	1.9
MC-DDH-014	105.00	106.00	1.00	3393584	0.039	0.2	31	1.6	6.5
MC-DDH-014	106.00	107.00	1.00	3393585	0.352	0.4	34	0.7	5.9
MC-DDH-014	107.00	108.00	1.00	3393586	0.010	0.2	26	1.2	3.2
MC-DDH-014	108.00	109.00	1.00	3393587	0.032	0.4	24	0.3	4.2
MC-DDH-014	109.00	110.00	1.00	3393589	0.012	-0.1	22	0.4	6.8
MC-DDH-014	110.00	111.00	1.00	3393590	0.020	0.1	20	0.3	3.8
MC-DDH-014	111.00	112.00	1.00	3393591	0.025	-0.1	21	0.1	2.1
MC-DDH-014	112.00	113.00	1.00	3393592	0.012	-0.1	22	0.2	1.7
MC-DDH-014	113.00	114.00	1.00	3393593	0.013	0.2	26	0.2	12.3
MC-DDH-014	114.00	115.00	1.00	3393594	0.009	0.1	26	0.2	3.4
MC-DDH-014	115.00	116.00	1.00	3393596	0.011	0.2	20	0.2	2.3
MC-DDH-014	116.00	117.00	1.00	3393597	0.008	-0.1	22	0.2	2.7
MC-DDH-014	117.00	118.00	1.00	3393598	0.009	-0.1	14	0.2	5.1
MC-DDH-014	118.00	119.00	1.00	3393599	0.015	-0.1	18	-0.1	3.6
MC-DDH-014	119.00	120.00	1.00	3393600	0.010	0.1	20	0.2	7.9
MC-DDH-014	120.00	121.00	1.00	3393601	0.007	0.1	20	2.0	4.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-014	121.00	122.00	1.00	3393603	0.006	-0.1	15	9.4	4.1
MC-DDH-015	0.00	1.00	1.00	3393605	0.316	2.3	69	2.0	9.3
MC-DDH-015	1.00	2.00	1.00	3393606	0.362	3.8	101	2.2	20.0
MC-DDH-015	2.00	3.00	1.00	3393607	0.160	1.7	69	1.7	14.2
MC-DDH-015	3.00	4.00	1.00	3393608	0.072	0.9	10	0.5	7.3
MC-DDH-015	4.00	5.00	1.00	3393609	0.028	0.2	7	0.4	3.9
MC-DDH-015	5.00	6.00	1.00	3393610	0.016	0.2	2	0.4	2.6
MC-DDH-015	6.00	7.00	1.00	3393612	0.020	0.5	17	0.4	5.9
MC-DDH-015	7.00	8.00	1.00	3393613	0.082	1.0	26	3.2	4.0
MC-DDH-015	8.00	9.00	1.00	3393614	0.109	3.3	65	3.5	3.4
MC-DDH-015	9.00	10.00	1.00	3393615	0.111	0.5	10	0.3	2.6
MC-DDH-015	10.00	11.00	1.00	3393616	0.145	3.2	33	0.8	10.1
MC-DDH-015	11.00	12.00	1.00	3393617	0.096	8.3	70	0.9	10.8
MC-DDH-015	12.00	13.00	1.00	3393619	1.113	30.4	402	11.3	55.0
MC-DDH-015	13.00	14.00	1.00	3393620	1.008	2.8	670	30.1	40.5
MC-DDH-015	14.00	15.00	1.00	3393621	0.200	1.3	178	15.2	19.1
MC-DDH-015	15.00	16.00	1.00	3393622	0.051	0.3	40	1.3	20.6
MC-DDH-015	16.00	17.00	1.00	3393623	0.276	1.4	94	6.9	15.5
MC-DDH-015	17.00	18.00	1.00	3393624	0.023	0.2	43	1.6	4.6
MC-DDH-015	18.00	19.00	1.00	3393626	0.022	0.4	27	1.0	16.9
MC-DDH-015	19.00	20.00	1.00	3393627	0.007	-0.1	9	0.3	9.3
MC-DDH-015	20.00	21.00	1.00	3393628	0.001	-0.1	3	0.3	24.3
MC-DDH-015	21.00	22.00	1.00	3393629	0.001	-0.1	3	-0.1	8.7
MC-DDH-015	22.00	23.00	1.00	3393630	0.008	-0.1	11	0.3	21.3
MC-DDH-015	23.00	24.00	1.00	3393631	0.015	-0.1	33	0.2	16.5
MC-DDH-015	24.00	25.00	1.00	3393633	0.025	0.1	48	0.2	21.2
MC-DDH-015	25.00	26.00	1.00	3393634	0.085	0.4	68	2.4	16.2
MC-DDH-015	26.00	27.00	1.00	3393635	0.087	0.5	75	2.6	15.8
MC-DDH-015	27.00	28.00	1.00	3393636	0.074	0.3	68	1.8	9.7
MC-DDH-015	28.00	29.00	1.00	3393637	0.077	0.4	63	1.4	9.8
MC-DDH-015	29.00	30.00	1.00	3393638	0.011	-0.1	8	0.7	28.4
MC-DDH-015	30.00	31.00	1.00	3393640	0.286	0.5	15	6.0	34.9
MC-DDH-015	31.00	32.00	1.00	3393641	0.495	2.3	136	3.1	21.2
MC-DDH-015	32.00	33.00	1.00	3393642	0.177	0.6	186	1.3	13.3
MC-DDH-015	33.00	34.00	1.00	3393643	0.253	1.4	158	2.4	23.3
MC-DDH-015	34.00	35.00	1.00	3393644	0.165	0.9	47	2.7	35.8
MC-DDH-015	35.00	36.00	1.00	3393645	0.242	0.5	45	2.9	19.6
MC-DDH-015	36.00	37.00	1.00	3393647	0.139	0.8	53	1.7	26.1
MC-DDH-015	37.00	38.00	1.00	3393648	0.089	-0.1	84	0.7	11.6
MC-DDH-015	38.00	39.00	1.00	3393649	0.398	0.2	105	1.0	19.1
MC-DDH-015	39.00	40.00	1.00	3393650	0.798	0.3	79	0.8	29.6
MC-DDH-015	40.00	41.00	1.00	3393651	0.357	0.3	81	0.9	29.1
MC-DDH-015	41.00	42.00	1.00	3393652	2.663	0.6	106	1.0	163.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	42.00	43.00	1.00	3393654	0.315	0.2	107	2.6	10.0
MC-DDH-015	43.00	44.00	1.00	3393655	0.785	0.2	131	0.9	39.0
MC-DDH-015	44.00	45.00	1.00	3393656	0.194	0.3	148	0.8	7.7
MC-DDH-015	45.00	46.00	1.00	3393657	0.182	0.3	208	3.0	24.8
MC-DDH-015	46.00	47.00	1.00	3393658	0.307	0.4	321	3.3	19.9
MC-DDH-015	47.00	48.00	1.00	3393659	0.350	0.1	130	2.2	13.3
MC-DDH-015	48.00	49.00	1.00	3393661	0.198	0.1	123	0.6	17.8
MC-DDH-015	49.00	50.00	1.00	3393662	0.453	0.1	143	0.9	21.1
MC-DDH-015	50.00	51.00	1.00	3393663	0.627	0.1	167	1.0	16.0
MC-DDH-015	51.00	52.00	1.00	3393664	0.778	0.4	159	1.0	85.7
MC-DDH-015	52.00	53.00	1.00	3393665	0.165	0.2	78	1.9	44.5
MC-DDH-015	53.00	54.00	1.00	3393666	0.250	0.2	112	1.7	40.8
MC-DDH-015	54.00	55.00	1.00	3393668	0.140	0.4	72	2.1	136.6
MC-DDH-015	55.00	56.00	1.00	3393669	4.633	0.6	55	0.8	8.3
MC-DDH-015	56.00	57.00	1.00	3393670	0.407	0.2	52	1.4	7.5
MC-DDH-015	57.00	58.00	1.00	3393671	0.391	0.3	195	1.5	14.4
MC-DDH-015	58.00	59.00	1.00	3393672	0.925	0.5	147	1.6	9.1
MC-DDH-015	59.00	60.00	1.00	3393673	1.010	0.7	199	3.8	17.1
MC-DDH-015	60.00	61.00	1.00	3393675	0.042	0.1	11	4.5	34.1
MC-DDH-015	61.00	62.00	1.00	3393676	0.006	-0.1	3	0.7	38.5
MC-DDH-015	62.00	63.00	1.00	3393677	0.012	-0.1	3	0.3	16.0
MC-DDH-015	63.00	64.00	1.00	3393678	0.001	-0.1	3	0.4	9.0
MC-DDH-015	64.00	65.00	1.00	3393679	0.005	-0.1	2	0.1	10.9
MC-DDH-015	65.00	66.00	1.00	3393680	0.006	-0.1	5	0.4	18.7
MC-DDH-015	66.00	67.00	1.00	3393682	0.007	-0.1	3	0.4	24.4
MC-DDH-015	67.00	68.00	1.00	3393683	0.006	-0.1	3	0.3	13.2
MC-DDH-015	68.00	69.00	1.00	3393684	0.015	0.2	25	1.4	77.5
MC-DDH-015	69.00	70.00	1.00	3393685	0.032	0.3	75	0.9	44.2
MC-DDH-015	70.00	71.00	1.00	3393686	0.044	0.4	46	0.4	17.9
MC-DDH-015	71.00	72.00	1.00	3393687	0.045	0.6	41	0.3	36.2
MC-DDH-015	72.00	73.00	1.00	3393689	0.024	0.4	50	2.1	53.7
MC-DDH-015	73.00	74.00	1.00	3393690	0.200	0.1	37	0.5	14.4
MC-DDH-015	74.00	75.00	1.00	3393691	0.021	-0.1	9	-0.1	15.7
MC-DDH-015	75.00	76.00	1.00	3393692	0.022	-0.1	15	-0.1	14.4
MC-DDH-015	76.00	77.00	1.00	3393693	0.029	0.1	12	0.3	15.8
MC-DDH-015	77.00	78.00	1.00	3393695	0.015	0.1	9	2.1	29.9
MC-DDH-015	78.00	79.00	1.00	3393696	0.014	0.1	11	2.0	48.4
MC-DDH-015	79.00	80.00	1.00	3393697	0.019	0.1	18	0.8	26.4
MC-DDH-015	80.00	81.00	1.00	3393698	0.046	0.2	50	1.1	27.4
MC-DDH-015	81.00	82.00	1.00	3393700	0.034	0.2	15	0.7	59.7
MC-DDH-015	82.00	83.00	1.00	3393701	0.030	0.3	18	0.4	65.3
MC-DDH-015	83.00	84.00	1.00	3393702	0.012	0.1	13	0.3	17.4
MC-DDH-015	84.00	85.00	1.00	3393703	0.009	-0.1	9	1.2	32.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	85.00	86.00	1.00	3393704	0.013	-0.1	9	0.5	34.9
MC-DDH-015	86.00	87.00	1.00	3393705	0.010	0.1	6	1.8	30.2
MC-DDH-015	87.00	88.00	1.00	3393707	0.046	0.2	44	1.7	18.5
MC-DDH-015	88.00	89.00	1.00	3393708	0.151	0.5	62	1.9	138.3
MC-DDH-015	89.00	90.00	1.00	3393709	0.056	0.2	49	1.4	21.1
MC-DDH-015	90.00	91.00	1.00	3393710	0.009	-0.1	8	0.8	18.4
MC-DDH-015	91.00	92.00	1.00	3393711	0.008	-0.1	4	0.5	22.1
MC-DDH-015	93.00	94.00	1.00	3393714	0.001	-0.1	2	0.2	22.2
MC-DDH-015	94.00	95.00	1.00	3393715	0.001	-0.1	4	0.2	25.2
MC-DDH-015	95.00	96.00	1.00	3393716	0.001	-0.1	3	0.2	19.3
MC-DDH-015	96.00	97.00	1.00	3393717	0.001	-0.1	4	0.2	37.0
MC-DDH-015	97.00	98.00	1.00	3393718	0.011	-0.1	7	1.0	55.8
MC-DDH-015	98.00	99.00	1.00	3393719	0.010	-0.1	3	0.5	36.6
MC-DDH-015	99.00	100.00	1.00	3393721	0.007	-0.1	3	0.7	13.6
MC-DDH-015	100.00	101.00	1.00	3393722	0.001	-0.1	2	0.2	19.9
MC-DDH-015	101.00	102.00	1.00	3393723	0.001	-0.1	3	0.8	25.7
MC-DDH-015	102.00	103.00	1.00	3393724	0.001	-0.1	3	0.3	20.0
MC-DDH-015	103.00	104.00	1.00	3393725	0.001	-0.1	3	0.1	13.8
MC-DDH-015	104.00	105.00	1.00	3393726	0.001	-0.1	3	0.2	14.6
MC-DDH-015	105.00	106.00	1.00	3393728	0.001	-0.1	2	0.2	14.1
MC-DDH-015	106.00	107.00	1.00	3393729	0.012	0.1	5	1.1	26.9
MC-DDH-015	107.00	108.00	1.00	3393730	0.001	-0.1	2	0.6	12.9
MC-DDH-015	108.00	109.00	1.00	3393731	0.005	-0.1	2	0.4	14.1
MC-DDH-015	109.00	110.00	1.00	3393732	0.010	0.1	2	0.5	16.1
MC-DDH-015	110.00	111.00	1.00	3393733	0.006	-0.1	2	0.1	13.3
MC-DDH-015	111.00	112.00	1.00	3393735	0.006	-0.1	2	0.2	15.1
MC-DDH-015	112.00	113.00	1.00	3393736	0.005	-0.1	1	0.3	13.8
MC-DDH-015	113.00	114.00	1.00	3393737	0.001	-0.1	2	0.3	20.8
MC-DDH-015	114.00	115.00	1.00	3393738	0.024	0.2	8	3.0	26.0
MC-DDH-015	115.00	116.00	1.00	3393739	0.012	-0.1	4	1.1	16.1
MC-DDH-015	117.00	118.00	1.00	3393742	0.001	-0.1	1	0.4	19.1
MC-DDH-015	118.00	119.00	1.00	3393743	0.007	-0.1	15	0.4	19.1
MC-DDH-015	119.00	120.00	1.00	3393744	0.007	-0.1	16	0.6	11.1
MC-DDH-015	120.00	121.00	1.00	3393745	0.011	-0.1	38	0.3	20.0
MC-DDH-015	121.00	122.00	1.00	3393746	0.011	0.1	52	0.6	12.1
MC-DDH-015	122.00	123.00	1.00	3393747	0.010	0.1	27	1.0	27.9
MC-DDH-015	123.00	124.00	1.00	3393749	0.008	-0.1	49	0.5	8.6
MC-DDH-015	124.00	125.00	1.00	3393750	0.026	-0.1	15	0.8	25.3
MC-DDH-015	125.00	126.00	1.00	3393751	0.084	-0.1	4	0.5	18.3
MC-DDH-015	126.00	127.00	1.00	3393752	0.008	-0.1	2	0.2	16.2
MC-DDH-015	127.00	128.00	1.00	3393753	0.008	-0.1	5	0.5	11.0
MC-DDH-015	128.00	129.00	1.00	3393754	0.006	-0.1	1	0.2	13.7
MC-DDH-015	129.00	130.00	1.00	3393756	0.006	-0.1	-1	0.4	20.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	130.00	131.00	1.00	3393757	0.023	0.2	12	0.6	25.0
MC-DDH-015	131.00	132.00	1.00	3393758	0.006	-0.1	-1	0.1	20.3
MC-DDH-015	132.00	133.00	1.00	3393759	0.009	-0.1	5	0.2	15.9
MC-DDH-015	133.00	134.00	1.00	3393760	0.009	-0.1	3	0.3	20.7
MC-DDH-015	134.00	135.00	1.00	3393761	0.006	-0.1	1	0.1	18.2
MC-DDH-015	135.00	136.00	1.00	3393763	0.007	-0.1	2	0.3	13.8
MC-DDH-015	136.00	137.00	1.00	3393764	0.006	-0.1	2	0.2	9.0
MC-DDH-015	137.00	138.00	1.00	3393765	0.009	-0.1	4	0.2	22.5
MC-DDH-015	138.00	139.00	1.00	3393766	0.007	-0.1	4	0.1	16.2
MC-DDH-015	139.00	140.00	1.00	3393767	0.009	-0.1	6	0.3	15.0
MC-DDH-015	141.00	142.00	1.00	3393770	0.001	-0.1	2	-0.1	12.4
MC-DDH-015	142.00	143.00	1.00	3393771	0.001	-0.1	2	0.2	20.2
MC-DDH-015	143.00	144.00	1.00	3393772	0.009	-0.1	6	0.2	13.4
MC-DDH-015	144.00	145.00	1.00	3393773	0.001	-0.1	1	0.1	27.3
MC-DDH-015	145.00	146.00	1.00	3393774	0.001	-0.1	2	0.2	18.8
MC-DDH-015	146.00	147.00	1.00	3393775	0.001	-0.1	4	0.3	13.4
MC-DDH-015	147.00	148.00	1.00	3393777	0.001	-0.1	1	0.1	2.6
MC-DDH-015	148.00	149.00	1.00	3393778	0.001	-0.1	3	-0.1	6.4
MC-DDH-015	149.00	150.00	1.00	3393779	0.015	-0.1	5	0.2	5.1
MC-DDH-015	150.00	151.00	1.00	3393780	0.001	-0.1	3	0.2	14.8
MC-DDH-015	151.00	152.00	1.00	3393781	0.008	-0.1	15	1.7	60.4
MC-DDH-015	152.00	153.00	1.00	3393782	0.008	-0.1	16	5.0	35.8
MC-DDH-015	153.00	154.00	1.00	3393784	0.008	-0.1	26	2.3	9.7
MC-DDH-015	154.00	155.00	1.00	3393785	0.021	0.3	61	2.7	56.8
MC-DDH-015	155.00	156.00	1.00	3393786	0.015	0.2	51	3.1	128.3
MC-DDH-015	156.00	157.00	1.00	3393787	0.007	-0.1	23	1.9	52.8
MC-DDH-015	157.00	158.00	1.00	3393788	0.007	-0.1	37	2.3	90.1
MC-DDH-015	158.00	159.00	1.00	3393789	0.009	-0.1	26	2.4	55.0
MC-DDH-015	159.00	160.00	1.00	3393791	0.006	-0.1	20	2.4	66.0
MC-DDH-015	160.00	161.00	1.00	3393792	0.007	-0.1	12	2.0	52.3
MC-DDH-015	161.00	162.00	1.00	3393793	0.005	-0.1	16	3.3	20.1
MC-DDH-015	162.00	163.00	1.00	3393794	0.001	0.2	25	135.6	49.0
MC-DDH-015	163.00	164.00	1.00	3393795	0.006	0.1	15	4.7	103.2
MC-DDH-015	165.00	166.00	1.00	3393798	0.006	0.2	8	2.0	83.0
MC-DDH-015	166.00	167.00	1.00	3393799	0.006	0.1	13	2.0	67.4
MC-DDH-015	167.00	168.00	1.00	3393800	0.010	0.2	13	1.7	93.5
MC-DDH-015	168.00	169.00	1.00	3393801	0.012	0.2	11	1.5	66.3
MC-DDH-015	169.00	170.00	1.00	3393802	0.016	0.2	9	0.6	75.9
MC-DDH-015	170.00	171.00	1.00	3393803	0.001	0.1	9	1.8	90.2
MC-DDH-015	171.00	172.00	1.00	3393805	0.005	0.1	10	3.0	54.3
MC-DDH-015	172.00	173.00	1.00	3393806	0.005	-0.1	5	1.8	30.1
MC-DDH-015	173.00	173.85	0.85	3393807	0.001	-0.1	12	2.3	24.8
MC-DDH-016	0.00	1.00	1.00	3393809	1.210	0.7	84	3.5	212.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-016	1.00	2.00	1.00	3393810	1.120	0.9	92	3.5	38.6
MC-DDH-016	2.00	3.00	1.00	3393811	1.090	1.5	89	3.4	46.6
MC-DDH-016	3.00	4.00	1.00	3393812	0.390	1.8	88	5.1	62.3
MC-DDH-016	4.00	5.00	1.00	3393813	0.230	0.4	79	3.7	50.9
MC-DDH-016	5.00	6.00	1.00	3393814	0.560	2.9	58	1.7	42.4
MC-DDH-016	6.00	7.00	1.00	3393816	7.400	3.3	43	0.5	19.1
MC-DDH-016	7.00	8.00	1.00	3393817	3.940	3.8	49	0.8	21.4
MC-DDH-016	8.00	9.00	1.00	3393818	1.890	9.0	42	0.8	33.2
MC-DDH-016	9.00	10.00	1.00	3393819	1.420	2.4	44	0.9	9.4
MC-DDH-016	10.00	11.00	1.00	3393820	1.310	5.1	54	0.8	9.9
MC-DDH-016	12.00	13.00	1.00	3393823	1.570	3.4	37	2.1	12.3
MC-DDH-016	13.00	14.00	1.00	3393824	0.370	0.9	40	1.1	7.3
MC-DDH-016	14.00	15.00	1.00	3393825	0.220	5.4	17	4.3	24.4
MC-DDH-016	15.00	16.00	1.00	3393826	0.110	6.2	13	4.7	26.9
MC-DDH-016	16.00	17.00	1.00	3393827	0.540	5.4	130	4.5	21.0
MC-DDH-016	17.00	18.00	1.00	3393828	0.150	1.2	35	3.8	5.9
MC-DDH-016	18.00	19.00	1.00	3393830	0.620	1.2	38	1.7	5.8
MC-DDH-016	19.00	20.00	1.00	3393831	-0.050	1.3	21	0.9	6.0
MC-DDH-016	20.00	21.00	1.00	3393832	0.200	2.1	54	1.8	7.2
MC-DDH-016	21.00	22.00	1.00	3393833	6.370	1.5	50	0.6	2.6
MC-DDH-016	22.00	23.00	1.00	3393834	5.680	6.9	64	1.3	15.6
MC-DDH-016	23.00	24.00	1.00	3393835	1.790	6.2	44	0.9	11.1
MC-DDH-016	24.00	25.00	1.00	3393837	0.730	15.0	44	0.8	31.3
MC-DDH-016	25.00	26.00	1.00	3393838	2.840	6.5	56	1.2	5.6
MC-DDH-016	26.00	27.00	1.00	3393839	1.090	1.8	38	0.6	4.5
MC-DDH-016	27.00	28.00	1.00	3393840	0.720	4.1	49	1.1	5.7
MC-DDH-016	28.00	29.00	1.00	3393841	0.170	1.3	59	2.0	11.4
MC-DDH-016	29.00	30.00	1.00	3393842	0.490	0.5	49	1.7	7.2
MC-DDH-016	30.00	31.00	1.00	3393844	2.150	1.3	64	2.6	43.0
MC-DDH-016	31.00	32.00	1.00	3393845	2.160	3.7	77	3.0	124.3
MC-DDH-016	32.00	33.00	1.00	3393846	1.850	4.3	254	8.4	207.5
MC-DDH-016	33.00	34.00	1.00	3393847	1.050	5.4	349	10.8	224.6
MC-DDH-016	34.00	35.00	1.00	3393848	1.200	6.5	367	10.4	219.3
MC-DDH-016	36.00	37.00	1.00	3393851	1.380	3.8	400	30.2	222.5
MC-DDH-016	37.00	38.00	1.00	3393852	0.730	3.0	393	24.0	236.0
MC-DDH-016	38.00	39.00	1.00	3393853	0.910	4.4	348	26.4	148.7
MC-DDH-016	39.00	40.00	1.00	3393854	0.350	2.8	276	19.8	135.6
MC-DDH-016	40.00	41.00	1.00	3393855	0.250	3.3	248	32.1	165.5
MC-DDH-016	41.00	42.00	1.00	3393856	0.700	4.4	365	32.8	236.7
MC-DDH-016	42.00	43.00	1.00	3393858	1.600	3.3	438	23.1	388.0
MC-DDH-016	43.00	44.00	1.00	3393859	6.060	3.1	391	13.7	285.0
MC-DDH-016	44.00	45.00	1.00	3393860	16.330	6.6	174	5.1	655.2
MC-DDH-016	45.00	46.00	1.00	3393861	0.150	0.2	37	1.0	4.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-016	46.00	47.00	1.00	3393862	0.160	0.4	70	0.8	4.1
MC-DDH-016	47.00	48.00	1.00	3393863	0.050	12.8	25	1.7	4.5
MC-DDH-016	48.00	49.00	1.00	3393865	0.090	5.5	25	1.2	2.6
MC-DDH-016	49.00	50.00	1.00	3393866	0.510	16.7	36	1.7	13.2
MC-DDH-016	50.00	51.00	1.00	3393867	0.390	2.6	51	0.7	2.8
MC-DDH-016	51.00	52.00	1.00	3393868	0.730	17.9	29	0.8	3.9
MC-DDH-016	52.00	53.00	1.00	3393869	1.190	1.0	51	1.7	1.4
MC-DDH-016	53.00	54.00	1.00	3393870	1.040	1.7	85	1.9	11.7
MC-DDH-016	54.00	55.00	1.00	3393872	1.070	3.9	74	4.6	22.3
MC-DDH-016	55.00	56.00	1.00	3393873	0.390	4.9	77	5.2	23.5
MC-DDH-016	56.00	57.00	1.00	3393874	0.210	4.1	78	4.4	35.3
MC-DDH-016	57.00	58.00	1.00	3393875	0.120	2.1	54	1.6	103.4
MC-DDH-016	58.00	59.00	1.00	3393876	-0.050	0.8	45	1.0	102.4
MC-DDH-016	60.00	61.00	1.00	3393879	0.520	1.9	68	1.3	101.0
MC-DDH-016	61.00	62.00	1.00	3393880	0.640	1.3	126	4.3	268.8
MC-DDH-016	62.00	63.00	1.00	3393881	2.090	4.0	182	3.9	320.3
MC-DDH-016	63.00	64.00	1.00	3393882	1.960	2.3	245	3.3	403.0
MC-DDH-016	64.00	65.00	1.00	3393883	1.300	2.3	183	4.4	355.7
MC-DDH-016	65.00	66.00	1.00	3393884	0.150	0.5	47	1.9	99.4
MC-DDH-016	66.00	67.00	1.00	3393886	0.660	0.8	86	2.4	41.8
MC-DDH-016	67.00	68.00	1.00	3393887	3.970	4.6	268	6.5	380.9
MC-DDH-016	68.00	69.00	1.00	3393888	1.620	1.6	204	5.7	329.6
MC-DDH-016	69.00	70.00	1.00	3393889	-0.050	-0.1	11	0.2	6.8
MC-DDH-016	70.00	71.00	1.00	3393890	-0.050	-0.1	8	-0.1	2.8
MC-DDH-016	71.00	72.00	1.00	3393891	-0.050	-0.1	2	-0.1	1.7
MC-DDH-016	72.00	73.00	1.00	3393893	-0.050	-0.1	1	-0.1	1.4
MC-DDH-016	73.00	74.00	1.00	3393894	-0.050	-0.1	4	-0.1	1.3
MC-DDH-016	74.00	75.00	1.00	3393895	-0.050	-0.1	4	-0.1	1.3
MC-DDH-016	75.00	76.00	1.00	3393896	-0.050	-0.1	4	0.1	2.1
MC-DDH-016	76.00	77.00	1.00	3393897	-0.050	-0.1	29	49.9	12.8
MC-DDH-016	77.00	78.00	1.00	3393898	-0.050	-0.1	52	24.8	32.9
MC-DDH-016	78.00	79.00	1.00	3393900	-0.050	0.2	50	23.1	32.2
MC-DDH-016	79.00	80.00	1.00	3393901	-0.050	-0.1	23	244.0	2.6
MC-DDH-016	80.00	81.00	1.00	3393902	-0.050	-0.1	77	70.5	3.1
MC-DDH-016	81.00	82.00	1.00	3393903	-0.050	0.2	33	3.8	9.6
MC-DDH-016	82.00	83.00	1.00	3393904	-0.050	-0.1	8	2.1	3.4
MC-DDH-016	84.00	85.00	1.00	3393907	-0.050	-0.1	3	0.2	2.2
MC-DDH-016	85.00	86.00	1.00	3393908	-0.050	-0.1	5	0.3	2.5
MC-DDH-016	86.00	87.00	1.00	3393909	-0.050	0.3	46	0.6	6.3
MC-DDH-016	87.00	88.00	1.00	3393910	-0.050	0.8	17	0.3	7.5
MC-DDH-016	88.00	89.00	1.00	3393911	-0.050	-0.1	-1	0.3	2.3
MC-DDH-016	89.00	90.00	1.00	3393912	-0.050	-0.1	6	-0.1	2.1
MC-DDH-016	90.00	91.00	1.00	3393914	0.007	-0.1	2	-0.1	2.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-016	91.00	92.00	1.00	3393915	0.006	-0.1	-1	-0.1	0.9
MC-DDH-016	92.00	93.00	1.00	3393916	0.005	-0.1	1	-0.1	1.2
MC-DDH-016	93.00	94.00	1.00	3393917	0.008	-0.1	-1	-0.1	1.2
MC-DDH-016	94.00	95.00	1.00	3393918	0.008	-0.1	3	-0.1	1.6
MC-DDH-016	95.00	96.00	1.00	3393919	0.006	-0.1	3	-0.1	1.0
MC-DDH-016	96.00	97.00	1.00	3393921	0.007	-0.1	1	-0.1	1.0
MC-DDH-016	97.00	98.00	1.00	3393922	0.006	-0.1	-1	0.3	0.8
MC-DDH-016	98.00	99.00	1.00	3393923	0.006	-0.1	-1	-0.1	1.1
MC-DDH-016	99.00	100.00	1.00	3393924	0.006	-0.1	5	0.4	1.6
MC-DDH-016	100.00	101.00	1.00	3393925	0.007	-0.1	3	0.2	1.4
MC-DDH-016	101.00	102.00	1.00	3393926	0.006	-0.1	1	-0.1	1.2
MC-DDH-016	102.00	103.00	1.00	3393928	0.007	-0.1	2	-0.1	2.2
MC-DDH-016	103.00	104.00	1.00	3393929	0.005	-0.1	-1	0.1	1.8
MC-DDH-016	104.00	105.00	1.00	3393930	0.005	-0.1	2	-0.1	0.7
MC-DDH-016	105.00	106.00	1.00	3393931	0.008	-0.1	3	0.6	3.2
MC-DDH-016	106.00	107.00	1.00	3393932	0.001	-0.1	2	0.2	2.7
MC-DDH-016	107.00	108.00	1.00	3393933	0.006	-0.1	16	0.3	2.4
MC-DDH-016	108.00	109.00	1.00	3393935	0.006	-0.1	7	0.2	3.4
MC-DDH-016	109.00	110.00	1.00	3393936	0.006	-0.1	1	-0.1	2.5
MC-DDH-016	110.00	111.00	1.00	3393937	0.005	0.3	3	0.1	2.9
MC-DDH-016	111.00	112.00	1.00	3393938	0.005	-0.1	3	0.4	2.6
MC-DDH-016	112.00	112.85	0.85	3393939	0.006	-0.1	2	0.2	1.4
MC-DDH-017	0.00	1.00	1.00	3393941	2.040	14.2	26	0.4	46.6
MC-DDH-017	1.00	2.00	1.00	3393942	2.071	4.7	23	0.5	15.1
MC-DDH-017	2.00	3.00	1.00	3393943	0.164	0.9	13	0.5	4.3
MC-DDH-017	3.00	4.00	1.00	3393944	0.123	0.5	15	1.1	2.9
MC-DDH-017	4.00	5.00	1.00	3393945	0.358	1.4	27	0.4	19.7
MC-DDH-017	5.00	6.00	1.00	3393946	0.260	1.4	22	0.4	25.4
MC-DDH-017	6.00	7.00	1.00	3393948	0.933	1.5	24	0.4	8.6
MC-DDH-017	7.00	8.00	1.00	3393949	1.202	1.2	25	0.5	16.9
MC-DDH-017	8.00	9.00	1.00	3393950	0.071	0.3	32	0.6	3.8
MC-DDH-017	9.00	10.00	1.00	3393951	0.031	0.6	20	1.4	12.9
MC-DDH-017	10.00	11.00	1.00	3393952	0.026	0.6	10	0.7	28.8
MC-DDH-017	11.00	12.00	1.00	3393953	0.020	1.3	31	0.5	51.9
MC-DDH-017	12.00	13.00	1.00	3393955	0.048	0.3	22	0.7	3.9
MC-DDH-017	13.00	14.00	1.00	3393956	0.069	0.7	23	0.9	16.0
MC-DDH-017	14.00	15.00	1.00	3393957	0.117	9.3	39	1.3	46.3
MC-DDH-017	15.00	16.00	1.00	3393958	0.094	9.9	40	1.3	43.8
MC-DDH-017	16.00	17.00	1.00	3393959	0.096	5.5	33	0.8	31.0
MC-DDH-017	17.00	18.00	1.00	3393960	0.349	4.8	26	1.0	18.4
MC-DDH-017	18.00	19.00	1.00	3393962	0.319	0.4	23	0.2	3.6
MC-DDH-017	19.00	20.00	1.00	3393963	0.292	7.3	18	0.7	16.7
MC-DDH-017	20.00	21.00	1.00	3393964	0.272	4.7	12	0.7	13.7

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-017	21.00	22.00	1.00	3393965	0.389	0.9	17	0.3	35.6
MC-DDH-017	22.00	23.00	1.00	3393966	0.711	1.1	18	0.2	14.0
MC-DDH-017	23.00	24.00	1.00	3393967	1.212	1.4	15	0.2	5.6
MC-DDH-017	24.00	25.00	1.00	3393969	1.988	2.0	18	0.3	6.4
MC-DDH-017	25.00	26.00	1.00	3393970	0.155	0.3	10	2.2	1.1
MC-DDH-017	26.00	27.00	1.00	3393971	0.035	-0.1	11	2.1	2.0
MC-DDH-017	27.00	28.00	1.00	3393972	0.063	-0.1	18	1.3	1.4
MC-DDH-017	28.00	29.00	1.00	3393973	0.092	-0.1	29	0.7	4.2
MC-DDH-017	29.00	30.00	1.00	3393974	0.022	-0.1	15	0.5	1.2
MC-DDH-017	30.00	31.00	1.00	3393976	0.012	-0.1	12	2.0	2.5
MC-DDH-017	31.00	32.00	1.00	3393977	0.023	-0.1	15	2.2	54.7
MC-DDH-017	32.00	33.00	1.00	3393978	0.009	-0.1	10	2.1	25.0
MC-DDH-017	33.00	34.00	1.00	3393979	0.020	-0.1	11	2.9	39.1
MC-DDH-017	34.00	35.00	1.00	3393980	0.001	-0.1	15	1.3	2.8
MC-DDH-017	35.00	36.00	1.00	3393981	0.043	0.1	27	10.0	20.2
MC-DDH-017	36.00	37.00	1.00	3393983	0.012	0.1	26	4.4	20.3
MC-DDH-017	37.00	38.00	1.00	3393984	0.006	-0.1	31	10.3	5.8
MC-DDH-017	38.00	39.00	1.00	3393985	0.013	0.1	64	1.4	58.9
MC-DDH-017	39.00	40.00	1.00	3393986	0.011	-0.1	151	4.3	30.0
MC-DDH-017	40.00	41.00	1.00	3393987	0.009	-0.1	61	5.6	22.4
MC-DDH-017	41.00	42.00	1.00	3393988	0.005	0.1	44	1.9	56.3
MC-DDH-017	42.00	43.00	1.00	3393990	0.007	0.1	37	1.6	26.6
MC-DDH-017	43.00	44.00	1.00	3393991	0.007	0.2	33	1.9	76.7
MC-DDH-017	44.00	45.00	1.00	3393992	0.034	0.1	42	3.1	21.1
MC-DDH-017	45.00	46.00	1.00	3393993	0.036	0.1	41	1.0	31.4
MC-DDH-017	46.00	47.00	1.00	3393994	0.025	0.1	46	2.7	19.4
MC-DDH-017	47.00	48.00	1.00	3393995	0.031	-0.1	49	1.6	17.2
MC-DDH-017	48.00	49.00	1.00	3393997	0.010	-0.1	9	0.7	13.9
MC-DDH-017	49.00	50.00	1.00	3393998	0.007	-0.1	11	1.2	19.0
MC-DDH-017	50.00	51.00	1.00	3393999	0.014	1.1	40	3.3	951.4
MC-DDH-017	51.00	52.00	1.00	3394000	0.001	0.7	10	1.4	599.4
MC-DDH-017	52.00	53.00	1.00	3398002	0.010	-0.1	5	0.7	26.9
MC-DDH-017	53.00	54.00	1.00	3398003	0.010	0.3	17	2.4	14.9
MC-DDH-017	54.00	55.00	1.00	3398004	0.015	-0.1	4	1.8	6.9
MC-DDH-017	55.00	56.00	1.00	3398005	0.021	-0.1	5	1.3	7.4
MC-DDH-017	56.00	57.00	1.00	3398006	0.011	-0.1	4	1.0	9.1
MC-DDH-017	57.00	58.00	1.00	3398007	0.015	0.1	4	1.2	8.7
MC-DDH-017	58.00	59.00	1.00	3398009	0.013	-0.1	4	1.3	8.3
MC-DDH-017	59.00	60.00	1.00	3398010	0.019	0.1	4	1.1	8.9
MC-DDH-017	60.00	61.00	1.00	3398011	0.016	-0.1	4	1.1	9.3
MC-DDH-017	61.00	62.00	1.00	3398012	0.046	-0.1	6	0.8	7.9
MC-DDH-017	62.00	63.00	1.00	3398013	0.035	-0.1	6	0.9	8.4
MC-DDH-017	63.00	64.00	1.00	3398014	0.010	-0.1	5	0.8	8.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-017	64.00	65.00	1.00	3398016	0.026	0.1	2	0.7	11.1
MC-DDH-017	65.00	66.00	1.00	3398017	0.015	-0.1	2	1.2	7.7
MC-DDH-017	66.00	67.00	1.00	3398018	0.011	0.1	5	2.3	10.0
MC-DDH-017	67.00	68.00	1.00	3398019	0.007	-0.1	4	1.4	29.8
MC-DDH-017	68.00	69.00	1.00	3398020	0.008	-0.1	-1	0.3	17.1
MC-DDH-017	69.00	70.00	1.00	3398021	0.017	0.4	23	2.6	31.5
MC-DDH-017	70.00	71.00	1.00	3398023	0.078	1.1	244	1.1	9.7
MC-DDH-017	71.00	72.00	1.00	3398024	0.029	0.5	30	1.9	4.8
MC-DDH-017	72.00	73.00	1.00	3398025	0.060	0.4	20	0.6	18.0
MC-DDH-017	73.00	74.00	1.00	3398026	0.042	2.3	48	0.7	35.0
MC-DDH-017	74.00	75.00	1.00	3398027	0.015	0.3	40	0.3	12.7
MC-DDH-017	75.00	76.00	1.00	3398028	0.005	0.2	32	0.1	8.0
MC-DDH-017	76.00	77.00	1.00	3398030	0.009	0.1	29	6.3	2.6
MC-DDH-017	77.00	78.00	1.00	3398031	0.006	0.1	56	5.2	4.5
MC-DDH-017	78.00	79.00	1.00	3398032	0.009	0.2	18	13.4	3.2
MC-DDH-017	79.00	80.00	1.00	3398033	0.005	0.2	12	5.9	5.2
MC-DDH-017	81.00	82.00	1.00	3398035	0.001	0.1	10	2.5	4.4
MC-DDH-017	82.00	83.00	1.00	3398036	0.009	-0.1	31	1.0	5.8
MC-DDH-017	83.00	84.00	1.00	3398037	0.016	0.2	50	2.2	6.8
MC-DDH-017	84.00	85.00	1.00	3398038	0.028	0.7	23	2.4	10.6
MC-DDH-017	85.00	86.00	1.00	3398039	0.013	0.6	25	0.3	5.8
MC-DDH-017	86.00	87.00	1.00	3398040	0.017	1.5	20	0.9	13.4
MC-DDH-017	87.00	88.00	1.00	3398042	0.048	0.2	30	0.3	3.7
MC-DDH-017	88.00	89.00	1.00	3398043	0.193	0.9	45	0.9	91.4
MC-DDH-017	89.00	90.00	1.00	3398044	0.270	0.6	18	0.9	51.4
MC-DDH-017	90.00	91.00	1.00	3398045	0.105	0.3	20	0.2	3.2
MC-DDH-017	91.00	92.00	1.00	3398046	0.020	0.3	54	1.4	9.4
MC-DDH-017	92.00	93.00	1.00	3398047	0.082	0.4	78	11.8	2.9
MC-DDH-017	93.00	94.00	1.00	3398049	0.043	-0.1	128	5.9	5.7
MC-DDH-017	94.00	95.00	1.00	3398050	0.073	-0.1	94	8.3	2.6
MC-DDH-017	95.00	96.00	1.00	3398051	0.053	0.4	45	4.0	8.3
MC-DDH-017	96.00	97.00	1.00	3398052	0.087	1.1	23	4.5	4.9
MC-DDH-017	97.00	98.00	1.00	3398053	0.055	0.6	19	2.4	5.8
MC-DDH-017	98.00	99.00	1.00	3398054	0.017	0.3	14	0.3	5.0
MC-DDH-017	99.00	100.00	1.00	3398056	0.001	0.3	10	0.5	3.3
MC-DDH-017	100.00	101.00	1.00	3398057	0.035	0.3	16	0.7	11.1
MC-DDH-017	101.00	102.00	1.00	3398058	0.006	-0.1	8	0.6	12.0
MC-DDH-017	102.00	103.00	1.00	3398059	0.001	-0.1	18	0.2	4.8
MC-DDH-017	103.00	104.00	1.00	3398060	0.001	-0.1	23	0.4	6.5
MC-DDH-017	104.00	105.00	1.00	3398061	0.001	-0.1	9	0.2	5.0
MC-DDH-017	105.00	106.00	1.00	3398063	0.005	-0.1	14	0.2	3.7
MC-DDH-017	106.00	107.00	1.00	3398064	0.005	-0.1	18	0.1	2.0
MC-DDH-017	107.00	108.00	1.00	3398065	0.001	-0.1	13	0.2	3.7

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-017	108.00	109.00	1.00	3398066	0.001	-0.1	9	0.4	7.4
MC-DDH-017	109.00	110.00	1.00	3398067	0.001	-0.1	10	0.6	15.3
MC-DDH-017	110.00	111.00	1.00	3398068	0.001	-0.1	22	0.7	14.6
MC-DDH-017	111.00	112.00	1.00	3398070	0.007	-0.1	29	1.9	52.0
MC-DDH-017	112.00	113.00	1.00	3398071	0.029	0.7	26	3.4	767.6
MC-DDH-017	113.00	114.00	1.00	3398072	0.011	0.4	18	2.2	391.5
MC-DDH-017	114.00	115.00	1.00	3398073	0.001	-0.1	12	1.8	2.5
MC-DDH-017	115.00	116.00	1.00	3398074	0.006	-0.1	15	0.7	10.5
MC-DDH-017	116.00	117.00	1.00	3398075	0.006	-0.1	58	1.7	22.5
MC-DDH-017	117.00	118.00	1.00	3398077	0.001	-0.1	9	2.9	3.9
MC-DDH-017	118.00	119.00	1.00	3398078	0.001	-0.1	14	1.4	43.7
MC-DDH-017	119.00	120.00	1.00	3398079	0.047	0.4	18	0.9	35.0
MC-DDH-017	120.00	121.00	1.00	3398080	0.013	0.6	21	0.6	48.2
MC-DDH-017	121.00	122.00	1.00	3398081	0.013	0.1	31	0.7	13.5
MC-DDH-017	122.00	123.00	1.00	3398082	0.001	-0.1	10	22.2	1.9
MC-DDH-017	123.00	124.00	1.00	3398084	0.001	-0.1	20	28.3	12.9
MC-DDH-017	124.00	125.00	1.00	3398085	0.006	-0.1	17	15.4	39.2
MC-DDH-017	125.00	125.05	0.05	3398086	0.001	-0.1	13	5.5	3.4

*Table 10-4: Assay Details*

<b>Drill Hole</b>	<b>From (m)</b>	<b>To (m)</b>	<b>Interval (m)</b>	<b>Sample #</b>	<b>Au ppm</b>	<b>Ag ppm</b>	<b>As ppm</b>	<b>Mo ppm</b>	<b>Cu ppm</b>
MC-DDH-001	15.05	16.05	1.00	2961915	0.153	1.3	60	4.5	61.2
MC-DDH-001	16.05	17.05	1.00	2961916	0.133	1.3	56	3.1	54.1
MC-DDH-001	17.05	18.05	1.00	2961917	0.016	0.1	10	0.3	14.6
MC-DDH-001	18.05	19.05	1.00	2961918	0.077	0.5	35	2.9	43.3
MC-DDH-001	19.05	20.05	1.00	2961920	0.055	0.3	40	1.5	34.4
MC-DDH-001	47.05	48.05	1.00	2961921	0.015	0.1	12	0.7	16.1
MC-DDH-001	48.05	49.05	1.00	2961922	0.021	0.1	27	0.2	8.1
MC-DDH-001	49.05	50.05	1.00	2961923	1.058	3.7	501	12.7	25.1
MC-DDH-001	50.05	51.05	1.00	2961924	0.354	3.5	168	15.9	51.6
MC-DDH-001	51.05	52.05	1.00	2961925	0.143	0.4	157	1.8	19.8
MC-DDH-001	52.05	53.05	1.00	2961926	0.746	0.5	63	1.0	3.7
MC-DDH-001	53.05	54.05	1.00	2961927	0.210	0.7	69	2.1	23.8
MC-DDH-001	54.05	55.05	1.00	2961928	0.210	0.5	60	7.8	44.7
MC-DDH-001	55.05	56.05	1.00	2961929	0.303	0.7	238	3.8	31.4
MC-DDH-001	56.05	57.05	1.00	2961930	0.107	0.6	102	0.9	42.7
MC-DDH-001	57.05	58.05	1.00	2961931	0.155	0.6	86	0.6	32.3
MC-DDH-001	58.05	59.05	1.00	2961932	0.063	0.3	60	0.7	40.5
MC-DDH-001	59.05	60.05	1.00	2961933	0.218	0.6	126	1.2	39.6
MC-DDH-001	60.05	61.05	1.00	2961935	0.099	0.6	78	0.6	41.7
MC-DDH-001	61.05	62.05	1.00	2961936	0.056	0.4	46	0.4	49.3
MC-DDH-001	62.05	63.05	1.00	2961937	0.022	0.1	12	0.2	5.3
MC-DDH-001	63.05	64.05	1.00	2961938	0.073	0.2	37	0.7	61.8
MC-DDH-001	65.05	66.05	1.00	2961941	0.038	0.2	10	0.2	65.3
MC-DDH-001	66.05	67.05	1.00	2961942	0.029	0.1	10	0.1	44.5
MC-DDH-001	67.05	68.05	1.00	2961943	0.029	0.1	7	0.1	5.6
MC-DDH-001	68.05	69.05	1.00	2961944	0.025	0.1	8	0.1	55.4
MC-DDH-001	76.05	77.05	1.00	2961946	0.086	0.1	3	0.1	78.4
MC-DDH-001	77.05	78.05	1.00	2961947	0.080	0.1	6	0.2	36.2
MC-DDH-001	81.05	82.05	1.00	2961948	0.026	0.2	12	0.1	21.7
MC-DDH-001	82.05	83.05	1.00	2961949	0.121	0.2	52	0.2	15.0
MC-DDH-001	83.05	84.05	1.00	2961950	0.105	0.7	87	0.9	110.6
MC-DDH-001	84.05	85.05	1.00	2961951	0.138	0.8	98	1.4	45.0
MC-DDH-001	85.05	86.05	1.00	2961953	0.201	1.0	91	1.2	61.0
MC-DDH-001	86.05	87.05	1.00	2961954	0.061	0.3	42	0.2	40.2
MC-DDH-001	87.05	88.05	1.00	2961955	0.041	0.4	32	0.4	25.6
MC-DDH-001	142.05	143.05	1.00	2961956	0.007	0.1	16	3.4	6.6
MC-DDH-001	143.05	144.05	1.00	2961957	0.007	0.1	57	1.8	10.7
MC-DDH-001	144.05	145.05	1.00	2961958	0.013	6.2	159	26.3	1748.8
MC-DDH-001	145.05	146.05	1.00	2961959	0.067	11.1	62	44.6	2565.2
MC-DDH-001	147.05	148.05	1.00	2961962	0.009	0.1	40	1.3	19.7
MC-DDH-001	148.05	149.05	1.00	2961963	0.007	0.1	42	1.5	14.6
MC-DDH-001	149.05	150.05	1.00	2961964	0.007	0.1	9	2.2	10.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	150.05	150.97	0.92	2961965	0.012	0.1	92	9.8	13.5
MC-DDH-011	112.00	113.00	1.00	2964341	0.000	-0.1	5	-0.1	1.1
MC-DDH-011	113.00	114.00	1.00	2964342	0.000	-0.1	1	-0.1	1.2
MC-DDH-011	114.00	115.00	1.00	2964343	0.008	-0.1	-1	-0.1	1.2
MC-DDH-011	115.00	116.00	1.00	2964344	0.000	-0.1	4	-0.1	0.9
MC-DDH-011	116.00	117.00	1.00	2964345	0.000	-0.1	3	0.4	15.6
MC-DDH-011	117.00	118.00	1.00	2964346	0.000	-0.1	5	0.4	77.1
MC-DDH-011	118.00	119.00	1.00	2964348	0.000	-0.1	10	0.3	58.1
MC-DDH-011	119.00	120.00	1.00	2964349	0.000	-0.1	2	0.1	3.7
MC-DDH-011	120.00	121.00	1.00	2964350	0.000	-0.1	6	-0.1	2.1
MC-DDH-002	18.05	19.05	1.00	2965152	0.029	0.4	30	0.5	26.1
MC-DDH-002	19.05	20.05	1.00	2965153	0.088	0.3	35	0.4	3.4
MC-DDH-002	20.05	21.05	1.00	2965154	0.258	0.9	25	0.4	4.9
MC-DDH-002	21.05	22.05	1.00	2965155	0.141	0.2	27	0.5	4.8
MC-DDH-002	52.05	53.05	1.00	2965157	0.066	0.5	54	3.8	25.0
MC-DDH-002	53.05	54.05	1.00	2965158	0.372	1.6	190	24.2	24.0
MC-DDH-002	54.05	55.05	1.00	2965159	0.337	2.0	142	17.0	29.1
MC-DDH-002	55.05	56.05	1.00	2965160	0.165	1.1	84	7.9	25.4
MC-DDH-002	56.05	57.05	1.00	2965161	0.182	1.2	107	13.3	25.7
MC-DDH-002	57.05	58.05	1.00	2965162	0.237	1.6	145	28.4	21.4
MC-DDH-002	58.05	59.05	1.00	2965164	0.382	2.8	266	36.5	26.1
MC-DDH-002	59.05	60.05	1.00	2965165	0.264	1.7	220	4.9	71.1
MC-DDH-002	60.05	61.05	1.00	2965166	0.142	1.1	52	1.2	38.4
MC-DDH-002	61.05	62.05	1.00	2965167	0.304	1.0	114	2.6	37.1
MC-DDH-002	62.05	63.05	1.00	2965168	0.303	0.9	98	1.7	18.8
MC-DDH-002	63.05	64.05	1.00	2965169	0.387	1.6	143	2.2	32.0
MC-DDH-002	64.05	65.05	1.00	2965170	0.308	1.0	37	0.9	12.4
MC-DDH-002	65.05	66.05	1.00	2965171	0.526	1.6	273	1.0	42.3
MC-DDH-002	66.05	67.05	1.00	2965172	0.881	1.9	164	1.0	21.5
MC-DDH-002	67.05	68.05	1.00	2965174	1.099	1.6	128	8.2	42.4
MC-DDH-002	68.05	69.05	1.00	2965175	2.747	0.6	25	0.3	28.4
MC-DDH-002	69.05	70.05	1.00	2965176	3.395	0.9	71	1.1	44.2
MC-DDH-002	70.05	71.05	1.00	2965177	0.323	1.6	376	7.1	31.1
MC-DDH-002	73.05	74.05	1.00	2965180	0.116	0.2	60	2.0	7.1
MC-DDH-002	76.05	77.05	1.00	2965181	0.011	0.1	5	0.2	3.1
MC-DDH-002	77.05	78.05	1.00	2965182	0.408	0.4	29	3.9	28.7
MC-DDH-002	85.05	86.05	1.00	2965183	0.037	0.4	22	1.0	23.7
MC-DDH-002	86.05	87.05	1.00	2965184	0.023	0.3	6	0.7	13.6
MC-DDH-002	87.05	88.05	1.00	2965185	0.030	0.4	10	0.7	11.1
MC-DDH-002	88.05	89.05	1.00	2965186	0.225	1.6	121	3.2	32.1
MC-DDH-002	89.05	90.05	1.00	2965188	0.010	0.1	4	0.3	1.3
MC-DDH-002	90.05	91.05	1.00	2965189	0.034	0.2	18	1.9	3.8
MC-DDH-002	91.05	92.05	1.00	2965190	0.054	0.3	26	2.8	4.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-002	92.05	93.05	1.00	2965191	0.047	0.3	6	3.6	2.6
MC-DDH-002	93.05	94.05	1.00	2965192	0.415	1.2	125	17.9	25.5
MC-DDH-002	94.05	95.05	1.00	2965193	0.290	0.6	121	4.7	9.5
MC-DDH-002	95.05	96.05	1.00	2965194	0.013	0.2	4	1.1	3.2
MC-DDH-002	105.05	106.05	1.00	2965196	0.275	1.0	8	0.3	170.0
MC-DDH-002	106.05	107.05	1.00	2965197	0.162	0.2	10	0.3	3.4
MC-DDH-002	107.05	108.05	1.00	2965198	0.543	0.8	22	0.1	26.1
MC-DDH-002	108.05	109.05	1.00	2965199	0.009	0.1	6	0.1	1.2
MC-DDH-002	109.05	110.05	1.00	2965200	0.019	0.2	26	0.2	2.4
MC-DDH-002	110.05	111.05	1.00	2965201	0.007	0.2	6	0.2	1.6
MC-DDH-002	111.05	112.05	1.00	2965202	0.007	0.2	8	0.3	2.2
MC-DDH-002	112.05	113.05	1.00	2965203	0.005	0.3	20	0.3	0.7
MC-DDH-002	113.05	114.05	1.00	2965204	0.005	0.2	5	0.1	1.4
MC-DDH-002	114.05	115.05	1.00	2965205	0.010	0.2	36	0.8	2.8
MC-DDH-002	115.05	116.05	1.00	2965207	0.024	0.4	22	0.5	3.8
MC-DDH-002	116.05	117.05	1.00	2965208	0.293	0.4	10	0.7	71.6
MC-DDH-002	117.05	118.05	1.00	2965209	1.392	0.5	25	1.0	11.5
MC-DDH-002	119.05	120.05	1.00	2965212	0.007	0.1	1	0.2	6.9
MC-DDH-002	120.05	121.05	1.00	2965213	0.005	0.1	3	0.4	1.8
MC-DDH-002	121.05	122.05	1.00	2965214	1.106	0.5	13	0.8	47.3
MC-DDH-002	122.05	123.05	1.00	2965215	1.303	0.5	43	0.2	37.7
MC-DDH-002	123.05	124.05	1.00	2965216	0.821	0.2	45	0.3	13.5
MC-DDH-002	124.05	124.25	0.20	2965218	0.688	0.2	13	0.2	5.1
MC-DDH-003	6.05	7.05	1.00	2965220	0.246	2.7	207	6.6	14.0
MC-DDH-003	7.05	8.05	1.00	2965221	0.057	0.7	35	0.8	3.1
MC-DDH-003	8.05	9.05	1.00	2965222	0.013	0.2	43	1.2	1.4
MC-DDH-003	9.05	10.05	1.00	2965223	0.026	0.1	44	1.7	1.4
MC-DDH-003	10.05	11.05	1.00	2965224	0.148	0.2	117	0.6	1.3
MC-DDH-003	11.05	12.05	1.00	2965226	0.199	0.2	47	0.8	2.0
MC-DDH-003	12.05	13.05	1.00	2965227	0.184	2.5	61	0.8	2.3
MC-DDH-003	13.05	14.05	1.00	2965228	0.127	0.7	33	3.1	2.8
MC-DDH-003	14.05	15.05	1.00	2965229	0.081	9.2	31	2.7	6.3
MC-DDH-003	15.05	16.05	1.00	2965230	0.169	3.5	16	1.7	3.7
MC-DDH-003	16.05	17.05	1.00	2965231	0.022	0.5	29	6.1	2.7
MC-DDH-003	17.05	18.05	1.00	2965232	0.031	0.4	58	170.4	32.6
MC-DDH-003	19.05	20.05	1.00	2965235	0.014	0.7	74	4.6	105.0
MC-DDH-003	20.05	21.05	1.00	2965236	0.005	0.1	67	1.8	65.2
MC-DDH-003	21.05	22.05	1.00	2965237	0.010	0.1	90	18.4	64.3
MC-DDH-003	22.05	23.05	1.00	2965238	0.028	1.8	49	0.9	4.1
MC-DDH-003	23.05	24.05	1.00	2965239	0.012	0.9	14	0.2	1.0
MC-DDH-003	24.05	25.05	1.00	2965240	0.010	0.1	22	0.2	1.6
MC-DDH-003	25.05	26.05	1.00	2965241	0.055	0.1	18	0.2	0.9
MC-DDH-003	26.05	27.05	1.00	2965243	0.045	0.2	25	0.2	1.3

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	27.05	28.05	1.00	2965244	0.005	0.1	7	0.1	0.6
MC-DDH-003	28.05	29.05	1.00	2965245	0.251	2.2	75	0.8	3.7
MC-DDH-003	29.05	30.05	1.00	2965246	0.020	0.4	26	0.5	3.4
MC-DDH-003	30.05	31.05	1.00	2965247	0.021	1.3	20	0.5	3.4
MC-DDH-003	31.05	32.05	1.00	2965248	0.065	2.7	65	0.8	8.4
MC-DDH-003	32.05	33.05	1.00	2965249	0.063	0.1	192	0.8	6.4
MC-DDH-003	33.05	34.05	1.00	2965250	0.086	11.1	119	1.2	9.7
MC-DDH-003	34.05	35.05	1.00	2965252	0.088	0.5	71	1.3	4.5
MC-DDH-003	35.05	36.05	1.00	2965253	0.171	0.1	68	1.2	2.1
MC-DDH-003	36.05	37.05	1.00	2965254	1.412	0.2	66	0.4	4.2
MC-DDH-003	37.05	38.05	1.00	2965255	0.560	0.1	50	0.4	2.7
MC-DDH-003	38.05	39.05	1.00	2965256	0.495	0.2	63	0.4	5.0
MC-DDH-003	39.05	40.05	1.00	2965257	0.372	0.1	70	0.2	3.0
MC-DDH-003	40.05	41.05	1.00	2965258	0.177	0.1	65	0.4	10.7
MC-DDH-003	41.05	42.05	1.00	2965259	2.247	0.3	61	0.4	20.0
MC-DDH-003	42.05	43.05	1.00	2965261	1.464	0.1	45	0.1	3.2
MC-DDH-003	43.05	44.05	1.00	2965262	2.957	0.2	38	0.2	2.3
MC-DDH-003	44.05	45.05	1.00	2965263	3.585	0.3	53	0.2	2.5
MC-DDH-003	45.05	46.05	1.00	2965264	5.225	0.5	45	0.1	2.1
MC-DDH-003	46.05	47.05	1.00	2965265	2.840	0.3	43	0.2	2.4
MC-DDH-003	48.05	49.05	1.00	2965268	3.688	0.5	38	0.2	7.5
MC-DDH-003	49.05	50.05	1.00	2965269	1.255	0.4	57	0.5	137.5
MC-DDH-003	50.05	51.05	1.00	2965270	4.322	0.5	49	0.2	4.3
MC-DDH-003	51.05	52.05	1.00	2965271	8.266	0.5	60	0.2	3.4
MC-DDH-003	52.05	53.05	1.00	2965272	10.000	0.8	33	0.2	2.7
MC-DDH-003	53.05	54.05	1.00	2965274	10.000	1.3	95	1.4	7.1
MC-DDH-003	54.05	55.05	1.00	2965275	6.391	0.6	33	1.4	9.6
MC-DDH-003	55.05	56.05	1.00	2965276	0.859	0.1	25	2.0	4.2
MC-DDH-003	56.05	57.05	1.00	2965277	10.000	0.8	38	0.9	6.8
MC-DDH-003	57.05	58.05	1.00	2965278	6.909	0.5	18	0.5	4.2
MC-DDH-003	59.05	60.05	1.00	2965281	6.549	0.5	19	1.6	8.9
MC-DDH-003	60.05	61.05	1.00	2965282	0.743	0.1	22	2.4	19.8
MC-DDH-003	61.05	62.05	1.00	2965283	3.931	0.4	18	1.6	18.2
MC-DDH-003	62.05	63.05	1.00	2965284	3.780	0.3	23	1.3	10.2
MC-DDH-003	63.05	64.05	1.00	2965285	1.338	0.1	27	1.3	14.7
MC-DDH-003	64.05	65.05	1.00	2965286	0.428	0.1	19	2.2	34.4
MC-DDH-003	65.05	66.05	1.00	2965288	0.373	0.2	10	1.0	57.0
MC-DDH-003	66.05	67.05	1.00	2965289	0.013	0.1	5	0.1	69.8
MC-DDH-003	67.05	68.05	1.00	2965290	0.025	0.1	6	0.5	63.2
MC-DDH-003	68.05	69.05	1.00	2965291	0.806	0.4	56	1.8	37.8
MC-DDH-003	69.05	70.05	1.00	2965292	1.398	0.4	33	1.1	39.7
MC-DDH-003	70.05	71.05	1.00	2965293	1.359	0.5	31	1.1	31.6
MC-DDH-003	71.05	72.05	1.00	2965294	0.615	0.7	38	1.3	17.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	72.05	73.05	1.00	2965296	0.891	0.4	38	1.5	11.0
MC-DDH-003	73.05	74.05	1.00	2965297	0.336	0.1	27	1.7	4.8
MC-DDH-003	74.05	75.05	1.00	2965298	0.862	0.2	19	2.0	14.4
MC-DDH-003	75.05	76.05	1.00	2965300	1.590	0.3	24	2.2	7.8
MC-DDH-003	76.05	77.05	1.00	2965301	0.719	0.2	27	1.3	6.8
MC-DDH-003	77.05	78.05	1.00	2965302	0.730	0.4	38	1.1	12.3
MC-DDH-003	78.05	79.05	1.00	2965303	1.934	0.5	16	0.7	7.8
MC-DDH-003	79.05	80.05	1.00	2965304	1.189	0.3	30	0.6	4.1
MC-DDH-003	80.05	81.05	1.00	2965305	0.704	0.6	144	1.8	20.9
MC-DDH-003	81.05	82.05	1.00	2965307	1.201	0.4	18	0.6	12.7
MC-DDH-003	82.05	83.05	1.00	2965308	0.596	0.3	24	0.9	6.0
MC-DDH-003	83.05	84.05	1.00	2965309	1.179	0.5	17	0.9	4.2
MC-DDH-003	84.05	85.05	1.00	2965310	0.394	0.5	71	0.5	13.8
MC-DDH-003	85.05	86.05	1.00	2965311	0.047	0.1	17	0.3	5.4
MC-DDH-003	86.05	87.05	1.00	2965312	0.107	0.2	36	0.8	17.9
MC-DDH-003	87.05	88.05	1.00	2965313	0.196	0.3	92	0.8	48.6
MC-DDH-003	88.05	89.05	1.00	2965314	0.166	0.5	126	1.5	59.9
MC-DDH-003	89.05	90.05	1.00	2965315	0.145	0.3	120	0.3	37.8
MC-DDH-003	90.05	91.05	1.00	2965317	0.134	0.3	104	0.6	37.1
MC-DDH-003	91.05	92.05	1.00	2965318	0.145	0.4	127	0.5	32.6
MC-DDH-003	92.05	93.05	1.00	2965319	0.107	0.2	91	0.5	39.7
MC-DDH-003	93.05	94.05	1.00	2965320	0.209	0.8	206	0.6	47.9
MC-DDH-003	94.05	95.05	1.00	2965321	0.007	0.1	2	0.2	1.6
MC-DDH-003	95.05	96.05	1.00	2965323	0.020	0.1	5	0.1	3.7
MC-DDH-003	96.05	97.05	1.00	2965324	0.009	0.1	1	0.2	1.4
MC-DDH-003	97.05	98.05	1.00	2965325	0.024	0.1	1	0.1	1.0
MC-DDH-003	98.05	99.05	1.00	2965326	0.022	0.1	4	0.1	1.9
MC-DDH-003	99.05	100.05	1.00	2965327	0.022	0.1	3	0.2	1.4
MC-DDH-003	100.05	101.05	1.00	2965328	0.016	0.1	1	0.2	1.6
MC-DDH-003	101.05	102.05	1.00	2965329	0.005	0.1	1	0.1	2.0
MC-DDH-003	102.05	103.05	1.00	2965330	0.006	0.1	4	0.1	2.3
MC-DDH-003	104.05	105.05	1.00	2965333	0.007	0.1	13	0.6	3.7
MC-DDH-003	105.05	106.05	1.00	2965334	0.009	0.1	3	0.6	10.8
MC-DDH-003	106.05	107.05	1.00	2965335	0.008	0.1	1	0.6	3.8
MC-DDH-003	107.05	108.05	1.00	2965336	0.005	0.1	1	1.1	8.5
MC-DDH-003	108.05	109.05	1.00	2965337	0.005	0.1	6	1.0	6.9
MC-DDH-003	109.05	110.05	1.00	2965338	0.005	0.1	2	0.7	4.9
MC-DDH-003	110.05	111.05	1.00	2965339	0.005	0.1	1	0.7	7.4
MC-DDH-003	111.05	112.05	1.00	2965341	0.005	0.1	1	0.6	3.9
MC-DDH-003	112.05	113.05	1.00	2965342	0.005	0.1	1	0.9	3.6
MC-DDH-003	113.05	114.05	1.00	2965343	0.007	0.1	8	0.7	3.7
MC-DDH-003	114.05	115.05	1.00	2965344	0.006	0.1	5	1.1	3.2
MC-DDH-003	115.05	116.05	1.00	2965345	0.005	0.1	18	1.7	2.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	116.05	117.05	1.00	2965346	0.005	0.1	10	2.3	3.5
MC-DDH-003	117.05	118.05	1.00	2965347	0.007	0.1	16	2.1	3.1
MC-DDH-003	118.05	119.05	1.00	2965348	0.007	0.1	9	1.5	2.7
MC-DDH-003	120.05	121.05	1.00	2966502	0.010	0.1	10	1.5	4.2
MC-DDH-003	121.05	122.05	1.00	2966503	0.006	0.1	7	2.1	5.2
MC-DDH-003	122.05	123.05	1.00	2966504	0.005	0.1	8	1.8	4.5
MC-DDH-003	123.05	124.05	1.00	2966505	0.005	0.1	27	1.9	4.4
MC-DDH-003	124.05	125.05	1.00	2966506	0.006	0.1	12	2.2	4.0
MC-DDH-003	125.05	126.05	1.00	2966507	0.007	0.1	13	1.7	4.2
MC-DDH-003	126.05	127.05	1.00	2966509	0.014	0.2	26	2.5	16.2
MC-DDH-003	127.05	128.05	1.00	2966510	0.292	1.3	31	1.2	443.9
MC-DDH-003	128.05	129.05	1.00	2966511	0.201	1.6	89	10.7	369.7
MC-DDH-003	129.05	130.05	1.00	2966512	0.440	0.7	72	25.1	83.2
MC-DDH-003	130.05	131.05	1.00	2966513	0.026	0.2	290	71.9	52.7
MC-DDH-003	131.05	132.05	1.00	2966514	0.409	1.9	92	46.6	131.8
MC-DDH-003	132.05	133.05	1.00	2966516	0.030	0.5	51	131.8	109.2
MC-DDH-003	133.05	134.05	1.00	2966517	0.110	0.6	179	200.6	197.1
MC-DDH-003	134.05	135.05	1.00	2966518	0.020	0.1	330	91.1	29.0
MC-DDH-003	135.05	136.05	1.00	2966519	0.006	0.1	41	2.2	38.5
MC-DDH-003	137.05	138.05	1.00	2966522	0.007	0.1	19	3.7	45.1
MC-DDH-003	138.05	139.05	1.00	2966523	0.017	0.1	74	3.2	63.3
MC-DDH-003	139.05	140.05	1.00	2966524	0.011	0.1	30	1.4	62.4
MC-DDH-003	140.05	141.05	1.00	2966525	0.009	0.1	57	2.9	89.2
MC-DDH-003	141.05	142.05	1.00	2966526	0.009	0.1	33	3.5	77.6
MC-DDH-003	142.05	143.05	1.00	2966527	0.012	0.2	87	3.0	144.9
MC-DDH-003	143.05	144.05	1.00	2966529	0.011	0.2	41	3.2	54.0
MC-DDH-003	144.05	145.05	1.00	2966530	0.008	0.1	22	1.3	29.3
MC-DDH-003	145.05	146.05	1.00	2966531	0.009	0.2	35	2.7	64.5
MC-DDH-003	146.05	147.05	1.00	2966532	0.013	0.3	45	2.6	155.8
MC-DDH-003	147.05	148.05	1.00	2966533	0.009	0.2	33	2.2	74.1
MC-DDH-003	148.05	149.05	1.00	2966534	0.010	0.1	54	2.3	58.2
MC-DDH-003	149.05	150.05	1.00	2966536	0.011	0.1	101	1.3	35.8
MC-DDH-003	150.05	151.05	1.00	2966537	0.013	0.1	37	1.1	77.7
MC-DDH-003	151.05	152.05	1.00	2966538	0.017	0.2	55	1.6	58.9
MC-DDH-003	152.05	153.05	1.00	2966539	0.010	0.1	27	1.9	16.4
MC-DDH-003	153.05	154.05	1.00	2966540	0.015	0.1	49	2.9	66.2
MC-DDH-003	154.05	155.05	1.00	2966541	0.051	0.4	72	3.9	81.0
MC-DDH-003	155.05	156.05	1.00	2966543	0.029	0.4	68	2.1	127.2
MC-DDH-003	156.05	157.05	1.00	2966544	0.012	0.2	87	1.9	114.4
MC-DDH-003	157.05	158.05	1.00	2966545	0.010	0.1	50	1.6	55.3
MC-DDH-003	158.05	159.05	1.00	2966546	0.012	0.1	15	1.8	73.6
MC-DDH-003	159.05	160.05	1.00	2966547	0.012	0.1	28	1.8	67.0
MC-DDH-003	161.05	162.05	1.00	2966550	0.016	0.1	60	1.1	44.7

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-003	162.05	163.05	1.00	2966551	0.036	0.3	52	2.0	98.8
MC-DDH-003	163.05	164.05	1.00	2966552	0.244	0.6	159	4.7	126.5
MC-DDH-003	164.05	164.70	0.65	2966553	0.022	0.4	46	2.5	79.5
MC-DDH-004	6.05	7.05	1.00	2966555	0.298	6.3	221	5.2	33.8
MC-DDH-004	7.05	8.05	1.00	2966556	0.085	3.6	130	14.5	21.3
MC-DDH-004	8.05	9.05	1.00	2966557	0.031	4.1	93	11.8	12.3
MC-DDH-004	9.05	10.05	1.00	2966558	0.125	3.9	107	7.9	34.3
MC-DDH-004	10.05	11.05	1.00	2966559	10.000	9.7	518	23.8	3070.9
MC-DDH-004	11.05	12.05	1.00	2966560	2.070	16.3	250	5.3	6725.8
MC-DDH-004	12.05	13.05	1.00	2966561	0.570	6.5	139	6.2	445.1
MC-DDH-004	13.05	14.05	1.00	2966562	0.114	4.7	194	1.9	40.9
MC-DDH-004	14.05	15.05	1.00	2966563	0.114	3.1	49	1.2	24.6
MC-DDH-004	15.05	16.05	1.00	2966564	0.821	6.5	95	4.0	991.1
MC-DDH-004	16.05	17.05	1.00	2966566	0.092	10.6	229	23.1	100.3
MC-DDH-004	17.05	18.05	1.00	2966567	0.033	2.6	67	3.6	15.6
MC-DDH-004	18.05	19.05	1.00	2966568	0.025	1.3	77	2.1	6.5
MC-DDH-004	19.05	20.05	1.00	2966569	0.039	1.0	95	3.1	4.6
MC-DDH-004	20.05	21.05	1.00	2966570	0.104	1.7	132	6.1	4.1
MC-DDH-004	21.05	22.05	1.00	2966572	0.050	1.2	73	7.7	6.0
MC-DDH-004	22.05	23.05	1.00	2966573	0.020	0.6	31	2.6	2.9
MC-DDH-004	23.05	24.05	1.00	2966574	0.014	0.2	22	1.9	2.2
MC-DDH-004	24.05	25.05	1.00	2966575	0.011	0.3	28	2.7	2.7
MC-DDH-004	25.05	26.05	1.00	2966576	0.012	0.3	10	0.6	3.6
MC-DDH-004	26.05	27.05	1.00	2966578	0.012	0.1	8	0.1	1.6
MC-DDH-004	27.05	28.05	1.00	2966579	0.015	0.1	1	0.8	3.0
MC-DDH-004	28.05	29.05	1.00	2966580	0.048	0.2	24	1.0	2.4
MC-DDH-004	29.05	30.05	1.00	2966581	0.015	0.1	2	0.2	1.8
MC-DDH-004	30.05	31.05	1.00	2966582	0.010	0.2	4	0.2	2.0
MC-DDH-004	31.05	32.05	1.00	2966584	0.010	0.4	7	0.3	4.7
MC-DDH-004	32.05	33.05	1.00	2966585	0.209	17.4	86	12.8	28.0
MC-DDH-004	33.05	34.05	1.00	2966586	0.091	4.8	68	4.8	12.6
MC-DDH-004	34.05	35.05	1.00	2966587	0.082	1.7	116	2.1	10.5
MC-DDH-004	36.05	36.60	0.55	2966590	0.056	1.1	61	1.3	8.4
MC-DDH-005	6.05	7.05	1.00	2966592	0.100	13.9	93	9.6	55.7
MC-DDH-005	7.05	8.05	1.00	2966593	0.080	12.8	119	8.7	40.7
MC-DDH-005	8.05	9.05	1.00	2966594	0.335	2.9	83	1.7	52.5
MC-DDH-005	9.05	10.05	1.00	2966595	0.101	2.1	53	1.1	21.0
MC-DDH-005	10.05	11.05	1.00	2966596	0.146	2.6	78	1.8	42.2
MC-DDH-005	11.05	12.05	1.00	2966597	0.061	5.2	49	1.0	19.7
MC-DDH-005	12.05	13.05	1.00	2966598	0.090	5.9	40	0.5	72.5
MC-DDH-005	13.05	14.05	1.00	2966599	0.035	0.3	25	0.6	8.8
MC-DDH-005	14.05	15.05	1.00	2966601	0.076	7.1	102	1.4	21.0
MC-DDH-005	15.05	16.05	1.00	2966602	0.152	7.6	78	3.0	27.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	16.05	17.05	1.00	2966603	0.132	4.3	98	4.6	23.0
MC-DDH-005	17.05	18.05	1.00	2966604	0.067	15.5	77	2.9	70.8
MC-DDH-005	18.05	19.05	1.00	2966605	0.036	2.7	64	1.9	44.1
MC-DDH-005	19.05	20.05	1.00	2966606	0.728	2.4	208	0.7	38.6
MC-DDH-005	21.05	22.05	1.00	2966609	0.007	0.1	12	0.1	2.9
MC-DDH-005	22.05	23.05	1.00	2966610	0.008	0.1	13	0.2	2.6
MC-DDH-005	23.05	24.05	1.00	2966611	0.032	1.7	62	2.4	4.1
MC-DDH-005	24.05	25.05	1.00	2966612	0.019	1.1	25	0.9	6.9
MC-DDH-005	25.05	26.05	1.00	2966613	0.019	0.7	11	0.4	2.6
MC-DDH-005	26.05	27.05	1.00	2966615	0.015	13.8	20	2.5	24.7
MC-DDH-005	27.05	28.05	1.00	2966616	0.008	12.7	12	1.5	25.2
MC-DDH-005	28.05	29.05	1.00	2966617	0.009	0.7	18	1.8	2.7
MC-DDH-005	29.05	30.05	1.00	2966618	0.012	2.2	8	0.9	4.4
MC-DDH-005	30.05	31.05	1.00	2966619	0.014	1.8	13	0.7	1.9
MC-DDH-005	32.05	33.05	1.00	2966622	0.245	2.3	124	1.5	6.4
MC-DDH-005	33.05	34.05	1.00	2966623	0.266	5.6	68	2.2	10.2
MC-DDH-005	34.05	35.05	1.00	2966624	0.273	34.4	89	7.2	59.1
MC-DDH-005	35.05	36.05	1.00	2966625	0.216	19.2	128	9.5	18.3
MC-DDH-005	36.05	37.05	1.00	2966626	0.020	6.4	34	1.2	15.4
MC-DDH-005	37.05	38.05	1.00	2966627	0.017	0.2	13	0.3	3.3
MC-DDH-005	38.05	39.05	1.00	2966628	0.015	0.1	8	0.1	1.5
MC-DDH-005	39.05	40.05	1.00	2966630	0.087	0.3	127	0.8	4.3
MC-DDH-005	40.05	41.05	1.00	2966631	0.005	0.1	4	0.1	0.9
MC-DDH-005	41.05	42.05	1.00	2966632	0.182	0.3	20	0.2	4.1
MC-DDH-005	42.05	43.05	1.00	2966633	0.028	0.1	6	0.1	1.2
MC-DDH-005	43.05	44.05	1.00	2966634	0.007	0.2	3	0.1	0.9
MC-DDH-005	44.05	45.05	1.00	2966635	0.021	0.1	19	0.1	1.9
MC-DDH-005	45.05	46.05	1.00	2966637	0.022	0.1	23	0.2	14.8
MC-DDH-005	46.05	47.05	1.00	2966638	0.005	0.1	16	0.1	2.9
MC-DDH-005	47.05	48.05	1.00	2966639	0.005	0.1	11	0.1	0.9
MC-DDH-005	48.05	49.05	1.00	2966640	0.005	0.1	6	0.1	0.5
MC-DDH-005	49.05	50.05	1.00	2966641	0.005	0.1	9	0.1	0.5
MC-DDH-005	50.05	51.05	1.00	2966643	0.005	0.1	6	0.1	1.6
MC-DDH-005	51.05	52.05	1.00	2966644	0.016	0.1	10	0.1	1.9
MC-DDH-005	52.05	53.05	1.00	2966645	0.021	0.1	15	0.2	1.8
MC-DDH-005	53.05	54.05	1.00	2966646	0.057	0.2	41	0.1	0.7
MC-DDH-005	54.05	55.05	1.00	2966647	0.043	0.1	25	0.1	0.7
MC-DDH-005	55.05	56.05	1.00	2966648	0.055	0.2	7	0.1	11.6
MC-DDH-005	57.05	58.05	1.00	2966651	0.009	0.1	5	0.6	6.9
MC-DDH-005	58.05	59.05	1.00	2966652	0.077	0.2	20	0.3	15.0
MC-DDH-005	59.05	60.05	1.00	2966653	0.213	0.2	19	0.1	4.9
MC-DDH-005	60.05	61.05	1.00	2966654	0.151	0.2	19	0.1	1.0
MC-DDH-005	61.05	62.05	1.00	2966655	0.258	0.2	14	0.2	7.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	62.05	63.05	1.00	2966656	0.153	0.5	42	0.2	8.0
MC-DDH-005	63.05	64.05	1.00	2966658	0.021	0.2	10	0.2	7.8
MC-DDH-005	64.05	65.05	1.00	2966659	0.052	0.2	30	0.1	10.1
MC-DDH-005	65.05	66.05	1.00	2966660	0.081	0.2	23	0.1	5.2
MC-DDH-005	66.05	67.05	1.00	2966661	0.169	0.4	50	0.2	5.0
MC-DDH-005	67.05	68.05	1.00	2966662	0.579	0.6	70	0.1	2.3
MC-DDH-005	68.05	69.05	1.00	2966663	0.012	0.2	36	0.1	4.2
MC-DDH-005	69.05	70.05	1.00	2966665	0.022	0.1	26	0.1	4.4
MC-DDH-005	70.05	71.05	1.00	2966666	0.008	0.1	28	0.1	1.9
MC-DDH-005	71.05	72.05	1.00	2966667	0.132	1.1	53	0.3	16.6
MC-DDH-005	72.05	73.05	1.00	2966668	0.138	2.9	72	0.5	30.3
MC-DDH-005	73.05	74.05	1.00	2966669	0.063	0.7	64	0.2	8.5
MC-DDH-005	74.05	75.05	1.00	2966670	0.158	0.7	173	0.7	17.7
MC-DDH-005	75.05	76.05	1.00	2966672	0.164	0.8	112	1.8	22.2
MC-DDH-005	76.05	77.05	1.00	2966673	0.115	0.4	84	3.2	17.1
MC-DDH-005	77.05	78.05	1.00	2966674	0.068	0.3	71	3.4	4.2
MC-DDH-005	78.05	79.05	1.00	2966675	0.044	0.3	57	2.5	7.8
MC-DDH-005	79.05	80.05	1.00	2966676	0.060	0.2	64	0.5	9.2
MC-DDH-005	80.05	81.05	1.00	2966677	0.005	0.1	13	0.2	0.8
MC-DDH-005	81.05	82.05	1.00	2966678	0.013	0.1	15	0.1	0.5
MC-DDH-005	83.05	84.05	1.00	2966681	0.030	1.1	28	0.2	2.1
MC-DDH-005	84.05	85.05	1.00	2966682	0.062	0.5	50	0.3	6.9
MC-DDH-005	85.05	86.05	1.00	2966683	0.044	0.3	22	0.1	1.8
MC-DDH-005	86.05	87.05	1.00	2966684	0.376	0.8	37	0.4	3.0
MC-DDH-005	87.05	88.05	1.00	2966685	0.243	8.8	73	0.5	19.4
MC-DDH-005	88.05	89.05	1.00	2966686	0.083	1.0	162	0.9	27.2
MC-DDH-005	89.05	90.05	1.00	2966688	0.103	5.0	76	0.9	22.7
MC-DDH-005	90.05	91.05	1.00	2966689	0.093	2.4	63	1.0	11.7
MC-DDH-005	91.05	92.05	1.00	2966690	0.214	4.7	136	1.5	11.1
MC-DDH-005	92.05	93.05	1.00	2966691	0.024	0.2	20	0.2	1.2
MC-DDH-005	93.05	94.05	1.00	2966692	0.097	0.5	65	0.2	2.6
MC-DDH-005	94.05	95.05	1.00	2966693	0.098	1.8	39	0.3	2.6
MC-DDH-005	95.05	96.05	1.00	2966694	0.283	1.5	116	1.5	29.9
MC-DDH-005	96.05	97.05	1.00	2966696	0.753	2.1	513	5.4	159.1
MC-DDH-005	97.05	98.05	1.00	2966697	0.051	0.3	19	0.2	10.1
MC-DDH-005	98.05	99.05	1.00	2966698	0.042	0.3	14	0.1	9.3
MC-DDH-005	99.05	100.05	1.00	2966699	0.096	0.4	85	0.4	20.1
MC-DDH-005	100.05	101.05	1.00	2966700	0.158	0.4	24	0.7	16.9
MC-DDH-005	101.05	102.05	1.00	2966701	0.128	0.5	46	0.7	30.4
MC-DDH-005	102.05	103.05	1.00	2966702	0.016	0.3	19	0.6	14.8
MC-DDH-005	104.05	105.05	1.00	2966705	0.279	1.2	164	1.2	31.9
MC-DDH-005	105.05	106.05	1.00	2966706	0.070	0.3	35	0.2	10.2
MC-DDH-005	106.05	107.05	1.00	2966708	0.036	0.3	35	0.2	3.7

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	107.05	108.05	1.00	2966709	0.076	0.8	72	4.1	31.5
MC-DDH-005	108.05	109.05	1.00	2966710	0.129	4.5	27	1.3	29.5
MC-DDH-005	109.05	110.05	1.00	2966711	0.136	1.8	53	2.5	64.2
MC-DDH-005	110.05	111.05	1.00	2966712	0.550	3.8	197	5.4	39.4
MC-DDH-005	111.05	112.05	1.00	2966714	0.136	1.2	56	1.9	12.2
MC-DDH-005	112.05	113.05	1.00	2966715	0.020	1.2	12	1.5	26.7
MC-DDH-005	113.05	114.05	1.00	2966716	0.005	-0.1	3	0.2	10.0
MC-DDH-005	114.05	115.05	1.00	2966717	0.016	0.2	12	0.3	23.4
MC-DDH-005	115.05	116.05	1.00	2966718	0.016	0.1	13	0.8	33.2
MC-DDH-005	116.05	117.05	1.00	2966719	0.001	-0.1	2	0.9	26.0
MC-DDH-005	118.05	119.05	1.00	2966722	0.001	-0.1	1	0.1	7.7
MC-DDH-005	119.05	120.05	1.00	2966723	0.001	-0.1	2	0.3	8.2
MC-DDH-005	120.05	121.05	1.00	2966724	0.005	-0.1	2	0.2	13.7
MC-DDH-005	121.05	122.05	1.00	2966725	0.001	-0.1	3	0.2	5.6
MC-DDH-005	122.05	123.05	1.00	2966726	0.001	-0.1	2	0.2	13.2
MC-DDH-005	123.05	124.05	1.00	2966727	0.001	-0.1	-1	0.2	13.4
MC-DDH-005	124.05	125.05	1.00	2966728	0.001	-0.1	1	0.1	8.3
MC-DDH-005	125.05	126.05	1.00	2966730	0.006	-0.1	2	0.3	27.6
MC-DDH-005	126.05	127.05	1.00	2966731	0.001	-0.1	-1	0.2	6.7
MC-DDH-005	127.05	128.05	1.00	2966732	0.007	-0.1	5	0.2	20.0
MC-DDH-005	128.05	129.05	1.00	2966733	0.009	-0.1	9	0.2	10.8
MC-DDH-005	129.05	130.05	1.00	2966734	0.001	-0.1	1	0.5	19.0
MC-DDH-005	130.05	131.05	1.00	2966735	0.001	-0.1	1	2.3	24.8
MC-DDH-005	131.05	132.05	1.00	2966736	0.010	-0.1	4	1.6	9.3
MC-DDH-005	132.05	133.05	1.00	2966738	0.006	-0.1	5	0.7	14.0
MC-DDH-005	133.05	134.05	1.00	2966739	0.006	-0.1	-1	0.8	17.7
MC-DDH-005	134.05	135.05	1.00	2966740	0.012	0.1	5	0.8	10.1
MC-DDH-005	135.05	136.05	1.00	2966741	0.007	-0.1	2	0.4	7.5
MC-DDH-005	136.05	137.05	1.00	2966742	0.001	-0.1	2	0.3	35.8
MC-DDH-005	137.05	138.05	1.00	2966743	0.019	0.2	13	0.4	21.2
MC-DDH-005	138.05	139.05	1.00	2966745	0.009	-0.1	5	0.4	29.6
MC-DDH-005	139.05	140.05	1.00	2966746	0.016	0.1	7	2.4	67.1
MC-DDH-005	140.05	141.05	1.00	2966747	0.001	-0.1	-1	0.2	13.6
MC-DDH-005	141.05	142.05	1.00	2966748	0.001	-0.1	1	0.4	18.9
MC-DDH-005	143.05	144.05	1.00	2966751	0.001	-0.1	-1	1.2	17.2
MC-DDH-005	144.05	145.05	1.00	2966752	0.007	-0.1	6	1.2	31.6
MC-DDH-005	145.05	146.05	1.00	2966753	0.877	0.4	39	0.5	11.5
MC-DDH-005	146.05	147.05	1.00	2966754	0.918	1.6	30	0.1	3.3
MC-DDH-005	147.05	148.05	1.00	2966756	0.515	0.4	17	0.2	2.3
MC-DDH-005	148.05	149.05	1.00	2966757	1.704	1.4	65	0.2	3.5
MC-DDH-005	149.05	150.05	1.00	2966758	1.661	2.7	28	0.1	2.1
MC-DDH-005	150.05	151.05	1.00	2966759	0.071	2.2	1	0.5	2.8
MC-DDH-005	151.05	152.05	1.00	2966760	2.014	0.9	46	0.2	5.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-005	152.05	153.05	1.00	2966761	1.385	1.6	49	0.3	10.9
MC-DDH-005	153.05	154.05	1.00	2966763	0.087	0.8	6	0.8	3.0
MC-DDH-005	154.05	155.05	1.00	2966764	0.372	6.6	8	0.5	1.9
MC-DDH-005	155.05	156.05	1.00	2966765	5.948	9.4	19	0.2	2.2
MC-DDH-005	156.05	157.05	1.00	2966766	0.456	1.5	18	0.1	1.5
MC-DDH-005	157.05	158.05	1.00	2966767	3.674	2.5	11	0.1	0.7
MC-DDH-005	158.05	159.05	1.00	2966768	5.264	5.9	9	0.3	1.2
MC-DDH-005	159.05	160.05	1.00	2966769	9.379	3.1	26	0.1	1.9
MC-DDH-005	160.05	161.05	1.00	2966771	4.273	3.4	39	0.2	4.8
MC-DDH-005	161.05	162.05	1.00	2966772	1.619	3.0	23	0.2	6.2
MC-DDH-005	162.05	163.05	1.00	2966773	1.495	4.4	33	0.1	2.2
MC-DDH-005	163.05	164.05	1.00	2966774	1.543	2.1	26	0.2	2.1
MC-DDH-005	164.05	165.05	1.00	2966775	1.284	1.8	27	0.2	2.8
MC-DDH-005	165.05	166.05	1.00	2966776	1.058	1.8	45	0.2	2.5
MC-DDH-005	166.05	167.05	1.00	2966777	1.286	1.4	20	0.1	3.9
MC-DDH-005	167.05	168.05	1.00	2966779	1.618	2.6	59	0.3	5.1
MC-DDH-005	168.05	169.05	1.00	2966780	0.062	0.5	8	0.3	2.7
MC-DDH-005	169.05	170.05	1.00	2966781	0.013	-0.1	1	-0.1	2.1
MC-DDH-005	170.05	171.05	1.00	2966782	0.028	-0.1	3	-0.1	3.3
MC-DDH-005	171.05	172.05	1.00	2966783	0.007	-0.1	8	-0.1	3.1
MC-DDH-005	172.05	173.05	1.00	2966784	0.007	-0.1	2	-0.1	2.6
MC-DDH-005	174.05	175.05	1.00	2966787	0.006	-0.1	7	-0.1	5.4
MC-DDH-005	175.05	176.05	1.00	2966788	0.001	-0.1	3	-0.1	3.0
MC-DDH-005	176.05	177.05	1.00	2966789	0.027	-0.1	-1	-0.1	3.7
MC-DDH-005	177.05	178.05	1.00	2966790	0.006	-0.1	-1	0.1	36.3
MC-DDH-005	178.05	179.05	1.00	2966791	0.007	-0.1	3	-0.1	13.1
MC-DDH-005	179.05	180.05	1.00	2966792	0.007	-0.1	2	-0.1	6.5
MC-DDH-005	180.05	181.05	1.00	2966794	0.012	-0.1	6	-0.1	4.1
MC-DDH-005	181.05	182.05	1.00	2966795	0.009	-0.1	8	0.1	2.3
MC-DDH-005	182.05	183.05	1.00	2966796	0.012	-0.1	15	0.1	21.6
MC-DDH-005	183.05	184.05	1.00	2966797	0.011	-0.1	-1	-0.1	4.6
MC-DDH-005	184.05	185.05	1.00	2966798	0.010	-0.1	3	-0.1	5.7
MC-DDH-005	185.05	186.05	1.00	2966799	0.016	-0.1	3	-0.1	6.3
MC-DDH-005	187.05	188.05	1.00	2966802	0.007	-0.1	-1	-0.1	5.5
MC-DDH-005	188.05	189.05	1.00	2966803	0.011	-0.1	-1	-0.1	1.9
MC-DDH-006	3.05	4.05	1.00	2966805	0.090	2.8	40	0.9	6.9
MC-DDH-006	4.05	5.05	1.00	2966806	0.051	1.9	48	1.0	7.2
MC-DDH-006	5.05	6.05	1.00	2966807	0.013	2.6	11	0.2	4.7
MC-DDH-006	6.05	7.05	1.00	2966808	0.056	0.3	37	0.3	35.3
MC-DDH-006	7.05	8.05	1.00	2966809	0.065	2.2	58	0.6	42.7
MC-DDH-006	8.05	9.05	1.00	2966810	0.051	2.5	17	0.4	14.7
MC-DDH-006	9.05	10.05	1.00	2966811	0.016	0.9	20	0.3	9.8
MC-DDH-006	10.05	11.05	1.00	2966812	0.052	3.3	21	0.3	11.7

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	11.05	12.05	1.00	2966814	0.109	1.7	25	0.4	39.7
MC-DDH-006	12.05	13.05	1.00	2966815	0.075	2.6	45	0.3	47.2
MC-DDH-006	13.05	14.05	1.00	2966816	0.020	0.7	44	0.3	9.0
MC-DDH-006	14.05	15.05	1.00	2966817	0.012	0.3	14	0.2	7.1
MC-DDH-006	15.05	16.05	1.00	2966818	0.001	-0.1	5	-0.1	0.4
MC-DDH-006	16.05	17.05	1.00	2966819	0.001	-0.1	4	-0.1	0.2
MC-DDH-006	17.05	18.05	1.00	2966820	0.001	-0.1	5	-0.1	0.3
MC-DDH-006	19.05	20.05	1.00	2966823	0.012	0.1	10	0.1	3.7
MC-DDH-006	20.05	21.05	1.00	2966824	0.012	-0.1	4	0.1	3.0
MC-DDH-006	21.05	22.05	1.00	2966825	0.001	-0.1	4	0.1	0.3
MC-DDH-006	22.05	23.05	1.00	2966826	0.019	0.2	26	0.3	1.2
MC-DDH-006	23.05	24.05	1.00	2966827	0.020	0.1	24	0.6	0.9
MC-DDH-006	24.05	25.05	1.00	2966828	0.001	-0.1	9	0.1	0.7
MC-DDH-006	25.05	26.05	1.00	2966829	0.001	-0.1	5	0.1	0.9
MC-DDH-006	26.05	27.05	1.00	2966831	0.086	0.7	54	15.2	9.5
MC-DDH-006	27.05	28.05	1.00	2966832	0.108	0.7	72	20.3	8.5
MC-DDH-006	28.05	29.05	1.00	2966833	0.016	-0.1	15	0.5	18.5
MC-DDH-006	29.05	30.05	1.00	2966834	0.008	-0.1	4	0.2	12.5
MC-DDH-006	30.05	31.05	1.00	2966835	0.006	-0.1	10	0.1	0.5
MC-DDH-006	31.05	32.05	1.00	2966836	0.005	-0.1	9	0.1	0.6
MC-DDH-006	32.05	33.05	1.00	2966837	0.019	0.1	30	10.7	3.0
MC-DDH-006	33.05	34.05	1.00	2966838	0.007	-0.1	22	0.1	3.4
MC-DDH-006	34.05	35.05	1.00	2966840	0.005	-0.1	28	0.1	2.8
MC-DDH-006	35.05	36.05	1.00	2966841	0.009	-0.1	24	-0.1	10.8
MC-DDH-006	36.05	37.05	1.00	2966842	0.011	0.2	18	0.5	5.7
MC-DDH-006	37.05	38.05	1.00	2966843	0.001	-0.1	27	-0.1	1.1
MC-DDH-006	38.05	39.05	1.00	2966844	0.036	-0.1	55	-0.1	1.2
MC-DDH-006	39.05	40.05	1.00	2966845	0.015	0.1	24	0.2	1.8
MC-DDH-006	40.05	41.05	1.00	2966846	0.018	0.1	30	0.2	1.5
MC-DDH-006	41.05	42.05	1.00	2966847	0.001	0.1	16	0.1	0.8
MC-DDH-006	42.05	43.05	1.00	2966849	0.045	0.1	13	0.2	4.9
MC-DDH-006	43.05	44.05	1.00	2966850	0.011	-0.1	5	-0.1	2.5
MC-DDH-006	44.05	45.05	1.00	2966851	0.010	-0.1	13	0.1	20.7
MC-DDH-006	45.05	46.05	1.00	2966852	0.035	0.2	39	0.2	6.3
MC-DDH-006	46.05	47.05	1.00	2966853	0.889	2.3	31	0.3	2.1
MC-DDH-006	48.05	49.05	1.00	2966856	0.022	-0.1	17	0.1	5.0
MC-DDH-006	49.05	50.05	1.00	2966857	0.006	0.1	5	-0.1	2.2
MC-DDH-006	50.05	51.05	1.00	2966858	0.007	0.1	10	-0.1	2.8
MC-DDH-006	51.05	52.05	1.00	2966859	0.005	0.2	17	-0.1	0.7
MC-DDH-006	52.05	53.05	1.00	2966860	0.006	-0.1	8	-0.1	1.8
MC-DDH-006	53.05	54.05	1.00	2966862	0.008	-0.1	12	0.1	3.1
MC-DDH-006	54.05	55.05	1.00	2966863	0.023	-0.1	9	-0.1	0.9
MC-DDH-006	55.05	56.05	1.00	2966864	0.046	-0.1	24	0.1	6.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	56.05	57.05	1.00	2966865	0.025	-0.1	5	0.1	9.3
MC-DDH-006	57.05	58.05	1.00	2966866	0.023	-0.1	6	-0.1	0.8
MC-DDH-006	59.05	60.05	1.00	2966869	0.292	0.9	42	0.1	1.4
MC-DDH-006	60.05	61.05	1.00	2966870	0.264	1.3	38	0.2	6.1
MC-DDH-006	61.05	62.05	1.00	2966871	0.078	0.6	46	0.3	1.1
MC-DDH-006	62.05	63.05	1.00	2966872	0.071	1.6	16	0.3	1.9
MC-DDH-006	63.05	64.05	1.00	2966873	0.291	2.3	23	0.4	1.3
MC-DDH-006	64.05	65.05	1.00	2966874	0.484	1.8	21	0.3	1.8
MC-DDH-006	65.05	66.05	1.00	2966876	0.432	4.9	55	1.9	6.2
MC-DDH-006	66.05	67.05	1.00	2966877	0.666	1.3	61	1.4	4.3
MC-DDH-006	67.05	68.05	1.00	2966878	0.601	0.8	28	0.6	3.5
MC-DDH-006	68.05	69.05	1.00	2966879	0.258	4.4	49	0.3	3.4
MC-DDH-006	69.05	70.05	1.00	2966880	0.347	2.4	112	1.2	6.1
MC-DDH-006	70.05	71.05	1.00	2966882	0.113	0.2	31	0.4	2.3
MC-DDH-006	71.05	72.05	1.00	2966883	0.118	1.7	33	2.3	5.5
MC-DDH-006	72.05	73.05	1.00	2966884	2.325	0.6	59	1.8	2.2
MC-DDH-006	73.05	74.05	1.00	2966885	0.910	1.5	38	0.2	21.7
MC-DDH-006	74.05	75.05	1.00	2966886	0.010	-0.1	4	0.4	2.1
MC-DDH-006	75.05	76.05	1.00	2966887	0.010	-0.1	-1	0.1	2.9
MC-DDH-006	76.05	77.05	1.00	2966888	0.008	-0.1	4	0.2	5.5
MC-DDH-006	78.05	79.05	1.00	2966891	0.006	-0.1	-1	0.2	2.0
MC-DDH-006	79.05	80.05	1.00	2966892	0.006	-0.1	2	0.1	1.9
MC-DDH-006	80.05	81.05	1.00	2966893	0.009	-0.1	-1	0.4	1.4
MC-DDH-006	81.05	82.05	1.00	2966894	0.011	-0.1	4	0.7	2.2
MC-DDH-006	82.05	83.05	1.00	2966895	0.016	0.2	7	0.9	5.1
MC-DDH-006	83.05	84.05	1.00	2966896	0.008	-0.1	-1	0.3	1.1
MC-DDH-006	84.05	85.05	1.00	2966897	0.009	-0.1	5	1.2	4.2
MC-DDH-006	85.05	86.05	1.00	2966899	0.011	-0.1	10	0.8	4.6
MC-DDH-006	86.05	87.05	1.00	2966900	0.304	0.2	22	0.2	7.5
MC-DDH-006	87.05	88.05	1.00	2966901	0.129	0.9	67	0.2	3.3
MC-DDH-006	88.05	89.05	1.00	2966902	0.594	0.8	23	-0.1	12.7
MC-DDH-006	89.05	90.05	1.00	2966903	3.299	3.6	146	0.3	9.9
MC-DDH-006	90.05	91.05	1.00	2966904	0.057	0.3	13	-0.1	0.9
MC-DDH-006	91.05	92.05	1.00	2966905	0.039	0.3	72	0.4	3.8
MC-DDH-006	92.05	93.05	1.00	2966906	4.022	1.7	99	0.3	4.0
MC-DDH-006	93.05	94.05	1.00	2966908	1.208	4.3	14	0.3	6.4
MC-DDH-006	94.05	95.05	1.00	2966909	2.639	1.8	19	0.3	4.6
MC-DDH-006	95.05	96.05	1.00	2966910	3.183	3.0	29	0.3	6.7
MC-DDH-006	96.05	97.05	1.00	2966911	0.120	1.9	40	0.4	5.8
MC-DDH-006	97.05	98.05	1.00	2966912	0.061	1.0	24	0.4	3.2
MC-DDH-006	98.05	99.05	1.00	2966913	0.025	0.1	16	0.1	0.8
MC-DDH-006	99.05	100.05	1.00	2966914	0.018	0.4	14	0.2	0.9
MC-DDH-006	100.05	101.05	1.00	2966915	0.007	0.1	15	-0.1	1.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	101.05	102.05	1.00	2966917	0.020	0.3	39	0.4	3.6
MC-DDH-006	102.05	103.05	1.00	2966918	0.006	0.6	17	6.5	5.7
MC-DDH-006	103.05	104.05	1.00	2966919	0.008	0.1	11	4.7	4.4
MC-DDH-006	104.05	105.05	1.00	2966920	0.005	0.4	20	5.2	192.4
MC-DDH-006	105.05	106.05	1.00	2966921	0.001	-0.1	21	4.0	62.4
MC-DDH-006	107.05	108.05	1.00	2966924	0.006	-0.1	28	2.4	9.8
MC-DDH-006	108.05	109.05	1.00	2966925	0.006	-0.1	38	12.9	9.6
MC-DDH-006	109.05	110.05	1.00	2966926	0.001	-0.1	22	6.8	5.8
MC-DDH-006	110.05	111.05	1.00	2966927	0.006	-0.1	27	7.4	11.5
MC-DDH-006	111.05	112.05	1.00	2966928	0.005	0.1	37	9.7	6.7
MC-DDH-006	112.05	113.05	1.00	2966930	0.007	-0.1	40	10.4	5.8
MC-DDH-006	113.05	114.05	1.00	2966931	0.001	-0.1	21	7.1	4.2
MC-DDH-006	114.05	115.05	1.00	2966932	0.001	-0.1	13	4.0	5.6
MC-DDH-006	115.05	116.05	1.00	2966933	0.005	-0.1	12	4.2	17.6
MC-DDH-006	116.05	117.05	1.00	2966934	0.010	-0.1	46	3.7	22.3
MC-DDH-006	118.05	119.05	1.00	2966937	0.008	0.8	75	7.6	71.2
MC-DDH-006	119.05	120.05	1.00	2966938	0.010	0.2	62	5.3	48.7
MC-DDH-006	120.05	121.05	1.00	2966939	0.012	0.3	62	13.4	78.6
MC-DDH-006	121.05	122.05	1.00	2966940	0.010	0.1	50	7.7	83.6
MC-DDH-006	122.05	123.05	1.00	2966941	0.013	-0.1	161	13.1	76.1
MC-DDH-006	123.05	124.05	1.00	2966942	0.010	0.1	48	18.9	50.4
MC-DDH-006	124.05	125.05	1.00	2966944	0.016	0.1	58	9.1	31.6
MC-DDH-006	125.05	126.05	1.00	2966945	0.013	0.1	102	8.2	29.1
MC-DDH-006	126.05	127.05	1.00	2966946	0.014	0.1	73	8.1	28.4
MC-DDH-006	127.05	128.05	1.00	2966947	0.009	-0.1	39	6.6	29.0
MC-DDH-006	128.05	129.05	1.00	2966948	0.009	0.1	42	13.6	31.8
MC-DDH-006	129.05	130.05	1.00	2966950	0.007	0.1	57	11.1	63.9
MC-DDH-006	130.05	131.05	1.00	2966951	0.008	0.1	39	29.5	23.3
MC-DDH-006	131.05	132.05	1.00	2966952	0.007	-0.1	35	10.4	15.8
MC-DDH-006	132.05	133.05	1.00	2966953	0.015	0.2	70	22.5	168.9
MC-DDH-006	133.05	134.05	1.00	2966954	0.010	-0.1	39	6.0	28.0
MC-DDH-006	134.05	135.05	1.00	2966955	0.008	-0.1	37	9.4	4.7
MC-DDH-006	135.05	136.05	1.00	2966956	0.011	-0.1	42	4.3	7.8
MC-DDH-006	137.05	138.05	1.00	2966959	0.006	-0.1	21	1.8	4.5
MC-DDH-006	138.05	139.05	1.00	2966960	0.005	-0.1	19	9.0	11.0
MC-DDH-006	139.05	140.05	1.00	2966961	0.005	-0.1	21	31.4	6.4
MC-DDH-006	140.05	141.05	1.00	2966962	0.006	-0.1	24	18.1	3.0
MC-DDH-006	141.05	142.05	1.00	2966963	0.001	-0.1	18	1.6	2.9
MC-DDH-006	142.05	143.05	1.00	2966964	0.001	-0.1	11	0.9	2.2
MC-DDH-006	143.05	144.05	1.00	2966965	0.001	-0.1	10	2.1	3.7
MC-DDH-006	144.05	145.05	1.00	2966967	0.001	-0.1	6	1.1	2.6
MC-DDH-006	145.05	146.05	1.00	2966968	0.005	-0.1	13	6.3	22.8
MC-DDH-006	146.05	147.05	1.00	2966969	0.010	0.3	51	6.3	113.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-006	147.05	148.05	1.00	2966970	0.011	0.3	56	4.6	146.5
MC-DDH-006	148.05	149.05	1.00	2966972	0.010	0.3	43	14.0	195.1
MC-DDH-006	149.05	150.05	1.00	2966973	0.010	0.2	34	10.2	58.8
MC-DDH-006	150.05	151.05	1.00	2966974	0.015	0.1	19	3.6	51.0
MC-DDH-006	151.05	152.05	1.00	2966975	0.005	-0.1	14	0.8	34.8
MC-DDH-006	152.05	153.05	1.00	2966976	0.001	-0.1	10	0.3	9.6
MC-DDH-006	153.05	154.05	1.00	2966977	0.008	-0.1	19	0.5	4.5
MC-DDH-006	154.05	155.05	1.00	2966979	0.001	-0.1	13	3.9	16.6
MC-DDH-006	155.05	156.05	1.00	2966980	0.006	-0.1	9	1.4	2.7
MC-DDH-006	156.05	157.05	1.00	2966981	0.001	-0.1	11	0.6	10.5
MC-DDH-006	157.05	158.05	1.00	2966982	0.001	0.5	7	0.6	4.7
MC-DDH-006	<b>158.05</b>	<b>159.05</b>	1.00	<b>2966983</b>	0.008	1.8	5	0.4	3.7
MC-DDH-006	<b>159.05</b>	<b>160.05</b>	1.00	<b>2966985</b>	0.019	0.1	14	1.4	6.4
MC-DDH-006	160.05	161.05	1.00	2966989	0.009	1.4	7	0.6	8.0
MC-DDH-006	161.05	162.05	1.00	2966990	0.001	0.3	5	0.9	3.9
MC-DDH-006	162.05	163.05	1.00	2966991	0.011	-0.1	14	1.4	2.5
MC-DDH-006	163.05	164.05	1.00	2966992	0.010	0.1	19	1.9	41.7
MC-DDH-006	164.05	165.05	1.00	2966994	0.010	-0.1	17	1.7	4.6
MC-DDH-006	165.05	166.05	1.00	2966995	0.005	0.6	14	2.8	2.4
MC-DDH-006	166.05	167.05	1.00	2966996	0.008	0.3	21	1.6	2.2
MC-DDH-006	167.05	168.05	1.00	2966997	0.007	-0.1	18	1.5	2.1
MC-DDH-006	168.05	169.05	1.00	2966998	0.006	-0.1	12	0.4	1.6
MC-DDH-006	170.05	171.05	1.00	3392002	0.009	-0.1	18	1.7	5.6
MC-DDH-006	171.05	172.05	1.00	3392003	0.006	-0.1	15	1.6	3.2
MC-DDH-006	172.05	173.05	1.00	3392004	0.009	-0.1	16	1.0	2.1
MC-DDH-006	173.05	174.05	1.00	3392005	0.001	-0.1	36	1.8	9.8
MC-DDH-006	174.05	175.05	1.00	3392006	0.006	-0.1	43	1.7	9.6
MC-DDH-006	175.05	176.05	1.00	3392007	0.001	0.3	13	1.0	10.6
MC-DDH-006	176.05	177.05	1.00	3392009	0.005	0.8	13	1.0	19.0
MC-DDH-006	177.05	178.05	1.00	3392010	0.006	0.2	12	1.1	13.9
MC-DDH-006	178.05	179.05	1.00	3392011	0.001	-0.1	6	0.8	2.1
MC-DDH-006	179.05	180.05	1.00	3392012	0.001	-0.1	6	3.2	9.7
MC-DDH-006	180.05	181.05	1.00	3392013	0.001	-0.1	4	1.3	2.7
MC-DDH-006	181.05	182.05	1.00	3392014	0.001	-0.1	5	1.7	7.1
MC-DDH-006	182.05	183.05	1.00	3392016	0.001	-0.1	5	4.9	29.4
MC-DDH-006	183.05	184.05	1.00	3392017	0.001	-0.1	4	3.8	4.5
MC-DDH-006	184.05	185.05	1.00	3392018	0.001	0.1	4	0.6	6.2
MC-DDH-006	185.05	186.05	1.00	3392019	0.001	-0.1	9	3.1	28.4
MC-DDH-006	186.05	187.05	1.00	3392020	0.011	0.2	13	2.1	46.1
MC-DDH-006	187.05	188.05	1.00	3392021	0.001	0.2	2	1.1	21.4
MC-DDH-006	188.05	189.05	1.00	3392023	0.001	0.2	4	2.2	11.6
MC-DDH-006	189.05	190.05	1.00	3392024	0.001	0.1	10	1.5	27.2
MC-DDH-006	190.05	190.62	0.57	3392025	0.001	-0.1	11	1.7	17.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	3.05	4.05	1.00	3392026	0.057	-0.1	76	1.3	17.9
MC-DDH-001	4.05	5.05	1.00	3392027	0.022	-0.1	33	0.8	19.3
MC-DDH-001	6.05	7.05	1.00	3392030	0.033	-0.1	54	1.3	16.9
MC-DDH-001	7.05	8.05	1.00	3392031	0.028	-0.1	52	1.1	19.8
MC-DDH-001	8.05	9.05	1.00	3392032	0.023	-0.1	25	0.4	32.2
MC-DDH-001	9.05	10.05	1.00	3392033	0.029	-0.1	17	0.2	21.8
MC-DDH-001	10.05	11.05	1.00	3392034	0.033	-0.1	36	0.7	15.4
MC-DDH-001	11.05	12.05	1.00	3392035	0.024	0.2	36	0.4	21.6
MC-DDH-001	12.05	13.05	1.00	3392037	0.027	0.1	32	1.0	25.5
MC-DDH-001	13.05	14.05	1.00	3392038	0.041	0.4	60	1.1	20.9
MC-DDH-001	14.05	15.05	1.00	3392039	0.102	2.2	56	3.7	70.1
MC-DDH-001	20.05	21.05	1.00	3392040	0.083	5.2	47	2.1	48.1
MC-DDH-001	21.05	22.05	1.00	3392041	0.038	0.3	40	0.8	13.3
MC-DDH-001	22.05	23.05	1.00	3392042	0.067	0.6	48	1.1	17.3
MC-DDH-001	23.05	24.05	1.00	3392044	0.038	0.2	38	0.9	19.5
MC-DDH-001	24.05	25.05	1.00	3392045	0.065	0.5	36	0.5	20.5
MC-DDH-001	25.05	26.05	1.00	3392046	0.032	0.2	16	0.3	14.9
MC-DDH-001	26.05	27.05	1.00	3392047	0.056	0.3	24	0.4	21.0
MC-DDH-001	27.05	28.05	1.00	3392048	0.021	0.1	24	0.5	20.3
MC-DDH-001	28.05	29.05	1.00	3392049	0.043	0.3	47	0.9	12.3
MC-DDH-001	29.05	30.05	1.00	3392051	0.039	0.3	26	1.3	25.6
MC-DDH-001	30.05	31.05	1.00	3392052	0.009	-0.1	5	0.7	38.4
MC-DDH-001	31.05	32.05	1.00	3392053	0.007	-0.1	4	0.3	17.4
MC-DDH-001	32.05	33.05	1.00	3392054	0.001	-0.1	3	0.3	15.9
MC-DDH-001	33.05	34.05	1.00	3392055	0.001	-0.1	1	0.3	13.7
MC-DDH-001	35.05	36.05	1.00	3392058	0.001	-0.1	1	0.1	11.4
MC-DDH-001	36.05	37.05	1.00	3392059	0.017	0.1	15	0.8	17.9
MC-DDH-001	37.05	38.05	1.00	3392060	0.354	-0.1	15	0.4	17.4
MC-DDH-001	38.05	39.05	1.00	3392061	0.006	-0.1	5	0.3	17.7
MC-DDH-001	39.05	40.05	1.00	3392062	0.008	-0.1	16	0.6	27.8
MC-DDH-001	40.05	41.05	1.00	3392063	0.001	-0.1	2	0.1	18.6
MC-DDH-001	41.05	42.05	1.00	3392065	0.001	-0.1	-1	0.5	34.1
MC-DDH-001	42.05	43.05	1.00	3392066	0.010	-0.1	17	0.3	20.0
MC-DDH-001	43.05	44.05	1.00	3392067	0.001	-0.1	2	0.5	13.5
MC-DDH-001	44.05	45.05	1.00	3392068	0.001	-0.1	2	0.9	22.7
MC-DDH-001	45.05	46.05	1.00	3392069	0.001	-0.1	2	0.3	12.0
MC-DDH-001	46.05	47.05	1.00	3392070	0.022	0.2	21	0.7	24.5
MC-DDH-001	69.05	70.05	1.00	3392072	0.029	0.1	42	0.2	30.0
MC-DDH-001	70.05	71.05	1.00	3392073	0.005	-0.1	3	-0.1	39.6
MC-DDH-001	71.05	72.05	1.00	3392074	0.050	0.2	37	0.2	13.5
MC-DDH-001	72.05	73.05	1.00	3392075	0.071	0.5	56	0.2	38.4
MC-DDH-001	73.05	74.05	1.00	3392076	0.069	0.9	56	0.7	69.5
MC-DDH-001	74.05	75.05	1.00	3392077	0.054	-0.1	33	0.1	10.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	75.05	76.05	1.00	3392079	0.018	-0.1	-1	0.2	74.3
MC-DDH-001	78.05	79.05	1.00	3392080	0.060	0.1	13	0.2	21.0
MC-DDH-001	79.05	80.05	1.00	3392081	0.009	-0.1	7	0.2	7.6
MC-DDH-001	80.05	81.05	1.00	3392082	0.008	-0.1	7	0.1	4.3
MC-DDH-001	88.05	89.05	1.00	3392083	0.008	-0.1	4	0.2	4.6
MC-DDH-001	90.05	91.05	1.00	3392086	0.001	-0.1	-1	0.2	8.8
MC-DDH-001	91.05	92.05	1.00	3392087	0.001	-0.1	6	0.1	4.9
MC-DDH-001	92.05	93.05	1.00	3392088	0.001	-0.1	3	0.1	2.7
MC-DDH-001	93.05	94.05	1.00	3392089	0.001	-0.1	-1	0.2	3.1
MC-DDH-001	94.05	95.05	1.00	3392090	0.001	-0.1	5	0.1	3.3
MC-DDH-001	95.05	96.05	1.00	3392091	0.017	0.1	12	0.3	21.2
MC-DDH-001	96.05	97.05	1.00	3392093	0.009	0.2	12	0.4	8.0
MC-DDH-001	97.05	98.05	1.00	3392094	0.021	0.1	21	0.4	13.4
MC-DDH-001	98.05	99.05	1.00	3392095	0.001	-0.1	5	-0.1	2.5
MC-DDH-001	99.05	100.05	1.00	3392096	0.001	-0.1	4	-0.1	2.1
MC-DDH-001	100.05	101.05	1.00	3392097	0.001	-0.1	2	-0.1	1.1
MC-DDH-001	101.05	102.05	1.00	3392098	0.001	-0.1	2	0.2	2.2
MC-DDH-001	102.05	103.05	1.00	3392100	0.001	-0.1	5	0.9	3.0
MC-DDH-001	103.05	104.05	1.00	3392101	0.001	-0.1	5	0.3	2.7
MC-DDH-001	104.05	105.05	1.00	3392102	0.001	-0.1	7	-0.1	1.9
MC-DDH-001	105.05	106.05	1.00	3392103	0.001	-0.1	2	1.0	3.6
MC-DDH-001	106.05	107.05	1.00	3392104	0.001	-0.1	4	-0.1	1.3
MC-DDH-001	107.05	108.05	1.00	3392105	0.001	-0.1	2	-0.1	0.7
MC-DDH-001	108.05	109.05	1.00	3392107	0.001	-0.1	5	0.1	2.2
MC-DDH-001	109.05	110.05	1.00	3392108	0.001	-0.1	-1	0.2	1.5
MC-DDH-001	110.05	111.05	1.00	3392109	0.001	-0.1	1	0.2	1.6
MC-DDH-001	111.05	112.05	1.00	3392110	0.001	-0.1	9	0.2	2.4
MC-DDH-001	112.05	113.05	1.00	3392111	0.001	-0.1	16	0.1	1.5
MC-DDH-001	113.05	114.05	1.00	3392112	0.001	-0.1	3	-0.1	1.0
MC-DDH-001	114.05	115.05	1.00	3392114	0.001	-0.1	18	0.3	2.8
MC-DDH-001	115.05	116.05	1.00	3392115	0.001	-0.1	5	-0.1	1.1
MC-DDH-001	116.05	117.05	1.00	3392116	0.001	-0.1	24	-0.1	1.5
MC-DDH-001	117.05	118.05	1.00	3392117	0.001	-0.1	6	0.2	1.0
MC-DDH-001	118.05	119.05	1.00	3392118	0.001	-0.1	6	0.5	6.6
MC-DDH-001	120.05	121.05	1.00	3392121	0.001	-0.1	33	0.3	1.1
MC-DDH-001	121.05	122.05	1.00	3392122	0.001	-0.1	2	0.2	3.3
MC-DDH-001	122.05	123.05	1.00	3392123	0.001	-0.1	4	0.7	2.1
MC-DDH-001	123.05	124.05	1.00	3392124	0.001	-0.1	5	1.2	3.3
MC-DDH-001	124.05	125.05	1.00	3392125	0.001	-0.1	2	1.6	2.3
MC-DDH-001	125.05	126.05	1.00	3392126	0.001	-0.1	6	1.8	2.1
MC-DDH-001	126.05	127.05	1.00	3392128	0.001	-0.1	9	1.6	3.0
MC-DDH-001	127.05	128.05	1.00	3392129	0.001	-0.1	4	0.7	2.3
MC-DDH-001	128.05	129.05	1.00	3392130	0.001	-0.1	2	1.6	2.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-001	129.05	130.05	1.00	3392131	0.001	-0.1	4	1.0	1.5
MC-DDH-001	130.05	131.05	1.00	3392132	0.001	-0.1	6	1.5	3.4
MC-DDH-001	131.05	132.05	1.00	3392133	0.007	-0.1	12	1.5	4.0
MC-DDH-001	132.05	133.05	1.00	3392135	0.001	-0.1	8	2.2	4.0
MC-DDH-001	133.05	134.05	1.00	3392136	0.006	-0.1	8	5.5	7.3
MC-DDH-001	134.05	135.05	1.00	3392137	0.006	-0.1	17	2.7	5.3
MC-DDH-001	135.05	136.05	1.00	3392138	0.001	-0.1	9	2.3	5.2
MC-DDH-001	136.05	137.05	1.00	3392139	0.006	-0.1	5	1.1	5.6
MC-DDH-001	137.05	138.05	1.00	3392140	0.001	-0.1	6	1.4	8.9
MC-DDH-001	138.05	139.05	1.00	3392142	0.008	-0.1	12	1.6	10.8
MC-DDH-001	139.05	140.05	1.00	3392143	0.006	-0.1	5	1.4	10.0
MC-DDH-001	140.05	141.05	1.00	3392144	0.008	-0.1	11	2.1	10.6
MC-DDH-001	141.05	142.05	1.00	3392145	0.007	0.2	22	2.3	6.8
MC-DDH-002	3.05	4.05	1.00	3392146	0.012	0.4	4	0.5	18.7
MC-DDH-002	5.05	6.05	1.00	3392149	0.010	0.1	6	0.2	17.9
MC-DDH-002	6.05	7.05	1.00	3392150	0.021	-0.1	5	0.3	23.5
MC-DDH-002	7.05	8.05	1.00	3392151	0.011	-0.1	3	0.5	29.6
MC-DDH-002	8.05	9.05	1.00	3392152	0.008	-0.1	6	0.6	22.1
MC-DDH-002	9.05	10.05	1.00	3392153	0.013	-0.1	11	0.4	25.0
MC-DDH-002	10.05	11.05	1.00	3392154	0.012	-0.1	7	1.5	20.9
MC-DDH-002	11.05	12.05	1.00	3392156	0.014	-0.1	5	0.4	20.6
MC-DDH-002	12.05	13.05	1.00	3392157	0.018	-0.1	6	0.6	23.8
MC-DDH-002	13.05	14.05	1.00	3392158	0.011	-0.1	6	0.3	19.6
MC-DDH-002	14.05	15.05	1.00	3392159	0.009	-0.1	6	0.3	14.7
MC-DDH-002	15.05	16.05	1.00	3392160	0.009	0.1	7	0.4	21.5
MC-DDH-002	16.05	17.05	1.00	3392161	0.017	0.1	9	0.2	11.6
MC-DDH-002	17.05	18.05	1.00	3392163	0.010	0.1	6	0.2	6.6
MC-DDH-002	22.05	23.05	1.00	3392164	0.035	0.5	18	0.3	14.0
MC-DDH-002	23.05	24.05	1.00	3392165	0.005	-0.1	3	0.2	15.4
MC-DDH-002	24.05	25.05	1.00	3392166	0.008	-0.1	1	0.2	13.1
MC-DDH-002	25.05	26.05	1.00	3392167	0.006	-0.1	2	0.3	13.0
MC-DDH-002	26.05	27.05	1.00	3392168	0.001	-0.1	-1	1.1	24.9
MC-DDH-002	27.05	28.05	1.00	3392170	0.009	-0.1	5	0.2	14.5
MC-DDH-002	28.05	29.05	1.00	3392171	0.006	-0.1	-1	0.3	15.2
MC-DDH-002	29.05	30.05	1.00	3392172	0.008	-0.1	3	0.6	18.4
MC-DDH-002	30.05	31.05	1.00	3392173	0.006	-0.1	-1	0.5	30.1
MC-DDH-002	31.05	32.05	1.00	3392174	0.001	-0.1	-1	0.4	16.7
MC-DDH-002	33.05	34.05	1.00	3392177	0.043	0.3	30	0.8	28.4
MC-DDH-002	34.05	35.05	1.00	3392178	0.076	0.6	49	1.2	37.1
MC-DDH-002	35.05	36.05	1.00	3392179	0.021	0.2	18	1.3	54.2
MC-DDH-002	36.05	37.05	1.00	3392180	0.089	0.9	23	1.5	42.8
MC-DDH-002	37.05	38.05	1.00	3392181	0.032	0.4	27	1.8	30.3
MC-DDH-002	38.05	39.05	1.00	3392182	0.015	0.1	21	0.7	16.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-002	39.05	40.05	1.00	3392184	0.011	-0.1	10	0.5	20.8
MC-DDH-002	40.05	41.05	1.00	3392185	0.053	0.4	67	1.5	24.8
MC-DDH-002	41.05	42.05	1.00	3392186	0.103	0.9	78	2.4	40.4
MC-DDH-002	42.05	43.05	1.00	3392187	0.072	0.3	77	3.1	17.6
MC-DDH-002	43.05	44.05	1.00	3392188	0.068	0.3	90	3.0	22.1
MC-DDH-002	44.05	45.05	1.00	3392189	0.029	0.1	53	1.4	16.8
MC-DDH-002	45.05	46.05	1.00	3392191	0.011	-0.1	24	0.8	22.3
MC-DDH-002	46.05	47.05	1.00	3392192	0.015	-0.1	21	0.4	16.9
MC-DDH-002	47.05	48.05	1.00	3392193	0.024	0.2	34	0.2	19.6
MC-DDH-002	48.05	49.05	1.00	3392194	0.044	0.7	33	0.9	31.7
MC-DDH-002	49.05	50.05	1.00	3392195	0.032	0.2	46	0.9	12.7
MC-DDH-002	50.05	51.05	1.00	3392196	0.076	0.4	67	3.5	11.1
MC-DDH-002	51.05	52.05	1.00	3392198	0.063	0.4	51	4.0	11.7
MC-DDH-002	71.05	72.05	1.00	3392199	0.036	0.2	20	3.0	3.9
MC-DDH-002	74.05	75.05	1.00	3392200	0.008	-0.1	-1	0.7	3.7
MC-DDH-002	75.05	76.05	1.00	3392201	0.012	-0.1	8	0.8	6.1
MC-DDH-002	78.05	79.05	1.00	3392202	0.023	0.1	4	0.7	5.9
MC-DDH-002	80.05	81.05	1.00	3392205	0.035	0.1	13	1.2	10.5
MC-DDH-002	81.05	82.05	1.00	3392206	0.015	-0.1	4	0.2	1.9
MC-DDH-002	82.05	83.05	1.00	3392207	0.013	-0.1	-1	0.9	1.9
MC-DDH-002	83.05	84.05	1.00	3392208	0.032	0.2	10	8.1	3.1
MC-DDH-002	84.05	85.05	1.00	3392209	0.013	-0.1	-1	1.1	2.9
MC-DDH-002	96.05	97.05	1.00	3392210	0.010	-0.1	3	0.6	2.1
MC-DDH-002	97.05	98.05	1.00	3392212	0.008	-0.1	7	0.4	3.0
MC-DDH-002	98.05	99.05	1.00	3392213	0.011	-0.1	7	1.1	5.4
MC-DDH-002	99.05	100.05	1.00	3392214	0.010	-0.1	6	0.4	2.9
MC-DDH-002	100.05	101.05	1.00	3392215	0.005	-0.1	4	0.2	1.4
MC-DDH-002	101.05	102.05	1.00	3392216	0.008	-0.1	4	0.4	1.8
MC-DDH-002	102.05	103.05	1.00	3392217	0.006	-0.1	4	0.1	1.2
MC-DDH-002	103.05	104.05	1.00	3392219	0.006	-0.1	2	-0.1	3.7
MC-DDH-002	104.05	105.05	1.00	3392220	0.001	-0.1	6	-0.1	2.3
MC-DDH-007	3.05	4.05	1.00	3392222	0.141	1.8	84	4.0	46.8
MC-DDH-007	4.05	5.05	1.00	3392223	0.065	1.1	46	1.4	19.7
MC-DDH-007	5.05	6.05	1.00	3392224	0.113	2.4	85	3.2	50.0
MC-DDH-007	6.05	7.05	1.00	3392225	0.048	1.7	44	0.6	18.0
MC-DDH-007	7.05	8.05	1.00	3392226	0.050	1.4	43	0.5	4.6
MC-DDH-007	8.05	9.05	1.00	3392227	0.041	2.0	42	0.5	7.3
MC-DDH-007	9.05	10.05	1.00	3392229	0.070	4.0	23	0.4	10.0
MC-DDH-007	10.05	11.05	1.00	3392230	0.059	1.5	26	0.2	5.5
MC-DDH-007	11.05	12.05	1.00	3392231	0.103	2.2	57	0.5	6.8
MC-DDH-007	12.05	13.05	1.00	3392232	0.069	4.0	54	0.3	22.5
MC-DDH-007	13.05	14.05	1.00	3392233	0.126	7.3	135	2.0	56.1
MC-DDH-007	15.05	16.05	1.00	3392236	0.190	0.8	164	1.0	31.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	16.05	17.05	1.00	3392237	0.056	0.4	88	1.8	37.7
MC-DDH-007	17.05	18.05	1.00	3392238	0.593	3.9	282	15.2	61.7
MC-DDH-007	18.05	19.05	1.00	3392239	0.181	1.7	125	14.1	14.4
MC-DDH-007	19.05	20.05	1.00	3392240	0.021	1.7	8	0.2	2.0
MC-DDH-007	20.05	21.05	1.00	3392241	0.016	-0.1	8	0.2	0.9
MC-DDH-007	21.05	22.05	1.00	3392243	0.020	0.2	26	0.2	1.6
MC-DDH-007	22.05	23.05	1.00	3392244	0.034	0.9	31	0.2	3.4
MC-DDH-007	23.05	24.05	1.00	3392245	0.050	0.5	121	0.7	1.0
MC-DDH-007	24.05	25.05	1.00	3392246	0.014	-0.1	60	2.5	1.9
MC-DDH-007	25.05	26.05	1.00	3392247	0.013	0.4	39	5.9	370.1
MC-DDH-007	26.05	27.05	1.00	3392248	0.120	4.0	55	20.9	13.6
MC-DDH-007	27.05	28.05	1.00	3392250	0.100	2.6	44	15.8	16.3
MC-DDH-007	28.05	29.05	1.00	3392251	0.154	1.9	68	1.4	22.8
MC-DDH-007	29.05	30.05	1.00	3392252	0.152	1.4	104	0.9	24.1
MC-DDH-007	30.05	31.05	1.00	3392253	0.213	3.1	161	1.2	24.0
MC-DDH-007	31.05	32.05	1.00	3392254	0.159	2.2	115	1.3	13.0
MC-DDH-007	32.05	33.05	1.00	3392255	0.142	3.0	106	7.8	15.8
MC-DDH-007	33.05	34.05	1.00	3392257	0.713	4.1	147	10.5	27.5
MC-DDH-007	34.05	35.05	1.00	3392258	2.974	14.3	69	2.7	50.2
MC-DDH-007	35.05	36.05	1.00	3392259	0.282	2.8	141	5.3	20.1
MC-DDH-007	36.05	37.05	1.00	3392260	0.296	4.3	92	27.4	24.9
MC-DDH-007	37.05	38.05	1.00	3392261	0.234	6.3	106	58.0	30.0
MC-DDH-007	39.05	40.05	1.00	3392264	0.033	0.2	22	2.8	15.5
MC-DDH-007	40.05	41.05	1.00	3392265	0.039	-0.1	15	1.0	3.6
MC-DDH-007	41.05	42.05	1.00	3392266	0.022	-0.1	16	1.8	15.8
MC-DDH-007	42.05	43.05	1.00	3392267	0.018	0.1	14	2.7	13.4
MC-DDH-007	43.05	44.05	1.00	3392268	0.007	-0.1	3	4.3	2.4
MC-DDH-007	44.05	45.05	1.00	3392269	0.015	-0.1	7	1.6	3.5
MC-DDH-007	45.05	46.05	1.00	3392271	0.019	-0.1	12	1.9	4.7
MC-DDH-007	46.05	47.05	1.00	3392272	0.022	-0.1	16	1.4	3.4
MC-DDH-007	47.05	48.05	1.00	3392273	0.318	-0.1	76	0.6	2.0
MC-DDH-007	48.05	49.05	1.00	3392274	0.053	-0.1	18	0.5	2.3
MC-DDH-007	49.05	50.05	1.00	3392275	0.025	0.2	16	1.5	5.7
MC-DDH-007	50.05	51.05	1.00	3392276	0.029	0.5	22	1.0	8.0
MC-DDH-007	51.05	52.05	1.00	3392278	0.068	3.0	58	3.5	17.9
MC-DDH-007	52.05	53.05	1.00	3392279	0.052	1.2	36	0.2	8.0
MC-DDH-007	53.05	54.05	1.00	3392280	0.015	1.5	25	0.3	6.3
MC-DDH-007	54.05	55.05	1.00	3392281	0.017	0.3	18	0.2	10.5
MC-DDH-007	55.05	56.05	1.00	3392282	0.039	0.5	43	-0.1	14.7
MC-DDH-007	56.05	57.05	1.00	3392283	0.028	0.4	29	0.4	6.3
MC-DDH-007	57.05	58.05	1.00	3392285	0.021	-0.1	10	4.5	3.0
MC-DDH-007	58.05	59.05	1.00	3392286	0.075	0.7	14	1.5	3.1
MC-DDH-007	59.05	60.05	1.00	3392287	0.043	0.4	25	0.9	17.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	60.05	61.05	1.00	3392288	0.018	0.3	11	0.3	13.4
MC-DDH-007	61.05	62.05	1.00	3392289	0.076	1.0	15	0.7	16.7
MC-DDH-007	63.05	64.05	1.00	3392292	0.018	0.2	11	1.5	3.8
MC-DDH-007	64.05	65.05	1.00	3392293	0.011	0.2	12	1.0	3.7
MC-DDH-007	65.05	66.05	1.00	3392294	0.030	0.9	32	2.9	1.9
MC-DDH-007	66.05	67.05	1.00	3392295	0.016	1.7	17	0.3	4.1
MC-DDH-007	67.05	68.05	1.00	3392296	0.116	4.8	48	0.5	6.0
MC-DDH-007	68.05	69.05	1.00	3392297	0.008	0.7	13	0.1	1.2
MC-DDH-007	69.05	70.05	1.00	3392299	0.676	39.8	244	67.5	56.0
MC-DDH-007	70.05	71.05	1.00	3392300	0.785	65.2	342	52.7	78.8
MC-DDH-007	71.05	72.05	1.00	3392301	1.490	4.7	108	0.6	10.8
MC-DDH-007	72.05	73.05	1.00	3392302	2.115	7.8	153	1.3	19.0
MC-DDH-007	73.05	74.05	1.00	3392303	0.870	6.9	46	0.6	9.0
MC-DDH-007	74.05	75.05	1.00	3392304	0.208	0.7	19	2.3	4.3
MC-DDH-007	75.05	76.05	1.00	3392306	0.050	0.6	26	1.4	6.7
MC-DDH-007	76.05	77.05	1.00	3392307	0.080	0.6	44	0.8	7.7
MC-DDH-007	77.05	78.05	1.00	3392308	0.071	0.3	22	0.1	1.9
MC-DDH-007	78.05	79.05	1.00	3392309	0.024	0.3	11	0.2	1.8
MC-DDH-007	79.05	80.05	1.00	3392310	0.079	0.4	19	0.2	1.3
MC-DDH-007	80.05	81.05	1.00	3392311	5.072	4.2	70	0.4	4.1
MC-DDH-007	81.05	82.05	1.00	3392313	1.329	3.6	141	3.7	13.7
MC-DDH-007	82.05	83.05	1.00	3392314	0.320	7.7	109	5.7	31.4
MC-DDH-007	83.05	84.05	1.00	3392315	0.561	1.1	20	0.3	4.4
MC-DDH-007	84.05	85.05	1.00	3392316	0.511	0.6	37	0.7	4.3
MC-DDH-007	85.05	86.05	1.00	3392317	0.152	0.3	40	0.5	5.9
MC-DDH-007	87.05	88.05	1.00	3392320	0.115	0.4	30	0.4	3.5
MC-DDH-007	88.05	89.05	1.00	3392321	0.023	0.1	10	0.5	8.0
MC-DDH-007	89.05	90.05	1.00	3392322	0.057	0.5	39	1.0	20.0
MC-DDH-007	90.05	91.05	1.00	3392323	0.018	-0.1	11	0.2	4.9
MC-DDH-007	91.05	92.05	1.00	3392324	0.007	-0.1	6	0.1	1.2
MC-DDH-007	92.05	93.05	1.00	3392325	0.054	0.2	7	0.5	1.5
MC-DDH-007	93.05	94.05	1.00	3392327	0.052	0.2	20	0.7	1.2
MC-DDH-007	94.05	95.05	1.00	3392328	0.016	0.2	17	0.6	3.1
MC-DDH-007	95.05	96.05	1.00	3392329	0.012	0.1	12	0.3	1.4
MC-DDH-007	96.05	97.05	1.00	3392331	0.001	0.2	33	0.1	2.1
MC-DDH-007	97.05	98.05	1.00	3392332	0.025	0.4	44	0.4	8.3
MC-DDH-007	98.05	99.05	1.00	3392333	0.029	0.6	45	0.8	29.1
MC-DDH-007	99.05	100.05	1.00	3392334	0.054	1.0	25	1.5	47.0
MC-DDH-007	100.05	101.05	1.00	3392335	0.017	0.2	9	2.1	28.9
MC-DDH-007	101.05	102.05	1.00	3392336	0.041	0.1	5	1.3	29.1
MC-DDH-007	102.05	103.05	1.00	3392338	0.057	0.2	11	1.0	57.5
MC-DDH-007	103.05	104.05	1.00	3392339	0.034	0.2	8	0.5	42.5
MC-DDH-007	104.05	105.05	1.00	3392340	0.022	0.4	15	3.1	75.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	105.05	106.05	1.00	3392341	0.037	0.3	11	2.5	73.5
MC-DDH-007	106.05	107.05	1.00	3392342	0.862	0.2	8	0.7	19.6
MC-DDH-007	108.05	109.05	1.00	3392345	0.140	0.4	107	0.6	128.4
MC-DDH-007	109.05	110.05	1.00	3392346	0.517	1.4	32	0.2	32.7
MC-DDH-007	110.05	111.05	1.00	3392347	0.008	-0.1	9	0.5	7.0
MC-DDH-007	111.05	112.05	1.00	3392348	0.008	0.1	11	0.3	2.9
MC-DDH-007	112.05	113.05	1.00	3392349	0.006	0.1	4	0.6	2.0
MC-DDH-007	113.05	114.05	1.00	3392350	0.001	-0.1	2	1.0	7.0
MC-DDH-007	114.05	115.05	1.00	3392352	0.001	-0.1	16	0.9	8.5
MC-DDH-007	115.05	116.05	1.00	3392353	0.012	0.7	8	2.3	36.5
MC-DDH-007	116.05	117.05	1.00	3392354	0.001	-0.1	9	2.7	5.6
MC-DDH-007	117.05	118.05	1.00	3392355	0.001	-0.1	10	2.9	5.7
MC-DDH-007	118.05	119.05	1.00	3392356	0.005	-0.1	29	1.9	4.9
MC-DDH-007	119.05	120.05	1.00	3392357	0.005	-0.1	31	1.2	4.1
MC-DDH-007	120.05	121.05	1.00	3392359	0.006	-0.1	16	2.9	7.4
MC-DDH-007	121.05	122.05	1.00	3392360	0.001	-0.1	22	4.6	7.0
MC-DDH-007	122.05	123.05	1.00	3392361	0.001	-0.1	12	2.4	5.4
MC-DDH-007	123.05	124.05	1.00	3392362	0.001	-0.1	17	3.2	8.5
MC-DDH-007	124.05	125.05	1.00	3392363	0.001	-0.1	13	1.9	18.4
MC-DDH-007	125.05	126.05	1.00	3392364	0.006	-0.1	14	1.6	14.5
MC-DDH-007	126.05	127.05	1.00	3392366	0.007	0.1	6	0.9	58.9
MC-DDH-007	127.05	128.05	1.00	3392367	0.111	0.4	12	0.3	60.7
MC-DDH-007	128.05	129.05	1.00	3392368	0.020	0.2	4	0.4	5.2
MC-DDH-007	129.05	130.05	1.00	3392369	0.032	5.8	10	0.8	27.1
MC-DDH-007	131.05	132.05	1.00	3392371	0.020	1.5	22	0.6	13.3
MC-DDH-007	132.05	133.05	1.00	3392373	0.006	-0.1	15	0.4	6.4
MC-DDH-007	133.05	134.05	1.00	3392374	0.001	-0.1	12	1.1	7.6
MC-DDH-007	134.05	135.05	1.00	3392375	0.009	0.1	10	1.7	29.9
MC-DDH-007	135.05	136.05	1.00	3392376	0.029	0.1	27	0.4	42.5
MC-DDH-007	136.05	137.05	1.00	3392377	0.015	0.3	17	0.7	188.1
MC-DDH-007	137.05	138.05	1.00	3392378	0.009	0.1	14	1.0	87.6
MC-DDH-007	138.05	139.05	1.00	3392380	0.005	0.2	13	1.3	13.9
MC-DDH-007	139.05	140.05	1.00	3392381	0.005	0.2	9	0.3	4.1
MC-DDH-007	140.05	141.05	1.00	3392382	0.001	-0.1	12	0.2	7.6
MC-DDH-007	141.05	142.05	1.00	3392383	0.001	0.2	22	1.8	72.4
MC-DDH-007	142.05	143.05	1.00	3392384	0.006	0.1	37	2.1	81.4
MC-DDH-007	143.05	144.05	1.00	3392385	0.001	0.1	15	2.0	54.0
MC-DDH-007	144.05	145.05	1.00	3392387	0.006	0.3	25	2.5	214.8
MC-DDH-007	145.05	146.05	1.00	3392388	0.001	0.2	29	1.8	70.3
MC-DDH-007	146.05	147.05	1.00	3392389	0.001	-0.1	31	1.8	48.4
MC-DDH-007	147.05	148.05	1.00	3392390	0.001	0.1	21	0.8	42.2
MC-DDH-007	148.05	149.05	1.00	3392391	0.001	0.2	24	1.5	25.6
MC-DDH-007	149.05	150.05	1.00	3392392	0.006	-0.1	19	2.0	51.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-007	150.05	150.97	0.92	3392394	0.001	-0.1	27	2.3	36.7
MC-DDH-008	3.00	4.00	1.00	3392395	0.044	1.3	53	5.8	15.0
MC-DDH-008	4.00	5.00	1.00	3392396	0.047	1.4	45	5.3	14.2
MC-DDH-008	5.00	6.00	1.00	3392397	0.033	0.4	83	1.4	7.8
MC-DDH-008	6.00	7.00	1.00	3392398	0.049	0.2	49	1.5	12.5
MC-DDH-008	8.00	9.00	1.00	3392401	0.038	0.5	70	0.5	9.1
MC-DDH-008	9.00	10.00	1.00	3392402	0.011	0.2	33	0.3	6.5
MC-DDH-008	10.00	11.00	1.00	3392403	0.028	1.0	45	0.3	7.0
MC-DDH-008	11.00	12.00	1.00	3392404	0.217	0.8	54	0.2	1.5
MC-DDH-008	12.00	13.00	1.00	3392405	0.139	1.0	37	0.3	3.7
MC-DDH-008	13.00	14.00	1.00	3392406	0.040	0.2	12	0.2	1.4
MC-DDH-008	14.00	15.00	1.00	3392408	0.135	0.9	13	0.3	3.6
MC-DDH-008	15.00	16.00	1.00	3392409	0.323	0.9	53	0.6	8.6
MC-DDH-008	16.00	17.00	1.00	3392410	0.047	0.1	22	0.4	9.4
MC-DDH-008	17.00	18.00	1.00	3392411	0.490	1.2	35	0.6	3.9
MC-DDH-008	18.00	19.00	1.00	3392412	0.608	3.4	75	0.9	3.0
MC-DDH-008	19.00	20.00	1.00	3392413	0.220	2.0	38	0.3	1.6
MC-DDH-008	20.00	21.00	1.00	3392415	0.017	0.6	26	0.3	4.9
MC-DDH-008	21.00	22.00	1.00	3392416	0.041	1.9	31	0.2	7.8
MC-DDH-008	22.00	23.00	1.00	3392417	0.110	0.9	23	0.2	2.8
MC-DDH-008	23.00	24.00	1.00	3392418	0.029	0.3	16	0.1	1.6
MC-DDH-008	24.00	25.00	1.00	3392419	0.048	0.9	15	0.2	1.2
MC-DDH-008	25.00	26.00	1.00	3392420	0.007	-0.1	9	0.1	0.8
MC-DDH-008	26.00	27.00	1.00	3392422	0.006	0.1	4	-0.1	3.8
MC-DDH-008	27.00	28.00	1.00	3392423	0.009	-0.1	5	-0.1	0.8
MC-DDH-008	28.00	29.00	1.00	3392424	0.001	-0.1	7	0.2	1.1
MC-DDH-008	29.00	30.00	1.00	3392425	0.012	-0.1	15	0.6	1.6
MC-DDH-008	30.00	31.00	1.00	3392426	0.022	0.2	36	0.6	2.5
MC-DDH-008	32.00	33.00	1.00	3392429	0.121	1.5	75	71.6	6.1
MC-DDH-008	33.00	34.00	1.00	3392431	0.036	0.3	14	0.2	1.8
MC-DDH-008	34.00	35.00	1.00	3392432	0.035	0.2	12	0.4	2.9
MC-DDH-008	35.00	36.00	1.00	3392433	0.058	0.7	9	0.6	3.3
MC-DDH-008	36.00	37.00	1.00	3392434	0.015	-0.1	8	0.4	2.9
MC-DDH-008	37.00	38.00	1.00	3392435	0.049	0.8	23	0.2	5.1
MC-DDH-008	38.00	39.00	1.00	3392436	0.055	0.4	31	1.4	7.3
MC-DDH-008	39.00	40.00	1.00	3392438	0.041	0.2	47	1.7	8.2
MC-DDH-008	40.00	41.00	1.00	3392439	0.067	0.3	41	1.3	4.3
MC-DDH-008	41.00	42.00	1.00	3392440	0.064	0.3	44	0.7	5.2
MC-DDH-008	42.00	43.00	1.00	3392441	0.051	0.2	35	0.6	4.0
MC-DDH-008	43.00	44.00	1.00	3392442	0.056	0.2	35	0.5	4.9
MC-DDH-008	45.00	46.00	1.00	3392445	0.060	0.1	50	0.1	2.6
MC-DDH-008	46.00	47.00	1.00	3392446	0.095	0.2	59	0.2	5.5
MC-DDH-008	47.00	48.00	1.00	3392447	0.030	-0.1	22	0.3	9.0

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	48.00	49.00	1.00	3392448	0.011	-0.1	8	0.1	1.9
MC-DDH-008	49.00	50.00	1.00	3392449	0.032	0.2	28	0.3	8.3
MC-DDH-008	50.00	51.00	1.00	3392450	0.006	-0.1	-1	0.1	1.0
MC-DDH-008	51.00	52.00	1.00	3392452	0.011	-0.1	22	0.3	2.1
MC-DDH-008	52.00	53.00	1.00	3392453	0.046	0.2	9	0.2	1.3
MC-DDH-008	53.00	54.00	1.00	3392454	0.056	0.1	18	0.2	2.9
MC-DDH-008	54.00	55.00	1.00	3392455	0.009	0.1	14	0.2	2.5
MC-DDH-008	55.00	56.00	1.00	3392456	0.006	0.1	6	0.1	4.9
MC-DDH-008	56.00	57.00	1.00	3392457	0.011	-0.1	6	0.2	1.4
MC-DDH-008	57.00	58.00	1.00	3392459	0.009	0.2	6	0.1	1.2
MC-DDH-008	58.00	59.00	1.00	3392460	0.031	1.6	18	0.3	2.6
MC-DDH-008	59.00	60.00	1.00	3392461	0.040	4.9	18	0.4	2.9
MC-DDH-008	60.00	61.00	1.00	3392462	0.074	3.0	25	0.5	1.5
MC-DDH-008	61.00	62.00	1.00	3392463	0.038	6.7	21	0.3	2.5
MC-DDH-008	63.00	64.00	1.00	3392466	0.325	4.8	52	1.3	3.5
MC-DDH-008	64.00	65.00	1.00	3392467	0.256	2.6	80	0.4	4.1
MC-DDH-008	65.00	66.00	1.00	3392468	0.401	1.1	31	0.3	2.4
MC-DDH-008	66.00	67.00	1.00	3392469	0.286	0.7	42	0.2	1.4
MC-DDH-008	67.00	68.00	1.00	3392470	1.585	1.2	104	0.2	1.5
MC-DDH-008	68.00	69.00	1.00	3392471	1.541	0.9	46	0.3	0.8
MC-DDH-008	69.00	70.00	1.00	3392473	3.602	1.3	95	0.2	0.8
MC-DDH-008	70.00	71.00	1.00	3392474	2.046	1.2	95	0.4	2.1
MC-DDH-008	71.00	72.00	1.00	3392475	2.118	4.5	51	0.4	2.1
MC-DDH-008	72.00	73.00	1.00	3392476	7.285	1.8	59	0.1	0.8
MC-DDH-008	73.00	74.00	1.00	3392477	2.981	0.7	38	0.3	1.2
MC-DDH-008	74.00	75.00	1.00	3392478	1.242	0.9	29	-0.1	0.8
MC-DDH-008	75.00	76.00	1.00	3392480	5.153	2.0	52	0.2	0.8
MC-DDH-008	76.00	77.00	1.00	3392481	5.772	1.5	56	0.1	0.7
MC-DDH-008	77.00	78.00	1.00	3392482	5.342	3.2	70	0.2	2.3
MC-DDH-008	78.00	79.00	1.00	3392483	6.193	8.2	63	-0.1	0.5
MC-DDH-008	79.00	80.00	1.00	3392484	0.108	0.2	11	0.2	1.9
MC-DDH-008	80.00	81.00	1.00	3392485	0.062	0.3	18	0.3	2.7
MC-DDH-008	81.00	82.00	1.00	3392487	0.122	6.5	6	0.3	2.3
MC-DDH-008	82.00	83.00	1.00	3392488	1.886	3.3	42	0.2	1.0
MC-DDH-008	83.00	84.00	1.00	3392489	0.105	0.5	31	-0.1	1.6
MC-DDH-008	84.00	85.00	1.00	3392490	0.016	0.1	41	0.1	2.7
MC-DDH-008	85.00	86.00	1.00	3392491	0.022	-0.1	8	0.6	2.8
MC-DDH-008	86.00	87.00	1.00	3392492	0.014	-0.1	9	0.4	33.1
MC-DDH-008	87.00	88.00	1.00	3392494	0.013	0.2	19	1.4	188.9
MC-DDH-008	88.00	89.00	1.00	3392495	0.018	0.2	8	2.9	54.6
MC-DDH-008	89.00	90.00	1.00	3392496	0.007	-0.1	10	2.6	11.2
MC-DDH-008	90.00	91.00	1.00	3392497	0.005	-0.1	5	5.2	2.2
MC-DDH-008	91.00	92.00	1.00	3392498	0.006	-0.1	6	11.7	3.1

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	93.00	94.00	1.00	3392501	0.006	-0.1	-1	0.9	2.9
MC-DDH-008	94.00	95.00	1.00	3392502	0.008	-0.1	31	0.2	1.3
MC-DDH-008	95.00	96.00	1.00	3392503	0.025	-0.1	29	0.2	3.6
MC-DDH-008	96.00	97.00	1.00	3392504	0.013	-0.1	17	8.7	17.7
MC-DDH-008	97.00	98.00	1.00	3392505	0.015	0.7	10	0.4	200.9
MC-DDH-008	98.00	99.00	1.00	3392506	0.017	0.1	7	0.1	0.6
MC-DDH-008	99.00	100.00	1.00	3392508	0.012	0.1	13	0.3	1.4
MC-DDH-008	100.00	101.00	1.00	3392509	0.025	0.1	9	0.3	1.3
MC-DDH-008	101.00	102.00	1.00	3392510	0.139	0.1	22	0.1	7.3
MC-DDH-008	102.00	103.00	1.00	3392511	0.092	0.4	15	0.2	4.3
MC-DDH-008	103.00	104.00	1.00	3392512	0.011	-0.1	2	0.1	13.1
MC-DDH-008	104.00	105.00	1.00	3392513	0.010	-0.1	22	0.1	0.7
MC-DDH-008	105.00	106.00	1.00	3392515	0.015	-0.1	4	0.3	2.2
MC-DDH-008	106.00	107.00	1.00	3392516	0.155	0.2	13	0.2	6.2
MC-DDH-008	107.00	108.00	1.00	3392517	0.295	0.5	13	0.1	11.4
MC-DDH-008	108.00	109.00	1.00	3392518	0.049	0.2	21	0.2	13.4
MC-DDH-008	109.00	110.00	1.00	3392519	0.006	-0.1	2	-0.1	3.7
MC-DDH-008	110.00	111.00	1.00	3392520	0.015	-0.1	-1	0.2	6.8
MC-DDH-008	111.00	112.00	1.00	3392522	0.015	0.1	8	0.1	4.9
MC-DDH-008	112.00	113.00	1.00	3392523	0.057	0.2	8	0.2	1.2
MC-DDH-008	113.00	114.00	1.00	3392524	0.042	0.2	12	0.1	1.2
MC-DDH-008	114.00	115.00	1.00	3392525	0.040	0.1	8	0.1	1.2
MC-DDH-008	115.00	116.00	1.00	3392526	0.040	0.1	15	0.1	0.5
MC-DDH-008	117.00	118.00	1.00	3392529	0.007	0.1	14	0.1	0.6
MC-DDH-008	118.00	119.00	1.00	3392530	0.038	0.1	20	-0.1	1.4
MC-DDH-008	119.00	120.00	1.00	3392531	0.022	-0.1	7	0.3	8.9
MC-DDH-008	120.00	121.00	1.00	3392532	0.029	-0.1	20	0.4	2.8
MC-DDH-008	121.00	122.00	1.00	3392533	1.634	0.5	15	0.5	2.6
MC-DDH-008	122.00	123.00	1.00	3392534	0.057	0.2	6	0.1	1.6
MC-DDH-008	123.00	124.00	1.00	3392536	0.317	0.1	18	0.2	4.3
MC-DDH-008	124.00	125.00	1.00	3392537	0.207	0.2	16	0.4	7.2
MC-DDH-008	125.00	126.00	1.00	3392538	0.122	0.5	7	0.2	8.8
MC-DDH-008	126.00	127.00	1.00	3392539	0.073	0.2	5	0.1	3.5
MC-DDH-008	127.00	128.00	1.00	3392540	0.028	0.2	7	0.1	3.3
MC-DDH-008	128.00	129.00	1.00	3392541	0.189	0.5	23	0.3	16.8
MC-DDH-008	129.00	130.00	1.00	3392543	0.009	-0.1	43	1.6	21.1
MC-DDH-008	130.00	131.00	1.00	3392544	0.006	-0.1	29	1.7	6.0
MC-DDH-008	131.00	132.00	1.00	3392545	0.006	-0.1	84	3.9	7.2
MC-DDH-008	132.00	133.00	1.00	3392546	0.007	-0.1	38	3.8	7.7
MC-DDH-008	133.00	134.00	1.00	3392547	0.006	-0.1	28	1.8	10.9
MC-DDH-008	135.00	136.00	1.00	3392550	0.008	-0.1	47	1.8	9.1
MC-DDH-008	136.00	137.00	1.00	3392551	0.005	-0.1	28	1.3	13.2
MC-DDH-008	137.00	138.00	1.00	3392552	0.009	-0.1	15	0.8	7.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	138.00	139.00	1.00	3392553	0.015	-0.1	36	1.0	21.9
MC-DDH-008	139.00	140.00	1.00	3392554	0.008	0.4	25	0.9	87.1
MC-DDH-008	141.00	142.00	1.00	3392557	0.064	0.5	21	0.2	1.6
MC-DDH-008	142.00	143.00	1.00	3392558	0.024	0.1	23	0.2	1.4
MC-DDH-008	143.00	144.00	1.00	3392559	0.029	-0.1	19	0.1	2.2
MC-DDH-008	144.00	145.00	1.00	3392560	0.072	0.3	65	0.2	10.6
MC-DDH-008	145.00	146.00	1.00	3392561	0.027	0.2	24	0.1	5.6
MC-DDH-008	146.00	147.00	1.00	3392562	0.015	0.7	25	4.8	234.6
MC-DDH-008	147.00	148.00	1.00	3392564	0.008	0.1	25	1.7	23.1
MC-DDH-008	148.00	149.00	1.00	3392565	0.010	0.3	40	3.1	218.6
MC-DDH-008	149.00	150.00	1.00	3392566	0.006	0.1	54	1.4	78.6
MC-DDH-008	150.00	151.00	1.00	3392567	0.010	0.2	128	5.3	118.5
MC-DDH-008	151.00	152.00	1.00	3392568	0.008	0.1	52	1.0	74.0
MC-DDH-008	152.00	153.00	1.00	3392569	0.007	0.2	50	3.3	93.4
MC-DDH-008	153.00	154.00	1.00	3392571	0.008	-0.1	29	1.2	44.1
MC-DDH-008	154.00	155.00	1.00	3392572	0.009	0.3	105	5.6	138.0
MC-DDH-008	155.00	156.00	1.00	3392573	0.007	0.3	19	2.2	109.6
MC-DDH-008	156.00	157.00	1.00	3392574	0.001	0.1	15	2.7	4.0
MC-DDH-008	157.00	158.00	1.00	3392575	0.075	-0.1	16	2.8	3.3
MC-DDH-008	158.00	159.00	1.00	3392576	0.001	-0.1	13	4.5	1.3
MC-DDH-008	159.00	160.00	1.00	3392578	0.001	-0.1	12	3.4	2.3
MC-DDH-008	160.00	161.00	1.00	3392579	0.001	-0.1	9	0.9	14.8
MC-DDH-008	161.00	162.00	1.00	3392580	0.007	-0.1	35	1.2	58.9
MC-DDH-008	162.00	163.00	1.00	3392581	0.001	-0.1	9	0.3	2.2
MC-DDH-008	163.00	164.00	1.00	3392582	0.006	-0.1	22	2.3	4.1
MC-DDH-008	165.00	166.00	1.00	3392585	0.006	-0.1	11	1.2	2.1
MC-DDH-008	166.00	167.00	1.00	3392586	0.009	-0.1	9	0.9	3.4
MC-DDH-008	167.00	168.00	1.00	3392587	0.006	-0.1	14	0.6	4.6
MC-DDH-008	168.00	169.00	1.00	3392588	0.007	-0.1	15	0.8	16.0
MC-DDH-008	169.00	170.00	1.00	3392589	0.007	-0.1	15	0.8	14.4
MC-DDH-008	170.00	171.00	1.00	3392590	0.024	0.5	30	2.3	8.3
MC-DDH-008	171.00	172.00	1.00	3392592	0.020	0.1	14	0.7	3.1
MC-DDH-008	172.00	173.00	1.00	3392593	0.014	0.1	35	1.2	2.4
MC-DDH-008	173.00	174.00	1.00	3392594	0.001	0.2	5	1.7	12.6
MC-DDH-008	174.00	175.00	1.00	3392595	0.001	-0.1	4	0.9	20.5
MC-DDH-008	175.00	176.00	1.00	3392596	0.001	-0.1	4	0.1	5.2
MC-DDH-008	176.00	177.00	1.00	3392597	0.023	-0.1	4	0.9	20.3
MC-DDH-008	177.00	178.00	1.00	3392599	0.006	0.2	5	3.7	1.5
MC-DDH-008	178.00	179.00	1.00	3392600	0.006	-0.1	-1	1.5	1.7
MC-DDH-008	179.00	180.00	1.00	3392601	0.007	-0.1	-1	1.1	3.7
MC-DDH-008	180.00	181.00	1.00	3392602	0.009	-0.1	6	4.0	25.2
MC-DDH-008	181.00	182.00	1.00	3392603	0.007	-0.1	4	0.5	3.4
MC-DDH-008	182.00	183.00	1.00	3392604	0.007	-0.1	13	0.8	20.3

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-008	183.00	184.00	1.00	3392606	0.007	-0.1	14	0.5	31.1
MC-DDH-008	184.00	185.00	1.00	3392607	0.007	-0.1	3	0.5	1.7
MC-DDH-008	185.00	186.00	1.00	3392608	0.010	0.1	3	0.6	6.6
MC-DDH-008	186.00	187.00	1.00	3392609	0.006	-0.1	3	0.2	1.6
MC-DDH-008	187.00	187.60	0.60	3392610	0.009	-0.1	4	0.4	3.0
MC-DDH-009	2.00	3.00	1.00	3392613	0.010	0.2	8	0.5	1.4
MC-DDH-009	3.00	4.00	1.00	3392614	0.005	-0.1	6	-0.1	0.4
MC-DDH-009	4.00	5.00	1.00	3392615	0.005	1.2	21	0.6	3.0
MC-DDH-009	5.00	6.00	1.00	3392616	0.033	2.3	41	0.7	10.0
MC-DDH-009	6.00	7.00	1.00	3392617	0.035	9.8	37	2.2	9.7
MC-DDH-009	7.00	8.00	1.00	3392618	0.014	2.3	12	0.7	6.8
MC-DDH-009	8.00	9.00	1.00	3392620	0.043	11.6	16	1.4	5.3
MC-DDH-009	9.00	10.00	1.00	3392621	0.031	3.0	81	1.5	10.6
MC-DDH-009	10.00	11.00	1.00	3392622	0.009	0.3	10	0.2	3.1
MC-DDH-009	11.00	12.00	1.00	3392623	0.007	-0.1	10	-0.1	0.8
MC-DDH-009	12.00	13.00	1.00	3392624	0.006	-0.1	10	-0.1	0.6
MC-DDH-009	14.00	15.00	1.00	3392627	0.012	0.5	10	0.2	0.8
MC-DDH-009	15.00	16.00	1.00	3392628	0.026	0.8	35	0.3	1.4
MC-DDH-009	16.00	17.00	1.00	3392629	0.028	0.5	23	0.9	3.6
MC-DDH-009	17.00	18.00	1.00	3392630	0.032	0.4	33	2.1	5.8
MC-DDH-009	18.00	19.00	1.00	3392631	0.011	2.1	9	1.3	1.1
MC-DDH-009	19.00	20.00	1.00	3392632	0.007	-0.1	-1	0.2	0.7
MC-DDH-009	20.00	21.00	1.00	3392634	0.007	-0.1	-1	-0.1	0.7
MC-DDH-009	21.00	22.00	1.00	3392635	0.007	-0.1	5	-0.1	1.0
MC-DDH-009	22.00	23.00	1.00	3392636	0.007	0.1	6	0.4	1.2
MC-DDH-009	23.00	24.00	1.00	3392637	0.010	0.1	5	0.2	1.4
MC-DDH-009	24.00	25.00	1.00	3392638	0.009	-0.1	6	0.2	3.4
MC-DDH-009	25.00	26.00	1.00	3392639	0.005	-0.1	-1	0.2	2.3
MC-DDH-009	26.00	27.00	1.00	3392641	0.006	-0.1	1	0.2	1.5
MC-DDH-009	27.00	28.00	1.00	3392642	0.006	-0.1	2	-0.1	1.0
MC-DDH-009	28.00	29.00	1.00	3392643	0.006	-0.1	7	0.2	1.9
MC-DDH-009	29.00	30.00	1.00	3392644	0.007	-0.1	9	0.2	0.8
MC-DDH-009	30.00	31.00	1.00	3392645	0.011	-0.1	8	0.4	1.1
MC-DDH-009	31.00	32.00	1.00	3392646	0.090	2.2	89	0.7	1.8
MC-DDH-009	32.00	33.00	1.00	3392648	0.016	0.3	157	0.6	3.7
MC-DDH-009	33.00	34.00	1.00	3392649	0.008	-0.1	15	0.3	6.8
MC-DDH-009	34.00	35.00	1.00	3392650	0.032	0.2	21	0.8	9.2
MC-DDH-009	35.00	36.00	1.00	3392651	0.027	0.3	14	3.1	32.4
MC-DDH-009	36.00	37.00	1.00	3392652	0.022	0.2	7	2.1	30.0
MC-DDH-009	38.00	39.00	1.00	3392655	0.012	0.1	7	0.3	1.2
MC-DDH-009	39.00	40.00	1.00	3392656	0.040	7.9	17	3.0	2.3
MC-DDH-009	40.00	41.00	1.00	3392657	0.048	10.7	8	2.0	3.9
MC-DDH-009	41.00	42.00	1.00	3392658	0.027	2.5	8	1.0	3.8

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	42.00	43.00	1.00	3392659	0.018	0.2	20	0.8	8.2
MC-DDH-009	43.00	44.00	1.00	3392660	0.006	-0.1	11	0.1	1.1
MC-DDH-009	44.00	45.00	1.00	3392662	0.006	-0.1	8	0.2	0.8
MC-DDH-009	45.00	46.00	1.00	3392663	0.006	-0.1	8	0.2	0.4
MC-DDH-009	46.00	47.00	1.00	3392664	0.006	-0.1	10	0.2	0.3
MC-DDH-009	47.00	48.00	1.00	3392665	0.008	-0.1	12	0.2	0.9
MC-DDH-009	48.00	49.00	1.00	3392666	0.052	4.5	38	2.4	13.6
MC-DDH-009	49.00	50.00	1.00	3392667	0.019	4.0	23	2.0	7.3
MC-DDH-009	50.00	51.00	1.00	3392669	0.008	0.2	1	3.4	2.1
MC-DDH-009	51.00	52.00	1.00	3392670	0.006	-0.1	4	2.4	20.9
MC-DDH-009	52.00	53.00	1.00	3392671	0.010	0.4	3	1.6	13.5
MC-DDH-009	53.00	54.00	1.00	3392672	0.008	0.1	6	28.2	2.3
MC-DDH-009	54.00	55.00	1.00	3392674	0.001	0.1	6	4.7	1.9
MC-DDH-009	55.00	56.00	1.00	3392675	0.001	-0.1	5	4.3	1.6
MC-DDH-009	56.00	57.00	1.00	3392676	0.017	-0.1	8	4.3	1.5
MC-DDH-009	57.00	58.00	1.00	3392677	0.001	0.4	3	34.8	7.9
MC-DDH-009	58.00	59.00	1.00	3392678	0.001	0.2	5	3.3	2.5
MC-DDH-009	59.00	60.00	1.00	3392679	0.005	0.1	7	6.0	4.6
MC-DDH-009	60.00	61.00	1.00	3392681	0.006	-0.1	8	0.8	3.5
MC-DDH-009	61.00	62.00	1.00	3392682	0.021	0.3	12	5.0	2.9
MC-DDH-009	62.00	63.00	1.00	3392683	0.014	-0.1	9	1.7	5.2
MC-DDH-009	63.00	64.00	1.00	3392684	0.005	-0.1	4	1.1	1.4
MC-DDH-009	64.00	65.00	1.00	3392685	0.006	-0.1	5	3.0	37.0
MC-DDH-009	65.00	66.00	1.00	3392686	0.005	-0.1	5	2.9	59.9
MC-DDH-009	66.00	67.00	1.00	3392688	0.006	0.2	9	2.8	75.4
MC-DDH-009	67.00	68.00	1.00	3392689	0.008	0.1	13	2.6	42.2
MC-DDH-009	68.00	69.00	1.00	3392690	0.012	0.2	39	5.1	75.8
MC-DDH-009	69.00	70.00	1.00	3392691	0.010	0.2	37	5.0	64.1
MC-DDH-009	70.00	71.00	1.00	3392692	0.007	0.1	6	3.6	17.3
MC-DDH-009	71.00	72.00	1.00	3392693	0.001	-0.1	9	0.5	1.2
MC-DDH-009	72.00	73.00	1.00	3392695	0.006	-0.1	11	5.1	29.4
MC-DDH-009	73.00	74.00	1.00	3392696	0.006	-0.1	13	3.0	15.1
MC-DDH-009	74.00	75.00	1.00	3392697	0.001	-0.1	13	0.5	4.9
MC-DDH-009	75.00	76.00	1.00	3392698	0.001	-0.1	10	0.7	5.6
MC-DDH-009	76.00	77.00	1.00	3392699	0.017	0.1	11	1.5	2.8
MC-DDH-009	77.00	78.00	1.00	3392700	0.014	-0.1	4	3.6	23.8
MC-DDH-009	78.00	79.00	1.00	3392702	0.001	0.3	7	7.6	15.0
MC-DDH-009	79.00	80.00	1.00	3392703	0.001	0.3	8	4.0	5.9
MC-DDH-009	80.00	81.00	1.00	3392704	0.007	0.3	7	3.8	7.6
MC-DDH-009	81.00	82.00	1.00	3392705	0.001	0.1	13	1.1	4.6
MC-DDH-009	82.00	83.00	1.00	3392706	0.001	-0.1	8	2.8	2.6
MC-DDH-009	83.00	84.00	1.00	3392707	0.001	-0.1	5	6.4	3.3
MC-DDH-009	84.00	85.00	1.00	3392709	0.001	0.1	9	1.6	4.3

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	85.00	86.00	1.00	3392710	0.007	0.1	12	3.8	4.4
MC-DDH-009	86.00	87.00	1.00	3392711	0.006	0.1	11	5.6	58.5
MC-DDH-009	87.00	88.00	1.00	3392712	0.008	0.5	9	4.5	5.2
MC-DDH-009	88.00	89.00	1.00	3392713	0.033	0.3	13	0.7	4.1
MC-DDH-009	89.00	90.00	1.00	3392714	0.084	0.8	19	0.2	0.8
MC-DDH-009	90.00	91.00	1.00	3392716	0.229	0.8	18	0.3	10.9
MC-DDH-009	91.00	92.00	1.00	3392717	1.067	1.0	26	0.3	7.4
MC-DDH-009	92.00	93.00	1.00	3392718	1.826	2.1	40	0.2	2.0
MC-DDH-009	93.00	94.00	1.00	3392719	0.604	1.5	17	-0.1	0.5
MC-DDH-009	94.00	95.00	1.00	3392720	1.116	2.4	8	-0.1	0.8
MC-DDH-009	95.00	96.00	1.00	3392721	3.524	3.9	26	-0.1	1.9
MC-DDH-009	96.00	97.00	1.00	3392723	0.138	2.1	68	0.9	5.6
MC-DDH-009	97.00	98.00	1.00	3392724	0.011	0.2	7	0.3	0.7
MC-DDH-009	98.00	99.00	1.00	3392725	0.007	-0.1	9	1.4	1.1
MC-DDH-009	99.00	100.00	1.00	3392726	0.007	-0.1	12	1.5	2.0
MC-DDH-009	100.00	101.00	1.00	3392727	0.012	-0.1	20	9.5	3.7
MC-DDH-009	101.00	102.00	1.00	3392728	0.001	-0.1	14	11.7	0.8
MC-DDH-009	102.00	103.00	1.00	3392730	0.006	-0.1	5	137.0	1.1
MC-DDH-009	103.00	104.00	1.00	3392731	0.009	-0.1	15	10.2	1.4
MC-DDH-009	104.00	105.00	1.00	3392732	0.009	0.4	9	1.1	1.3
MC-DDH-009	105.00	106.00	1.00	3392733	0.012	0.8	6	2.5	1.0
MC-DDH-009	106.00	107.00	1.00	3392734	0.006	0.1	8	0.8	0.7
MC-DDH-009	107.00	108.00	1.00	3392735	0.007	0.5	10	2.4	1.7
MC-DDH-009	108.00	109.00	1.00	3392737	0.007	0.2	13	2.1	2.1
MC-DDH-009	109.00	110.00	1.00	3392738	0.017	1.5	26	0.2	1.9
MC-DDH-009	110.00	111.00	1.00	3392739	0.007	0.2	12	3.1	1.4
MC-DDH-009	111.00	112.00	1.00	3392740	0.006	0.2	17	0.3	0.9
MC-DDH-009	112.00	113.00	1.00	3392741	0.517	8.8	1266	1.4	28.3
MC-DDH-009	113.00	114.00	1.00	3392742	1.051	12.5	2089	3.7	45.0
MC-DDH-009	114.00	115.00	1.00	3392744	0.015	-0.1	37	1.8	1.8
MC-DDH-009	115.00	116.00	1.00	3392745	0.006	-0.1	10	0.6	2.6
MC-DDH-009	116.00	117.00	1.00	3392746	0.001	0.2	27	0.3	6.8
MC-DDH-009	117.00	118.00	1.00	3392747	0.008	0.6	22	3.0	2.0
MC-DDH-009	118.00	119.00	1.00	3392748	0.001	-0.1	23	0.7	0.7
MC-DDH-009	119.00	120.00	1.00	3392749	0.001	-0.1	11	0.7	0.4
MC-DDH-009	120.00	121.00	1.00	3392751	0.001	-0.1	3	0.3	0.9
MC-DDH-009	121.00	122.00	1.00	3392752	0.001	-0.1	5	0.9	0.4
MC-DDH-009	122.00	123.00	1.00	3392753	0.001	-0.1	6	1.0	0.6
MC-DDH-009	123.00	124.00	1.00	3392754	0.001	-0.1	11	1.9	0.7
MC-DDH-009	124.00	125.00	1.00	3392755	0.007	-0.1	11	5.7	1.7
MC-DDH-009	125.00	126.00	1.00	3392756	0.001	-0.1	10	2.0	0.8
MC-DDH-009	126.00	127.00	1.00	3392758	0.001	-0.1	6	1.0	2.5
MC-DDH-009	127.00	128.00	1.00	3392759	0.009	-0.1	13	1.7	1.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	128.00	129.00	1.00	3392760	0.001	-0.1	6	0.5	5.7
MC-DDH-009	129.00	130.00	1.00	3392761	0.005	-0.1	20	1.1	5.5
MC-DDH-009	130.00	131.00	1.00	3392762	0.001	-0.1	13	1.4	4.9
MC-DDH-009	131.00	132.00	1.00	3392763	0.001	-0.1	13	1.8	2.3
MC-DDH-009	132.00	133.00	1.00	3392765	0.001	0.2	19	3.2	16.5
MC-DDH-009	133.00	134.00	1.00	3392766	0.001	-0.1	15	1.8	73.9
MC-DDH-009	134.00	135.00	1.00	3392767	0.001	0.2	15	6.5	103.6
MC-DDH-009	135.00	136.00	1.00	3392768	0.001	-0.1	15	3.7	2.4
MC-DDH-009	136.00	137.00	1.00	3392769	0.001	-0.1	14	0.8	0.7
MC-DDH-009	137.00	138.00	1.00	3392770	0.006	0.8	10	2.5	3.7
MC-DDH-009	138.00	139.00	1.00	3392772	0.001	0.1	15	1.0	7.3
MC-DDH-009	139.00	140.00	1.00	3392773	0.001	0.1	16	1.2	0.9
MC-DDH-009	140.00	141.00	1.00	3392774	0.001	-0.1	21	0.3	-0.1
MC-DDH-009	141.00	142.00	1.00	3392775	0.001	-0.1	12	0.3	1.5
MC-DDH-009	142.00	143.00	1.00	3392776	0.001	-0.1	10	1.5	5.1
MC-DDH-009	143.00	144.00	1.00	3392778	0.006	-0.1	13	0.4	1.8
MC-DDH-009	144.00	145.00	1.00	3392779	0.006	-0.1	11	0.6	2.2
MC-DDH-009	145.00	146.00	1.00	3392780	0.012	-0.1	15	1.0	24.9
MC-DDH-009	146.00	147.00	1.00	3392781	0.011	0.2	15	1.1	40.7
MC-DDH-009	147.00	148.00	1.00	3392782	0.012	-0.1	11	6.0	1.5
MC-DDH-009	148.00	149.00	1.00	3392783	0.008	0.2	7	1.1	66.3
MC-DDH-009	149.00	150.00	1.00	3392785	0.006	0.2	14	0.6	69.6
MC-DDH-009	150.00	151.00	1.00	3392786	0.011	0.2	15	2.7	104.3
MC-DDH-009	151.00	152.00	1.00	3392787	0.001	0.2	18	1.8	118.3
MC-DDH-009	152.00	153.00	1.00	3392788	0.006	0.6	59	2.5	374.0
MC-DDH-009	153.00	154.00	1.00	3392789	0.006	0.4	81	9.0	268.4
MC-DDH-009	154.00	155.00	1.00	3392790	0.005	0.9	55	5.3	447.1
MC-DDH-009	155.00	156.00	1.00	3392792	0.009	0.3	13	4.6	51.6
MC-DDH-009	156.00	157.00	1.00	3392793	0.007	0.1	10	0.8	2.8
MC-DDH-009	157.00	158.00	1.00	3392794	0.015	0.1	12	3.3	4.0
MC-DDH-009	158.00	159.00	1.00	3392795	0.020	-0.1	11	0.9	2.3
MC-DDH-009	159.00	160.00	1.00	3392796	0.007	0.3	6	2.3	2.6
MC-DDH-009	160.00	161.00	1.00	3392797	0.016	0.2	27	0.9	6.2
MC-DDH-009	161.00	162.00	1.00	3392799	0.008	-0.1	15	0.2	1.2
MC-DDH-009	162.00	163.00	1.00	3392800	0.009	-0.1	10	0.4	1.3
MC-DDH-009	163.00	164.00	1.00	3392801	0.010	0.2	32	26.6	1.8
MC-DDH-009	164.00	165.00	1.00	3392802	0.019	0.4	11	0.8	1.9
MC-DDH-009	165.00	166.00	1.00	3392803	0.027	0.2	67	1.3	2.2
MC-DDH-009	166.00	167.00	1.00	3392804	0.008	-0.1	7	2.5	2.2
MC-DDH-009	167.00	168.00	1.00	3392806	0.022	0.2	16	1.9	10.2
MC-DDH-009	168.00	169.00	1.00	3392807	0.019	0.3	21	1.6	5.6
MC-DDH-009	169.00	170.00	1.00	3392808	0.029	0.4	37	3.5	10.2
MC-DDH-009	170.00	171.00	1.00	3392809	0.012	0.3	32	2.8	85.5

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	171.00	172.00	1.00	3392810	0.007	-0.1	19	1.6	23.3
MC-DDH-009	172.00	173.00	1.00	3392811	0.009	-0.1	8	0.8	5.2
MC-DDH-009	173.00	174.00	1.00	3392813	0.008	-0.1	5	1.8	2.0
MC-DDH-009	174.00	175.00	1.00	3392814	0.008	-0.1	4	2.5	3.4
MC-DDH-009	175.00	176.00	1.00	3392815	0.007	-0.1	3	0.4	2.9
MC-DDH-009	176.00	177.00	1.00	3392816	0.006	-0.1	5	0.7	3.8
MC-DDH-009	177.00	178.00	1.00	3392817	0.006	-0.1	9	0.6	7.6
MC-DDH-009	178.00	179.00	1.00	3392818	0.005	-0.1	5	0.6	3.8
MC-DDH-009	179.00	180.00	1.00	3392820	0.008	-0.1	6	0.6	6.2
MC-DDH-009	180.00	181.00	1.00	3392821	0.001	-0.1	3	0.1	4.4
MC-DDH-009	181.00	182.00	1.00	3392822	0.005	0.1	9	0.5	32.8
MC-DDH-009	182.00	183.00	1.00	3392823	0.036	-0.1	11	0.3	3.5
MC-DDH-009	183.00	184.00	1.00	3392824	0.006	-0.1	8	0.3	2.7
MC-DDH-009	184.00	185.00	1.00	3392825	0.005	-0.1	6	0.7	5.0
MC-DDH-009	185.00	186.00	1.00	3392827	0.009	0.2	11	0.7	16.4
MC-DDH-009	186.00	187.00	1.00	3392828	0.007	0.2	15	0.9	40.5
MC-DDH-009	187.00	188.00	1.00	3392829	0.067	1.2	46	1.4	38.1
MC-DDH-009	188.00	189.00	1.00	3392830	0.064	0.8	114	4.4	8.0
MC-DDH-009	189.00	190.00	1.00	3392831	0.041	0.5	38	0.8	4.3
MC-DDH-009	190.00	191.00	1.00	3392832	0.090	1.2	71	0.6	11.4
MC-DDH-009	191.00	192.00	1.00	3392834	0.201	3.9	94	5.2	15.6
MC-DDH-009	192.00	193.00	1.00	3392835	0.400	8.1	151	1.5	12.6
MC-DDH-009	193.00	194.00	1.00	3392836	0.282	4.4	457	1.6	28.8
MC-DDH-009	194.00	195.00	1.00	3392837	0.172	3.7	160	1.0	35.8
MC-DDH-009	195.00	196.00	1.00	3392838	0.224	5.6	304	5.2	214.0
MC-DDH-009	196.00	197.00	1.00	3392839	0.263	5.1	409	4.8	194.9
MC-DDH-009	197.00	198.00	1.00	3392841	0.112	0.8	115	5.8	15.7
MC-DDH-009	198.00	199.00	1.00	3392842	0.063	2.1	40	0.7	9.8
MC-DDH-009	199.00	200.00	1.00	3392843	0.056	1.9	22	0.6	4.9
MC-DDH-009	200.00	201.00	1.00	3392844	0.049	0.5	28	2.9	4.6
MC-DDH-009	201.00	202.00	1.00	3392845	0.017	0.3	18	1.2	4.5
MC-DDH-009	202.00	203.00	1.00	3392846	0.013	0.2	11	0.9	4.3
MC-DDH-009	203.00	204.00	1.00	3392848	0.010	0.2	14	1.2	9.4
MC-DDH-009	204.00	205.00	1.00	3392849	0.043	0.5	64	1.1	13.2
MC-DDH-009	205.00	206.00	1.00	3392850	0.156	2.4	228	2.0	77.6
MC-DDH-009	206.00	207.00	1.00	3392851	0.248	4.5	410	2.3	341.0
MC-DDH-009	207.00	208.00	1.00	3392852	0.015	0.3	11	0.8	2.7
MC-DDH-009	208.00	209.00	1.00	3392853	0.169	1.5	138	0.8	11.7
MC-DDH-009	209.00	210.00	1.00	3392855	0.479	3.4	377	1.9	152.2
MC-DDH-009	210.00	211.00	1.00	3392856	0.048	1.3	55	1.0	9.0
MC-DDH-009	211.00	212.00	1.00	3392857	0.062	0.9	34	0.5	6.7
MC-DDH-009	212.00	213.00	1.00	3392858	0.012	0.1	18	2.1	7.1
MC-DDH-009	213.00	214.00	1.00	3392859	0.022	0.3	13	1.8	7.9

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-009	214.00	215.00	1.00	3392860	0.019	0.3	18	1.2	8.3
MC-DDH-009	215.00	216.00	1.00	3392862	0.027	0.4	33	3.3	39.3
MC-DDH-009	216.00	217.00	1.00	3392863	0.024	0.2	32	2.7	38.8
MC-DDH-009	217.00	218.00	1.00	3392864	0.043	0.2	55	6.4	19.5
MC-DDH-009	218.00	219.00	1.00	3392865	0.033	0.4	50	2.5	140.8
MC-DDH-009	219.00	220.00	1.00	3392866	0.010	0.2	12	1.5	23.9
MC-DDH-009	220.00	221.00	1.00	3392867	0.017	0.1	8	11.1	3.9
MC-DDH-009	221.00	222.00	1.00	3392869	0.016	0.2	11	1.7	5.3
MC-DDH-009	222.00	223.00	1.00	3392870	0.042	0.5	33	2.5	8.8
MC-DDH-009	223.00	224.00	1.00	3392871	0.052	0.3	34	1.6	6.9
MC-DDH-009	224.00	225.00	1.00	3392872	0.048	0.3	35	1.9	22.9
MC-DDH-009	225.00	226.00	1.00	3392873	0.022	0.3	29	4.2	5.8
MC-DDH-009	226.00	227.00	1.00	3392874	0.067	1.4	40	2.0	10.4
MC-DDH-009	227.00	228.00	1.00	3392876	0.020	0.3	15	1.9	8.0
MC-DDH-009	228.00	229.00	1.00	3392877	0.078	0.2	24	0.8	15.5
MC-DDH-009	229.00	230.00	1.00	3392878	0.047	1.3	19	3.9	106.0
MC-DDH-009	230.00	231.00	1.00	3392879	0.029	0.3	21	3.7	3.2
MC-DDH-009	231.00	232.00	1.00	3392880	0.009	-0.1	14	3.5	2.4
MC-DDH-009	232.00	233.00	1.00	3392881	0.009	0.4	9	3.9	7.7
MC-DDH-009	233.00	234.00	1.00	3392883	0.008	0.1	16	1.4	9.0
MC-DDH-009	234.00	235.00	1.00	3392884	0.007	0.1	9	1.9	6.3
MC-DDH-009	235.00	236.00	1.00	3392885	0.021	0.2	7	1.3	5.4
MC-DDH-009	236.00	237.00	1.00	3392886	0.009	-0.1	8	1.4	2.6
MC-DDH-009	237.00	238.00	1.00	3392887	0.017	0.1	12	2.9	3.1
MC-DDH-009	238.00	239.00	1.00	3392888	0.013	-0.1	13	1.2	2.7
MC-DDH-009	239.00	240.00	1.00	3392890	0.018	-0.1	9	1.8	5.1
MC-DDH-009	240.00	241.00	1.00	3392891	0.025	0.1	24	6.7	1.8
MC-DDH-009	241.00	242.00	1.00	3392892	0.009	-0.1	15	4.2	1.3
MC-DDH-009	242.00	243.00	1.00	3392893	0.017	-0.1	20	0.8	1.8
MC-DDH-009	243.00	244.00	1.00	3392894	0.011	-0.1	12	0.6	0.9
MC-DDH-009	244.00	245.00	1.00	3392895	0.009	0.2	30	2.0	1.7
MC-DDH-009	245.00	245.52	0.52	3392897	0.010	0.1	13	2.1	3.4
MC-DDH-010	1.00	2.00	1.00	3392899	0.029	4.6	28	2.2	30.2
MC-DDH-010	2.00	3.00	1.00	3392900	0.043	3.6	16	0.8	20.6
MC-DDH-010	3.00	4.00	1.00	3392901	0.069	1.9	16	0.9	19.1
MC-DDH-010	4.00	5.00	1.00	3392902	0.043	5.5	29	1.1	4.4
MC-DDH-010	5.00	6.00	1.00	3392903	0.053	9.7	33	1.6	6.0
MC-DDH-010	6.00	7.00	1.00	3392904	0.012	0.3	10	0.3	1.4
MC-DDH-010	7.00	8.00	1.00	3392906	0.063	9.8	43	2.5	18.7
MC-DDH-010	8.00	9.00	1.00	3392907	0.027	1.4	29	0.7	2.3
MC-DDH-010	9.00	10.00	1.00	3392908	0.008	0.1	8	0.2	1.3
MC-DDH-010	10.00	11.00	1.00	3392909	0.012	2.3	2	0.3	3.5
MC-DDH-010	11.00	12.00	1.00	3392910	0.040	2.5	70	1.1	6.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-010	12.00	13.00	1.00	3392911	0.030	1.0	33	0.6	8.0
MC-DDH-010	13.00	14.00	1.00	3392913	0.045	4.2	56	3.1	12.1
MC-DDH-010	14.00	15.00	1.00	3392914	0.225	37.4	50	2.6	191.4
MC-DDH-010	15.00	16.00	1.00	3392915	0.133	6.5	13	0.8	21.5
MC-DDH-010	16.00	17.00	1.00	3392916	0.121	2.1	5	0.2	2.4
MC-DDH-010	17.00	18.00	1.00	3392917	0.031	13.4	39	2.8	39.6
MC-DDH-010	18.00	19.00	1.00	3392918	0.275	7.5	13	1.4	27.4
MC-DDH-010	19.00	20.00	1.00	3392920	0.090	0.2	15	0.6	5.6
MC-DDH-010	20.00	21.00	1.00	3392921	0.068	0.3	14	0.7	2.6
MC-DDH-010	21.00	22.00	1.00	3392922	0.045	6.9	10	1.5	6.9
MC-DDH-010	22.00	23.00	1.00	3392923	0.010	0.1	5	0.1	0.5
MC-DDH-010	23.00	24.00	1.00	3392924	0.005	-0.1	6	-0.1	0.4
MC-DDH-010	24.00	25.00	1.00	3392925	0.008	-0.1	11	0.1	1.4
MC-DDH-010	25.00	26.00	1.00	3392927	0.006	0.1	6	-0.1	0.6
MC-DDH-010	26.00	27.00	1.00	3392928	0.006	-0.1	-1	-0.1	0.3
MC-DDH-010	27.00	28.00	1.00	3392929	0.006	0.1	-1	-0.1	0.4
MC-DDH-010	28.00	29.00	1.00	3392930	0.006	0.3	3	-0.1	0.7
MC-DDH-010	29.00	30.00	1.00	3392931	0.008	-0.1	3	0.1	0.6
MC-DDH-010	30.00	31.00	1.00	3392932	0.005	-0.1	2	-0.1	0.7
MC-DDH-010	31.00	32.00	1.00	3392934	0.007	-0.1	14	-0.1	2.5
MC-DDH-010	32.00	33.00	1.00	3392935	0.006	-0.1	7	-0.1	0.8
MC-DDH-010	33.00	34.00	1.00	3392936	0.011	-0.1	8	0.1	0.9
MC-DDH-010	34.00	35.00	1.00	3392937	0.012	2.1	-1	0.3	5.1
MC-DDH-010	35.00	36.00	1.00	3392938	0.012	0.6	16	0.7	67.0
MC-DDH-010	36.00	37.00	1.00	3392939	0.007	0.3	9	1.8	26.5
MC-DDH-010	37.00	38.00	1.00	3392941	0.008	0.5	11	0.3	3.2
MC-DDH-010	38.00	39.00	1.00	3392942	0.008	0.2	14	0.5	7.3
MC-DDH-010	39.00	40.00	1.00	3392943	0.011	2.4	18	0.5	5.3
MC-DDH-010	40.00	41.00	1.00	3392944	0.032	11.7	16	1.8	72.1
MC-DDH-010	41.00	42.00	1.00	3392945	0.021	0.2	46	0.9	18.3
MC-DDH-010	42.00	43.00	1.00	3392946	0.007	0.3	38	1.9	3.5
MC-DDH-010	43.00	44.00	1.00	3392948	0.009	0.2	21	0.8	26.1
MC-DDH-010	44.00	45.00	1.00	3392949	0.011	0.1	47	0.5	29.6
MC-DDH-010	45.00	46.00	1.00	3392950	0.021	0.7	43	0.5	643.7
MC-DDH-010	46.00	47.00	1.00	3392951	0.048	1.1	40	0.2	1133.3
MC-DDH-010	47.00	48.00	1.00	3392952	0.011	0.5	6	2.1	8.1
MC-DDH-010	48.00	49.00	1.00	3392953	0.010	-0.1	5	2.9	4.5
MC-DDH-010	49.00	50.00	1.00	3392955	0.006	-0.1	5	1.3	1.3
MC-DDH-010	50.00	51.00	1.00	3392956	0.006	-0.1	4	15.7	1.3
MC-DDH-010	51.00	52.00	1.00	3392957	0.008	-0.1	8	12.4	2.2
MC-DDH-010	52.00	53.00	1.00	3392958	0.154	-0.1	36	5.5	4.1
MC-DDH-010	53.00	54.00	1.00	3392959	0.033	-0.1	13	5.6	2.8
MC-DDH-010	54.00	55.00	1.00	3392960	0.351	0.1	5	1.4	1.9

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-010	55.00	56.00	1.00	3392962	0.105	0.1	4	2.0	20.0
MC-DDH-010	56.00	57.00	1.00	3392963	0.313	3.1	18	2.8	347.6
MC-DDH-010	57.00	58.00	1.00	3392964	0.049	1.4	28	1.5	81.4
MC-DDH-010	58.00	59.00	1.00	3392965	0.072	0.8	10	0.6	9.3
MC-DDH-010	59.00	60.00	1.00	3392966	0.033	0.3	16	0.3	15.5
MC-DDH-010	60.00	61.00	1.00	3392967	0.019	-0.1	11	0.5	4.3
MC-DDH-010	61.00	62.00	1.00	3392969	0.021	0.2	12	0.3	3.4
MC-DDH-010	62.00	63.00	1.00	3392970	0.025	0.1	6	1.0	7.1
MC-DDH-010	63.00	64.00	1.00	3392971	0.070	0.2	13	1.9	12.6
MC-DDH-010	64.00	65.00	1.00	3392972	0.028	0.1	13	1.0	5.7
MC-DDH-010	65.00	66.00	1.00	3392973	0.034	0.3	21	1.5	13.6
MC-DDH-010	66.00	67.00	1.00	3392974	0.041	-0.1	16	0.5	4.2
MC-DDH-010	67.00	68.00	1.00	3392976	0.035	0.1	3	0.4	8.1
MC-DDH-010	68.00	69.00	1.00	3392977	0.011	0.2	8	0.2	6.9
MC-DDH-010	69.00	70.00	1.00	3392978	0.017	0.2	11	1.0	5.3
MC-DDH-010	70.00	71.00	1.00	3392979	0.010	0.2	7	0.3	2.0
MC-DDH-010	71.00	72.00	1.00	3392980	0.009	0.1	3	0.4	2.8
MC-DDH-010	72.00	73.00	1.00	3392981	0.014	0.8	3	0.3	5.2
MC-DDH-010	73.00	74.00	1.00	3392983	0.061	4.3	25	1.4	14.9
MC-DDH-010	74.00	75.00	1.00	3392984	0.020	0.2	2	0.2	2.1
MC-DDH-010	75.00	76.00	1.00	3392985	0.037	0.2	34	0.1	3.7
MC-DDH-010	76.00	77.00	1.00	3392986	0.043	0.1	26	0.2	4.1
MC-DDH-010	77.00	78.00	1.00	3392987	0.015	-0.1	10	0.1	2.3
MC-DDH-010	78.00	79.00	1.00	3392988	0.036	0.2	19	0.2	8.5
MC-DDH-010	79.00	80.00	1.00	3392990	0.011	-0.1	10	0.2	2.2
MC-DDH-010	80.00	81.00	1.00	3392991	0.017	0.1	6	0.2	1.9
MC-DDH-010	81.00	82.00	1.00	3392992	0.008	0.1	8	-0.1	1.0
MC-DDH-010	82.00	83.00	1.00	3392993	1.336	0.4	40	0.1	9.0
MC-DDH-010	83.00	84.00	1.00	3392994	1.844	0.4	47	0.1	2.0
MC-DDH-010	84.00	85.00	1.00	3392995	1.093	0.4	39	0.2	4.3
MC-DDH-010	85.00	86.00	1.00	3392997	0.774	0.6	60	-0.1	5.0
MC-DDH-010	86.00	87.00	1.00	3392998	1.397	0.5	36	0.2	3.1
MC-DDH-010	87.00	88.00	1.00	3392999	0.220	0.1	8	-0.1	7.3
MC-DDH-010	88.00	89.00	1.00	3393000	2.005	0.5	52	0.5	8.1
MC-DDH-010	89.00	90.00	1.00	3393001	0.349	0.4	17	0.3	61.4
MC-DDH-010	90.00	91.00	1.00	3393002	0.099	1.2	20	1.2	709.7
MC-DDH-010	91.00	92.00	1.00	3393004	0.040	0.6	33	4.0	134.1
MC-DDH-010	92.00	93.00	1.00	3393005	0.171	1.2	25	0.6	56.0
MC-DDH-010	93.00	94.00	1.00	3393006	0.105	0.2	31	1.9	11.3
MC-DDH-010	94.00	95.00	1.00	3393007	0.085	0.4	67	1.8	60.3
MC-DDH-010	95.00	96.00	1.00	3393008	0.025	-0.1	8	0.2	6.3
MC-DDH-010	96.00	97.00	1.00	3393009	0.018	-0.1	2	0.2	4.7
MC-DDH-010	97.00	98.00	1.00	3393011	0.013	-0.1	4	0.1	3.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-010	98.00	99.00	1.00	3393012	0.920	0.5	30	0.2	19.3
MC-DDH-010	99.00	100.00	1.00	3393013	1.392	1.3	50	0.7	425.8
MC-DDH-010	100.00	100.65	0.65	3393014	0.198	0.6	44	0.3	21.4
MC-DDH-011	1.00	2.00	1.00	3393016	0.077	0.4	84	4.2	44.1
MC-DDH-011	2.00	3.00	1.00	3393017	0.033	0.2	57	2.5	38.7
MC-DDH-011	3.00	4.00	1.00	3393018	0.076	0.3	41	3	44.6
MC-DDH-011	4.00	5.00	1.00	3393019	0.229	0.3	35	1.7	14.5
MC-DDH-011	5.00	6.00	1.00	3393020	0.457	0.7	46	2.4	45.4
MC-DDH-011	6.00	7.00	1.00	3393021	0.193	0.5	37	2.4	50.4
MC-DDH-011	7.00	8.00	1.00	3393023	0.139	0.2	44	1.9	52.1
MC-DDH-011	8.00	9.00	1.00	3393024	0.012	-0.1	23	1.1	9.7
MC-DDH-011	9.00	10.00	1.00	3393025	0.053	-0.1	27	0.9	12.0
MC-DDH-011	10.00	11.00	1.00	3393026	0.028	-0.1	42	0.6	9.1
MC-DDH-011	11.00	12.00	1.00	3393027	0.320	0.4	67	1.5	19.6
MC-DDH-011	12.00	13.00	1.00	3393028	0.566	1.2	56	3.4	27.3
MC-DDH-011	13.00	14.00	1.00	3393030	0.902	2.8	50	0.9	4.8
MC-DDH-011	14.00	15.00	1.00	3393031	0.357	1.7	27	1.2	5.3
MC-DDH-011	15.00	16.00	1.00	3393032	0.214	0.3	23	0.3	2.1
MC-DDH-011	16.00	17.00	1.00	3393033	1.370	0.8	63	0.4	2.4
MC-DDH-011	17.00	18.00	1.00	3393034	1.062	0.2	21	0.2	1.1
MC-DDH-011	18.00	19.00	1.00	3393035	0.642	0.2	28	0.4	0.9
MC-DDH-011	19.00	20.00	1.00	3393037	0.263	0.1	42	0.4	1.5
MC-DDH-011	20.00	21.00	1.00	3393038	0.074	0.1	73	21.9	1.2
MC-DDH-011	21.00	22.00	1.00	3393039	0.029	0.5	15	0.7	2.4
MC-DDH-011	22.00	23.00	1.00	3393040	0.661	1.5	26	0.4	1.2
MC-DDH-011	23.00	24.00	1.00	3393041	0.109	0.7	15	0.3	1.1
MC-DDH-011	24.00	25.00	1.00	3393042	0.336	0.6	9	0.2	0.6
MC-DDH-011	25.00	26.00	1.00	3393044	0.911	1.1	24	0.3	1.5
MC-DDH-011	26.00	27.00	1.00	3393045	0.943	0.2	26	0.4	1.2
MC-DDH-011	27.00	28.00	1.00	3393046	3.911	0.6	85	0.3	0.5
MC-DDH-011	28.00	29.00	1.00	3393047	6.926	4.0	161	0.4	1.5
MC-DDH-011	29.00	30.00	1.00	3393048	0.296	0.9	18	0.3	2.2
MC-DDH-011	30.00	31.00	1.00	3393049	0.035	-0.1	13	0.2	1.7
MC-DDH-011	31.00	32.00	1.00	3393051	0.048	0.2	21	0.2	4.3
MC-DDH-011	32.00	33.00	1.00	3393052	0.159	0.3	15	0.5	1.4
MC-DDH-011	33.00	34.00	1.00	3393053	1.107	1.0	19	0.3	1.4
MC-DDH-011	34.00	35.00	1.00	3393054	1.396	0.3	36	0.7	1.1
MC-DDH-011	35.00	36.00	1.00	3393055	0.968	0.2	22	0.8	1.2
MC-DDH-011	36.00	37.00	1.00	3393056	0.317	0.2	53	1.6	1.7
MC-DDH-011	37.00	38.00	1.00	3393058	0.073	0.2	37	1.1	10.3
MC-DDH-011	38.00	39.00	1.00	3393059	0.037	0.2	15	0.7	2.4
MC-DDH-011	39.00	40.00	1.00	3393060	0.024	-0.1	7	0.6	2.2
MC-DDH-011	40.00	41.00	1.00	3393061	0.034	-0.1	16	1.4	0.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-011	41.00	42.00	1.00	3393062	3.221	3.0	75	1.0	1.7
MC-DDH-011	42.00	43.00	1.00	3393063	0.353	1.4	157	10.4	14.3
MC-DDH-011	43.00	44.00	1.00	3393065	0.628	2.6	238	15.4	19.8
MC-DDH-011	44.00	45.00	1.00	3393066	0.601	1.0	174	1.1	8.8
MC-DDH-011	45.00	46.00	1.00	3393067	0.913	0.6	71	1.1	1.4
MC-DDH-011	46.00	47.00	1.00	3393068	1.507	0.9	65	0.7	3.9
MC-DDH-011	47.00	48.00	1.00	3393069	1.274	0.7	82	0.9	2.6
MC-DDH-011	48.00	49.00	1.00	3393070	0.776	0.5	61	2.7	0.8
MC-DDH-011	49.00	50.00	1.00	3393072	1.642	0.4	86	1.4	1.0
MC-DDH-011	50.00	51.00	1.00	3393073	1.369	0.4	76	0.9	1.3
MC-DDH-011	51.00	52.00	1.00	3393074	1.050	0.3	75	1.1	4.4
MC-DDH-011	52.00	53.00	1.00	3393075	2.414	0.6	95	1.2	3.6
MC-DDH-011	53.00	54.00	1.00	3393076	0.320	0.1	79	1.0	10.0
MC-DDH-011	54.00	55.00	1.00	3393077	2.536	0.8	91	0.7	412.3
MC-DDH-011	55.00	56.00	1.00	3393079	7.166	1.9	117	0.5	475.2
MC-DDH-011	56.00	57.00	1.00	3393080	1.911	0.6	54	1.2	6.4
MC-DDH-011	57.00	58.00	1.00	3393081	0.040	-0.1	38	16.1	4.9
MC-DDH-011	58.00	59.00	1.00	3393082	0.021	-0.1	51	39.2	3.1
MC-DDH-011	59.00	60.00	1.00	3393083	0.070	-0.1	71	14.0	8.2
MC-DDH-011	60.00	61.00	1.00	3393084	0.104	-0.1	41	1.2	5.7
MC-DDH-011	61.00	62.00	1.00	3393086	0.212	-0.1	63	1.2	2.7
MC-DDH-011	62.00	63.00	1.00	3393087	0.314	0.2	117	2.1	2.4
MC-DDH-011	63.00	64.00	1.00	3393088	0.191	-0.1	22	0.5	1.3
MC-DDH-011	64.00	65.00	1.00	3393089	0.012	-0.1	24	2.1	0.8
MC-DDH-011	65.00	66.00	1.00	3393090	0.018	-0.1	15	1.2	0.9
MC-DDH-011	66.00	67.00	1.00	3393091	0.009	-0.1	17	1.2	1.1
MC-DDH-011	67.00	68.00	1.00	3393093	0.023	0.1	20	0.9	4.1
MC-DDH-011	68.00	69.00	1.00	3393094	0.014	-0.1	19	0.8	1.6
MC-DDH-011	69.00	70.00	1.00	3393095	0.008	-0.1	19	0.6	1.0
MC-DDH-011	70.00	71.00	1.00	3393096	0.014	-0.1	21	1.0	1.2
MC-DDH-011	71.00	72.00	1.00	3393097	0.023	-0.1	34	2.5	2.9
MC-DDH-011	72.00	73.00	1.00	3393098	0.089	-0.1	65	1.6	4.0
MC-DDH-011	73.00	74.00	1.00	3393100	0.125	-0.1	102	3.9	2.2
MC-DDH-011	74.00	75.00	1.00	3393101	0.032	-0.1	50	2.6	4.7
MC-DDH-011	75.00	76.00	1.00	3393102	0.048	0.4	43	2.0	2.7
MC-DDH-011	76.00	77.00	1.00	3393103	0.521	0.2	66	1.3	6.5
MC-DDH-011	77.00	78.00	1.00	3393104	0.423	0.2	131	0.6	4.6
MC-DDH-011	78.00	79.00	1.00	3393105	0.490	0.2	28	0.6	9.8
MC-DDH-011	79.00	80.00	1.00	3393107	1.527	0.3	37	3.5	37.5
MC-DDH-011	80.00	81.00	1.00	3393108	2.131	1.5	56	0.9	14.1
MC-DDH-011	81.00	82.00	1.00	3393109	0.013	-0.1	2	0.4	0.7
MC-DDH-011	82.00	83.00	1.00	3393110	0.008	-0.1	2	-0.1	0.6
MC-DDH-011	83.00	84.00	1.00	3393111	0.007	-0.1	2	0.1	0.6

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-011	84.00	85.00	1.00	3393112	0.005	-0.1	-1	-0.1	0.6
MC-DDH-011	85.00	86.00	1.00	3393114	0.007	-0.1	23	2.5	8.8
MC-DDH-011	86.00	87.00	1.00	3393115	0.013	0.3	24	8.1	61.6
MC-DDH-011	87.00	88.00	1.00	3393116	0.005	0.3	12	4.4	48.1
MC-DDH-011	88.00	89.00	1.00	3393117	0.005	-0.1	3	0.7	2.2
MC-DDH-011	89.00	90.00	1.00	3393118	0.010	-0.1	11	10.4	4.1
MC-DDH-011	90.00	91.00	1.00	3393119	0.006	0.1	43	5.9	17.2
MC-DDH-011	91.00	92.00	1.00	3393121	0.001	-0.1	11	0.7	3.7
MC-DDH-011	92.00	93.00	1.00	3393122	0.001	-0.1	5	0.3	2.2
MC-DDH-011	93.00	94.00	1.00	3393123	0.001	-0.1	3	0.3	1.8
MC-DDH-011	94.00	95.00	1.00	3393124	0.006	-0.1	5	0.2	1.9
MC-DDH-011	95.00	96.00	1.00	3393125	0.011	-0.1	8	0.4	3.5
MC-DDH-011	96.00	97.00	1.00	3393126	0.001	-0.1	-1	0.1	1.6
MC-DDH-011	97.00	98.00	1.00	3393128	0.022	0.1	4	0.8	9.4
MC-DDH-011	98.00	99.00	1.00	3393129	0.014	-0.1	3	0.8	8.5
MC-DDH-011	99.00	100.00	1.00	3393130	0.051	0.4	24	4.3	34.5
MC-DDH-011	100.00	101.00	1.00	3393131	0.099	0.5	26	2.4	51.5
MC-DDH-011	101.00	102.00	1.00	3393132	0.084	0.5	31	6.3	35.2
MC-DDH-011	102.00	103.00	1.00	3393133	0.009	-0.1	8	0.5	6.9
MC-DDH-011	103.00	104.00	1.00	3393135	0.001	-0.1	3	0.2	2.6
MC-DDH-011	104.00	105.00	1.00	3393136	0.001	-0.1	-1	0.2	1.5
MC-DDH-011	105.00	106.00	1.00	3393137	0.001	-0.1	-1	-0.1	1.3
MC-DDH-011	106.00	107.00	1.00	3393138	0.001	-0.1	5	-0.1	1.8
MC-DDH-011	107.00	108.00	1.00	3393139	0.001	-0.1	-1	-0.1	1.1
MC-DDH-011	108.00	109.00	1.00	3393140	0.001	-0.1	-1	-0.1	1.8
MC-DDH-011	109.00	110.00	1.00	3393142	0.001	-0.1	3	-0.1	1.0
MC-DDH-011	110.00	111.00	1.00	3393143	0.005	-0.1	1	-0.1	3.8
MC-DDH-011	111.00	112.00	1.00	3393144	0.005	-0.1	-1	-0.1	2.3
MC-DDH-011	121.00	122.00	1.00	3393151	0.000	-0.1	2	-0.1	2.4
MC-DDH-011	122.00	123.00	1.00	3393152	0.000	-0.1	-1	0.1	2.5
MC-DDH-011	123.00	124.00	1.00	3393153	0.013	-0.1	7	0.2	2.0
MC-DDH-011	124.00	125.00	1.00	3393155	0.000	-0.1	1	-0.1	2.6
MC-DDH-011	125.00	126.00	1.00	3393156	0.000	-0.1	3	0.2	8.3
MC-DDH-011	126.00	127.00	1.00	3393157	0.000	-0.1	9	0.1	2.8
MC-DDH-011	127.00	128.00	1.00	3393158	0.000	-0.1	5	-0.1	2.0
MC-DDH-011	128.00	129.00	1.00	3393159	0.008	-0.1	9	0.2	3.8
MC-DDH-011	129.00	130.00	1.00	3393160	0.039	0.2	99	1.7	397.5
MC-DDH-011	130.00	131.00	1.00	3393162	0.021	0.2	138	15.4	264.8
MC-DDH-011	131.00	132.00	1.00	3393163	0.029	0.2	173	16.1	650.6
MC-DDH-011	132.00	133.00	1.00	3393164	0.053	0.6	55	1.0	1718.6
MC-DDH-011	133.00	134.00	1.00	3393165	0.000	-0.1	7	0.3	8.6
MC-DDH-011	134.00	135.00	1.00	3393166	0.000	-0.1	8	0.1	3.4
MC-DDH-011	135.00	136.00	1.00	3393167	0.007	-0.1	6	0.1	2.4

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-011	136.00	137.00	1.00	3393169	0.000	-0.1	3	-0.1	23.6
MC-DDH-011	137.00	138.00	1.00	3393170	0.000	-0.1	7	-0.1	5.3
MC-DDH-011	138.00	139.00	1.00	3393171	0.034	0.1	23	0.5	48.1
MC-DDH-011	139.00	140.00	1.00	3393172	0.011	-0.1	10	0.1	2.8
MC-DDH-011	140.00	141.00	1.00	3393173	0.009	-0.1	8	0.2	5.6
MC-DDH-011	141.00	142.00	1.00	3393174	0.010	-0.1	6	0.4	8.9
MC-DDH-011	142.00	143.00	1.00	3393176	0.016	0.3	12	0.5	14.5
MC-DDH-011	143.00	144.00	1.00	3393177	0.000	-0.1	5	-0.1	2.3
MC-DDH-011	144.00	145.00	1.00	3393178	0.000	-0.1	5	-0.1	2.0
MC-DDH-011	145.00	146.00	1.00	3393179	0.000	-0.1	7	-0.1	1.6
MC-DDH-011	146.00	147.00	1.00	3393180	0.078	-0.1	48	0.2	5.8
MC-DDH-011	147.00	148.00	1.00	3393181	0.006	-0.1	17	0.2	3.8
MC-DDH-011	148.00	149.00	1.00	3393183	0.000	-0.1	18	0.3	2.4
MC-DDH-011	149.00	150.00	1.00	3393184	0.000	-0.1	4	0.2	1.1
MC-DDH-011	150.00	151.00	1.00	3393185	0.000	-0.1	3	-0.1	0.7
MC-DDH-011	151.00	152.00	1.00	3393186	0.000	-0.1	4	-0.1	0.8
MC-DDH-011	152.00	153.00	1.00	3393187	0.000	-0.1	-1	-0.1	1.1
MC-DDH-011	153.00	154.00	1.00	3393188	0.000	-0.1	2	0.5	0.7
MC-DDH-011	154.00	155.00	1.00	3393190	0.010	0.1	12	4.8	2.1
MC-DDH-011	155.00	156.00	1.00	3393191	0.000	-0.1	3	0.3	0.7
MC-DDH-011	156.00	156.30	0.30	3393192	0.000	-0.1	2	8.5	0.6
MC-DDH-012	1.00	2.00	1.00	3393193	0.064	1.8	55	1.7	5.3
MC-DDH-012	2.00	3.00	1.00	3393194	0.037	2.0	21	2.6	5.0
MC-DDH-012	3.00	4.00	1.00	3393195	0.017	0.3	17	0.8	2.0
MC-DDH-012	4.00	5.00	1.00	3393197	0.008	-0.1	13	0.5	1.0
MC-DDH-012	5.00	6.00	1.00	3393198	0.035	1.9	49	0.9	4.6
MC-DDH-012	6.00	7.00	1.00	3393199	0.013	1.6	20	0.5	5.2
MC-DDH-012	7.00	8.00	1.00	3393200	0.015	0.4	22	0.8	3.4
MC-DDH-012	8.00	9.00	1.00	3393201	0.028	0.1	16	0.5	1.3
MC-DDH-012	9.00	10.00	1.00	3393202	0.244	0.8	192	2.1	24.4
MC-DDH-012	10.00	11.00	1.00	3393204	0.093	-0.1	23	0.8	2.9
MC-DDH-012	11.00	12.00	1.00	3393205	0.040	0.2	24	0.9	3.3
MC-DDH-012	12.00	13.00	1.00	3393206	0.020	-0.1	12	1.0	3.0
MC-DDH-012	13.00	14.00	1.00	3393207	0.014	0.1	10	1.0	2.1
MC-DDH-012	14.00	15.00	1.00	3393208	0.011	-0.1	7	3.3	1.1
MC-DDH-012	15.00	16.00	1.00	3393209	0.041	0.3	7	2.2	5.1
MC-DDH-012	16.00	17.00	1.00	3393211	0.256	0.2	5	2.2	2.3
MC-DDH-012	17.00	18.00	1.00	3393212	0.017	0.2	9	10.0	1.5
MC-DDH-012	18.00	19.00	1.00	3393213	0.117	-0.1	5	5.4	2.5
MC-DDH-012	19.00	20.00	1.00	3393214	0.016	-0.1	12	0.4	0.6
MC-DDH-012	20.00	21.00	1.00	3393215	0.012	-0.1	8	7.9	14.2
MC-DDH-012	21.00	22.00	1.00	3393216	0.009	-0.1	4	5.5	1.4
MC-DDH-012	22.00	23.00	1.00	3393218	0.021	-0.1	10	0.9	2.3

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-012	23.00	24.00	1.00	3393219	0.071	-0.1	27	0.3	1.3
MC-DDH-012	24.00	25.00	1.00	3393220	0.773	0.3	102	0.4	1.1
MC-DDH-012	25.00	26.00	1.00	3393221	0.350	0.1	85	0.4	1.0
MC-DDH-012	26.00	27.00	1.00	3393222	0.046	0.8	18	0.5	2.8
MC-DDH-012	27.00	28.00	1.00	3393223	0.033	-0.1	43	0.6	3.1
MC-DDH-012	28.00	29.00	1.00	3393225	0.050	0.8	16	0.7	1.2
MC-DDH-012	29.00	30.00	1.00	3393226	1.544	3.1	45	1.4	1.2
MC-DDH-012	30.00	31.00	1.00	3393227	0.939	7.7	46	2.0	5.7
MC-DDH-012	31.00	32.00	1.00	3393228	0.933	0.6	123	0.4	0.9
MC-DDH-012	32.00	33.00	1.00	3393229	1.058	3.1	83	0.7	0.3
MC-DDH-012	33.00	34.00	1.00	3393230	0.968	1.3	51	0.5	1.1
MC-DDH-012	34.00	35.00	1.00	3393232	1.747	0.4	44	0.4	3.2
MC-DDH-012	35.00	36.00	1.00	3393233	1.269	1.3	31	0.4	2.0
MC-DDH-012	36.00	37.00	1.00	3393234	0.536	1.1	30	0.3	1.0
MC-DDH-012	37.00	38.00	1.00	3393235	0.015	-0.1	9	0.3	0.6
MC-DDH-012	38.00	39.00	1.00	3393236	0.013	0.2	3	0.1	0.7
MC-DDH-012	39.00	40.00	1.00	3393237	0.008	-0.1	8	0.2	0.4
MC-DDH-012	40.00	41.00	1.00	3393239	0.001	-0.1	5	0.2	1.5
MC-DDH-012	41.00	42.00	1.00	3393240	0.001	0.2	2	0.1	0.4
MC-DDH-012	42.00	43.00	1.00	3393241	0.006	0.2	11	0.9	0.4
MC-DDH-012	43.00	44.00	1.00	3393242	2.328	4.3	61	1.0	1.3
MC-DDH-012	44.00	45.00	1.00	3393243	3.702	0.9	72	0.3	1.8
MC-DDH-012	45.00	46.00	1.00	3393244	0.462	0.1	40	0.4	1.7
MC-DDH-012	46.00	47.00	1.00	3393246	0.480	5.1	47	1.1	16.5
MC-DDH-012	47.00	48.00	1.00	3393247	0.909	0.3	47	0.8	14.5
MC-DDH-012	48.00	49.00	1.00	3393248	0.433	0.7	47	1.1	24.7
MC-DDH-012	49.00	50.00	1.00	3393249	0.063	0.1	23	1.0	1.0
MC-DDH-012	50.00	51.00	1.00	3393250	0.201	-0.1	13	0.7	-0.1
MC-DDH-012	51.00	52.00	1.00	3393251	0.026	0.9	20	0.8	0.4
MC-DDH-012	52.00	53.00	1.00	3393253	0.209	0.2	32	0.6	0.8
MC-DDH-012	53.00	54.00	1.00	3393254	0.678	0.2	28	0.3	0.2
MC-DDH-012	54.00	55.00	1.00	3393255	0.128	-0.1	36	0.5	5.1
MC-DDH-012	55.00	56.00	1.00	3393256	10.000	0.8	55	0.5	16.1
MC-DDH-012	56.00	57.00	1.00	3393257	5.478	2.0	50	1.0	3.7
MC-DDH-012	57.00	58.00	1.00	3393258	6.526	1.4	39	0.5	3.0
MC-DDH-012	58.00	59.00	1.00	3393260	2.896	0.6	55	0.7	13.0
MC-DDH-012	59.00	60.00	1.00	3393261	1.028	0.2	67	0.3	8.3
MC-DDH-012	60.00	61.00	1.00	3393262	0.171	-0.1	60	0.4	3.1
MC-DDH-012	61.00	62.00	1.00	3393263	2.481	0.3	46	0.2	2.0
MC-DDH-012	62.00	63.00	1.00	3393264	9.590	1.4	46	-0.1	1.5
MC-DDH-012	63.00	64.00	1.00	3393265	3.211	0.4	65	0.2	2.1
MC-DDH-012	64.00	65.00	1.00	3393267	6.149	0.7	48	0.1	1.0
MC-DDH-012	65.00	66.00	1.00	3393268	8.566	1.2	64	0.1	1.8

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-012	66.00	67.00	1.00	3393269	8.742	1.2	66	0.2	4.0
MC-DDH-012	67.00	68.00	1.00	3393270	1.883	0.2	55	0.4	3.2
MC-DDH-012	68.00	69.00	1.00	3393271	0.722	-0.1	40	0.1	0.7
MC-DDH-012	69.00	70.00	1.00	3393272	7.597	0.5	31	0.5	1.4
MC-DDH-012	70.00	71.00	1.00	3393274	8.892	1.9	57	0.6	3.1
MC-DDH-012	71.00	72.00	1.00	3393275	5.430	2.6	63	0.6	2.8
MC-DDH-012	72.00	73.00	1.00	3393276	6.536	3.6	139	1.0	58.5
MC-DDH-012	73.00	74.00	1.00	3393277	0.016	-0.1	9	0.1	1.0
MC-DDH-012	74.00	75.00	1.00	3393278	0.019	-0.1	4	0.2	0.9
MC-DDH-012	75.00	76.00	1.00	3393279	0.030	-0.1	8	-0.1	1.3
MC-DDH-012	76.00	77.00	1.00	3393281	0.006	-0.1	3	-0.1	1.3
MC-DDH-012	77.00	78.00	1.00	3393282	0.008	-0.1	4	-0.1	1.0
MC-DDH-012	78.00	79.00	1.00	3393283	0.014	-0.1	5	0.1	0.9
MC-DDH-012	79.00	80.00	1.00	3393284	0.001	-0.1	-1	0.3	1.5
MC-DDH-012	80.00	81.00	1.00	3393285	0.008	-0.1	7	-0.1	1.2
MC-DDH-012	81.00	82.00	1.00	3393286	0.001	-0.1	5	0.2	2.0
MC-DDH-012	82.00	83.00	1.00	3393288	0.008	-0.1	3	-0.1	2.3
MC-DDH-012	83.00	84.00	1.00	3393289	0.010	-0.1	2	0.2	1.3
MC-DDH-012	84.00	85.00	1.00	3393290	0.006	-0.1	2	0.3	1.2
MC-DDH-012	85.00	86.00	1.00	3393291	0.032	-0.1	18	0.5	1.4
MC-DDH-012	86.00	87.00	1.00	3393292	0.009	-0.1	15	-0.1	1.6
MC-DDH-012	87.00	88.00	1.00	3393293	0.015	-0.1	8	0.1	1.0
MC-DDH-012	88.00	89.00	1.00	3393295	0.028	0.1	12	0.7	1.2
MC-DDH-012	89.00	90.00	1.00	3393296	0.009	-0.1	14	0.4	1.3
MC-DDH-012	90.00	92.00	2.00	3393297	0.063	0.1	11	0.2	11.6
MC-DDH-012	92.00	93.00	1.00	3393298	0.011	-0.1	5	-0.1	1.7
MC-DDH-012	93.00	94.00	1.00	3393299	0.010	-0.1	8	0.1	1.4
MC-DDH-012	94.00	95.00	1.00	3393300	0.005	-0.1	8	0.2	5.2
MC-DDH-012	95.00	96.00	1.00	3393302	0.007	-0.1	8	0.4	5.6
MC-DDH-012	96.00	97.00	1.00	3393303	0.006	-0.1	-1	-0.1	1.9
MC-DDH-012	97.00	98.00	1.00	3393304	0.012	-0.1	9	1.8	2.2
MC-DDH-012	98.00	99.00	1.00	3393305	0.021	0.4	15	8.2	3.8
MC-DDH-012	99.00	100.00	1.00	3393306	0.017	0.6	32	5.7	5.9
MC-DDH-012	100.00	101.00	1.00	3393307	0.036	1.2	39	3.1	15.9
MC-DDH-012	101.00	102.00	1.00	3393309	0.036	0.3	36	0.7	10.1
MC-DDH-012	102.00	102.60	0.60	3393310	0.011	-0.1	4	0.9	5.0
MC-DDH-012	102.60	103.70	1.10	3393311	0.016	-0.1	4	0.5	3.4
MC-DDH-013	1.00	2.00	1.00	3393313	0.056	8.0	30	12.0	25.5
MC-DDH-013	2.00	3.00	1.00	3393314	0.153	11.7	36	13.3	40.0
MC-DDH-013	3.00	4.00	1.00	3393315	0.057	7.6	24	14.8	32.2
MC-DDH-013	4.00	5.00	1.00	3393316	0.010	0.3	15	4.4	1.9
MC-DDH-013	5.00	6.00	1.00	3393317	0.016	0.1	19	11.5	1.4
MC-DDH-013	6.00	7.00	1.00	3393318	0.058	0.4	36	1.5	11.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-013	7.00	8.00	1.00	3393320	0.083	6.2	39	1.0	30.7
MC-DDH-013	8.00	9.00	1.00	3393321	0.040	2.2	23	3.3	3.5
MC-DDH-013	9.00	10.00	1.00	3393322	0.100	7.2	25	19.7	26.4
MC-DDH-013	10.00	11.00	1.00	3393323	0.115	2.6	76	5.4	11.5
MC-DDH-013	11.00	12.00	1.00	3393324	0.360	3.0	304	11.2	23.3
MC-DDH-013	12.00	13.00	1.00	3393325	0.322	9.1	214	26.5	50.2
MC-DDH-013	13.00	14.00	1.00	3393327	0.929	13.8	531	23.6	72.3
MC-DDH-013	14.00	15.00	1.00	3393328	0.235	3.5	176	4.2	18.8
MC-DDH-013	15.00	16.00	1.00	3393329	0.092	1.1	83	3.1	4.8
MC-DDH-013	16.00	17.00	1.00	3393330	0.136	0.4	143	2.4	4.1
MC-DDH-013	17.00	18.00	1.00	3393331	0.734	1.9	56	13.3	13.0
MC-DDH-013	18.00	19.00	1.00	3393332	6.581	1.8	74	5.7	18.0
MC-DDH-013	19.00	20.00	1.00	3393334	0.236	0.7	34	2.9	11.5
MC-DDH-013	20.00	21.00	1.00	3393335	0.477	1.0	16	0.2	1.6
MC-DDH-013	21.00	22.00	1.00	3393336	0.198	0.6	28	0.2	2.5
MC-DDH-013	22.00	23.00	1.00	3393337	0.696	1.0	33	0.2	1.0
MC-DDH-013	23.00	24.00	1.00	3393338	2.333	2.5	44	0.3	1.5
MC-DDH-013	24.00	25.00	1.00	3393339	1.619	1.6	47	0.3	3.0
MC-DDH-013	25.00	26.00	1.00	3393341	3.269	6.5	45	0.2	1.7
MC-DDH-013	26.00	27.00	1.00	3393342	0.786	1.3	19	0.3	2.2
MC-DDH-013	27.00	28.00	1.00	3393343	0.092	0.4	81	0.4	2.9
MC-DDH-013	28.00	29.00	1.00	3393344	0.409	26.3	39	1.1	16.9
MC-DDH-013	29.00	30.00	1.00	3393345	0.320	11.1	30	0.8	2.5
MC-DDH-013	30.00	31.00	1.00	3393346	1.438	2.7	90	0.4	1.4
MC-DDH-013	31.00	32.00	1.00	3393348	0.036	0.8	18	0.5	5.0
MC-DDH-013	32.00	33.00	1.00	3393349	0.296	0.7	32	0.2	1.3
MC-DDH-013	33.00	34.00	1.00	3393350	0.289	5.6	42	0.2	4.7
MC-DDH-013	34.00	35.00	1.00	3393351	0.568	2.2	60	0.2	1.2
MC-DDH-013	35.00	36.00	1.00	3393352	0.136	0.3	21	0.2	2.2
MC-DDH-013	36.00	37.00	1.00	3393353	0.144	0.4	15	-0.1	0.8
MC-DDH-013	37.00	38.00	1.00	3393355	0.024	0.2	20	-0.1	2.0
MC-DDH-013	38.00	39.00	1.00	3393356	0.014	0.2	9	0.2	61.9
MC-DDH-013	39.00	40.00	1.00	3393357	0.026	1.7	12	0.4	1.5
MC-DDH-013	40.00	41.00	1.00	3393358	0.011	0.3	9	0.1	0.7
MC-DDH-013	41.00	42.00	1.00	3393359	0.044	1.2	18	0.2	3.2
MC-DDH-013	42.00	43.00	1.00	3393360	0.019	0.3	23	0.4	1.0
MC-DDH-013	43.00	44.00	1.00	3393362	0.115	-0.1	67	0.7	1.6
MC-DDH-013	44.00	45.00	1.00	3393363	0.367	0.2	58	0.4	10.7
MC-DDH-013	45.00	46.00	1.00	3393364	0.203	-0.1	32	0.3	7.1
MC-DDH-013	46.00	47.00	1.00	3393365	0.401	0.2	53	0.2	5.2
MC-DDH-013	47.00	48.00	1.00	3393366	1.294	0.4	66	0.2	3.7
MC-DDH-013	48.00	49.00	1.00	3393367	3.533	0.7	85	0.4	302.0
MC-DDH-013	49.00	50.00	1.00	3393369	3.335	1.5	468	0.3	21.3

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-013	50.00	51.00	1.00	3393370	1.584	0.5	102	0.2	2.2
MC-DDH-013	51.00	52.00	1.00	3393371	2.281	1.3	96	0.3	4.4
MC-DDH-013	52.00	53.00	1.00	3393372	4.061	0.7	51	0.2	5.3
MC-DDH-013	53.00	54.00	1.00	3393373	4.484	0.6	30	-0.1	2.4
MC-DDH-013	54.00	55.00	1.00	3393374	1.187	0.3	26	0.5	119.2
MC-DDH-013	55.00	56.00	1.00	3393376	1.795	0.2	17	0.2	3.9
MC-DDH-013	56.00	57.00	1.00	3393377	4.774	0.5	40	0.1	2.8
MC-DDH-013	57.00	58.00	1.00	3393378	0.666	0.1	16	0.5	2.3
MC-DDH-013	58.00	59.00	1.00	3393379	0.130	-0.1	12	0.2	1.1
MC-DDH-013	59.00	60.00	1.00	3393380	0.037	-0.1	9	0.1	0.5
MC-DDH-013	60.00	61.00	1.00	3393381	0.090	-0.1	17	1.5	1.5
MC-DDH-013	61.00	62.00	1.00	3393383	0.058	0.1	31	0.6	1.2
MC-DDH-013	62.00	63.00	1.00	3393384	0.102	-0.1	22	0.6	2.4
MC-DDH-013	63.00	64.00	1.00	3393385	0.111	-0.1	48	1.6	12.4
MC-DDH-013	64.00	65.00	1.00	3393386	1.168	0.4	51	1.0	21.4
MC-DDH-013	65.00	66.00	1.00	3393387	0.790	0.3	43	1.0	11.5
MC-DDH-013	66.00	67.00	1.00	3393388	2.995	0.4	24	1.2	11.2
MC-DDH-013	67.00	68.00	1.00	3393390	0.635	0.3	92	2.2	14.5
MC-DDH-013	68.00	69.00	1.00	3393391	0.880	0.6	33	2.3	4.2
MC-DDH-013	69.00	70.00	1.00	3393392	0.426	0.3	31	1.2	4.6
MC-DDH-013	70.00	71.00	1.00	3393393	0.775	0.3	27	1.8	4.9
MC-DDH-013	71.00	72.00	1.00	3393394	0.881	0.2	34	1.1	5.1
MC-DDH-013	72.00	73.00	1.00	3393395	1.114	0.6	19	0.9	6.3
MC-DDH-013	73.00	74.00	1.00	3393397	2.788	0.4	35	0.7	5.9
MC-DDH-013	74.00	75.00	1.00	3393398	0.904	0.2	24	0.9	2.0
MC-DDH-013	75.00	76.00	1.00	3393399	4.847	1.1	18	0.7	5.5
MC-DDH-013	76.00	77.00	1.00	3393400	6.910	1.9	18	0.7	6.7
MC-DDH-013	77.00	78.00	1.00	3393401	1.861	0.9	106	0.7	5.5
MC-DDH-013	78.00	79.00	1.00	3393402	0.677	0.5	118	1.2	10.0
MC-DDH-013	79.00	80.00	1.00	3393404	0.085	-0.1	24	0.3	5.8
MC-DDH-013	80.00	81.00	1.00	3393405	1.059	0.4	61	0.4	7.0
MC-DDH-013	81.00	82.00	1.00	3393406	0.011	-0.1	4	0.5	1.6
MC-DDH-013	82.00	83.00	1.00	3393408	0.136	0.2	14	0.4	8.3
MC-DDH-013	83.00	84.00	1.00	3393409	1.017	0.8	175	1.2	48.8
MC-DDH-013	84.00	85.00	1.00	3393410	0.107	0.2	31	0.4	12.0
MC-DDH-013	85.00	86.00	1.00	3393411	0.246	0.4	82	0.6	42.5
MC-DDH-013	86.00	87.00	1.00	3393412	0.027	0.1	15	0.2	44.4
MC-DDH-013	87.00	88.00	1.00	3393413	0.172	0.6	100	0.6	20.4
MC-DDH-013	88.00	89.00	1.00	3393415	0.513	1.1	348	0.9	20.3
MC-DDH-013	89.00	90.00	1.00	3393416	0.645	1.1	371	0.5	53.7
MC-DDH-013	90.00	91.00	1.00	3393417	0.384	1.8	252	0.3	57.1
MC-DDH-013	91.00	92.00	1.00	3393418	0.029	-0.1	9	0.2	7.6
MC-DDH-013	92.00	93.00	1.00	3393419	0.125	0.2	49	0.2	23.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-013	93.00	94.00	1.00	3393420	0.050	0.2	20	0.1	46.8
MC-DDH-013	94.00	95.00	1.00	3393422	0.023	-0.1	3	0.1	4.5
MC-DDH-013	95.00	96.00	1.00	3393423	0.113	0.1	12	0.2	12.2
MC-DDH-013	96.00	97.00	1.00	3393424	0.011	-0.1	8	0.2	3.2
MC-DDH-013	97.00	98.00	1.00	3393425	0.011	0.4	8	0.2	2.2
MC-DDH-013	98.00	99.00	1.00	3393426	0.011	-0.1	9	0.2	1.9
MC-DDH-013	99.00	100.00	1.00	3393427	0.019	-0.1	10	0.4	2.0
MC-DDH-013	100.00	101.00	1.00	3393429	0.022	-0.1	11	0.3	2.7
MC-DDH-013	101.00	102.00	1.00	3393430	0.011	-0.1	8	0.3	2.5
MC-DDH-013	102.00	103.00	1.00	3393431	0.042	-0.1	13	1.2	2.9
MC-DDH-013	103.00	104.00	1.00	3393432	0.020	-0.1	107	6.3	1.9
MC-DDH-013	104.00	105.00	1.00	3393433	0.009	-0.1	5	0.7	2.9
MC-DDH-013	105.00	106.00	1.00	3393434	0.007	-0.1	10	2.7	1.9
MC-DDH-013	106.00	107.00	1.00	3393436	0.010	-0.1	-1	1.2	2.4
MC-DDH-013	107.00	108.00	1.00	3393437	0.011	-0.1	9	2.2	3.1
MC-DDH-013	108.00	109.00	1.00	3393438	0.016	-0.1	7	0.6	11.8
MC-DDH-013	109.00	110.00	1.00	3393439	0.011	-0.1	4	0.5	2.9
MC-DDH-013	110.00	111.00	1.00	3393440	0.014	-0.1	5	0.6	4.1
MC-DDH-013	111.00	112.00	1.00	3393441	0.009	-0.1	8	0.6	2.5
MC-DDH-013	112.00	113.00	1.00	3393443	0.012	-0.1	3	0.4	4.4
MC-DDH-013	113.00	114.00	1.00	3393444	0.007	-0.1	-1	0.4	3.6
MC-DDH-013	114.00	115.00	1.00	3393445	0.007	-0.1	3	0.4	5.6
MC-DDH-013	115.00	116.00	1.00	3393446	0.020	-0.1	3	0.4	8.2
MC-DDH-013	116.00	117.00	1.00	3393447	0.010	-0.1	7	0.5	4.4
MC-DDH-013	117.00	118.00	1.00	3393448	0.009	-0.1	3	0.4	3.9
MC-DDH-013	118.00	119.00	1.00	3393450	0.009	-0.1	6	0.5	4.3
MC-DDH-013	119.00	120.00	1.00	3393451	0.007	-0.1	-1	0.3	4.3
MC-DDH-013	120.00	121.00	1.00	3393452	0.006	-0.1	5	0.4	5.4
MC-DDH-013	121.00	122.00	1.00	3393453	0.006	-0.1	5	0.4	3.5
MC-DDH-013	122.00	123.00	1.00	3393454	0.006	-0.1	6	0.6	20.0
MC-DDH-013	123.00	124.00	1.00	3393455	0.001	-0.1	4	1.3	5.5
MC-DDH-013	124.00	125.00	1.00	3393457	0.006	-0.1	7	1.5	4.8
MC-DDH-013	125.00	126.00	1.00	3393458	0.001	-0.1	3	1.0	6.2
MC-DDH-013	126.00	126.57	0.57	3393459	0.005	-0.1	5	1.3	14.9
MC-DDH-014	0.00	1.00	1.00	3393461	0.121	9.8	83	2.4	33.3
MC-DDH-014	1.00	2.00	1.00	3393462	0.070	0.8	65	0.9	16.8
MC-DDH-014	2.00	3.00	1.00	3393463	0.059	0.5	41	0.8	11.7
MC-DDH-014	3.00	4.00	1.00	3393464	0.079	6.5	46	0.9	18.7
MC-DDH-014	4.00	5.00	1.00	3393465	0.116	16.6	35	0.7	24.4
MC-DDH-014	5.00	6.00	1.00	3393466	0.052	3.1	14	0.3	5.3
MC-DDH-014	6.00	7.00	1.00	3393468	0.110	5.9	54	0.7	80.7
MC-DDH-014	7.00	8.00	1.00	3393469	0.046	1.1	57	1.2	17.6
MC-DDH-014	8.00	9.00	1.00	3393470	0.119	0.7	111	2.7	25.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-014	9.00	10.00	1.00	3393471	0.023	0.3	50	0.4	5.6
MC-DDH-014	10.00	11.00	1.00	3393472	0.047	0.9	90	0.4	1.8
MC-DDH-014	11.00	12.00	1.00	3393473	0.053	0.4	50	0.2	1.4
MC-DDH-014	12.00	13.00	1.00	3393475	0.029	0.2	115	0.3	3.9
MC-DDH-014	13.00	14.00	1.00	3393476	1.057	3.9	357	1.1	14.8
MC-DDH-014	14.00	15.00	1.00	3393477	5.397	5.5	47	0.5	10.2
MC-DDH-014	15.00	16.00	1.00	3393478	6.077	1.9	27	0.1	2.5
MC-DDH-014	16.00	17.00	1.00	3393479	10.000	7.2	28	-0.1	8.4
MC-DDH-014	17.00	18.00	1.00	3393480	4.981	3.9	35	0.3	36.5
MC-DDH-014	18.00	19.00	1.00	3393482	0.440	4.8	28	1.5	19.7
MC-DDH-014	19.00	20.00	1.00	3393483	0.084	0.3	18	2.0	23.7
MC-DDH-014	20.00	21.00	1.00	3393484	0.035	0.1	15	1.2	5.3
MC-DDH-014	21.00	22.00	1.00	3393485	0.058	0.2	11	0.2	1.8
MC-DDH-014	22.00	23.00	1.00	3393486	0.056	0.3	60	0.7	6.0
MC-DDH-014	23.00	24.00	1.00	3393487	0.030	0.2	83	2.2	5.0
MC-DDH-014	24.00	25.00	1.00	3393489	0.216	1.7	107	2.5	15.6
MC-DDH-014	25.00	26.00	1.00	3393490	0.245	6.0	115	3.0	46.9
MC-DDH-014	26.00	27.00	1.00	3393491	0.112	1.1	64	2.4	16.0
MC-DDH-014	27.00	28.00	1.00	3393492	0.027	0.2	23	0.9	4.0
MC-DDH-014	28.00	29.00	1.00	3393494	0.051	0.3	30	1.0	4.0
MC-DDH-014	29.00	30.00	1.00	3393495	0.091	0.5	57	6.4	7.8
MC-DDH-014	30.00	31.00	1.00	3393496	0.034	0.3	36	1.8	5.3
MC-DDH-014	31.00	32.00	1.00	3393497	0.024	0.2	26	0.8	5.4
MC-DDH-014	32.00	33.00	1.00	3393498	0.068	0.8	42	28.7	10.3
MC-DDH-014	33.00	34.00	1.00	3393499	0.089	0.7	74	5.9	10.9
MC-DDH-014	34.00	35.00	1.00	3393501	0.147	1.4	116	17.2	10.5
MC-DDH-014	35.00	36.00	1.00	3393502	0.102	1.5	61	7.0	18.6
MC-DDH-014	36.00	37.00	1.00	3393503	0.052	0.3	10	0.4	1.7
MC-DDH-014	37.00	38.00	1.00	3393504	0.044	2.4	17	0.5	5.0
MC-DDH-014	38.00	39.00	1.00	3393505	0.289	1.6	20	0.5	1.8
MC-DDH-014	39.00	40.00	1.00	3393506	0.029	0.2	15	0.2	1.0
MC-DDH-014	40.00	41.00	1.00	3393508	0.013	-0.1	6	0.2	1.5
MC-DDH-014	41.00	42.00	1.00	3393509	0.007	0.1	6	0.2	0.9
MC-DDH-014	42.00	43.00	1.00	3393510	0.019	-0.1	12	0.3	0.8
MC-DDH-014	43.00	44.00	1.00	3393511	0.112	0.5	28	0.5	2.3
MC-DDH-014	44.00	45.00	1.00	3393512	0.061	1.2	16	0.2	1.6
MC-DDH-014	45.00	46.00	1.00	3393513	0.049	0.2	5	0.1	0.7
MC-DDH-014	46.00	47.00	1.00	3393515	0.141	0.3	13	0.9	28.1
MC-DDH-014	47.00	48.00	1.00	3393516	0.020	0.2	34	3.6	79.9
MC-DDH-014	48.00	49.00	1.00	3393517	0.026	0.3	68	4.4	99.0
MC-DDH-014	49.00	50.00	1.00	3393518	0.022	0.4	55	5.1	211.3
MC-DDH-014	50.00	51.00	1.00	3393519	0.034	0.5	80	5.2	275.6
MC-DDH-014	51.00	52.00	1.00	3393520	0.023	0.4	75	5.1	155.9

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-014	52.00	53.00	1.00	3393522	0.033	0.3	68	10.0	109.5
MC-DDH-014	53.00	54.00	1.00	3393523	0.017	0.2	53	4.8	128.0
MC-DDH-014	54.00	55.00	1.00	3393524	0.015	0.2	47	6.0	86.2
MC-DDH-014	55.00	56.00	1.00	3393525	0.014	0.2	45	5.8	73.9
MC-DDH-014	56.00	57.00	1.00	3393526	0.012	0.1	27	6.5	40.8
MC-DDH-014	57.00	58.00	1.00	3393527	0.030	0.3	33	3.5	85.8
MC-DDH-014	58.00	59.00	1.00	3393529	0.025	0.2	38	3.7	56.3
MC-DDH-014	59.00	60.00	1.00	3393530	0.030	0.2	40	3.0	67.9
MC-DDH-014	60.00	61.00	1.00	3393531	0.019	0.4	34	7.9	111.7
MC-DDH-014	61.00	62.00	1.00	3393532	0.020	0.3	33	5.5	103.9
MC-DDH-014	62.00	63.00	1.00	3393533	0.022	0.3	59	8.3	95.5
MC-DDH-014	63.00	64.00	1.00	3393534	0.017	0.3	83	7.4	121.6
MC-DDH-014	64.00	65.00	1.00	3393536	0.006	-0.1	5	6.4	30.6
MC-DDH-014	65.00	66.00	1.00	3393537	0.014	0.2	13	5.3	8.9
MC-DDH-014	66.00	67.00	1.00	3393538	0.031	-0.1	29	2.8	3.0
MC-DDH-014	67.00	68.00	1.00	3393539	0.024	-0.1	33	2.4	1.4
MC-DDH-014	68.00	69.00	1.00	3393540	0.017	-0.1	18	3.4	1.4
MC-DDH-014	69.00	70.00	1.00	3393542	0.010	-0.1	5	2.5	1.4
MC-DDH-014	70.00	71.00	1.00	3393543	0.009	0.1	8	1.3	10.1
MC-DDH-014	71.00	72.00	1.00	3393544	0.006	-0.1	5	2.3	34.1
MC-DDH-014	72.00	73.00	1.00	3393545	0.010	0.1	21	5.7	47.8
MC-DDH-014	73.00	74.00	1.00	3393546	0.012	0.2	94	3.4	121.4
MC-DDH-014	74.00	75.00	1.00	3393547	0.013	0.3	136	4.6	101.1
MC-DDH-014	75.00	76.00	1.00	3393548	0.026	0.3	132	2.9	171.1
MC-DDH-014	76.00	77.00	1.00	3393550	0.013	0.2	20	3.7	144.1
MC-DDH-014	77.00	78.00	1.00	3393551	0.007	-0.1	11	2.2	6.5
MC-DDH-014	78.00	79.00	1.00	3393552	0.008	-0.1	9	3.0	27.6
MC-DDH-014	79.00	80.00	1.00	3393553	0.007	-0.1	10	3.2	6.1
MC-DDH-014	80.00	81.00	1.00	3393554	0.008	-0.1	6	4.6	12.4
MC-DDH-014	81.00	82.00	1.00	3393555	0.007	-0.1	6	0.5	1.8
MC-DDH-014	82.00	83.00	1.00	3393557	0.013	-0.1	8	1.6	3.1
MC-DDH-014	83.00	84.00	1.00	3393558	0.234	-0.1	22	8.2	1.6
MC-DDH-014	84.00	85.00	1.00	3393559	0.137	-0.1	9	12.8	1.2
MC-DDH-014	85.00	86.00	1.00	3393560	0.009	0.1	13	4.1	1.0
MC-DDH-014	86.00	87.00	1.00	3393561	0.009	-0.1	5	3.5	1.3
MC-DDH-014	87.00	88.00	1.00	3393562	0.017	-0.1	17	1.4	2.3
MC-DDH-014	88.00	89.00	1.00	3393564	0.006	-0.1	7	1.7	1.0
MC-DDH-014	89.00	90.00	1.00	3393565	0.006	-0.1	14	0.3	2.7
MC-DDH-014	90.00	91.00	1.00	3393566	0.009	-0.1	19	0.3	1.1
MC-DDH-014	91.00	92.00	1.00	3393567	0.008	-0.1	19	0.3	1.9
MC-DDH-014	92.00	93.00	1.00	3393568	0.092	0.2	37	0.4	2.4
MC-DDH-014	93.00	94.00	1.00	3393569	0.078	0.5	105	2.5	26.4
MC-DDH-014	94.00	95.00	1.00	3393571	0.085	0.4	136	1.6	19.2

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-014	95.00	96.00	1.00	3393572	0.067	0.4	104	1.5	34.7
MC-DDH-014	96.00	97.00	1.00	3393573	0.042	0.3	56	1.3	40.0
MC-DDH-014	97.00	98.00	1.00	3393574	0.012	0.1	21	1.0	10.5
MC-DDH-014	98.00	99.00	1.00	3393575	0.033	0.3	54	1.0	9.6
MC-DDH-014	99.00	100.00	1.00	3393576	0.027	0.2	56	1.2	8.4
MC-DDH-014	100.00	101.00	1.00	3393578	0.010	-0.1	9	0.9	4.4
MC-DDH-014	101.00	102.00	1.00	3393579	0.018	0.3	11	1.1	7.3
MC-DDH-014	102.00	103.00	1.00	3393580	0.009	-0.1	10	0.9	2.3
MC-DDH-014	103.00	104.00	1.00	3393582	0.001	-0.1	4	0.5	1.5
MC-DDH-014	104.00	105.00	1.00	3393583	0.007	-0.1	5	0.5	1.9
MC-DDH-014	105.00	106.00	1.00	3393584	0.039	0.2	31	1.6	6.5
MC-DDH-014	106.00	107.00	1.00	3393585	0.352	0.4	34	0.7	5.9
MC-DDH-014	107.00	108.00	1.00	3393586	0.010	0.2	26	1.2	3.2
MC-DDH-014	108.00	109.00	1.00	3393587	0.032	0.4	24	0.3	4.2
MC-DDH-014	109.00	110.00	1.00	3393589	0.012	-0.1	22	0.4	6.8
MC-DDH-014	110.00	111.00	1.00	3393590	0.020	0.1	20	0.3	3.8
MC-DDH-014	111.00	112.00	1.00	3393591	0.025	-0.1	21	0.1	2.1
MC-DDH-014	112.00	113.00	1.00	3393592	0.012	-0.1	22	0.2	1.7
MC-DDH-014	113.00	114.00	1.00	3393593	0.013	0.2	26	0.2	12.3
MC-DDH-014	114.00	115.00	1.00	3393594	0.009	0.1	26	0.2	3.4
MC-DDH-014	115.00	116.00	1.00	3393596	0.011	0.2	20	0.2	2.3
MC-DDH-014	116.00	117.00	1.00	3393597	0.008	-0.1	22	0.2	2.7
MC-DDH-014	117.00	118.00	1.00	3393598	0.009	-0.1	14	0.2	5.1
MC-DDH-014	118.00	119.00	1.00	3393599	0.015	-0.1	18	-0.1	3.6
MC-DDH-014	119.00	120.00	1.00	3393600	0.010	0.1	20	0.2	7.9
MC-DDH-014	120.00	121.00	1.00	3393601	0.007	0.1	20	2.0	4.6
MC-DDH-014	121.00	122.00	1.00	3393603	0.006	-0.1	15	9.4	4.1
MC-DDH-015	0.00	1.00	1.00	3393605	0.316	2.3	69	2.0	9.3
MC-DDH-015	1.00	2.00	1.00	3393606	0.362	3.8	101	2.2	20.0
MC-DDH-015	2.00	3.00	1.00	3393607	0.160	1.7	69	1.7	14.2
MC-DDH-015	3.00	4.00	1.00	3393608	0.072	0.9	10	0.5	7.3
MC-DDH-015	4.00	5.00	1.00	3393609	0.028	0.2	7	0.4	3.9
MC-DDH-015	5.00	6.00	1.00	3393610	0.016	0.2	2	0.4	2.6
MC-DDH-015	6.00	7.00	1.00	3393612	0.020	0.5	17	0.4	5.9
MC-DDH-015	7.00	8.00	1.00	3393613	0.082	1.0	26	3.2	4.0
MC-DDH-015	8.00	9.00	1.00	3393614	0.109	3.3	65	3.5	3.4
MC-DDH-015	9.00	10.00	1.00	3393615	0.111	0.5	10	0.3	2.6
MC-DDH-015	10.00	11.00	1.00	3393616	0.145	3.2	33	0.8	10.1
MC-DDH-015	11.00	12.00	1.00	3393617	0.096	8.3	70	0.9	10.8
MC-DDH-015	12.00	13.00	1.00	3393619	1.113	30.4	402	11.3	55.0
MC-DDH-015	13.00	14.00	1.00	3393620	1.008	2.8	670	30.1	40.5
MC-DDH-015	14.00	15.00	1.00	3393621	0.200	1.3	178	15.2	19.1
MC-DDH-015	15.00	16.00	1.00	3393622	0.051	0.3	40	1.3	20.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	16.00	17.00	1.00	3393623	0.276	1.4	94	6.9	15.5
MC-DDH-015	17.00	18.00	1.00	3393624	0.023	0.2	43	1.6	4.6
MC-DDH-015	18.00	19.00	1.00	3393626	0.022	0.4	27	1.0	16.9
MC-DDH-015	19.00	20.00	1.00	3393627	0.007	-0.1	9	0.3	9.3
MC-DDH-015	20.00	21.00	1.00	3393628	0.001	-0.1	3	0.3	24.3
MC-DDH-015	21.00	22.00	1.00	3393629	0.001	-0.1	3	-0.1	8.7
MC-DDH-015	22.00	23.00	1.00	3393630	0.008	-0.1	11	0.3	21.3
MC-DDH-015	23.00	24.00	1.00	3393631	0.015	-0.1	33	0.2	16.5
MC-DDH-015	24.00	25.00	1.00	3393633	0.025	0.1	48	0.2	21.2
MC-DDH-015	25.00	26.00	1.00	3393634	0.085	0.4	68	2.4	16.2
MC-DDH-015	26.00	27.00	1.00	3393635	0.087	0.5	75	2.6	15.8
MC-DDH-015	27.00	28.00	1.00	3393636	0.074	0.3	68	1.8	9.7
MC-DDH-015	28.00	29.00	1.00	3393637	0.077	0.4	63	1.4	9.8
MC-DDH-015	29.00	30.00	1.00	3393638	0.011	-0.1	8	0.7	28.4
MC-DDH-015	30.00	31.00	1.00	3393640	0.286	0.5	15	6.0	34.9
MC-DDH-015	31.00	32.00	1.00	3393641	0.495	2.3	136	3.1	21.2
MC-DDH-015	32.00	33.00	1.00	3393642	0.177	0.6	186	1.3	13.3
MC-DDH-015	33.00	34.00	1.00	3393643	0.253	1.4	158	2.4	23.3
MC-DDH-015	34.00	35.00	1.00	3393644	0.165	0.9	47	2.7	35.8
MC-DDH-015	35.00	36.00	1.00	3393645	0.242	0.5	45	2.9	19.6
MC-DDH-015	36.00	37.00	1.00	3393647	0.139	0.8	53	1.7	26.1
MC-DDH-015	37.00	38.00	1.00	3393648	0.089	-0.1	84	0.7	11.6
MC-DDH-015	38.00	39.00	1.00	3393649	0.398	0.2	105	1.0	19.1
MC-DDH-015	39.00	40.00	1.00	3393650	0.798	0.3	79	0.8	29.6
MC-DDH-015	40.00	41.00	1.00	3393651	0.357	0.3	81	0.9	29.1
MC-DDH-015	41.00	42.00	1.00	3393652	2.663	0.6	106	1.0	163.9
MC-DDH-015	42.00	43.00	1.00	3393654	0.315	0.2	107	2.6	10.0
MC-DDH-015	43.00	44.00	1.00	3393655	0.785	0.2	131	0.9	39.0
MC-DDH-015	44.00	45.00	1.00	3393656	0.194	0.3	148	0.8	7.7
MC-DDH-015	45.00	46.00	1.00	3393657	0.182	0.3	208	3.0	24.8
MC-DDH-015	46.00	47.00	1.00	3393658	0.307	0.4	321	3.3	19.9
MC-DDH-015	47.00	48.00	1.00	3393659	0.350	0.1	130	2.2	13.3
MC-DDH-015	48.00	49.00	1.00	3393661	0.198	0.1	123	0.6	17.8
MC-DDH-015	49.00	50.00	1.00	3393662	0.453	0.1	143	0.9	21.1
MC-DDH-015	50.00	51.00	1.00	3393663	0.627	0.1	167	1.0	16.0
MC-DDH-015	51.00	52.00	1.00	3393664	0.778	0.4	159	1.0	85.7
MC-DDH-015	52.00	53.00	1.00	3393665	0.165	0.2	78	1.9	44.5
MC-DDH-015	53.00	54.00	1.00	3393666	0.250	0.2	112	1.7	40.8
MC-DDH-015	54.00	55.00	1.00	3393668	0.140	0.4	72	2.1	136.6
MC-DDH-015	55.00	56.00	1.00	3393669	4.633	0.6	55	0.8	8.3
MC-DDH-015	56.00	57.00	1.00	3393670	0.407	0.2	52	1.4	7.5
MC-DDH-015	57.00	58.00	1.00	3393671	0.391	0.3	195	1.5	14.4
MC-DDH-015	58.00	59.00	1.00	3393672	0.925	0.5	147	1.6	9.1

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	59.00	60.00	1.00	3393673	1.010	0.7	199	3.8	17.1
MC-DDH-015	60.00	61.00	1.00	3393675	0.042	0.1	11	4.5	34.1
MC-DDH-015	61.00	62.00	1.00	3393676	0.006	-0.1	3	0.7	38.5
MC-DDH-015	62.00	63.00	1.00	3393677	0.012	-0.1	3	0.3	16.0
MC-DDH-015	63.00	64.00	1.00	3393678	0.001	-0.1	3	0.4	9.0
MC-DDH-015	64.00	65.00	1.00	3393679	0.005	-0.1	2	0.1	10.9
MC-DDH-015	65.00	66.00	1.00	3393680	0.006	-0.1	5	0.4	18.7
MC-DDH-015	66.00	67.00	1.00	3393682	0.007	-0.1	3	0.4	24.4
MC-DDH-015	67.00	68.00	1.00	3393683	0.006	-0.1	3	0.3	13.2
MC-DDH-015	68.00	69.00	1.00	3393684	0.015	0.2	25	1.4	77.5
MC-DDH-015	69.00	70.00	1.00	3393685	0.032	0.3	75	0.9	44.2
MC-DDH-015	70.00	71.00	1.00	3393686	0.044	0.4	46	0.4	17.9
MC-DDH-015	71.00	72.00	1.00	3393687	0.045	0.6	41	0.3	36.2
MC-DDH-015	72.00	73.00	1.00	3393689	0.024	0.4	50	2.1	53.7
MC-DDH-015	73.00	74.00	1.00	3393690	0.200	0.1	37	0.5	14.4
MC-DDH-015	74.00	75.00	1.00	3393691	0.021	-0.1	9	-0.1	15.7
MC-DDH-015	75.00	76.00	1.00	3393692	0.022	-0.1	15	-0.1	14.4
MC-DDH-015	76.00	77.00	1.00	3393693	0.029	0.1	12	0.3	15.8
MC-DDH-015	77.00	78.00	1.00	3393695	0.015	0.1	9	2.1	29.9
MC-DDH-015	78.00	79.00	1.00	3393696	0.014	0.1	11	2.0	48.4
MC-DDH-015	79.00	80.00	1.00	3393697	0.019	0.1	18	0.8	26.4
MC-DDH-015	80.00	81.00	1.00	3393698	0.046	0.2	50	1.1	27.4
MC-DDH-015	81.00	82.00	1.00	3393700	0.034	0.2	15	0.7	59.7
MC-DDH-015	82.00	83.00	1.00	3393701	0.030	0.3	18	0.4	65.3
MC-DDH-015	83.00	84.00	1.00	3393702	0.012	0.1	13	0.3	17.4
MC-DDH-015	84.00	85.00	1.00	3393703	0.009	-0.1	9	1.2	32.9
MC-DDH-015	85.00	86.00	1.00	3393704	0.013	-0.1	9	0.5	34.9
MC-DDH-015	86.00	87.00	1.00	3393705	0.010	0.1	6	1.8	30.2
MC-DDH-015	87.00	88.00	1.00	3393707	0.046	0.2	44	1.7	18.5
MC-DDH-015	88.00	89.00	1.00	3393708	0.151	0.5	62	1.9	138.3
MC-DDH-015	89.00	90.00	1.00	3393709	0.056	0.2	49	1.4	21.1
MC-DDH-015	90.00	91.00	1.00	3393710	0.009	-0.1	8	0.8	18.4
MC-DDH-015	91.00	92.00	1.00	3393711	0.008	-0.1	4	0.5	22.1
MC-DDH-015	93.00	94.00	1.00	3393714	0.001	-0.1	2	0.2	22.2
MC-DDH-015	94.00	95.00	1.00	3393715	0.001	-0.1	4	0.2	25.2
MC-DDH-015	95.00	96.00	1.00	3393716	0.001	-0.1	3	0.2	19.3
MC-DDH-015	96.00	97.00	1.00	3393717	0.001	-0.1	4	0.2	37.0
MC-DDH-015	97.00	98.00	1.00	3393718	0.011	-0.1	7	1.0	55.8
MC-DDH-015	98.00	99.00	1.00	3393719	0.010	-0.1	3	0.5	36.6
MC-DDH-015	99.00	100.00	1.00	3393721	0.007	-0.1	3	0.7	13.6
MC-DDH-015	100.00	101.00	1.00	3393722	0.001	-0.1	2	0.2	19.9
MC-DDH-015	101.00	102.00	1.00	3393723	0.001	-0.1	3	0.8	25.7
MC-DDH-015	102.00	103.00	1.00	3393724	0.001	-0.1	3	0.3	20.0

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	103.00	104.00	1.00	3393725	0.001	-0.1	3	0.1	13.8
MC-DDH-015	104.00	105.00	1.00	3393726	0.001	-0.1	3	0.2	14.6
MC-DDH-015	105.00	106.00	1.00	3393728	0.001	-0.1	2	0.2	14.1
MC-DDH-015	106.00	107.00	1.00	3393729	0.012	0.1	5	1.1	26.9
MC-DDH-015	107.00	108.00	1.00	3393730	0.001	-0.1	2	0.6	12.9
MC-DDH-015	108.00	109.00	1.00	3393731	0.005	-0.1	2	0.4	14.1
MC-DDH-015	109.00	110.00	1.00	3393732	0.010	0.1	2	0.5	16.1
MC-DDH-015	110.00	111.00	1.00	3393733	0.006	-0.1	2	0.1	13.3
MC-DDH-015	111.00	112.00	1.00	3393735	0.006	-0.1	2	0.2	15.1
MC-DDH-015	112.00	113.00	1.00	3393736	0.005	-0.1	1	0.3	13.8
MC-DDH-015	113.00	114.00	1.00	3393737	0.001	-0.1	2	0.3	20.8
MC-DDH-015	114.00	115.00	1.00	3393738	0.024	0.2	8	3.0	26.0
MC-DDH-015	115.00	116.00	1.00	3393739	0.012	-0.1	4	1.1	16.1
MC-DDH-015	117.00	118.00	1.00	3393742	0.001	-0.1	1	0.4	19.1
MC-DDH-015	118.00	119.00	1.00	3393743	0.007	-0.1	15	0.4	19.1
MC-DDH-015	119.00	120.00	1.00	3393744	0.007	-0.1	16	0.6	11.1
MC-DDH-015	120.00	121.00	1.00	3393745	0.011	-0.1	38	0.3	20.0
MC-DDH-015	121.00	122.00	1.00	3393746	0.011	0.1	52	0.6	12.1
MC-DDH-015	122.00	123.00	1.00	3393747	0.010	0.1	27	1.0	27.9
MC-DDH-015	123.00	124.00	1.00	3393749	0.008	-0.1	49	0.5	8.6
MC-DDH-015	124.00	125.00	1.00	3393750	0.026	-0.1	15	0.8	25.3
MC-DDH-015	125.00	126.00	1.00	3393751	0.084	-0.1	4	0.5	18.3
MC-DDH-015	126.00	127.00	1.00	3393752	0.008	-0.1	2	0.2	16.2
MC-DDH-015	127.00	128.00	1.00	3393753	0.008	-0.1	5	0.5	11.0
MC-DDH-015	128.00	129.00	1.00	3393754	0.006	-0.1	1	0.2	13.7
MC-DDH-015	129.00	130.00	1.00	3393756	0.006	-0.1	-1	0.4	20.8
MC-DDH-015	130.00	131.00	1.00	3393757	0.023	0.2	12	0.6	25.0
MC-DDH-015	131.00	132.00	1.00	3393758	0.006	-0.1	-1	0.1	20.3
MC-DDH-015	132.00	133.00	1.00	3393759	0.009	-0.1	5	0.2	15.9
MC-DDH-015	133.00	134.00	1.00	3393760	0.009	-0.1	3	0.3	20.7
MC-DDH-015	134.00	135.00	1.00	3393761	0.006	-0.1	1	0.1	18.2
MC-DDH-015	135.00	136.00	1.00	3393763	0.007	-0.1	2	0.3	13.8
MC-DDH-015	136.00	137.00	1.00	3393764	0.006	-0.1	2	0.2	9.0
MC-DDH-015	137.00	138.00	1.00	3393765	0.009	-0.1	4	0.2	22.5
MC-DDH-015	138.00	139.00	1.00	3393766	0.007	-0.1	4	0.1	16.2
MC-DDH-015	139.00	140.00	1.00	3393767	0.009	-0.1	6	0.3	15.0
MC-DDH-015	141.00	142.00	1.00	3393770	0.001	-0.1	2	-0.1	12.4
MC-DDH-015	142.00	143.00	1.00	3393771	0.001	-0.1	2	0.2	20.2
MC-DDH-015	143.00	144.00	1.00	3393772	0.009	-0.1	6	0.2	13.4
MC-DDH-015	144.00	145.00	1.00	3393773	0.001	-0.1	1	0.1	27.3
MC-DDH-015	145.00	146.00	1.00	3393774	0.001	-0.1	2	0.2	18.8
MC-DDH-015	146.00	147.00	1.00	3393775	0.001	-0.1	4	0.3	13.4
MC-DDH-015	147.00	148.00	1.00	3393777	0.001	-0.1	1	0.1	2.6

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-015	148.00	149.00	1.00	3393778	0.001	-0.1	3	-0.1	6.4
MC-DDH-015	149.00	150.00	1.00	3393779	0.015	-0.1	5	0.2	5.1
MC-DDH-015	150.00	151.00	1.00	3393780	0.001	-0.1	3	0.2	14.8
MC-DDH-015	151.00	152.00	1.00	3393781	0.008	-0.1	15	1.7	60.4
MC-DDH-015	152.00	153.00	1.00	3393782	0.008	-0.1	16	5.0	35.8
MC-DDH-015	153.00	154.00	1.00	3393784	0.008	-0.1	26	2.3	9.7
MC-DDH-015	154.00	155.00	1.00	3393785	0.021	0.3	61	2.7	56.8
MC-DDH-015	155.00	156.00	1.00	3393786	0.015	0.2	51	3.1	128.3
MC-DDH-015	156.00	157.00	1.00	3393787	0.007	-0.1	23	1.9	52.8
MC-DDH-015	157.00	158.00	1.00	3393788	0.007	-0.1	37	2.3	90.1
MC-DDH-015	158.00	159.00	1.00	3393789	0.009	-0.1	26	2.4	55.0
MC-DDH-015	159.00	160.00	1.00	3393791	0.006	-0.1	20	2.4	66.0
MC-DDH-015	160.00	161.00	1.00	3393792	0.007	-0.1	12	2.0	52.3
MC-DDH-015	161.00	162.00	1.00	3393793	0.005	-0.1	16	3.3	20.1
MC-DDH-015	162.00	163.00	1.00	3393794	0.001	0.2	25	135.6	49.0
MC-DDH-015	163.00	164.00	1.00	3393795	0.006	0.1	15	4.7	103.2
MC-DDH-015	165.00	166.00	1.00	3393798	0.006	0.2	8	2.0	83.0
MC-DDH-015	166.00	167.00	1.00	3393799	0.006	0.1	13	2.0	67.4
MC-DDH-015	167.00	168.00	1.00	3393800	0.010	0.2	13	1.7	93.5
MC-DDH-015	168.00	169.00	1.00	3393801	0.012	0.2	11	1.5	66.3
MC-DDH-015	169.00	170.00	1.00	3393802	0.016	0.2	9	0.6	75.9
MC-DDH-015	170.00	171.00	1.00	3393803	0.001	0.1	9	1.8	90.2
MC-DDH-015	171.00	172.00	1.00	3393805	0.005	0.1	10	3.0	54.3
MC-DDH-015	172.00	173.00	1.00	3393806	0.005	-0.1	5	1.8	30.1
MC-DDH-015	173.00	173.85	0.85	3393807	0.001	-0.1	12	2.3	24.8
MC-DDH-016	0.00	1.00	1.00	3393809	1.210	0.7	84	3.5	212.0
MC-DDH-016	1.00	2.00	1.00	3393810	1.120	0.9	92	3.5	38.6
MC-DDH-016	2.00	3.00	1.00	3393811	1.090	1.5	89	3.4	46.6
MC-DDH-016	3.00	4.00	1.00	3393812	0.390	1.8	88	5.1	62.3
MC-DDH-016	4.00	5.00	1.00	3393813	0.230	0.4	79	3.7	50.9
MC-DDH-016	5.00	6.00	1.00	3393814	0.560	2.9	58	1.7	42.4
MC-DDH-016	6.00	7.00	1.00	3393816	7.400	3.3	43	0.5	19.1
MC-DDH-016	7.00	8.00	1.00	3393817	3.940	3.8	49	0.8	21.4
MC-DDH-016	8.00	9.00	1.00	3393818	1.890	9.0	42	0.8	33.2
MC-DDH-016	9.00	10.00	1.00	3393819	1.420	2.4	44	0.9	9.4
MC-DDH-016	10.00	11.00	1.00	3393820	1.310	5.1	54	0.8	9.9
MC-DDH-016	12.00	13.00	1.00	3393823	1.570	3.4	37	2.1	12.3
MC-DDH-016	13.00	14.00	1.00	3393824	0.370	0.9	40	1.1	7.3
MC-DDH-016	14.00	15.00	1.00	3393825	0.220	5.4	17	4.3	24.4
MC-DDH-016	15.00	16.00	1.00	3393826	0.110	6.2	13	4.7	26.9
MC-DDH-016	16.00	17.00	1.00	3393827	0.540	5.4	130	4.5	21.0
MC-DDH-016	17.00	18.00	1.00	3393828	0.150	1.2	35	3.8	5.9
MC-DDH-016	18.00	19.00	1.00	3393830	0.620	1.2	38	1.7	5.8

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-016	19.00	20.00	1.00	3393831	-0.050	1.3	21	0.9	6.0
MC-DDH-016	20.00	21.00	1.00	3393832	0.200	2.1	54	1.8	7.2
MC-DDH-016	21.00	22.00	1.00	3393833	6.370	1.5	50	0.6	2.6
MC-DDH-016	22.00	23.00	1.00	3393834	5.680	6.9	64	1.3	15.6
MC-DDH-016	23.00	24.00	1.00	3393835	1.790	6.2	44	0.9	11.1
MC-DDH-016	24.00	25.00	1.00	3393837	0.730	15.0	44	0.8	31.3
MC-DDH-016	25.00	26.00	1.00	3393838	2.840	6.5	56	1.2	5.6
MC-DDH-016	26.00	27.00	1.00	3393839	1.090	1.8	38	0.6	4.5
MC-DDH-016	27.00	28.00	1.00	3393840	0.720	4.1	49	1.1	5.7
MC-DDH-016	28.00	29.00	1.00	3393841	0.170	1.3	59	2.0	11.4
MC-DDH-016	29.00	30.00	1.00	3393842	0.490	0.5	49	1.7	7.2
MC-DDH-016	30.00	31.00	1.00	3393844	2.150	1.3	64	2.6	43.0
MC-DDH-016	31.00	32.00	1.00	3393845	2.160	3.7	77	3.0	124.3
MC-DDH-016	32.00	33.00	1.00	3393846	1.850	4.3	254	8.4	207.5
MC-DDH-016	33.00	34.00	1.00	3393847	1.050	5.4	349	10.8	224.6
MC-DDH-016	34.00	35.00	1.00	3393848	1.200	6.5	367	10.4	219.3
MC-DDH-016	36.00	37.00	1.00	3393851	1.380	3.8	400	30.2	222.5
MC-DDH-016	37.00	38.00	1.00	3393852	0.730	3.0	393	24.0	236.0
MC-DDH-016	38.00	39.00	1.00	3393853	0.910	4.4	348	26.4	148.7
MC-DDH-016	39.00	40.00	1.00	3393854	0.350	2.8	276	19.8	135.6
MC-DDH-016	40.00	41.00	1.00	3393855	0.250	3.3	248	32.1	165.5
MC-DDH-016	41.00	42.00	1.00	3393856	0.700	4.4	365	32.8	236.7
MC-DDH-016	42.00	43.00	1.00	3393858	1.600	3.3	438	23.1	388.0
MC-DDH-016	43.00	44.00	1.00	3393859	6.060	3.1	391	13.7	285.0
MC-DDH-016	44.00	45.00	1.00	3393860	16.330	6.6	174	5.1	655.2
MC-DDH-016	45.00	46.00	1.00	3393861	0.150	0.2	37	1.0	4.2
MC-DDH-016	46.00	47.00	1.00	3393862	0.160	0.4	70	0.8	4.1
MC-DDH-016	47.00	48.00	1.00	3393863	0.050	12.8	25	1.7	4.5
MC-DDH-016	48.00	49.00	1.00	3393865	0.090	5.5	25	1.2	2.6
MC-DDH-016	49.00	50.00	1.00	3393866	0.510	16.7	36	1.7	13.2
MC-DDH-016	50.00	51.00	1.00	3393867	0.390	2.6	51	0.7	2.8
MC-DDH-016	51.00	52.00	1.00	3393868	0.730	17.9	29	0.8	3.9
MC-DDH-016	52.00	53.00	1.00	3393869	1.190	1.0	51	1.7	1.4
MC-DDH-016	53.00	54.00	1.00	3393870	1.040	1.7	85	1.9	11.7
MC-DDH-016	54.00	55.00	1.00	3393872	1.070	3.9	74	4.6	22.3
MC-DDH-016	55.00	56.00	1.00	3393873	0.390	4.9	77	5.2	23.5
MC-DDH-016	56.00	57.00	1.00	3393874	0.210	4.1	78	4.4	35.3
MC-DDH-016	57.00	58.00	1.00	3393875	0.120	2.1	54	1.6	103.4
MC-DDH-016	58.00	59.00	1.00	3393876	-0.050	0.8	45	1.0	102.4
MC-DDH-016	60.00	61.00	1.00	3393879	0.520	1.9	68	1.3	101.0
MC-DDH-016	61.00	62.00	1.00	3393880	0.640	1.3	126	4.3	268.8
MC-DDH-016	62.00	63.00	1.00	3393881	2.090	4.0	182	3.9	320.3
MC-DDH-016	63.00	64.00	1.00	3393882	1.960	2.3	245	3.3	403.0

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-016	64.00	65.00	1.00	3393883	1.300	2.3	183	4.4	355.7
MC-DDH-016	65.00	66.00	1.00	3393884	0.150	0.5	47	1.9	99.4
MC-DDH-016	66.00	67.00	1.00	3393886	0.660	0.8	86	2.4	41.8
MC-DDH-016	67.00	68.00	1.00	3393887	3.970	4.6	268	6.5	380.9
MC-DDH-016	68.00	69.00	1.00	3393888	1.620	1.6	204	5.7	329.6
MC-DDH-016	69.00	70.00	1.00	3393889	-0.050	-0.1	11	0.2	6.8
MC-DDH-016	70.00	71.00	1.00	3393890	-0.050	-0.1	8	-0.1	2.8
MC-DDH-016	71.00	72.00	1.00	3393891	-0.050	-0.1	2	-0.1	1.7
MC-DDH-016	72.00	73.00	1.00	3393893	-0.050	-0.1	1	-0.1	1.4
MC-DDH-016	73.00	74.00	1.00	3393894	-0.050	-0.1	4	-0.1	1.3
MC-DDH-016	74.00	75.00	1.00	3393895	-0.050	-0.1	4	-0.1	1.3
MC-DDH-016	75.00	76.00	1.00	3393896	-0.050	-0.1	4	0.1	2.1
MC-DDH-016	76.00	77.00	1.00	3393897	-0.050	-0.1	29	49.9	12.8
MC-DDH-016	77.00	78.00	1.00	3393898	-0.050	-0.1	52	24.8	32.9
MC-DDH-016	78.00	79.00	1.00	3393900	-0.050	0.2	50	23.1	32.2
MC-DDH-016	79.00	80.00	1.00	3393901	-0.050	-0.1	23	244.0	2.6
MC-DDH-016	80.00	81.00	1.00	3393902	-0.050	-0.1	77	70.5	3.1
MC-DDH-016	81.00	82.00	1.00	3393903	-0.050	0.2	33	3.8	9.6
MC-DDH-016	82.00	83.00	1.00	3393904	-0.050	-0.1	8	2.1	3.4
MC-DDH-016	84.00	85.00	1.00	3393907	-0.050	-0.1	3	0.2	2.2
MC-DDH-016	85.00	86.00	1.00	3393908	-0.050	-0.1	5	0.3	2.5
MC-DDH-016	86.00	87.00	1.00	3393909	-0.050	0.3	46	0.6	6.3
MC-DDH-016	87.00	88.00	1.00	3393910	-0.050	0.8	17	0.3	7.5
MC-DDH-016	88.00	89.00	1.00	3393911	-0.050	-0.1	-1	0.3	2.3
MC-DDH-016	89.00	90.00	1.00	3393912	-0.050	-0.1	6	-0.1	2.1
MC-DDH-016	90.00	91.00	1.00	3393914	0.007	-0.1	2	-0.1	2.2
MC-DDH-016	91.00	92.00	1.00	3393915	0.006	-0.1	-1	-0.1	0.9
MC-DDH-016	92.00	93.00	1.00	3393916	0.005	-0.1	1	-0.1	1.2
MC-DDH-016	93.00	94.00	1.00	3393917	0.008	-0.1	-1	-0.1	1.2
MC-DDH-016	94.00	95.00	1.00	3393918	0.008	-0.1	3	-0.1	1.6
MC-DDH-016	95.00	96.00	1.00	3393919	0.006	-0.1	3	-0.1	1.0
MC-DDH-016	96.00	97.00	1.00	3393921	0.007	-0.1	1	-0.1	1.0
MC-DDH-016	97.00	98.00	1.00	3393922	0.006	-0.1	-1	0.3	0.8
MC-DDH-016	98.00	99.00	1.00	3393923	0.006	-0.1	-1	-0.1	1.1
MC-DDH-016	99.00	100.00	1.00	3393924	0.006	-0.1	5	0.4	1.6
MC-DDH-016	100.00	101.00	1.00	3393925	0.007	-0.1	3	0.2	1.4
MC-DDH-016	101.00	102.00	1.00	3393926	0.006	-0.1	1	-0.1	1.2
MC-DDH-016	102.00	103.00	1.00	3393928	0.007	-0.1	2	-0.1	2.2
MC-DDH-016	103.00	104.00	1.00	3393929	0.005	-0.1	-1	0.1	1.8
MC-DDH-016	104.00	105.00	1.00	3393930	0.005	-0.1	2	-0.1	0.7
MC-DDH-016	105.00	106.00	1.00	3393931	0.008	-0.1	3	0.6	3.2
MC-DDH-016	106.00	107.00	1.00	3393932	0.001	-0.1	2	0.2	2.7
MC-DDH-016	107.00	108.00	1.00	3393933	0.006	-0.1	16	0.3	2.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-016	108.00	109.00	1.00	3393935	0.006	-0.1	7	0.2	3.4
MC-DDH-016	109.00	110.00	1.00	3393936	0.006	-0.1	1	-0.1	2.5
MC-DDH-016	110.00	111.00	1.00	3393937	0.005	0.3	3	0.1	2.9
MC-DDH-016	111.00	112.00	1.00	3393938	0.005	-0.1	3	0.4	2.6
MC-DDH-016	112.00	112.85	0.85	3393939	0.006	-0.1	2	0.2	1.4
MC-DDH-017	0.00	1.00	1.00	3393941	2.040	14.2	26	0.4	46.6
MC-DDH-017	1.00	2.00	1.00	3393942	2.071	4.7	23	0.5	15.1
MC-DDH-017	2.00	3.00	1.00	3393943	0.164	0.9	13	0.5	4.3
MC-DDH-017	3.00	4.00	1.00	3393944	0.123	0.5	15	1.1	2.9
MC-DDH-017	4.00	5.00	1.00	3393945	0.358	1.4	27	0.4	19.7
MC-DDH-017	5.00	6.00	1.00	3393946	0.260	1.4	22	0.4	25.4
MC-DDH-017	6.00	7.00	1.00	3393948	0.933	1.5	24	0.4	8.6
MC-DDH-017	7.00	8.00	1.00	3393949	1.202	1.2	25	0.5	16.9
MC-DDH-017	8.00	9.00	1.00	3393950	0.071	0.3	32	0.6	3.8
MC-DDH-017	9.00	10.00	1.00	3393951	0.031	0.6	20	1.4	12.9
MC-DDH-017	10.00	11.00	1.00	3393952	0.026	0.6	10	0.7	28.8
MC-DDH-017	11.00	12.00	1.00	3393953	0.020	1.3	31	0.5	51.9
MC-DDH-017	12.00	13.00	1.00	3393955	0.048	0.3	22	0.7	3.9
MC-DDH-017	13.00	14.00	1.00	3393956	0.069	0.7	23	0.9	16.0
MC-DDH-017	14.00	15.00	1.00	3393957	0.117	9.3	39	1.3	46.3
MC-DDH-017	15.00	16.00	1.00	3393958	0.094	9.9	40	1.3	43.8
MC-DDH-017	16.00	17.00	1.00	3393959	0.096	5.5	33	0.8	31.0
MC-DDH-017	17.00	18.00	1.00	3393960	0.349	4.8	26	1.0	18.4
MC-DDH-017	18.00	19.00	1.00	3393962	0.319	0.4	23	0.2	3.6
MC-DDH-017	19.00	20.00	1.00	3393963	0.292	7.3	18	0.7	16.7
MC-DDH-017	20.00	21.00	1.00	3393964	0.272	4.7	12	0.7	13.7
MC-DDH-017	21.00	22.00	1.00	3393965	0.389	0.9	17	0.3	35.6
MC-DDH-017	22.00	23.00	1.00	3393966	0.711	1.1	18	0.2	14.0
MC-DDH-017	23.00	24.00	1.00	3393967	1.212	1.4	15	0.2	5.6
MC-DDH-017	24.00	25.00	1.00	3393969	1.988	2.0	18	0.3	6.4
MC-DDH-017	25.00	26.00	1.00	3393970	0.155	0.3	10	2.2	1.1
MC-DDH-017	26.00	27.00	1.00	3393971	0.035	-0.1	11	2.1	2.0
MC-DDH-017	27.00	28.00	1.00	3393972	0.063	-0.1	18	1.3	1.4
MC-DDH-017	28.00	29.00	1.00	3393973	0.092	-0.1	29	0.7	4.2
MC-DDH-017	29.00	30.00	1.00	3393974	0.022	-0.1	15	0.5	1.2
MC-DDH-017	30.00	31.00	1.00	3393976	0.012	-0.1	12	2.0	2.5
MC-DDH-017	31.00	32.00	1.00	3393977	0.023	-0.1	15	2.2	54.7
MC-DDH-017	32.00	33.00	1.00	3393978	0.009	-0.1	10	2.1	25.0
MC-DDH-017	33.00	34.00	1.00	3393979	0.020	-0.1	11	2.9	39.1
MC-DDH-017	34.00	35.00	1.00	3393980	0.001	-0.1	15	1.3	2.8
MC-DDH-017	35.00	36.00	1.00	3393981	0.043	0.1	27	10.0	20.2
MC-DDH-017	36.00	37.00	1.00	3393983	0.012	0.1	26	4.4	20.3
MC-DDH-017	37.00	38.00	1.00	3393984	0.006	-0.1	31	10.3	5.8

Royal Road Minerals  
NI 43-101 Technical Report for the Luna Roja Property

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-017	38.00	39.00	1.00	3393985	0.013	0.1	64	1.4	58.9
MC-DDH-017	39.00	40.00	1.00	3393986	0.011	-0.1	151	4.3	30.0
MC-DDH-017	40.00	41.00	1.00	3393987	0.009	-0.1	61	5.6	22.4
MC-DDH-017	41.00	42.00	1.00	3393988	0.005	0.1	44	1.9	56.3
MC-DDH-017	42.00	43.00	1.00	3393990	0.007	0.1	37	1.6	26.6
MC-DDH-017	43.00	44.00	1.00	3393991	0.007	0.2	33	1.9	76.7
MC-DDH-017	44.00	45.00	1.00	3393992	0.034	0.1	42	3.1	21.1
MC-DDH-017	45.00	46.00	1.00	3393993	0.036	0.1	41	1.0	31.4
MC-DDH-017	46.00	47.00	1.00	3393994	0.025	0.1	46	2.7	19.4
MC-DDH-017	47.00	48.00	1.00	3393995	0.031	-0.1	49	1.6	17.2
MC-DDH-017	48.00	49.00	1.00	3393997	0.010	-0.1	9	0.7	13.9
MC-DDH-017	49.00	50.00	1.00	3393998	0.007	-0.1	11	1.2	19.0
MC-DDH-017	50.00	51.00	1.00	3393999	0.014	1.1	40	3.3	951.4
MC-DDH-017	51.00	52.00	1.00	3394000	0.001	0.7	10	1.4	599.4
MC-DDH-017	52.00	53.00	1.00	3398002	0.010	-0.1	5	0.7	26.9
MC-DDH-017	53.00	54.00	1.00	3398003	0.010	0.3	17	2.4	14.9
MC-DDH-017	54.00	55.00	1.00	3398004	0.015	-0.1	4	1.8	6.9
MC-DDH-017	55.00	56.00	1.00	3398005	0.021	-0.1	5	1.3	7.4
MC-DDH-017	56.00	57.00	1.00	3398006	0.011	-0.1	4	1.0	9.1
MC-DDH-017	57.00	58.00	1.00	3398007	0.015	0.1	4	1.2	8.7
MC-DDH-017	58.00	59.00	1.00	3398009	0.013	-0.1	4	1.3	8.3
MC-DDH-017	59.00	60.00	1.00	3398010	0.019	0.1	4	1.1	8.9
MC-DDH-017	60.00	61.00	1.00	3398011	0.016	-0.1	4	1.1	9.3
MC-DDH-017	61.00	62.00	1.00	3398012	0.046	-0.1	6	0.8	7.9
MC-DDH-017	62.00	63.00	1.00	3398013	0.035	-0.1	6	0.9	8.4
MC-DDH-017	63.00	64.00	1.00	3398014	0.010	-0.1	5	0.8	8.1
MC-DDH-017	64.00	65.00	1.00	3398016	0.026	0.1	2	0.7	11.1
MC-DDH-017	65.00	66.00	1.00	3398017	0.015	-0.1	2	1.2	7.7
MC-DDH-017	66.00	67.00	1.00	3398018	0.011	0.1	5	2.3	10.0
MC-DDH-017	67.00	68.00	1.00	3398019	0.007	-0.1	4	1.4	29.8
MC-DDH-017	68.00	69.00	1.00	3398020	0.008	-0.1	-1	0.3	17.1
MC-DDH-017	69.00	70.00	1.00	3398021	0.017	0.4	23	2.6	31.5
MC-DDH-017	70.00	71.00	1.00	3398023	0.078	1.1	244	1.1	9.7
MC-DDH-017	71.00	72.00	1.00	3398024	0.029	0.5	30	1.9	4.8
MC-DDH-017	72.00	73.00	1.00	3398025	0.060	0.4	20	0.6	18.0
MC-DDH-017	73.00	74.00	1.00	3398026	0.042	2.3	48	0.7	35.0
MC-DDH-017	74.00	75.00	1.00	3398027	0.015	0.3	40	0.3	12.7
MC-DDH-017	75.00	76.00	1.00	3398028	0.005	0.2	32	0.1	8.0
MC-DDH-017	76.00	77.00	1.00	3398030	0.009	0.1	29	6.3	2.6
MC-DDH-017	77.00	78.00	1.00	3398031	0.006	0.1	56	5.2	4.5
MC-DDH-017	78.00	79.00	1.00	3398032	0.009	0.2	18	13.4	3.2
MC-DDH-017	79.00	80.00	1.00	3398033	0.005	0.2	12	5.9	5.2
MC-DDH-017	81.00	82.00	1.00	3398035	0.001	0.1	10	2.5	4.4

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-017	82.00	83.00	1.00	3398036	0.009	-0.1	31	1.0	5.8
MC-DDH-017	83.00	84.00	1.00	3398037	0.016	0.2	50	2.2	6.8
MC-DDH-017	84.00	85.00	1.00	3398038	0.028	0.7	23	2.4	10.6
MC-DDH-017	85.00	86.00	1.00	3398039	0.013	0.6	25	0.3	5.8
MC-DDH-017	86.00	87.00	1.00	3398040	0.017	1.5	20	0.9	13.4
MC-DDH-017	87.00	88.00	1.00	3398042	0.048	0.2	30	0.3	3.7
MC-DDH-017	88.00	89.00	1.00	3398043	0.193	0.9	45	0.9	91.4
MC-DDH-017	89.00	90.00	1.00	3398044	0.270	0.6	18	0.9	51.4
MC-DDH-017	90.00	91.00	1.00	3398045	0.105	0.3	20	0.2	3.2
MC-DDH-017	91.00	92.00	1.00	3398046	0.020	0.3	54	1.4	9.4
MC-DDH-017	92.00	93.00	1.00	3398047	0.082	0.4	78	11.8	2.9
MC-DDH-017	93.00	94.00	1.00	3398049	0.043	-0.1	128	5.9	5.7
MC-DDH-017	94.00	95.00	1.00	3398050	0.073	-0.1	94	8.3	2.6
MC-DDH-017	95.00	96.00	1.00	3398051	0.053	0.4	45	4.0	8.3
MC-DDH-017	96.00	97.00	1.00	3398052	0.087	1.1	23	4.5	4.9
MC-DDH-017	97.00	98.00	1.00	3398053	0.055	0.6	19	2.4	5.8
MC-DDH-017	98.00	99.00	1.00	3398054	0.017	0.3	14	0.3	5.0
MC-DDH-017	99.00	100.00	1.00	3398056	0.001	0.3	10	0.5	3.3
MC-DDH-017	100.00	101.00	1.00	3398057	0.035	0.3	16	0.7	11.1
MC-DDH-017	101.00	102.00	1.00	3398058	0.006	-0.1	8	0.6	12.0
MC-DDH-017	102.00	103.00	1.00	3398059	0.001	-0.1	18	0.2	4.8
MC-DDH-017	103.00	104.00	1.00	3398060	0.001	-0.1	23	0.4	6.5
MC-DDH-017	104.00	105.00	1.00	3398061	0.001	-0.1	9	0.2	5.0
MC-DDH-017	105.00	106.00	1.00	3398063	0.005	-0.1	14	0.2	3.7
MC-DDH-017	106.00	107.00	1.00	3398064	0.005	-0.1	18	0.1	2.0
MC-DDH-017	107.00	108.00	1.00	3398065	0.001	-0.1	13	0.2	3.7
MC-DDH-017	108.00	109.00	1.00	3398066	0.001	-0.1	9	0.4	7.4
MC-DDH-017	109.00	110.00	1.00	3398067	0.001	-0.1	10	0.6	15.3
MC-DDH-017	110.00	111.00	1.00	3398068	0.001	-0.1	22	0.7	14.6
MC-DDH-017	111.00	112.00	1.00	3398070	0.007	-0.1	29	1.9	52.0
MC-DDH-017	112.00	113.00	1.00	3398071	0.029	0.7	26	3.4	767.6
MC-DDH-017	113.00	114.00	1.00	3398072	0.011	0.4	18	2.2	391.5
MC-DDH-017	114.00	115.00	1.00	3398073	0.001	-0.1	12	1.8	2.5
MC-DDH-017	115.00	116.00	1.00	3398074	0.006	-0.1	15	0.7	10.5
MC-DDH-017	116.00	117.00	1.00	3398075	0.006	-0.1	58	1.7	22.5
MC-DDH-017	117.00	118.00	1.00	3398077	0.001	-0.1	9	2.9	3.9
MC-DDH-017	118.00	119.00	1.00	3398078	0.001	-0.1	14	1.4	43.7
MC-DDH-017	119.00	120.00	1.00	3398079	0.047	0.4	18	0.9	35.0
MC-DDH-017	120.00	121.00	1.00	3398080	0.013	0.6	21	0.6	48.2
MC-DDH-017	121.00	122.00	1.00	3398081	0.013	0.1	31	0.7	13.5
MC-DDH-017	122.00	123.00	1.00	3398082	0.001	-0.1	10	22.2	1.9
MC-DDH-017	123.00	124.00	1.00	3398084	0.001	-0.1	20	28.3	12.9
MC-DDH-017	124.00	125.00	1.00	3398085	0.006	-0.1	17	15.4	39.2

Drill Hole	From (m)	To (m)	Interval (m)	Sample #	Au ppm	Ag ppm	As ppm	Mo ppm	Cu ppm
MC-DDH-017	125.00	125.05	0.05	3398086	0.001	-0.1	13	5.5	3.4

Mr Nigel Chapman (QP) considers the practices used by RYR for the 2019 are sufficient for purpose, i.e. exploration drilling and the indication of the continuation of gold mineralisation to depth. Mr

Mr Nigel Chapman (QP) recommends that any subsequent drilling programs consider the following:

- Topographic survey of collar location and drill orientation
- Continuous down hole survey
- Modifying sample intervals to reflect geology

## 11 Sampling Preparation, Analyses and Security

RYR has written Standard Operating Procedures (SOP's) for various sampling methodologies. Senior RYR technical staff are provided with copies of the SOP's and are instructed to comply with SOP's when sampling.

During his site visit, Mr Nigel Chapman (QP) discussed the SOP's for float, channel, and half core sampling with senior members of RYR technical staff. Mr Chapman confirms that the various sampling process according to the SOP's are understood by senior members of RYR technical team. Mr Chapman considers that the SOP's details industry standard sampling practices.

The sampling processes detailed in the SOP's have been summarised in Sections 11.1 to 11.4 of this Technical Report.

### 11.1 Float Sampling

According to RYR's written procedures for Luna Roja (reference) the float sampling process is:

- Identify float sample
- Record location using handheld GPS
- Assign a unique sample number from serialised sample book
- Break open the sample and describe its' features
- Make a photographic record of the rock
- Seal the sample in a bag marked with the unique sample number
- The targeted sample weight is between 3 kg
- Quality Control samples including; blank, certified reference materials and duplicates are submitted with samples at predetermined intervals at a rate of approximately 1 every 7 samples
- The sampling geologist is responsible for delivering their samples to secure RYR storage
- The sampling geologist is responsible for capturing sample details in an excel datasheet

### 11.2 Channel Sampling

According to RYR's written procedures for Luna Roja, the channel sampling process is:

- Record the centre of the channel location suing handheld GPS
- Clean the area to be sampled with a stiff brush and mark the channel using spray paint
- A circular saw is to be used to cut parallel lines in rock, separated by 2 cm and 5 cm deep, perpendicular lines are cut to mark the beginning and end of each sample. A hammer and chisel is used to prise the sample out.
- Sample pieces are placed into a sampled bag with a unique sample number
- Make a photographic record of the channel and channel sample
- Seal the sample in a bag marked with the unique sample number
- Targeted samples weight is 4 kg per meter
- Quality Control samples including; blank, certified reference materials and duplicates are submitted with samples at predetermined intervals at a rate of approximately 1 every 7 samples
- The sampling geologist is responsible for delivering their samples to secure RYR storage
- The sampling geologist is responsible for capturing sample details in an excel datasheet

### 11.3 Half Core Sampling

The sampling process for half core sampling is:

- Drill core is cleaned reconstructed and logged
- Strict 1m sample intervals are marked on core a core boxes and the sample interval is described
- A unique sample number is assigned to each interval
- A cut line is marked from along the entirety of the sample interval
- Quality Control (QC) samples are inserted into the sample sequence. Every seventh sample in the sequence is a QC sample alternating between certified coarse and fine blanks, certified high- and low-grade CRM's, coarse duplicates, and pulverised duplicates.
  - In the case of coarse duplicates consisted of a coarse rejects split of the half-core collected in the laboratory during the core crushing process; an empty labelled bag is submitted to the analytical laboratory with instruction to add a crushed and split duplicate of the previous sample
- Core samples are cut using a diamond core-saw with a circular blade
- Samples are placed in a bag labelled with the corresponding sample number and sealed with a security tape and cable tie.
- Samples are packaged into large sacks and stored under lock and key controlled by a senior RYR employee until delivery to the analytical laboratory
- Targeted sample weight is 2kg/m
- 

### 11.4 Sample Analysis

All samples are submitted to Bureau Veritas' preparation laboratory in Managua. Once prepared Bureau Veritas courier samples to their Vancouver laboratory for fire assay AAS and ICP-MS analysis. Bureau Veritas is independent, ISO certified, commercial laboratory. Hemco and RYR are independent of Bureau Veritas.

Analytical limits reported by Bureau Veritas for have been summarised in Table 11-1 (fire assay) and Table 11-2 (ICP-MS)

Table 11-1: Detection limits for Fire Assay AAS

Sample Type	Element	Lower Detection Limit
Rock	Au	0.005 ppm

Table 11-2: Select detection limits for ICP-MS (all sample types)

Element	Lower Detection Limit
Ag	0.1 ppm
As	1 ppm
Mo	0.1 ppm
Cu	0.1 ppm

## 11.5 Analytical Methods

All samples taken by RYR have been submitted for gold analysis via fire assay AAS, and most samples have been submitted for multi-element ICP-MS.

Mr Nigel Chapman (QP) notes that fire assay AAS and ICP-MS are industry standard techniques widely used for the exploration of precious and base metal deposits.

On their website the Bureau Veritas Minerals (<http://acmelab.com/services/quality-control/>) sample preparation process incorporates several important steps. These steps lay the groundwork for all analyses and is key to the overall high quality of the analytical results. Included in these steps is:

- Sample log-in and reconciliation against the client-supplied list. An electronic reconciliation is sent out for each job, which indicates methods, any potential missing samples, TAT, etc.
- Sample drying.
- Crushing and pulverizing rock, core, or other solid media, or sieving soils and sediments. The lab typically crushes the entire sample and the sample mass to be pulverized can be varied based on client preference.
- Most importantly, our labs undertake a rigorous QAQC program to ensure consistent results. A sieve test is used to monitor the process on select and random samples at the primary crushing and pulverizing stage, as well as monitor the wear surfaces of plates, bowls and other equipment problems.

These tests are recorded and produced for your review. If there is a non-conformance in the quality standard, the process is reviewed and corrected. This rigorous policy applies to any material that is reported or used in the analytical process.

International standard sample preparation in general follows the following process:

- Soil samples are oven dried at 60°C
- Crushed to 70% less than 2 mm and 250 g is separated using a riffle splitter
- An air gun is used to clean crushing equipment and riffle splitter between samples. A silica flush is passed through the crushing equipment after every sample.
- Sample rejects are retained by the laboratory and returned to RYR
- The 250 g split is pulverised to >85% passing through 200 mesh or 74 microns
- An air gun is used to clean crushing equipment and riffle splitter between samples. A silica flush is passed through the crushing equipment after every sample.

- 30g split taken for fire assay with analysis by Atomic Absorption Spectrometry (AAS)
- 1g split undergoes a four-acid digest prior to multielement ICP Mass Spectrometry (MS) analysis
- Samples are securely packaged and couriered from Managua to Vancouver using commercial courier. Samples are analysed in Vancouver.

## 11.6 Sample Security (Chain of Custody)

RYR has a formal chain of custody procedure for sample handling and based on discussion with RYR employee's Mr Chapman (QP) understands the following:

Float, soil, and chip channel samples taken by RYR remain in their secure custody until RYR deliver samples to the Bureau Veritas preparation laboratory in Managua.

Drill core is delivered to RYR's secure warehouse by the drilling contractor and received by the RYR geologists. Drill core samples are prepared by RYR and stored in secure custody until RYR deliver samples to the Bureau Veritas preparation laboratory in Managua.

Mr Chapman (QP) notes that certified reference materials are kept in secure storage.

## 11.7 Quality Control Performance

Mr Nigel Chapman (QP) has reviewed the performance of Quality Control (QC) samples submitted for analysis by RYR with half core samples, his analysis focused on gold assays and is summarised in figures Figure 11-1 to Figure 11-6.

Based on his analysis of the QC assay data, Mr Chapman (QP) notes the following:

- Sample 3392486, a non-certified coarse blank sample, assayed significantly above anticipated values and represent cross contamination during the crushing phase of sample preparation. However, as the blank is not certified, it is not possible to draw a definitive conclusion. Mr Chapman notes that this assay brings in to question the reliability of other samples in the same batch
- Multiple certified fine blanks assayed at or below the lower detectable limits for gold (0.005 ppm), all fine blanks assayed within three times the lower detectable limit. These assays are as would be expected
- All coarse duplicates assayed within 20% of the original assay, this suggest a relatively uniform distribution of gold
- Most pulp duplicates assay within 10% of the original assay, this is indicative of adequate sample preparation and homogenisation prior to assay. There are three significant outliers (samples 2965267, 3393850 and 3398069) these samples could be indicative of poor homogenisation or agglomeration of coarser gold particles
- Analysis of low-grade CRM 521 was generally within expected ranges. There are a number of examples where the CRM assayed above and below the expected range, which may bring in to question the reliability of other samples from the batch. CRM 521 is a lower grade CRM, the numerous examples of assays beyond the expected range could be indicative of poor precision at lower grade.
- Analysis of high-grade CRM 524 was generally within expected ranges. There are, however, four consecutive samples that assayed below detectable limits, this brings in to question the reliability of other samples in the batch. It is possible that samples assayed from the same batch have underreported gold grade.




Figure 11-1: Coase non-certified Blank Performance




Figure 11-2: Certified Blank Performance




Figure 11-3: QC Coarse duplicate Performance




Figure 11-4: Pulp duplicate performance




Figure 11-5: QC CRM Oreas 524 Performance




Figure 11-6: QC CRM Oreas 521 Performance

## 11.8 Qualified Persons Opinion on the Adequacy of Sample Preparation, Security and Analysis

Mr Nigel Chapman (QP) has reviewed RYR's sample preparation, sample security, and the analysis used for assaying and concludes the following:

- Procedures adopted by RYR for sample preparation and security are adequate for a green field exploration program
- RYR use an independent and ISO certified laboratory for sample analysis. The analysis techniques used are industry standard and appropriate for the sample type.
- A review of the QC performance indicates potential cross contamination at the crushing stage of sample preparation and potentially poor analytical precision at lower gold grades. Mr Chapman (QP) recommends that analysis of all samples submitted to Bureau Veritas is rigorously and consistently monitored, use of an umpire laboratory to cross check analysis is also recommended
- RYR maintain prepared samples in secure storage prior to delivering the preparation laboratory. This is good practice
- QC samples submitted for analysis with drill core suggest reliable sample preparation and gold analysis.

Mr Nigel Chapman (QP) recommends that subsequent exploration programs consider the following:

- Channel samples are to be continued to be taken using a circular rock saw powered by a small petrol generator
- Drill sample intervals are defined based on geological bounds, including lithology, alteration, and mineralisation
- Drill samples intervals should not include more than one core diameter
- QC samples should be targeted where possible, i.e. blank samples should be placed between obviously mineralised samples, and duplicate samples are taken of obviously mineralised samples
- Half core duplicate samples should be used in place of quarter core duplicates. It is important that photographic records are kept of all core.
- Core should be orientated core to assist in more fully understanding the structure and orientation of the veins / structures
- Accurate and reliable magnetic susceptibility meters be used whilst logging core

## 12 Data Verification

Mr Nigel Chapman (QP) has undertaken the following data verification during his site visit, Mr Chapman was employed on contract as VP Exploration by RYR during the time of his site visit:

- Cross-checked assay values recorded in spreadsheets against original laboratory certificates
- Review of drill collar locations using handheld GPS to confirm approximate location of drill collars (Figure 12-1)
- Visited artisanal operations to review in-situ mineralisation styles and (Figure 12-2)
- Review of drill core (Figure 12-3) from drill holes MCDDH004, and MCDDH005
- Review of drill sample numbers to confirm the accurate marking of sample numbers in the drill core (Figure 12-3).

As is industry standard, Mr Chapman (QP) notes that his verification steps have been punctual, the results of which suggest reliable data. Punctual data checks do not guarantee that unchecked data is of the same reliability.



Figure 12-1: Luna Roja Drill Collars MCDDH004 and MCDDH005



Figure 12-2: Photographs of artisanal operations at the Property



Figure 12-3: Reviewing core from the Property stored at the RYR Core Shed in Rosita

## **13 Mineral Processing and Metallurgical Testing**

Luna Roja is not an advanced property, item 13 does not form part of this Technical Report.

## **14 Mineral Resource Estimates**

Luna Roja is not an advanced property, item 14 does not form part of this Technical Report.

## **15 Mineral Reserves Estimates**

Luna Roja is not an advanced property, item 15 does not form part of this Technical Report.

## **16 Mining Methods**

Luna Roja is not an advanced property, item 16 does not form part of this Technical Report.

## **17 Recovery Methods**

Luna Roja is not an advanced property, item 17 does not form part of this Technical Report.

## **18 Project Infrastructure**

Luna Roja is not an advanced property, item 18 does not form part of this Technical Report.

## **19 Market Studies and Contracts**

Luna Roja is not an advanced property, item 19 does not form part of this Technical Report.

## **20 Environmental Studies, Permitting and Social or Community Impact**

Luna Roja is not an advanced property, item 20 does not form part of this Technical Report.

## **21 Capital and Operating Costs**

Luna Roja is not an advanced property, item 21 does not form part of this Technical Report.

## **22 Economic Analysis**

Luna Roja is not an advanced property, item 22 does not form part of this Technical Report.

## 23 Adjacent Properties

Mr Chapman (QP) notes that adjacent properties are not necessarily indicative of the mineralisation at Luna Roja, and he has not independently verified the information reported in Section 23 of this Technical Report.

The Golden Triangle of Nicaragua is estimated to have had historical production totalling more than 5 million oz of gold (Au), 4 million oz of silver (Ag), 158,000 tons of copper (Cu), and 106,000 tons of zinc (Zn) (Arengi, et al, 2003).

Calibre Mining Corp (Calibre) is a TSX.v listed gold miner (symbol CXB) with active mining operations in Nicaragua including in the Golden Triangle. Calibre has an interest in a number of properties in the Golden Triangle, including; Primavera, Rosita DJV, Eastern Borosi, and Cerro Aeropuerto Figure 23-1.

Primavera is a gold copper porphyry located approximately 12 km south of Luna Roja. CXB has reported an NI 43-101 inferred resource for Primavera (CXB Corporate Presentation, May 2020) in which they have 100% interest (Table 23-1).

Table 23-1: Inferred resource - Calibre Primavera Property

Inferred Resource	Tonnes (x 1000)	Au g/t	Ag g/t	Cu %
Primavera	44,974	0.54	1.1	0.22

Cerro Aeropuerto is a gold and silver project considered prospective for skarn and low-sulphidation epithermal mineralisation located approximately 48 km southwest of Luna Roja. CXB has reported an NI 43-101 inferred resource for Cerro Aeropuerto (CXB Corporate Presentation, May 2020) in which they have 100% interest <sup>8</sup>

Table 23-2: Inferred resource - Calibre Cerro Aeropuerto Property

Inferred Resource	Tonnes (x 1000)	Au g/t	Ag g/t
Cerro Aeropuerto	6,052	3.64	16.2

Eastern Borosi is a gold vein system located approximately 21 km northeast of Luna Roja. CXB has reported an NI 43-101 inferred resource for Eastern Borosi (CXB Corporate Presentation, May 2020) in which they have 49% interest (Table 23-3).

Table 23-3: Inferred resource - Calibre Eastern Borosi Property

Inferred Resource	Tonnes (x 1000)	Au g/t	Ag g/t
Eastern Borosi Project	2,165	4.93	80

---

<sup>8</sup> Not shown on Fig 23-1

Rosita DJV is a low-sulphidation epithermal gold system located approximately 3.5 km south southeast of Luna Roja. CXB has reported an NI 43-101 indicated and inferred resource for Rosita DJV (CXB Corporate Presentation, May 2020) in which they have 33% interest (Table 23-4 and Table 23-5).

Table 23-4: Indicated resource - Calibre Rosita DJV Property

Indicated Resource	Tonnes (x 1000)	Au g/t	Ag g/t	Cu %
Rosita DJV	2,132	0.47	7.3	0.50

Table 23-5: Inferred resource - Calibre Rosita DJV Property

Inferred Resource	Tonnes (x 1000)	Au g/t	Ag g/t	Cu %
Rosita DJV	1,780	0.49	9.0	0.46




Figure 23-1: Adjacent Properties

## 24 Other Relevant Data and Information

Mr Nigel Chapman (QP) is not aware of any other relevant data or information required for the understanding of the Luna Roja Property.

## 25 Interpretation and Conclusions

The Luna Roja Project is located in the ‘Golden Triangle’ area in north-eastern Nicaragua, in the Rosita municipality of the North Caribbean Coast Autonomous Region, approximately 285 km northeast of Managua and 110 km west of the coastal town of Puerto Cabezas.

RYR 2019 drill campaign demonstrates that outcropping gold mineralisation related to skarn mineralization continues to at least 150m depth. The geology and structure observed in the core shows the host rocks are both folded and offset by faulting.

Ground based magnetic and gravity geophysical surveys have demonstrated they are a useful tool to outline blind drill targets, outline structures and indicate the presence of possible mineralisation.

Further drilling is required to test potential extensions of skarn mineralisation southeast and undercover of the area drilled in 2019.

Geophysical anomalies like those in the areas drilled in 2019 occur in areas with no outcrop and are compelling exploration targets

Mr Chapman (QP) considers that the exploration methodology, execution, data collection, sample preparation, analysis, and security procedures at the LRP and the QA/QC program as designed and implemented by RYR is adequate for this early stage of project development and the assay results are reliable.

Attention must be paid to the ongoing mining operations currently in the oxide zone and to the volume of mineralisation being removed.

## 26 Recommendations

Mr Nigel Chapman (QP) considers that additional exploration at the Property is warranted and he has recommended programs of diamond drilling. The recommended exploration programs are designed to drill test strike and dip extensions of mineralisation and to in-fill the area drilled in 2019. Additional exploration is recommended to test magnetic and microgravity anomalies identified as a possible intrusive hosting an endoskarn at depth SW of hole MC-DDH-017.

Recommended drilling programs, based on 3450m of diamond drilling, inclusive of laboratory and logistical costs are estimated to cost US\$1.44M (Table 26-1).

The diamond drill campaign in the area drilled in 2019 should be, in part, designed to target the potential strike extensions of the Project to the south east as defined by the 2020 geophysical surveys. It is envisaged that 4 to 6 holes be drilled on an approximate 100m x 100m spacing in this SE extension to extend the mineralisation intersected in 2019 drilling programme.

The second aspect or phase the proposed drilling programme is to more closely drill the 2019 drill pattern to attempt to calculate an Inferred Resource. Drill hole spacing should be appropriate to comply with NI 43-101 to be able to support an Inferred Mineral Resource.

In any future drilling programmes all core should be orientated and the appropriate orientated structural data recorded and analysed to aid in further understanding the geometry and structural controls on the mineralisation.

More structural data and samples should be collected within the project area and analysed.

It is strongly recommended that the current RYR and Hemco databases be combined, QAQC'd and organised into a single corporate database which is managed by industry standard software.

Additionally, it is recommended the impact of the artisanal mining operations is quantified in terms of economics and environmental impact.

Table 26-1: Proposed Exploration Budget

Item	Units / No /Metres	Unit Cost	Amount (US\$)
Diamond Drilling	3450	150	517,500
Assays	4000	40	160,000
Salaries / Technical Support			220,000
Metallurgical Testing			30,000
Mapping and Surveying			40,000
Additional Technical Studies			55,000
Regional Sampling and Fieldwork			60,000
Consumable Supplies and Software			95,000
Environmental Studies			65,000
Artisanal Mining Agreements Study			50,000
Preliminary Economic Assessment			145,000
<b>Total</b>			<b>1,437,500</b>

## 27 References

- Arce, 2020 – Geophysical Surveys Microgravimetry Total Field Magnetometry, March 2020.
- Arengi, J. T. et al, 2003, Technical Report on the Hemco Concession, Northeast Nicaragua for RNC Gold Inc.; unpublished consultant's Report, 158 pp.
- Bevan, P. A., 1973, Rosita Mine – a brief history and geologic description; Canadian Institute of Mining and Metallurgy, Bull.
- Calibre Mining Corp, Corporate Presentation, May 2020  
[https://d5sokjhuws5y9.cloudfront.net/assets/files/4417/calibre\\_mining\\_corporate\\_update\\_presentation\\_may\\_24\\_fin.pdf](https://d5sokjhuws5y9.cloudfront.net/assets/files/4417/calibre_mining_corporate_update_presentation_may_24_fin.pdf)
- Donnelly, T. W., Horne, G. S., Finch, R. C., and Lopez-Ramos, E., 1990, Northern Central America; the Maya and Chortis Blocks, in Dengo, G., Case, J. E, ed., Geology of North America Volume H, The Caribbean Region, Geological Society of America, p. 37-76.
- Email1: 5<sup>th</sup> June 2020. Royal Road CEO Tin Coughlin and RN Chapman
- Leyton, B., 1994. Geophysical studies and image analysis in north-eastern Nicaragua, Central America, Licentiate thesis, Luleå° University of Technology, Luleå°, Sweden
- MCR-HEMCO DIA Monte Carmelo, April 2019
- MCR-HEMCO Convenio de Servidumbres Minera Concesiones No 664RNMC2006 and No669RNMC2006
- Plecash, J., Hopper, RV., and Staff, 1963, Operations at La Luz Mines and Rosita Mines, Nicaragua, Central America: Paper presented at the CIM Annual Meeting, Edmonton, Alberta, April 2, 1963, 27 p.
- Sundblad, K., Cumming, G. L., and Krstic, D., 1991, Lead Isotope Evidence for the Formation of Epithermal Gold Quartz Veins in the Chortis Block, Nicaragua: Economic Geology, v. 86, p. 944-959.
- Wu, Y., 2012, Rosita Cu-Au-Ag Project, RAAN, Nicaragua, NI 43-101 Technical Report on Mineral Resource Estimate of Rosita Stockpiles
- Law 387 -  
<http://legislacion.asamblea.gob.ni/Normaweb.nsf/b92aaea87dac762406257265005d21f7/1958966e108358c7062570a100581a15?OpenDocument>.
- Agreement 1 (Right of Access) - DISPOCISION ADMINISTRATVA CRACCN NO. DA/30-04-2019-02